L-H-490a
January 11, 1965
SUPERSEDING
Int. Fed. Spec. L-H-00490 (GSA-FSS)
November 18, 1963

FEDERAL SPECIFICATION

HOLDER, CARD-LABEL, (PLASTIC)

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope. This specification covers the requirements for pressure-sensitive adhesive-mounting, transparent plastic card-label holders with insertable blank labels. (See 6.1.)

1.2 Classification.

1.2.1 *Types, styles, and classes.* Card-label holders covered by this specification shall be of the following types, styles, and classes, as specified (see 3.3 and 6.2).

Type I—Cellulose acetate butyrate or ethylcellulose plastic.
Style A—Extruded, seamless tubing (partially flattened).
Class 1—Clear with white label insert.
Class 2—Tinted with white label insert.
Style B—Extruded, seamless triangular tubing.
Class 1—Clear with white label insert.
Type II—Cellulose acetate propionate plastic.
Style C—Extruded, seamless tubing (partially flattened).
Style D—Extruded, folded flat strip, open one edge.
Class 1—Clear with white label insert.
Class 2—Tinted with white label insert.
Type III—Cellulose triacetate plastic.
Style E—Folded strip with thermoformed bead one edge, open on other edge.
Class 1—Clear with white label insert.
Class 3—Clear with tinted plastic inserts and white label inserts.

1.2.2 *Width.* Card-label holders shall be of the following widths as specified in the contract or order (see 6.2).

Inches—3/8, 1/2, 3/4, 1, 2.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards. The following specifications and standards, of the issues in effect on date of invitations for bids or request for proposal, form a part of this specification to the extent specified herein:

Federal Specifications:

L-P-349—Plastic Compounds, Molding, Cellulose Acetate Butyrate; and Molded or Extruded Parts.
L-P-504—Plastic Sheet and Film, Cellulose Acetate.
UU-P-31—Paper, General Specifications and Methods of Testing.
PPP-B-636—Box, Fiberboard.

Federal Standards:

Fed. Std. No. 102—Preservation, Packaging, and Packing Levels.
Fed. Std. No. 123—Marking for Domestic Shipment (Civilian Agencies).

FSC 9905

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

Fed. Test Method Std. No. 175—Adhesives: Methods of Testing.

Fed. Test Method Std. No. 406—Plastics: Methods of Testing.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D.C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105—Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issues in effect on date of invitation for bids or request for proposal, shall apply.

American Society for Testing and Materials Standards:

D-1562-60—Cellulose Acetate Propionate Molding and Extrusions Compounds.

D-817-62T—Testing Cellulose Acetate Propionate and Cellulose Acetate Butyrate.

D-568-61T—Flammability of Plastics 0.050 Inch and Under in Thickness.

D-787-63—Ethyl Cellulose Molding and Extrusion Compounds.

D-785-62—Test for Rockwell Hardness of Plastics.

D-570-63—Test for Water Absorption of Plastics.

D-256-56—Test for Impact Resistance of Plastics and Electrical Insulating Materials.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania.)

3. REQUIREMENTS

3.1 Preproduction sample approval. When specified (see 6.2), before production is commenced, a sample of the items to be supplied shall be submitted to the contracting officer or his authorized representative for approval. The approval of the preproduction sample does not relieve the contractor of responsibility for compliance with all applicable provisions of this specification.

3.2 General requirements. The plastic "stick-on" type card-label holders shall be in the types, styles, classes, and widths as specified in the contract or order (see 1.2 and 6.2). At the option of the manufacturer, the pressure-sensitive adhesive material may be applied to one side of the plastic tubing or strips by means of a woven or non-woven cloth tape, or (ester) type) cellular polyurethane foam tape with the adhesive on both sides of the tape, or applied directly to one side of the plastic with no cloth or other binder. The holders shall have an easily-removable sheet or film to serve as a protective backing for the adhesive while holders are in storage. The holders with the folding type paper insert labels shall be sealed in polyethylene bags.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

3.3 Material. Material shall be as specified herein. Details of material required not definitely specified shall be in accordance with good commercial quality for the purpose intended.

3.3.1 *Plastic.*

3.3.1.1 *Type I.* The material from which the plastic tubing, for type I holders, is extruded shall be transparent virgin cellulose acetate butyrate meeting the requirements for type I of L-P-349; or transparent virgin ethylcellulose meeting the physical properties specified in table I. The tubing shall be of uniform thickness throughout and shall be free from cracks, splits, and crazing. The wall thickness of the tubes shall be 0.015 inch ± 0.003 inch.

3.3.1.1.1 *Style A.* Internal width dimensions of the tubing shall be as specified (see 1.2.2 and 6.2), plus an allowance factor to assure a smooth unbinding fit of the paper insert over the entire length of the label. The space between the front and back wall of the tubing, provided for the insertion of the label, shall be 1/16 inch ± 1/64 inch.

3.3.1.1.2 *Style B.* Internal width dimensions of the tubing shall be 1/2 inch or 1 inch, as specified (see 6.2), plus an allowance factor to assure a smooth unbinding fit of the paper insert over the entire length of the label. The tubing shall be angled 45° forming a triangular holder with two face surfaces; one face of the tube shall be for viewing and the other face of the tube shall be coated with pressure-sensitive adhesive (see 3.3.2). A continuation of the above-mentioned faces shall form an inverted angle approximately 1/4 inch deep to securely hold the label insert and to indicate the position as to whether the holder shall be affixed above or below eye level.

TABLE I. *Physical properties for ethylcellulose plastic*

Property	Unit measure	Value required
Tensile strength, 73° F.	P.s.i.	5400
Elongation, 73° F.	Percent	20
Impact strength, IZOD, min.,		
⅛″ x ½″ bar at 73° F.	Ft. lb./1W of notch	2.5
⅛″ x ½″ bar at 0° F.	Ft. lb./1W of notch	0.6
Heat dist. temp. 66 p.s.i. (annealed)	°F.	190
Rockwell indentation hardness	R-Scale	108
Water absorption (24 hr.)		
Total water absorbed	Percent	1.4
Soluble matter extracted	Percent	0.4

3.3.1.2 *Type II.* The material from which the plastic tubing and strips for type II holders is extruded shall be transparent virgin cellulose acetate propionate meeting the physical property requirements for grade I of ASTM D-1562-60 as tested under ASTM D-817-62T. The tubing and strips shall be of uniform thickness throughout and shall be free from cracks, splits, and crazing.

3.3.1.2.1 *Style C.* The tubing for style C holders shall be seamless. The forming of a flat strip into a tube is prohibited. Internal width dimensions of the tubing shall be as specified (see 1.2.2 and 6.2), plus an allowance factor to assure a smooth unbinding fit of the paper insert over the entire length of the label. The space between the front and back wall of the tubing, provided for the insertion of the label, shall be 1/16 inch ± 1/64 inch. The wall thickness of the tube shall be 0.0175 inch ± 0.003 inch.

3.3.1.2.2 *Style D.* The plastic for style D holders shall be folded on one edge forming a flat strip and open on the other edge for insertion of the label insert. Internal width dimensions of the plastic strips shall be as specified (see 1.2.2 and 6.2), plus an allowance factor to assure a smooth unbinding fit of the paper insert over the entire length of the label. The space between the front and

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

back wall of the strip shall be sufficient for the insertion of the label. The wall thickness of the strips shall be 0.0175 inch ± 0.003 inch.

3.3.1.3 *Type III.* The material from which the plastic strips for type III holders is extruded shall be transparent virgin cellulose triacetate meeting the physical properties specified in table II. The wall thickness of the plastic strips shall be 0.010 inch ± 0.0025 inch. The strip shall be of uniform thickness throughout and shall be free from cracks, splits, and crazing. The tinted plastic inserts for class 3 holders shall be extruded from 0.075 inch gauge cellulose acetate, meeting the requirements for type I of L-P-504. Internal width dimensions of the plastic strips shall be as specified (see 1.2.2 and 6.2), plus an allowance factor to assure a smooth unbinding fit of the paper insert over the entire length of the label.

3.3.1.3.1 *Style E.* The plastic strips for style E holders shall be folded with a thermoformed bead on one edge and open on the other edge for insertion of the label and tinted plastic inserts. The space between the front and back wall of the strips shall be sufficient to assure a smooth fit of the label and, when required, the tinted plastic insert.

TABLE II. *Type III holders—physical properties for cellulose triacetate plastic*

Property	Unit measurement	Value required
Tensile strength (Instron)	p.s.i.	9,000 to 11,000
Total elongation	percent	25 to 40
Tear resistance (Elmendorf)	grams	100 to 300
Flammability:		
Area burned	inch	6 to 10
Burning time	secs.	self-extinguishing
Tensile heat distortion temperature (2 percent elongation at 50 p.s.i.)	°F.	260-280
Moisture absorption (24 hr.)		
Total water absorbed	percent	3 to 4
Soluble matter extracted	percent	0.5 to 1.5

3.3.1.4 *Finish.* Unless otherwise specified (see 6.2), the outer surface of the face of the plastic tubing and strips for types I, II, and III holders shall have a matte finish to prevent reflected light from interfering with readability of the insert labels. The matte finish shall not visibly reduce the light transmittance of the tubing and strips.

3.3.1.5 *Dimensions.* Plastic card-label holders shall be in lengths as specified (see 6.2). Internal width dimensions of the plastic tubing and strips shall be 3/8, 1/2, 3/4, 1, and 2 inches as specified (see 1.2.2). The mating insert labels and tinted plastic inserts (for type III holders) shall have nominal width of 3/8, 1/2, 3/4, 1, and 2 inches with a minus tolerance of 1/64 inch.

3.3.1.6 *Colors.* The color of the plastic for class 1, types I, II, and III holders and class 3, type III holders shall be clear; the colors for class 2, types I and II holders and the tinted plastic inserts for class 3, type III holders shall be amber, blue, green, pink, and red, or other commercially available colors, as specified (see 6.2).

3.3.2 *Adhesives.* The adhesive shall be a pressure-sensitive, water insoluble, homogeneous material capable of withstanding changes of temperature and humidity experienced in normal atmospheric conditions (see 3.3.2.1). The pressure-sensitive adhesive shall require no moisture, heat, or other special preparations prior to application of the label holders to the surface on which it is being applied. The adhesive shall have a minimum peel or stripping value of 3 pounds per inch of width in accordance with method 1041.1 of Fed. Test Method Std. No. 175 and as specified in 4.5.2. All parts of the surface(s) to which the adhesive is applied shall have no bare spots or air pockets. The adhesive shall be of uniform thickness and there shall be no tendency, when removing the protective backing, for the adhesive to separate from the plastic tubing and strips. The adhesive shall be compatible with types I, II, and III plastics, the protective backing, and with all finishes customarily used for steel furniture.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

3.3.2.1 *Storage stability (shelf life).* Types I, II, and III holders shall meet the adhesion to glass test specified in 4.5.2 and show no evidence of deterioration or change in the properties of the adhesive or protective backing such as to make the holders unfit for use when stored under warehouse conditions at a temperature of 70° to 90°F. (21° to 32°C.) and 50 percent ± 2 percent relative humidity for one year. A contractor's certificate of compliance will be a basis for acceptance (see 4.5.1).

3.3.2.2 *Protective backing.* The backing provided for protection of the adhesive material while the card-label holder is in storage (see 3.2 and 3.3.2.1), shall be a plastic sheet or film or other chemical treated material that releases easily yet protects the adhesive from deterioration by aging when stored under normal conditions. Waxed, oil treated, or other release liner impregnated with materials incompatible to the adhesive will not be accepted. The protective sheet shall completely cover the adhesive area to afford maximum protection, and shall extend ~~5/8 ± 1/8~~ inch beyond one end of the plastic holder or beyond the edge of the adhesive on not less than two sides to facilitate its removal. Flammability rating of the backing shall be a maximum of 24 square inches per minute when tested in accordance with ASTM D-568-62T.

3.3.3 *Paper.* Paper used for insert labels shall be of stock weighing 110 pounds (25-1/2 inches by 30-1/2 inches, 500 sheets) having a thickness of not less than 0.0055 inch, and shall conform to the requirements of UU-P-31 when tested as specified in 4.5.3.

3.3.3.1 *Insert labels.* The insert labels shall be furnished in sheet form, minimum 6 inches wide, suitable for entry into a typewriter carriage. Sheets shall be arranged with alternate score lines and perforations to permit tearing off individual (double height) labels in such a manner as to require that they be folded along their longitudinal center line to fit the plastic holder. Four double-fold labels in the length as specified (see 6.2) shall be furnished for each label holder. The labels shall be white in color and have a smooth finish suitable for writing on with pencil or pen and ink without feathering.

3.4 **Workmanship.** The finished holders shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels (AQLs).

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 **Contractor's inspection responsibility.** Unless otherwise specified in the contract or order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. The Government reserves the right to perform any inspection where such inspections are deemed neccessary to assure that supplies and services conform to prescribed requirements.

4.2 **Preproduction sampling inspection.** When a preproduction sample is required, inspection shall be made of one card-label holder for conformance with all applicable provisions of this specification (see 3.1).

4.3 **Sampling for inspection.** Sampling for inspection shall be performed in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated. For purposes of sampling, an inspection lot for examinations and tests shall consist of all material of the same type, style, and class submitted for inspection and delivery at one time.

4.3.1 *Inspection of materials and components.* In accordance with 4.1, the supplier is responsible for insuring that materials and components used were manufactured, tested and inspected in accordance with the requirements of referenced subsidiary spec-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

ifications and standards to the extent specified, or, if none, in accordance with this specification. In the event of conflict, this specification shall govern.

4.4 Inspection of the end item.

4.4.1 *Examination of the end item.* Examination of the end item shall be made in accordance with the classification of defects, inspection levels and AQLs set forth below. The lot size, for purpose of determining the sample size in accordance with MIL-STD-105, shall be expressed in units of strips of card-label holders for examinations in 4.4.1.1 and 4.4.1.2. For examination in 4.4.1.3 the lot size shall be expressed in units of intermediate packages.

4.4.1.1 *Examination of the end item for defects in material, construction, appearance and workmanship.* The sample unit for this examination shall be one strip of card-label holders. Not more than two strips shall be selected from any one flexible plastic envelope. Defects shall be noted as indicated in table III.

TABLE III. *Classification of defects*

Examine	Defects
Holder and insert label	Not sealed in polyethylene bags.
Adhesive	Not applied uniformly; does not have protective covering of sheet or film. Separates from plastic tubing or strip when protective backing is pulled from it.
Protective backing	Does not extend beyond the adhesive on at least 2 side edges or $\frac{5}{8} \pm \frac{1}{8}$ inch beyond one end. Not as specified.
Tubing or strip	Cracked, split, or crazed; not of uniform thickness throughout; rough or sharp edges; sharp corners; edges not straight or square.
Construction, design and workmanship	Not as required.
Reading surface of plastic	Stained, rough, or discolored.
Color	Not as specified.
Insert labels	Not scored for folding on longitudinal center; not double-fold type with four usable surfaces conforming to 3.3.3.1.

4.4.1.2 *Examination of the end item for dimensional defects.* The sample unit for this examination shall be one strip of card-label holders. Any dimensional requirement which is not within the dimensional tolerances specified shall be scored as a defect.

4.4.1.3 *Examination of the end item for quantitive requirements.* The sample unit for this examination shall be one intermediate package of card-label holders.

Examine	Defect
Unit package	Not 10 strips of card-label holders 12 inches or less in length per unit package. Not 25 strips of card-label holders over 12 inches to 18 inches in length per unit package. Not packaged in flexible plastic envelope, when applicable. Plastic envelope, when applicable, not as specified; envelope not sealed on one end.
Intermediate package	Not 5 unit packages of one size 12 inches or less in length per intermediate container, when applicable. Unit packages of one size over 12 inches in length not packaged in intermediate container when so specified.
Level C packaging	Packaging not accomplished in a neat and secure manner. Less than the specified or indicated number of card-label holder strips per package.

4.4.1.4 *Inspection levels and AQLs for examinations.* The inspection levels and AQLs expressed in defects per 100 units shall be as follows:

Examination paragraph	Inspection level	AQL
4.4.1.1	S-4	1.5
4.4.1.2	S-2	2.5
4.4.1.3	S-2	2.5

4.4.2 *Testing of the end item.* The end item shall be tested for the characteristic requirements as indicated in 4.5. Test results

Source: https://assist.dla.mil - Downloaded: 2026-01-28T14:49Z
Check the source to verify that this is the current version before use.

on specimens of the plastic may be performed on the material prior to fabrication of the end item. Five determinations shall be made for each characteristic. Any failure to meet unit or average requirements, as applicable, shall be cause for rejection.

4.4.3 *Examination of preparation for delivery.* An examination shall be made to determine compliance with the packing and marking requirements of section 5 herein and contract as applicable. The lot size shall be expressed in units of shipping containers fully packed and selected just prior to the sealing operations. Shipping containers fully prepared for delivery shall be examined for closure defects. The inspection level shall be S-2 and the AQL expressed in defects per 100 units shall be 4.0.

Examine	Defect
Material	Any packing material or component not as specified.
	Any component missing or malformed.
Contents	Less than the specified or indicated number of intermediate containers per shipping container.
Workmanship	Inadequate application of componerts as applicable, such as incomplete or insecure sealing of container flaps, insufficient or insecure tape banding or strapping; bulge or distortion of shipping container; loose packaging in a manner which results in shifting of contents in handling and shipment.
	Broken, bruised, dented, or otherwise damaged shipping container in a manner which may result in loss or injury to contents.
Marking (intermediate and shipping containers)	Omitted, incomplete, incorrect, illegible; of improper size, location, method or medium of application.

4.5 Tests. The methods of testing specified in Fed. Test Method Std. ~~No.~~ 406, wherever applicable and as specified in table IV shall be followed.

TABLE IV. *Test methods for plastics*

Tests	Fed. Std. 406 No.	ASTM No.[1]
Tensile properties of thin plastic sheets and film.	1013	D-822-59T
Tearing resistance of film and sheeting.	1121	D-1004-59T
Flammability of plastics 0.050 inch and under in thickness.	2022	D-568-61T
Water absorption of plastics	7031	D-570-63
Heat-distortion temperature	2011.1	D-150-47T
Impact, resistance, izod	1071	D-256-56
Rockwell indentation hardness test	1081	D-785-62

[1] The American Society for Testing and Materials designations are given for reference only; there may be a difference between the ASTM method and the method specified in Fed. Std. No. 406, however, in some cases the methods are technically identical.

4.5.1 *Storage stability (shelf life).* The contractor shall submit a certificate of compliance to the contracting officer certifying that the holders furnished meet the storage stability requirements specified in 3.3.2.1 of this specification.

4.5.2 *Adhesion test.* A 6-inch length of a sample holder of the width specified shall be applied to the surface of a piece of plate glass 1/4 by 5 by 15 inches. The adhesive side of the holder shall be firmly pressed onto the plate glass using necessary thumb pressure to ensure maximum contact. The holder shall be located across the 5-inch dimension of the glass, near the center of the 15-inch dimension, such that with one end of the holder flush with the edge of the glass, the other end will project one inch beyond the opposite edge of the glass. The force required to pull the holder from the glass surface shall be measured in pounds and/or ounces mounting the glass on a suitable gantry type of support on the platform of a dial indicating scale such that the force exerted to remove the sample may be read in pounds and/or ounces on the scale dial. The force shall be applied in a downward di-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

tion at an angle of approximately 90° om the plane of the sample by means of a suitably shaped wood slat inserted into the full length of the opening in the plastic tube of the holder. The wood slat shall be 8 inches long shaped and sized to conform to the internal cross-sectional shape of the plastic tube, but shall cause no distortion which might affect the test results. The glass surface shall be prepared for the test by thoroughly washing with a suitable detergent and water, after which it shall be rinsed in running water to remove all traces of detergent. The glass shall then be dried with a clean lintless cloth and cleaned with carbon tetrachloride applied on a lintless cloth. After the carbon tetrachloride has evaporated the glass shall be wiped with a dry lintless cloth. Minimum adhesive value in pounds for 6-inch sample of nominal width shall be as follows:

3/8 inch—3 pounds
1/2 inch—4 pounds
3/4 inch—5 pounds
1 inch—6 pounds
2 inch—10 pounds

4.5.3 *Paper test.* The paper used for the insert labels shall be tested in accordance with the following test methods described in UU-P-31 for requirements specified in 3.3.3 and 3.3.3.1.

Basis weight—Test method no. 110
Tearing resistance—Test method no. 170
Thickness—Test method no. 173

5. PREPARATION FOR DELIVERY

For civil agency procurement, the definitions and applications of the levels of packaging and packing shall be in accordance with Fed. Std. No. 102.

5.1 Packaging. Packaging shall be level A, B, or C, as specified (see 6.2).

5.1.1 *Level A or B.* Ten strips of one size, elve inches or less in length, shall be packaged in a flexible plastic envelope. The envelope sealed on one end shall have a flap on the open end of sufficient length to retain the contents until used.

Twenty-five strips of one size, over twelve inches and up to eighteen inches in length, shall be packaged in a flexible plastic bag. The bag shall be of sufficient length to provide for a complete sealed closure.

5.1.2 *Level C.* The label holders shall be packaged in accordance with industries commercial practice.

5.1.3 *Intermediate packaging.* Five envelopes of label holder strips, twelve inches or less in length, shall be intermediate packaged in a folding paperboard box or paperboard sleeve with at least one end closed. Unless otherwise specified (see 6.2), the label holder strips, over twelve inches and up to eighteen inches in length, shall not be intermediate packaged.

5.2 Packing. Packing shall be level A, B, or C, as specified (see 6.2).

5.2.1 *Level A.* The label holder strips shall be packed in close-fitting boxes conforming to PPP-B-636, V3c, style RSC. The boxes shall be closed, waterproof sealed with tape, and reinforced with bands of filament tape in accordance with the appendix to the box specification.

5.2.2 *Level B.* Unless otherwise specified (see 6.2), eight intermediate packages of label holder strips, twelve inches or less in length; or fifteen bags of strips, over twelve inches and up to eighteen inches in length, shall be packed in a close-fitting box, conforming to PPP-B-636 type CF, domestic, style RSC. The box shall be closed and sealed in accordance with the appendix to the box specification.

5.2.3 *Level C.* The label holder strips shall be packed to insure carrier acceptance and safe delivery to destination in containers

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

complying with the rules and regulations applicable to the mode of transportation.

5.3 Marking.

5.3.1 *Civil agencies.* In addition to markings required by the contract or order, the interior packages and shipping containers shall be marked in accordance with Fed. Std. No. 123.

5.3.2 *Military agencies.* In addition to markings required by the contract or order, the interior packages and shipping containers shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The plastic card label holders are intended for use in mounting on shelves, bins, sorting cases, desk trays, and cabinet drawers.

6.2 Ordering data. Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.
(*b*) Type, style, and class required (see 1.2.1).
(*c*) Width of holder required (see 1.2.2).
(*d*) Length of holder required (see 3.3.1.5)
(*e*) Color required (see 3.3.1.6).
(*f*) Whether preproduction sample is required (see 3.1).
(*g*) If other than a matte finish is required (see 3.3.1.4).
(*h*) Size of insert labels (see 3.3.3.1).
(*i*) Selection of applicable packaging and packing levels (see 5.1 and 5.2).

6.3 Transportation description. Transportation descriptions and minimum weights applicable to this commodity are:

Rail:

Plastic articles, not otherwise indexed by name.
Carload minimum weights: 10,000 and 30,000 pounds, subject to Rule 34, Uniform Freight Classification.

Motor:

Plastic articles, not otherwise indexed.
Truckload minimum weights: 10,000, 16,000, 21,000 and 30,000 pounds, subject to Rule 115, National Motor Freight Classification.

6.4 Level B packaging and packing shall be used by ordering agencies only when shipment is known to be made to a holding supply depot or warehouse from which partial shipment will be made to ultimate consumers.

Military Interests

CUSTODIANS:

Army—GL

Navy—YD

Air Force—69

Interested Activities:

Review

Army—MO

Navy—YD

User

Army—MD, SM

Navy—MC

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.