INCH-POUND

L-P-377C
w/ AMENDMENT 1
27 June 2014
SUPERSEDING
L-P-377C
March 23 1994

FEDERAL SPECIFICATION

PLASTIC SHEET AND STRIP, POLYESTER

This specification is approved by the Commissioner, Federal Supply Services Administration, for the use of all Federal agencies.

1. SCOPE

1.1 Scope. This specification contains requirements not covered by the drawings for the polyester-type plastic sheet film.

1.2 Classification. Polyester plastic sheet and strip material are of the following types and compositions, as specified (see 6.2)

1.2.1 Types. The types of Polyester film are as follow:

Type I	-	General purpose film
Type II	-	Highly transparent film
Type III	-	Highly transparent film with good dimensional stability
Type IV	-	High tensile-strength film with the greatest strength the longitudinal direction
Type V	-	Weatherable film processing good transparency and resistance to outdoor aging
Type VI	-	Heat shrinkable film

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this standard or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

Comments, suggestions, or questions on this document should be addressed to: Commander, US Army ARDEC, Attn: RDAR-EIQ-SE, Picatinny Arsenal, New Jersey 07806-5000 or emailed to usarmy.picatinny.ardec.list.ardec-stdzn-branch@mail.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at https://assist.dla.mil.

AMSC N/A FSC 8135

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the solicitation or contract.

COMERCIAL ITEM DESCRIPTION

A-A-203	- Kraft wrapping paper
A-A-2601	- Clip, paper wire

FEDERAL STANDARDS

FED-STD-123	- Marking for shipment (Civil agencies)

DEPARTMENT OF DEFENSE STANDARDS

MIL-STD-129	- Military Marking for Shipment and Storage
MIL-STD-147	- Palletized Unit Loads
MIL-STD-1916	- DOD Preferred Method for Acceptance of Product

(Copies of these documents are available online at http://quicksearch.dla.mil or from the Standardization Documents Order Desk, 700 Robbins Avenue, Bldg. 4D, Philadelphia, PA 19111-5094)

2.3 Non-Government publications. The following document(s) form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents are those cited in the solicitation or contract.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D374M	- Standard Test Method for Thickness of Solid Electrical Insulation (Metric)
ASTM D882	- Standard Test Method for Tensile Properties of Thin Plastic Sheeting
ASTM D1003	- Standard Test Method for Haze and Luminous Transmittance of Transparent Plastics
ASTM D3951	- Standard Practices for Commercial Packaging
ASTM D6251/D6251M	- Standard Specification for Natural Wood-Cleated Panelboard Shipping Boxes

(Copies of ASTM standards are available online from http://www.astm.org or American Society for Testing and Materials, 1916 Race Street, Philadelphia PA, 19103-1187)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents in or through libraries or other international services)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Material. The film covered by this specification shall be manufactured from a polyester-type polymer. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.2 Dimensions and tolerances.

3.2.1 Thickness. The film thickness shall be as specified in Table I when tested as specified in 4.2.6.

TABLE I. Thickness and tolerances.

Thickness, nominal, inch	Thickness, inch		Type Availability
	Minimum	Maximum	
0.00035	0.00023	0.00046	II, III
0.00050	0.00035	0.00064	I, II, III, IV
0.00065	0.00052	0.00078	VI
0.00075	0.00052	0.00097	II, III, IV
0.00080	0.00076	0.00084	VI
0.00100	0.00070	0.00120	I, II, III, IV
0.00150	0.00110	0.00170	I, III, IV
0.00200	0.00160	0.00240	I, III, V
0.00300	0.00270	0.00330	I, III, V
0.00500	0.00400	0.00590	I, III, V
0.00750	0.00610	0.00890	I, III
0.01000	0.00830	0.01150	I, III
0.01400	0.01180	0.01620	I

3.2.2 Roll sizes. The film shall be furnished in rolls conforming to the requirements in tables II, III, and IV. Tolerance shall be ± 1/16 inch. For roll cores of 1-1/8 inch outside diameter (O.D.), a plastic tube may be used in lieu of a paperboard tube, for durability.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

TABLE II. Roll cores. 1/

Film thickness, nominal, inch	Film type					
	I	II	III	IV	V	VI
0.00025	-	A, B, C	-	-	-	-
0.00035	-	A, B, C	-	-	-	-
0.00050	A, B, C	A, B, C	-	A, B, C	-	-
0.00065	-	-	-	-	-	A, B, C
0.00075	-	A, B, C	-	A, B, C	-	-
0.00100	A, B, C	A, B, C	-	A, B, C	-	-
0.00150	A, B, C	-	A, B, C	-	-	-
0.00200	A, B, C	-	A, B, C	-	A, B	-
0.00300	A, B, C	-	A, B, C	-	B, C	-
0.00500	B, C	-	B, C	-	B, C	-
0.00750	B, C	-	B, C	-	-	-
0.01000	B, C	-	-	-	-	-
0.01400	B, C	-	-	-	-	-

1/ Roll core inside diameters (I.D.): A = 1-1/8 inches, B = 3 inches and C = 6 inches

TABLE III. Roll dimensions and tolerances.

Roll core I.D., inches	Film thickness, nominal, inch	Roll O.D., inches 1/	Roll width, inches		
			Minimum	Maximum	Tolerance
1 -1/8	0.0005 & below	6	½	18	1/32
3	0.0005 & below	9-1/2	½	18	1/32
6	0.0005 & below	11 & 14	½	18	1/32
3	0.0005 & below	9-1/2	18-1/16	60 2/	⅛
6	0.0005 & below	11 & 14	18-1/16	60 2/	1/16
3	0.00075 & over	3-1/2	½	60 2/	1/32
6	0.00075 & over	11 & 14	1 3/	60 2/	1/32

1/ Roll O.D. tolerances ± ¼ inch.
2/ Maximum width: Type IV = 52 inches; Type III, 0.0015 inch and 0.002 inch = 57 in.
3/ Below 0.001 inch thickness, the minimum roll width is 1-1/2 inches.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

TABLE IV. Roll splices.

Film thickness, nominal, inch	Roll core I.D., inches			
	1-1/8	3	6 (11 inches O.D.) 1/	6 (14 inches O.D.) 1/
0.00035 & below	4	6	6	8
0.0005 through .001	3	4	4	6
0.0015 & over	1	2	2	4

1/ O.D. of roll in conjunction with 6 inch roll core I.D.

3.2.3 Flat cuts. The film shall be furnished in flat cuts conforming to the requirements in table V.

TABLE V. Flat cut requirements.

Film type and film thickness, nominal, inch	Flat cut size 1/	
	Minimum	Maximum
I, II, III, VI 0.0005 through 0.010	One dimension equal to 2 inches and/or the sum of the dimensions equal to 12 inches	43 inches in length by 43 inches in width

1/ Any size between this limits may be obtained.
Tolerances are ± 1/16 inch.

3.3 Property values.

3.3.1 Tensile strength and elongation. The tensile strength and elongation of the film shall conform to the requirements in table VI when tested as specified in 4.2.6.

Table VI. Tensile strength and elongation.

Film thickness, nominal, inch	Type	Tensile strength, pounds per square inch, minimum	Elongation, percent, minimum
0.00015	II	17,000	45
0.00025, 0.00035	II, III	18,000	55
0.00050	I, II, III	20,000	75
0.00050	IV	34,000 1/	15 1/
0.00065	VI	18,000	70

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

Table VI. Tensile strength and elongation. - Continued

0.00075	II, III	20,000	75
0.00075	IV	34,000 1/	15 1/
0.00080	VI	MD-24600 PSI/TD-26800 PSI	MD 165%/TD 125%
0.00100	I, II, III	20,000	80
0.00100	IV	34,000 1/	15
0.00150	I, III	20,000	90
0.00150	IV	34,000 1/	15 1/
0.00200, 0.00300	I, III, V 2/	20,000	90
0.00500, 0.00750	I, III, V	20,000	90
0.01000	I, III	20,000	100
0.01400	I	16,000	100

1/ This requirement applies only to the longitudinal direction (machine direction) of the film.
2/ Not available in type V at 0.00200-inch thickness.

3.3.2 Dimensional stability, types I through V films, The dimensional stability of the film shall conform to the requirements in table VII when tested as specified in 4.2.6.

TABLE VII. Dimensional stability, types I through V films.

Film thickness, nominal, inch	Type	Shrinkage, percent, maximum	
		At 150ºC	At 200ºC
0.00015 through 0.001	II	4.0	----
0.00025, 0.00035	III	----	7.0
0.0005,0.00075	I, III	----	9.0
0.0005,0.00075, 0.001	IV	13.0 1/	----
0.001	I, III	----	8.0
0.0015 through 0.010	I, III, V	----	7.0
0.014	I	----	10.0

1/ This requirement applies only to the longitudinal direction (machine direction) of the film.

3.3.2.1 Dimensional stability, type VI film only. The shrinkage of type VI film (0.00065 THICKNESS) shall be 35% minimum and 60% maximum when tested as specified in 4.2.6. The shrinkage of type VI film (0.00080 TARGET THICKNESS) shall be 25% minimum and 35% maximum when tested as specified in 4.2.6.

3.3.3 Haze types I, II and III films only. The haze of the film shall conform to the requirements in table VII when tested as specified in 4.2.6.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

TABLE VIII. Haze types I, II, III films only.

Film thickness, nominal, inch	Type	Haze, percent light scattered, maximum
0.00025	II, III	5.0
0.00035	II, III	5.0
0.00050	I	12.3
0.00050	II, III	4.0
0.00075	II, III	4.2
0.00100	I	18.1
0.00100	II, III	4.3
0.00015	I	28.0
0.00015	III	4.3
0.00200	I	37.5
0.00200	III	4.0
0.00300	I	60.0
0.00300	III	6.0
0.00500	I	76.0
0.00500	III	6.0
0.00750	I	87.0
0.00750	III	9.2
0.01000	I	100.0
0.01000	III	20.0

3.3.4 Optical transmittance, type V film only. The optical transmittance of light though type V film shall be no greater than 50 percent when tested as specified in 4.2.6.

3.4 Workmanship. All parts and assemblies shall be fabricated and loaded in a thorough workmanship manner. They shall be free of burrs, cracks, dirt, grease, rust, corrosion products and other foreign matter. The cleaning method used shall not be injurious to any part nor shall the parts be contaminated by the cleaning agent. Exterior surface coatings shall be continuous except for a few light scratches not exposing based material. All required markings shall be neatly and sharply defined.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

4.1.1 Responsibility for compliance. All items shall meet all requirements of section 3 and 5. The inspections set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.2 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be in accordance with MIL-STD-1916.

4.2.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.2.2 End item visual examination. The end items shall be examined for the defects listed in table IX. The lot size shall be expressed in units of rolls or flat cuts of plastic sheet. The sample unit shall be one yard full width for rolls or one sheet full size for flat cuts. The inspection level shall be in accordance with MIL-STD-1916 Verification Level (VL) IV and the finding of any defect shall be cause for rejection of the lot.

TABLE IX. End item visual defects.

Examine	Defect
Workmanship	Any dirt, oil, or foreign matter affecting appearance or disability Any deep gouge or scratch Any holes including pinholes Any rough or sharp edge Any cut, blister, bubble, tear, scuff, crack, or crease Any pimple or pit Any chipping Any spot, stain, or other discoloration affecting appearance or usability Not clear or clarity not uniform Not uniformly transparent

4.2.3 End item dimensional examination. The end items shall be examined for the defects listed below. The lot size shall be expressed in units of rolls or flat cuts of plastic sheet. The sample unit shall be one yard full width for rolls or one sheet full size for flat cuts. Inspection shall be in accordance with MIL-STD-1916 VL-I and the finding of any defect shall be cause for rejection of the lot.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

Examine	Defect
Size of sheets	Any variation greater than tolerances specified in the contract or order
Width of roll	Any width deviation greater then specified in table III

4.2.4 End item packaging examination of rolls and sheets. The end item shall be examined for the defects listed below. The lot size shall be expressed in units of rolls or flat cuts of plastic sheet. The sample unit shall be one complete roll or one package of flat cut sheets. Inspection shall be in accordance with MIL-STD-1916 VL-I and the finding of any defect shall be cause for rejection of the lot.

Examine	Defect
Unrolling of rolls	Not suitably restrained from unwinding Material blocks to the extent that unrolling causes damage or tearing rendering material unserviceable Any splice beyond specific limits Roll weight exceeds specified limits Diameter less than specified Diameter more than specified
Separation of sheets	Flat cut sheets not slip sheeted Sheets block to the extent that separation causes damage or tearing rendering material unserviceable

4.2.5 End item coverage content examination. The lot size shall be expressed in units of rolls or flat cuts of plastic sheet. The sample unit shall be one complete roll or one package of flat cut sheets. Inspection shall be in accordance with MIL-STD-1916 VL-I. Any average length per roll or average count per package for sheets (flat cuts) less than specified or indicated shall be cause for rejection of the lot.

4.2.6 End item testing. The end item shall be tested for the characteristics listed in table X. The lot size shall be expressed in units of rolls or flat cuts of plastic sheet. The sample unit shall be one roll or one package of flat cut sheets. A sample quantity of 21 square feet of material shall be taken from the sample unit. Discard a minimum of three turns of film from a roll before selecting a sample. In cutting the test specimens, no portion of the sample shall be taken closer than 10 percent of the width of the film from either edge. Inspection shall be in accordance with MIL-STD-1916 VL-I. All requirements are applicable to the lot average. The lot shall be unacceptable if one or more sample units fail to meet any test requirement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

Table X. End item tests

Characteristic	Reference to requirement	Reference to test	Number of determinations per sample unit	Results reported as numerically to nearest 2/
Thickness	3.2.1	4.3.2	10	0.00001 inch
Tensile strength	3.3.1	ASTM D882 1/	5	500 pounds per square inch
Elongation	3.3.1	ASTM D882	5	5 percent
Dimensional stability	3.3.2	4.3.3, 4.3.3.1, and 4.3.3.2	5	0.1 percent
Haze (types I, II, & III only)	3.3.3	Procedure A of ASTM D1003	1	0.1 percent
Optical transmittance (type V only)	3.3.4	4.3.4	1	1 percent

1/ (a) Specimen size shall be 1 inch by 5 inches.
(b) Separation between jaws shall be 2 inches.
(c) Thickness of specimens shall be determined before testing.

2/ All test reports shall contain the individual values utilized in expressing the final result.

4.2.7 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. Inspection shall be in accordance with MIL-STD-1916 VL-I and a finding of any defect shall be cause for rejection of the lot

Examine	Defect
Marking	Omitted; incorrect; illegible; of improper size, location, sequence or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of component, such as: incomplete sealing or enclosure of flap, improper taping, loose strapping, or inadequate stapling
Content	Number per container is more or less than required

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

4.2.8 Palletization examination. The fully packaged and palletized en items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit loads, fully packaged. Inspection shall be in accordance with MIL-STD-1916 VL-I and the finding of any defect shall be cause for rejection of the lot.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; or improper size, location, sequence, or method of application

4.3 Methods of inspection.

4.3.1 Standard conditioning. Unless otherwise specified herein, or applicable test method, samples for test shall be conditioned at a temperature of 73.5ºF ± 2ºF (23ºC ± 1ºC) and a relative humidity of 50 percent ± 4 percent for a period of not less than 16 hours.

4.3.2 Thickness. Thickness of the film shall be determined in accordance with ASTM D374, method A or C. For films with a nominal thickness of 0.00015, 0.00025, and 0.00035-inch, the thickness shall be measured by the above method; however, the film shall be built up by using the number of plies specified below and dividing the readings by the number of plies used.

Thickness (nominal), inch	Number of plies used to determine thickness
0.0015	4
0.0025	2
0.0035	2

Measure at 10 randomly selected points from a minimum area of 12 square inches. The average of the ten readings shall fall within the specified limits.

4.3.3 Dimensional stability, type I, II, III and V films. The film shrinkage shall be determined on five specimens conditioned according to 4.3.1 before and after test. The specimens shall be 10 inches by 10 inches by width of split roll if this dimension is less than 10 inches. Three measurements shall be made in the longitudinal direction (machine direction) and in the transverse direction. All measurements shall be accurate to 1/32 inch. Specimens shall be tested by freely suspending them in an oven controlled to 150ºC ± 1ºC for type II and V film and 200ºC ± 1ºC for type I and III film. The test period shall be 30 minutes. Specimens are to be

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

cooled and conditioned in accordance with 4.3.1 before measurements are made. The percent shrinkage shall be computed from the three measurements before and after test.

4.3.3.1 Dimensional stability, type IV film only. Type IV film shrinkage shall be determined on five specimens conditioned in accordance with 4.3.1. Before testing, the specimens shall be ¼ inch by 15 inches and cut so that the long dimension is parallel to the longitudinal direction (machine direction) of the film. Mark a pair of lines 12 inches apart on each sample. Measure the distance between the lines on specimens conditioned according to 4.3.1 to the nearest 0.01 inch before and after test. Specimens shall be tested by placing a paper clip conforming to Gem pattern, type I, A-A-2601, capacity 1/16 inch at each end and freely suspending the assembly in an oven controlled to 150ºC ± 1ºC. The test period shall be five minutes. The percent shrinkage shall be computed from the 5 measurement average before and after test.

4.3.3.2 Dimensional stability, type VI film only. Five specimens 5 inches by 5 inches shall be measured to the nearest 0.1 inch and then immersed in boiling water (100 ºC) for 30 seconds. Remove, cool, lay flat and smooth out wrinkles. Measure the samples to the nearest 0.1 inch. The percent shrinkage shall be calculated as follows:

$$\frac{\text{(Original dimension - Final dimension)}}{\text{Original dimension}} \times 100 = \text{Percent Shrinkage}$$

4.3.4 Optical transmittance, type V film only. The optical transmittance shall be determined in accordance with the following procedure. The test equipment shall be Bausch & Lomb Spectronic "20" Colorimeter or equivalent. Five test specimens, randomly selected from the roll, shall be cut to ¾ inch by 2 inches. The procedure is to allow the instrument to warm up. The wavelength control shall be set to 400 millimicrons. Adjust the instrument to read zero transmittance. Insert an empty specimen holder into the one inch test tube adapter and adjust the needle to read 100 percent transmittance. Place a specimen between the holder halves and read percent transmittance.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial, as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Rolls. Plastic shall be rolled on a convoluted or spiral-wound chipboard or plastic tube. Each roll shall be wrapped with 30 pound minimum basis weight kraft paper conforming to A-A-203, or plastic film 0.002 inch minimum thickness. The roll shall be wrapped so that the wrap completely encircles the roll at least once with a minimum overlap of three inches, and the width of the overlap shall be sufficient to fold over and protect the ends of the roll. The wrapping shall be secure with tape.

5.1.1.2 Flat cuts. Five hundred sheets, of one type, thickness and size, shall be stacked on a fiberboard. The bundle shall be wrapped in 30 pound minimum basis weight kraft paper

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

conforming to A-A-203, or plastic film 0.002 inch minimum thickness. Wrapping shall be secure with tape.

5.1.2 Commercial preservation. Plastic shall be preserved in accordance with ASTM D3951.

5.2 Packing. Packing shall be level A, B or Commercial, as specified (see 6.2)

5.2.1 Level A. Plastic, preserved as specified, shall be packed in a natural wood-cleated panelboard box conforming to ASTM D6251/D6251M. Boxes shall be closed and strapped.

5.2.3 Commercial packing. Plastic, preserved as specified, shall be packed in accordance with ASTM D3951.

5.3 Palletization. Plastic, packed as specified, shall be palletized on a 4-way entry pallet in accordance with MIL-STD-147. Each prepared load shall be bonded with straps in accordance with bonding means C and D or film bonding F or G.

5.4 Marking. Marking of unit packs, shipping containers and unit loads shall be in accordance with MIL-STD-129 or FED-STD-123.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The polyester film cover by this specification is intended for general usage in packaging and industrial applications.

6.2 Acquisition requirements. Acquisition requirements must specify the following:

a. Title, number, and date of this specification.
b. Type required (see 1.2.1).
c. Whether rolls or flat cuts are required (see 3.2)
   (1) Rolls: Thickness and width required.
   (2) Flat cuts: Thickness, applicable dimensions, and tolerances.
d. Roll core size (see 3.2.2).
e. Roll O. D. (see table III).
f. Selection of applicable levels of preservation and packing (see 5.1 and 5.2)

6.3 Amendment 1 includes ECP R05B3028 which added an additional film thickness and ECP R13Q2001 which updated the specification by removing cancelled specifications and by replacing a superseded specification.

6.4 Subject term (key word) listing.
Moisture barrier

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.

Waterproof covering

6.5 Amendment notations. The margins of this specification are marked with vertical lines to indicate where changes from the previous issue were made. This was done as convenience only and the Government assumes no liability whatsoever for any inaccuracies in those notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationships to the last previous issue.

Custodian:
Army – AR
Navy -AS
Air Force - 69

Preparing activity:
Army – AR
(Project: 8135-2014-005)

Review activities:
Army – AV, GL, MI, SM
Navy – CG, SA
Air Force – 03, 11
DLA - DH

NOTE: The activities listed above were interest in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:09Z
Check the source to verify that this is the current version before use.