L-P-410A
Amendment-3
May 21, 1974
SUPERSEDING
Amendment-2
December 15, 1969

FEDERAL SPECIFICATION

PLASTIC, POLYAMIDE (NYLON), RIGID: RODS, TUBES, FLATS, MOLDED AND CAST PARTS

This amendment, which forms a part of Federal Specification L-P-410a, dated March 16, 1966, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

Page 1

Paragraph 1.2, Delete lines 10 and 11, and substitute: "Polyhexamethylene amide, (Nylon 6/9, 6/10, and 6/12), low moisture absorption polyamide."
Paragraph 1.2.1, line 2. Delete "sebacamide (Nylon 6/10)" and substitute: "amide (Nylon 6/9, 6/10, and 6/12)."

Paragraph 2.2. Delete Federal Standard No. 102, and title.

Page 2

Paragraph 3.2, lines 4 and 5. Delete "sebacamide (Nylon 6/10)" and substitute "amide (Nylon 6/9, 6/10, and 6/12)."
Paragraph 3.4, line 3. Delete "6/10" and substitute: "6/9, 6/10, and 6/12."

Page 3

TABLE I, Column 2 (Nylon 6/6), opposite tensile strength for rods 1 inch and under. Delete "13,000" and substitute "11,000." For rods over 1 inch delete "12,000" and substitute "13,000."

TABLE I, Column 5 title. Delete "sebacamide (Nylon 6/10)" and substitute "amide (Nylon 6/9, 6/10, and 6/12)."
Column 5, opposite specific gravity minimum. Delete "1.07" and substitute "1.05."

TABLE I, Column 6. Delete reference "Table XI" and substitute "Table XIV."

Paragraph 3.5.1, line 3. Delete "Nylon 6/10" and substitute "Nylon 6/9, 6/10, and 6/12."

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

Page 4

TABLE II, Column 3 (Nylon 6), opposite Rockwell R scale hardness minimum. Delete "105" and substitute "114." Opposite water absorption, maximum, percent: After 24 hours immersion, delete "2.5" and substitute "1.9."

TABLE II. Column 5 title. Delete "sebacamide (Nylon 6/10)" and substitute "amide (Nylon 6/9, 6/10, and 6/12)."
Column 5. Opposite water absorption after 24 hours immersion, delete "0.5" and substitute "0.6." Opposite water absorption at saturation, delete "4.0" and substitute "5.0."

Page 5

TABLE V, Column 3, opposite flats 3/16 inch thickness and over. Delete "and diameter."

Page 8

Paragraph 4.3.3, line 11. Delete "6/10" and substitute "6/9, 6/10, and 6/12."

Page 12

Paragraph 4.4.10.2, line 5. Delete "6/10" and substitute "6/9, 6/10, and 6/12."
Paragraph 4.4.11, line 12. After copper, add "cold-rolled hard."

Pages 12 and 13

Under Section 5, "PREPARATION FOR DELIVERY"-Delete 1st paragraph in its entirety.

Page 14

Paragraph 6.1, line 3. Delete "6/10" and substitute "6/9, 6/10, and 6/12."

Paragraph 6.7. Delete and substitute:

6.7 International standardization agreement. Certain provisions of this specification are the subject of international standardization agreement ABC-NAVY-17c. When amendment, revision, or cancellation of this specification is proposed which will effect or violate the international agreement concerned, the preparing activity will take appro-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.

priate reconciliation action through international standardization channels including departmental standardization offices, if required.

MILITARY CUSTODIANS
Army - MR
Air Force - 11

Review Activities
Army - EL, MI, ME, PA, WC
Navy - SH, EC, OS
Air Force - 84

User Activities:
Navy - MC

CIVIL AGENCY COORDINATING ACTIVITIES:
GSA-FSS
COM-NBS
VA-DMS
DOT-FIS

Preparing Activity:
Navy - AS
(Project No. 9330-0631)

☆U.S. GOVERNMENT PRINTING OFFICE: 1981—703-023/4682

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:10Z
Check the source to verify that this is the current version before use.