INCH-POUND

MIL-PRF-19500/615A
3 May 1996
SUPERSEDING
MIL-S-19500/615
10 December 1993

PERFORMANCE SPECIFICATION

SEMICONDUCTOR DEVICE, FIELD EFFECT RADIATION HARDENED TRANSISTOR, P-CHANNEL, SILICON,
TYPES 2N7382 AND 2N7383
JANTXV M, D AND R AND JANS M, D AND R

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the detail requirements for a P-channel, Radiation Hardened, enhancement mode, MOSFET, power transistor intended for use in high density power switching applications. Two levels of product assurance are provided for each device type as specified in MIL-PRF-19500, with avalanche energy ratings (E_{AS}) and maximum avalanche current (I_{AS}).

1.2 Physical dimensions. See figure 1 (T0-257AA).

1.3 Maximum ratings. Unless otherwise specified, T_C = +25°C.

Type	Min $V_{(BR)DSS}$ V_{GS} = 0 V I_D =-1.0 mA dc	P_T 1/	P_T 1/ T_A = +25°C (free air)	V_{GS}	I_{D1} 2/	I_{D2} 2/ T_C = +100°C	T_J and T_{STG}
	V dc	W	W	V dc	A dc	A dc	°C
2N7382	-100	75	2	±20	-11.0	-7.0	-55 to +150
2N7383	-200	75	2	±20	-6.5	-4.1	-55 to +150

Type	I_S	I_{DM}	V_{ISO} 70,000 feet altitude	Max $r_{DS(on)}$ 1/ V_{GS} =-12 V dc $I_D = I_{D2}$		$R_{\Theta JC}$ max	E_{AS}	I_{AS}
				T_J = +25°C	T_J = +150°C			
	A dc	A(pk)		ohms	ohms	°C/W	mJ	A dc
2N7382	-11.0	-44	---	0.30	0.60	1.67	165	-11.0
2N7383	-6.5	-26	---	0.80	1.68	1.67	171	-6.5

1/ Derated linearly by 0.6 W/°C for T_C > +25°C; $P_T = \frac{T_{Jmax} - T_C}{R_{\Theta JC}}$

2/ $I_D = \sqrt{\frac{T_{Jmax} - T_c}{(R_{\Theta JC}) \times (R_{DS_{on}} \text{ at } T_{Jmax})}}$

3/ I_{DM} = 4 x I_{D1}; I_{D1} as calculated by footnote 2/.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Electronics Supply Center, ATTN: DESC-ELDT, 1507 Wilmington Pike, Dayton, OH 45444-5765, by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 5961

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics. Unless otherwise specified, T_C = +25° C.

Type	Min $V_{(BR)DSS}$ V_{GS} = 0 V I_D =-1.0 mA dc	$V_{GS(th)1}$ $V_{DS} \geq V_{GS}$ I_D =-1.0 mA dc	I_{DSS} max V_{GS} = 0 V	Max $r_{DS(on)1}$ 1/ V_{GS} =-12 V; $I_D = I_{D2}$
			V_{DS} = 80% of rated V_{DS}	T_J = +25° C
	V dc	V dc	µA dc	ohms
		Min Max		
2N7382	-100	-2.0 -4.0	-25	0.30
2N7383	-200	-2.0 -4.0	-25	0.80

1/ Pulsed (see 4.5.1).

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATION

DEPARTMENT OF DEFENSE

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

STANDARD

MILITARY

MIL-STD-750 - Test Methods for Semiconductor Devices.

(Unless otherwise indicated, copies of the above specifications, standards, and handbooks are available from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)


2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein (except for related associated specifications or specification sheets), the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Associated detail specification. The individual item requirements shall be in accordance with MIL-PRF-19500 and as specified herein.

3.2 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as defined in MIL-PRF-19500.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.



Ltr	Dimensions			
	Millimeters		Inches	
	Min	Max	Min	Max
BL	10.41	10.67	.410	.420
BL_1		.84		.033
CH	4.83	5.08	.190	.200
LD	0.64	0.89	.025	.035
LL	15.24	16.51	.600	.650
LO	3.05 BSC		.120 BSC	
LS	2.54 BSC		.100 BSC	
MHD	3.56	3.81	.140	.150
MHO	13.39	13.64	.527	.537
TL	16.38	16.89	.645	.665
TT	0.89	1.14	.035	.045
TW	10.41	10.67	.410	.420
Term 1	Drain			
Term 2	Source			
Term 3	Gate			

NOTES:
1. Dimensions are in millimeters.
2. Equivalents are given for general information only.
3. All terminals are isolated from case.
4. The preferred measurements used herein are the metric units. However, this transistor was designed using inch-pound units of measurement. In case of conflicts between the metric and inch-pound units, the inch-pound units shall be the rule.
5. This area is for the lead feed-thru eyelets (configuration is optional, but will not extend beyond this zone.

FIGURE 1. Dimensions and configuration (T0-257AA).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

3.3 Design, construction, and physical dimensions. The design, construction, and physical dimensions shall be as specified in MIL-PRF-19500, and on figure 1 herein. Methods used for electrical isolation of the terminal feedthroughs shall employ materials that contain a minimum of 90 percent AL_2O_3 (ceramic). Examples of such construction techniques are metalized ceramic eyelets or ceramic walled packages. The preferred measurements used herein are the metric units. However, this transistor was designed using inch-pound units of measurement. In case of conflicts between the metric and inch-pound units, the inch-pound units shall be rule.

3.3.1 Lead material and finish. Lead material shall be Kovar, Alloy 52, and a copper core is permitted. Lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition requirement (see 6.2).

3.3.2 Internal construction. Multiple chip construction shall not be permitted.

3.4 Marking. Marking shall be in accordance with MIL-PRF-19500. At the option of the manufacturer, marking of country of origin may be omitted from the body of the transistor, but shall be retained on the initial container.

3.5 Electrostatic discharge protection. The devices covered by this specification require electrostatic protection.

3.5.1 Handling. MOS devices must be handled with certain precautions to avoid damage due to the accumulation of static charge. The following handling procedures shall be followed:

a. Devices shall be handled on benches with conductive handling devices.

b. Ground test equipment, tools, and personnel handling devices.

c. Do not handle devices by the leads.

d. Store devices in conductive foam or carriers.

e. Avoid use of plastic, rubber, or silk in MOS areas.

f. Maintain relative humidity above 50 percent, if practical.

g. Care shall be exercised, during test and troubleshooting, to apply not more than maximum rated voltage to any lead.

h. Gate must be terminated to source. $R \leq 100$ k, whenever bias voltage is to be applied drain to source.

3.6 Qualification. Devices furnished under this specification shall be products that are authorized by the qualifying activity for listing on the applicable qualified products list before contract award (see 4.2 and 6.2).

4. QUALITY ASSURANCE PROVISIONS

4.1 Classification of Inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).

b. Screening (see 4.3)

c. Conformance inspection (see 4.4).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500.

4.2.1 Group E inspection. Group E inspection shall be in accordance with table III herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

4.3 Screening (JANS and JANTXV levels). Screening shall be in accordance with table IV of MIL-PRF-19500, and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table IV of MIL-PRF-19500)	Measurement	
	JANS levels	JANTXV levels
1/	Thermal response 4.5.3	Thermal response 4.5.3
1/, 2/	Method 3470, see 4.5.5	Method 3470, see 4.5.5
1/, 2/	Gate stress test 4.5.4	Gate stress test 4.5.4
9 1/	I_{GSS1}, I_{DSS1}, subgroup 2 of table I herein	Subgroup 2 of table I herein
10	Method 1042, test condition B	Method 1042, test condition B
11	I_{GSS1}, I_{DSS1}, $r_{DS(on)1}$, $V_{GS(th)1}$ subgroup 2 of table I herein. ΔI_{GSS1} = ±20 nA dc or ±100% of initial value, whichever is greater. ΔI_{DSS1} = ±25 µA dc or ±100% of initial value, whichever is greater.	I_{GSS1}, I_{DSS1}, $r_{DS(on)1}$, $V_{GS(th)1}$ subgroup 2 of table I herein.
12	Method 1042, test condition A, t = 240 hours	Method 1042, test condition A
13	Subgroup 2 and 3 of table I herein. ΔI_{GSS1} = ±20 nA dc or ±100% of initial value, whichever is greater. ΔI_{DSS1} = ±25 µA dc or ±100% of initial value, whichever is greater. $\Delta r_{DS(on)(1)}$ = ±20% of initial value. $\Delta V_{GS(th)1}$ = ±20% of initial value.	Subgroup 2 of table I herein. ΔI_{GSS1} = ±20 nA dc or ±100% of initial value, whichever is greater. ΔI_{DSS1} = ±25 µA dc or ±100% of initial value, whichever is greater. $\Delta r_{DS(on)(1)}$ = ±20% of initial value. $\Delta V_{GS(th)1}$ = ±20% of initial value.

1/ Shall be performed anytime before screen 10.
2/ This is a stress test designed to ensure a rugged product.

4.4 Quality conformance inspection. Quality conformance inspection shall be in accordance with MIL-PRF-19500.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with MIL-PRF-19500, and table I herein. Electrical measurements (end points) and delta requirements shall be in accordance with the inspections of table I, group A, subgroup 2 herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VIa (JANS) and table VIb (JANTX and JANTXV) of MIL-PRF-19500, and as follows. Electrical measurements (end points) shall be in accordance with the applicable inspections of table I, group A, subgroup 2 herein.

4.4.2.1 Group B inspection, table VIa (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
3	1051	Condition G.
4	1042	The heating cycle shall be 1 minute minimum.
5	1042	ondition A; V_{DS} = 80 percent of rated; T_A = +175° C; t = 120 hours; read and record $V_{(BR)DSS}$ (pre and post) at I_D = -1 mA; read and record I_{DSS} (pre and post) in accordance with table 1, group A, subgroup 2. Delta $V_{(BR)DSS}$ shall not exceed 10%; delta I_{DSS} shall not exceed 50 µA.
5	1042	Condition B; V_{GS} = 80 percent of rated; T_A = +175° C; t = 24 hours.
6	3161	See 4.5.2

4.4.2.2 Group B inspection, table VIb (JANTX and JANTXV) of MIL-PRF-19500.

Subgroup	Method	Condition
2	1051	Test condition G.
3	1042	The heating cycle shall be 1 minute minimum.
3	2037	Test condition A.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VII of MIL-PRF-19500, and as follows. Electrical measurements (end points) shall be in accordance with the applicable inspections of table I, group A, subgroup 2 herein.

4.4.3.1 Group C inspection, table VII of MIL-PRF-19500.

Subgroup	Method	Condition
2	2036	Test condition A, weight = 10 lbs., t = 10 seconds.
6	1042	The heating cycle shall be 1 minute minimum.

4.5 Methods of inspection. Methods of inspection shall be as specified in appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurements shall be as specified in section 4 of MIL-STD-750.

4.5.2 Thermal resistance. Thermal resistance measurements shall be performed in accordance with method 3161 of MIL-STD-750. The maximum limit of $R_{\Theta JC(max)}$ shall be 1.67° C/W. The following parameter measurements shall apply:

a. Measuring current (I_M): 10 mA.
b. Drain heating current (I_H): 1.5 A minimum.
c. Heating time (t_H): Steady-state (see MIL-STD-750, method 3161 for definition).
d. Drain-source heating voltage (V_H): 20 V minimum.
e. Measurement time delay (t_{MD}): 30 to 60 µs maximum.
f. Sample window time (t_{SW}): 10 µs maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

4.5.3 Thermal impedance ($Z_{\Theta JC}$ measurements). The $Z_{\Theta JC}$ measurements shall be performed in accordance with MIL-STD-750, method 3161. The maximum limit (not to exceed figure 2, thermal impedance curves and the group A, subgroup 2 limits) for $Z_{\Theta JC}$ in screening (table IV of MIL-PRF-19500) shall be derived by each vendor by means of statistical process control. When the process has exhibited control and capability, the capability data shall be used to establish the fixed screening limit. In addition to screening, once a fixed limit has been established, monitor all future sealing lots using a random five piece sample from each lot to be plotted on the applicable X, R chart. If a lot exhibits an out of control condition, the entire lot shall be removed from the line and held for Engineering evaluation and disposition. This procedure may be used in lieu of an in line process monitor.

a. Measuring current (I_M): 10 mA.
b. Drain heating current (I_H): 1.5 A minimum.
c. Heating time (t_H): 10 ms.
d. Drain-source heating voltage (V_H): 20 V minimum.
e. Measurement time delay (t_{MD}): 30 to 60 μs maximum.
f. Sample window time (t_{SW}): 10 μs maximum.

4.5.4 Gate stress test.

a. V_{GS} = ±24 V min.
b. t = 250 µs min.

4.5.5 Single pulse avalanche energy (E_{AS}).

a. Peak current (I_{AS}): I_{D1}.
b. Peak gate voltage (V_{GS}): -12 V.
c. Gate to source resistor (R_{GS}): $25 \leq R_{GS} \leq 200\ \Omega$.
d. Initial case temperature: +25° C +10° C, -5° C.
e. Inductance: $(2\ E_{AS}/(I_{AS})^2)((V_{BR} - V_{DD})/V_{BR})$ mH minimum.
f. Number of pulses to be applied: 1 pulse minimum.
g. Supply voltage V_{DD} = -50 V, or -25 V for 100 V devices.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical inspection	2071					
Subgroup 2						
Thermal impedance 2/	3161	See 4.5.3	$Z_{\Theta JC}$		0.82	°C/W
Breakdown voltage, drain to source	3407	V_{GS} = 0 V dc, I_D = -1.0 mA; Bias condition C	$V_{(BR)DSS}$			
2N7382				-100		V dc
2N7383				-200		V dc
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$; I_D = -1.0 mA	$V_{GS(th)1}$	-2.0	-4.0	V dc
Gate current	3411	V_{GS} = ±20 V dc; V_{DS} = 0 V dc; Bias condition C	I_{GSS1}		±100	nA dc
Drain current	3413	V_{GS} = 0 V dc; V_{DS} = 80% of rated V_{DS}; Bias condition C	I_{DSS1}		-25	µA dc
Static drain to source on-state resistance	3421	V_{GS} =-12 V dc; Condition A; Pulsed (see 4.5.1); I_D = rated I_{D2} (see 1.3)	$r_{DS(on)1}$			
2N7382					0.30	Ω
2N7383					0.80	Ω
Static drain to source on-state resistance	3421	V_{GS} =-12 V dc; Condition A; Pulsed (see 4.5.1); I_D = rated I_{D1} (see 1.3)	$r_{DS(on)2}$			
2N7382					0.35	Ω
2N7383					0.92	Ω
Forward voltage (source drain diode)	4011	V_{GS} = 0 V dc; I_D = rated I_{D1}; Pulsed (see 4.5.1)	V_{SD}			
2N7382					-3.0	V
2N7383					-5.0	V

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 3						
High temperature operation		T_A = +125° C				
Gate current	3411	Bias condition C; V_{GS} = ±20 V dc; V_{DS} = 0 V dc	I_{GSS2}		±200	nA dc
Drain current	3413	Bias condition C; V_{GS} = 0 V dc; V_{DS} = 80% of rated V_{DS}	I_{DSS3}		-0.25	mA dc
Static drain to source on-state	3421	V_{GS} = -12 V dc; Pulsed (see 4.5.1); I_D = rated I_{D2}	$r_{DS(on)3}$			
2N7382					0.54	Ω
2N7383					1.60	Ω
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$; I_D = -1.0 mA dc	$V_{GS(th)2}$	-1.0		V dc
Low temperature operation		T_A = -55° C				
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$; I_D = -1.0 mA dc	$V_{GS(th)3}$		-5.0	V dc
Subgroup 4						
Switching time test	3472	I_D = rated I_{D1}; V_{GS} = -12 V dc; Gate drive impedance = 7.5Ω; V_{DD} = 50% of $V_{(BR)DSS}$				
Turn-on delay time			$t_{d(on)}$			
2N7382					30	ns
2N7383					50	ns
Rise time			t_r			
2N7382					70	ns
2N7383					90	ns
Turn-off delay time			$t_{d(off)}$			
2N7382					70	ns
2N7383					90	ns
Fall time			t_f			
2N7382					70	ns
2N7383					90	ns

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 4 - continued						
Forward transconductance	3475	$I_D = I_{D2}$; V_{DD} = -15 V dc Pulsed (see 4.5.1)	g_{fs}			
2N7382				2.5		S
2N7383				2.5		S
Subgroup 5						
Safe operating area test (high voltage)	3474	See figures 3 and 4; t_p = 10 ms; V_{DS} = 80% of rated $V_{(BR)DSS}$				
Electrical measurements		See table I, group A, subgroup 2				
Subgroup 6						
Not applicable						
Subgroup 7						
Gate charge	3471	Condition B				
On-state gate charge			$Q_{g(on)}$			
2N7382					35	nC
2N7383					35	nC
Gate to source charge			Q_{gs}			
2N7382					10.0	nC
2N7383					10.0	nC
Gate to drain charge			Q_{gd}			
2N7382					25	nC
2N7383					25	nC
Reverse recovery time	3473	di/dt ≤ -100 A/µs; V_{DD} ≤ -50 V; $I_D = I_{D1}$	t_{rr}			
2N7382					250	ns
2N7383					400	ns

1/ For sampling plan, see MIL-PRF-19500.

2/ This test is required for the following end-point measurements only:

JANS - group B, subgroups 3 and 4; JANTXV - group B, subgroups 2 and 3; group C, subgroup 6; group E, subgroup 1

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

TABLE II. Group D inspection.

Inspection	MIL-STD-750		Symbol	Pre-irradiation limits		Post-irradiation limits		Unit
1/ 3/	Method	Conditions		M,D, and R		M,D, and R		
				Min	Max	Min	Max	
Subgroup 2		T_C = +25°C						
Steady-state total dose irradiation (V_{GS} BIAS) 2/	1019	V_{GS} = -12 V; V_{DS} = 0 V						
Steady-state total dose irradiation (V_{DS} BIAS) 2/	1019	V_{GS} = 0 V; V_{DS} = 80 percent of rated V_{DS} (preirradiation)						
End-point electricals								
Breakdown voltage, drain to source	3407	V_{GS} = 0 V; I_D = -1 mA; Bias condition C	$V_{(BR)DSS}$					
2N7382				-		-100		V dc
2N7383				100		-200		V dc
Gate to source 3/ voltage (threshold)	3403	$V_{DS} \geq V_{GS}$; I_D = -1 mA	$V_{GS(th)}$	- 200				
2N7382					-4.0	-2.0	-4.0	V dc
2N7383					-4.0	-2.0	-4.0	V dc
Gate current	3411	V_{GS} = -20 V; V_{DS} = 0 V; Bias condition C	I_{GSSF1}	-2.0 -2.0	-100		-100	nA dc
Gate current	3411	V_{GS} = +20 V; V_{DS} = 0 V; Bias condition C	I_{GSSR1}		100		100	nA dc

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

TABLE II. Group D inspection - Continued.

Inspection	MIL-STD-750		Symbol	Pre-irradiation limits		Post-irradiation limits		Unit
1/ 3/	Method	Conditions		M,D, and R		M,D, and R		
				Min	Max	Min	Max	
Subgroup 2 - Continued.								
Drain current	3413	V_{GS} = 0 V; Bias condition C; VDS = 80% of rated V_{DS} (preirradiation)	I_{DSS}					
2N7382					- 25		- 25	µA dc
2N7383					- 25		- 25	µA dc
Static drain to source on-state resistance	3421	V_{GS} = -12 V; Condition A; Pulsed see 4.5.1; $I_D = I_{D2}$	$r_{DS(ON)1}$					
2N7382					0.30		0.30	ohm
2N7383					0.80		0.80	ohm
Forward voltage source drain diode	4011	V_{GS} = 0 V; $I_D = I_{D1}$; Bias condition C	V_{SD}					
2N7382					-3.0		-3.0	V
2N7383					-5.0		-5.0	V

1/ For sampling plan see MIL-PRF-19500.
2/ Separate samples shall be pulled for each bias.
3/ Group D qualification may be performed anytime prior to lot formation. Wafers qualified to these group D QCI requirements may be used for any other detail specification utilizing the same die design.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

TABLE III. Group E inspection (all quality levels) for qualification only.

Inspection	MIL-STD-750		Qualification inspection
	Method	Conditions	
Subgroup 1			45 devices, c = 0
Temperature cycling	1051	Test condition G; 500 cycles	
Hermetic seal	1071		
Fine leak Gross leak			
Electrical measurements		See table I, group A, subgroup 2	
Subgroup 2 1/			45 devices, c = 0
Steady-state reverse bias	1042	Condition A; 1000 hours	
Electrical measurements		See table I, group A, subgroup 2	
Steady-state gate bias	1042	Condition B; 1,000 hours	
Electrical measurements		See table I, group A, subgroup 2	
Subgroup 3			
Not applicable			
Subgroup 4			5 devices, c = 0
Thermal resistance	3161	See 4.5.2	
Subgroup 5			
Not applicable			

1/ A separate sample for each test may be pulled.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.




FIGURE 2. Thermal response curves.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.




FIGURE 3. Safe operating area graphs.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.




FIGURE 4. Safe operating area graphs.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When actual packaging of material is to be performed by DoD personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Points' packaging activity within the Military Department or Defense Agency, or within the Military Departments' System Command. Packaging data retrieval is available from the managing Military Departments' or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

5.2 Marking. Unless otherwise specified (see 6.2), marking shall be in accordance with MIL-STD-129.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Notes. The notes specified in MIL-PRF-19500 are applicable to this specification.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Issue of DODISS to be cited in the solicitation.

b. Lead formation and finish as specified (see 3.3.1).

c. Product assurance level and type designator.

6.3 Supersession data. This specification supersedes DESC drawing 89009, dated 19 December 1989.

CONCLUDING MATERIAL

Custodians:
Army - CR
Navy - EC
Air Force - 17
NASA - NA

Review activities:
Army - AR, MI, SM
Navy - AS, CG, MC
Air Force - 13, 19, 85, 99

Preparing activity:
DLA - ES

(Project 5961-1833)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.

2. The submitter of this form must complete blocks 4, 5, 6, and 7.

3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	**1. DOCUMENT NUMBER** MIL-PRF-19500/615A	**2. DOCUMENT DATE (YYMMDD)** 96/05/03

3. DOCUMENT TITLE SEMICONDUCTOR DEVICE, FIELD EFFECT RADIATION HARDENED TRANSISTOR, P-CHANNEL, SILICON, TYPES 2N7382 AND 2N7383 JANTXV M, D AND R AND JANS M, D AND R

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME Alan Barone	b. TELEPHONE (Include Area Code) (1) Commercial 513-296-6048 (2) AUTOVON 986-6048
c. ADDRESS (Include Zip Code) Defense Electronics Supply Center ATTN: DESC-ELDT Dayton, OH 45444-5765	**IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT:** Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:12Z
Check the source to verify that this is the current version before use.