The documentation process conversion measures necessary to comply with this revision shall be completed by 22 August 2000.

INCH-POUND

MIL-PRF-19500/675
22 May 2000

PERFORMANCE SPECIFICATION

SEMICONDUCTOR DEVICE, FIELD EFFECT RADIATION HARDENED
(TOTAL DOSE AND SINGLE EVENT EFFECTS)
TRANSISTORS, N-CHANNEL, SILICON TYPES 2N7463T2 AND 2N7464T2 AND U5 SUFFIXES
JANTXVR AND JANSR

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the performance requirements for an N-channel, enhancement-mode, MOSFET, radiation hardened (total dose and Single Event Effects), power transistor. Two levels of product assurance are provided for each device type as specified in MIL-PRF-19500, with avalanche energy maximum rating (E_{AS}) and maximum avalanche current (I_{AS}).

1.2 Physical dimensions. See figure 1, TO-205AF and figure 2 (U5, LCC).

1.3 Maximum ratings. Unless otherwise specified, T_A = +25°C.

Type (4)	P_T (1) T_C = +25°C	P_T T_A = +25°C (free air)	V_{DS}	V_{DG}	V_{GS}	I_{D1} (2) T_C = +25°C	I_{D2} T_C = +100°C	I_S (2)	I_{DM} (3)	T_{op} and T_{STG}	V_{ISO} 70,000 foot altitude
	W	W	V dc	V dc	V dc	A dc	A dc	A dc	A(pk)	°C	V dc
2N7463	25	0.8	400	400	±20	3.0	1.9	3.0	12	-55 to	400
2N7464	25	0.8	500	500	±20	2.6	1.6	2.6	10.4	+150	500

(1) Derate linearly 0.2 W/°C for T_C > +25°C;

(2) $$I_D = \sqrt{\frac{T_J \max - T_C}{(R_{\Theta JC}) x (R_{DS_{on}} at\, T_{Jmax})}}$$

(3) I_{DM} = 4 X I_{D1} as calculated in footnote (2).

(4) Unless otherwise specified, electrical characteristics, ratings and conditions for “U5” suffix devices (surface mount LCC) are identical to the corresponding non “U5” suffix devices.


Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: (Defense Supply Center, Columbus, ATTN: DSCC/VAC, Post Office Box 3990, Columbus, OH 43216-5000), by using the addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 5961

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.


Dimensions				
Ltr	Inches		Millimeters	
	Min	Max	Min	Max
CD	.315	.355	8.01	9.01
CH	.160	.180	4.07	4.57
HD	.340	.370	8.64	9.39
LC	.200 BSC		5.08 BSC	
LD	.016	.021	0.41	0.53
LL	.500	.750	12.70	19.05
LU	.016	.019	0.41	0.48
L1	---	.050	---	1.27
L2	.250	---	6.35	---
P	.070	---	1.78	---
Q	---	.050	---	1.27
r	.009	.041	0.23	1.04
TL	.029	.045	0.74	1.14
TW	.028	.034	0.72	0.86
a	45°			



NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given in parentheses for general information only.
3. Lead number 1 is the source, lead number 2 is the gate, lead number 4 is omitted from this outline. The drain is number 3 and is electrically connected to the case.
4. In accordance with ANSI Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 1. Physical dimensions for TO-205AF (2N7463T2 and 2N7464T2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.



Dimensions				
Sym.	Inches		Millimeters	
	Min	Max	Min	Max
BL	.345	.360	8.77	9.14
BW	.280	.295	7.12	7.49
CH	.095	.115	2.42	2.92
LL1	.040	.055	1.02	1.39
LL2	.055	.065	1.40	1.65
LS	.050 BSC		1.27 BSC	
LS1	.025 BSC		0.635 BSC	
LS2	.008 BSC		0.203 BSC	
LW	.020	.030	0.51	0.76
Q1	.105 REF		2.67 REF	
Q2	.120 REF		3.05 REF	
Q3	.045	.055	1.15	1.39
TL	.070	.080	1.78	2.03
TW	.120	.130	3.05	3.30

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for general information only.
3. In accordance with ANSI Y14.5M, diameters are equivalent to ϕx symbology.

FIGURE 2. Physical dimensions for LCC (2N7463U5 and 2N7464U5).

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

1.4 Primary electrical characteristics at T_C = +25°C.

Type	Min $V_{(BR)DSS}$ V_{GS} = 0 I_D = 1.0 mA dc	$V_{GS(TH)}$ $V_{DS} \geq V_{GS}$ I_D = 1.0 mA dc		Max I_{DSS1} V_{GS} = 0 V_{DS} = 80 percent of rated V_{DS}	Max $r_{DS(ON)}$ (1) V_{GS} = 12 V dc		$R_{\theta JC}$ max	E_{AS} at I_{D1}	I_{AS}
					T_J = +25°C at I_{D2}	T_J = +150°C at I_{D2}			
	V dc	V dc		µA dc	ohm	ohm	°C/W	mJ	A
		Min	Max						
2N7463	400	2.5	4.5	50	1.2	2.7	5.0	140	3.0
2N7464	500	2.5	4.5	50	1.6	3.6	5.0	148	2.6

(1) Pulsed (see 4.5.1).

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements documents cited in sections 3 and 4 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DoDISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATION

DEPARTMENT OF DEFENSE

MIL-PRF-19500 - Semiconductor Devices, General Specification for.

STANDARD

DEPARTMENT OF DEFENSE

MIL-STD-750 - Test Methods for Semiconductor Devices.

(Unless otherwise indicated, copies of the above specifications, standards, and handbooks are available from the Document Automation and Production Services (DAPS), Building 4D (DPM-DODSSP), 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein (except for related associated specifications or specification sheets), the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 General. The requirements for acquiring the product described herein shall consist of this document and MIL-PRF-19500.

3.2 Qualification. Devices furnished under this specification shall be products that are manufactured by a manufacturer authorized by the qualifying activity for listing on the applicable qualified manufacturer's list (QML) before contract award (see 4.2 and 6.3).

3.3 Abbreviations, symbols, and definitions. Abbreviations, symbols, and definitions used herein shall be as specified in MIL-PRF-19500 and as follows.

I_{AS} - Rated avalanche current, nonrepetitive

3.4 Interface requirements and physical dimensions. The interface requirements and physical dimensions shall be as specified in MIL-PRF-19500 and on figures 1 (TO-205AF) and 2 (LCC) herein.

3.4.1 Lead finish. Unless otherwise specified, lead finish shall be solderable in accordance with MIL-PRF-19500, MIL-STD-750, and herein. Where a choice of lead finish is desired, it shall be specified in the acquisition document (see 6.2).

3.4.2 Internal construction. Multiple chip construction is not be permitted to meet the requirements of this specification.

3.5 Electrostatic discharge protection. The devices covered by this specification require electrostatic discharge protection.

3.5.1 Handling. MOS devices must be handled with certain precautions to avoid damage due to the accumulation of static charge. However, the following handling practices are recommended (see 3.5).

a. Devices should be handled on benches with conductive handling devices.
b. Ground test equipment, tools, and personnel handling devices.
c. Do not handle devices by the leads.
d. Store devices in conductive foam or carriers.
e. Avoid use of plastic, rubber, or silk in MOS areas.
f. Maintain relative humidity above 50 percent if practical.
g. Care should be exercised during test and troubleshooting to apply not more than maximum rated voltage to any lead.
h. Gate must be terminated to source, $R \leq 100$ k, whenever bias voltage is to be applied drain to source.

3.6 Electrical performance characteristics. Unless otherwise specified herein, the electrical performance characteristics are as specified in 1.3, 1.4, and table I herein.

3.7 Electrical test requirements. The electrical test requirements shall be group A as specified herein.

3.8 Marking. Marking shall be in accordance with MIL-PRF-19500.

3.9 Workmanship. Semiconductor devices shall be processed in such a manner as to be uniform in quality and shall be free from other defects that will affect life, serviceability, or appearance.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. Qualification inspection (see 4.2).
b. Screening (see 4.3)
c. Conformance inspection (see 4.4).

4.2 Qualification inspection. Qualification inspection shall be in accordance with MIL-PRF-19500.

4.2.1 Group E inspection. Group E inspection shall be conducted in accordance with MIL-PRF-19500 and table III herein. Endpoint electrical measurements shall be in accordance with the applicable tests of table I, group A, subgroup 2 herein.

4.2.1.1 Single Event Effects. Design capability shall be tested on the initial qualification and thereafter whenever a major die design or process change is introduced. Figure 3 illustrates the design safe operation area. End-point measurements shall be in accordance with table III.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

4.3 Screening (JANS and JANTXV levels only). Screening shall be in accordance with MIL-PRF-19500 (table IV), and as specified herein. The following measurements shall be made in accordance with table I herein. Devices that exceed the limits of table I herein shall not be acceptable.

Screen (see table IV of MIL-PRF-19500)	Measurement	
	JANS level	JANTXV level
(1)	Method 3470, E_{AS} (see 4.5.4)	Method 3470, E_{AS} (see 4.5.4)
3c (1)	Method 3161, thermal impedance (see 4.5.3)	Method 3161, thermal impedance (see 4.5.3)
(1)	Gate stress test (see 4.5.5)	Gate stress test (see 4.5.5)
9 (1)	Subgroup 2 of table I herein; I_{GSSF1}, I_{GSSR1}, I_{DSS1}	Not applicable
10	MIL-STD-750, method 1042, test condition B	MIL-STD-750, method 1042, test condition B
11	Subgroup 2 of table I herein; I_{GSSF1}, I_{GSSR1}, I_{DSS1}, $r_{DS(on)1}$, $V_{GS(TH)1}$ ΔI_{GSSF1} = ± 20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ± 20 nA dc or ± 100 percent of initial value, whichever is greater. ΔI_{DSS1} = ± 10 µA dc or ± 100 percent of initial value, whichever is greater.	Subgroup 2 of table I herein; I_{GSSF1}, I_{GSSR1}, I_{DSS1}, $r_{DS(on)1}$, $V_{GS(TH)1}$
12	MIL-STD-750, method 1042; test condition A	MIL-STD-750, method 1042; test condition A
13	Subgroups 2 and 3 of table I herein; ΔI_{GSSF1} = ± 20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ± 20 nA dc or ± 100 percent of initial value, whichever is greater. ΔI_{DSS1} = ± 10 µA dc or ± 100 percent of initial value, whichever is greater. $\Delta r_{DS(on)1}$ = ± 20 percent of initial value $\Delta V_{GS(TH)1}$ = ± 20 percent of initial value	Subgroups 2 and 3 of table I herein; ΔI_{GSSF1} = ± 20 nA dc or ±100 percent of initial value, whichever is greater. ΔI_{GSSR1} = ± 20 nA dc or ± 100 percent of initial value, whichever is greater. ΔI_{DSS1} = ± 10 µA dc or ± 100 percent of initial value, whichever is greater. $\Delta r_{DS(on)1}$ = ± 20 percent of initial value $\Delta V_{GS(TH)1}$ = ± 20 percent of initial value

(1) Shall be performed anytime before screen 10.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

4.4 Conformance inspection. Conformance inspection shall be in accordance with MIL-PRF-19500, and as specified herein. Alternate flow is allowed for quality conformance inspection in accordance with MIL-PRF-19500.

4.4.1 Group A inspection. Group A inspection shall be conducted in accordance with table V of MIL-PRF-19500. End-point electrical measurements shall be in accordance with table I, group A, subgroup 2 herein.

4.4.2 Group B inspection. Group B inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VIa (JANS) and table VIb (JANTX and JANTXV) of MIL-PRF-19500, and herein. Electrical measurements (endpoints) shall be in accordance with table I, group A, subgroup 2 herein.

4.4.2.1 Group B inspection, table VIa (JANS) of MIL-PRF-19500.

Subgroup	Method	Condition
B3	1051	Test condition G, 100 cycles.
B3	2075	See 3.4.2.
B3	2037	Test condition A, all internal wires for each device shall be pulled separately.
B3	2077	Scanning electron microscope (SEM) qualification may be performed anytime prior to lot formation.
B4	1042	Test condition D, 2,000 cycles. No heat sink nor forced-air cooling on the device shall be permitted during the on cycle. The heating cycle shall be 30 seconds minimum.
B5	1042	Test condition B, V_{GS} = rated T_A = +175°C, t = 24 hours.
B5	1042	Test condition A, V_{DS} = rated; T_A = +175°C; t = 120 hours.
B5	2037	Not applicable.
B6	3161	Not applicable.

4.4.2.2 Group B inspection, table VIb (JANTX and JANTXV) of MIL-PRF-19500.

Subgroup	Method	Condition
B2	1051	Test condition G, 25 cycles. (45 total, including 20 cycles performed in screening)
B3	1042	Test condition D, 2,000 cycles. No heat sink nor forced-air cooling on the device shall be permitted during the on cycle. The heating cycle shall be 30 seconds minimum.
B3	2037	Test condition A. All internal bond wires for each device shall be pulled separately.
B4	2075	See 3.4.2.
B4	2077	Not applicable.
B5 and B6		Not applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

4.4.3 Group C inspection. Group C inspection shall be conducted in accordance with the conditions specified for subgroup testing in table VII of MIL-PRF-19500 and as follows. Electrical measurements (end-points) shall be in accordance with the applicable of table I, group A, subgroup 2 herein.

Subgroup	Method	Condition
C2	1056	Test condition B.
C2	2036	Test condition E (applicable to TO - 205AF only).
C2	1021	Omit initial conditioning.
C5	3161	See 4.5.2
C6	1042	Test condition D, 6,000 cycles. . No heat sink nor forced-air cooling on the device shall be permitted during the on cycle. The heating cycle shall be 30 seconds minimum.
C6	2037	Test condition A. All internal bond wires for each device shall be pulled separately. (Wire bond pull test performed if devices continued from Group B)
C7	1018	No pre-bake required.

4.4.4 Group D Inspection. Group D inspection shall be conducted in accordance with table VIII of MIL-PRF-19500 and table II herein.

4.5 Methods of inspection. Methods of inspection shall be as specified in the appropriate tables and as follows.

4.5.1 Pulse measurements. Conditions for pulse measurement shall be as specified in section 4 of MIL-STD-750.

4.5.2 Thermal resistance. Thermal resistance measurements shall be performed in accordance with method 3161 of MIL-STD-750. The maximum limit of $R_{\theta JC(max)}$ = 5.0°C/W. The following parameter measurements shall apply:

a. Measuring current (I_M) ..... 10 mA.
b. Drain heating current (I_H) ..... 1 A (1.3 A minimum for LCC).
c. Heating time (t_H) ..... Steady-state (see MIL-STD-750, method 3161 for definition).
d. Drain-source heating voltage (V_H) ..... 25 V (15 V for LCC).
e. Measurement time delay (t_{MD}) ..... 30 µs to 60 µs.
f. Sample window time (t_{SW}) ..... 10 µs maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

4.5.3 Thermal impedance ($Z_{\theta JC}$ measurements). The $Z_{\theta JC}$ measurements shall be performed in accordance with MIL-STD-750, method 3161. The maximum limit (not to exceed figure 4, thermal impedance curves and the group A, subgroup 2 limits) for $Z_{\theta JC}$ in screening (table IV of MIL-PRF-19500) shall be derived by each vendor by means of statistical process control. When the process has exhibited control and capability, the capability data shall be used to establish the fixed screening limit. In addition to screening, once a fixed limit has been established, monitor all future sealing lots using a random five piece sample from each lot to be plotted on the applicable X, R chart. If a lot exhibits an out of control condition, the entire lot shall be removed from the line and held for Engineering evaluation and disposition. This procedure may be used in lieu of an in line procedure.

a. Measuring current (I_M) ..... 10 mA.
b. Drain heating current (I_H) ..... 1 A minimum (1.3 A minimum for LCC).
c. Heating time (t_H) ..... 10 ms.
d. Drain-source heating voltage (V_H)- ..... 25 V (15 V for LCC).
e. Measurement time delay (t_{MD}) ..... 30 µs to 60 µs.
f. Sample window time (t_{SW}) ..... 10 µs maximum.

4.5.4 Single pulse avalanche energy (E_{AS}).

a. Peak current (I_{AS}). ..... I_{AS}(max)
b. Peak gate voltage (V_{GS})- ..... 12 V.
c. Gate to source resistor (R_{GS}) ..... $25\Omega \leq R_{GS} \leq 200\Omega$.
d. Initial case temperature (T_C) ..... +25°C +10°C, -5°C.
e. Inductance (L) ..... $\left[\frac{2E_{AS}}{(I_{DI})^2}\right]\frac{[(V_{BR} - V_{DD})]}{V_{BR}}$ *mH minimum*
f. Number of pulses to be applied ..... 1 pulse minimum.
g. Supply voltage (V_{DD}) ..... 50 V

4.5.5 Gate stress test.

a. V_{GS} = 30 V minimum.
b. t = 250 µs minimum

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 1						
Visual and mechanical inspection	2071					
Subgroup 2						
Thermal impedance 2/	3161	See 4.5.3	$Z_{\theta JC}$		1.40	°C/W
Breakdown voltage, drain to source	3407	V_{GS} = 0 V dc, I_D = 1 mA dc, bias condition C	$V_{(BR)DSS}$			
2N7463				400		v dc
2N7464				500		V dc
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$ I_D = 1 mA dc	$V_{GS(TH)1}$	2.5	4.5	V dc
Gate current	3411	V_{GS} = +20 V dc and -20 V dc, bias condition C, V_{DS} = 0	I_{GSS1}		±100	nA dc
Drain current	3413	V_{GS} = 0 V dc, bias condition C, V_{DS} = 80 percent of rated V_{DS}	I_{DSS1}		50	µA dc
Static drain to source on-state resistance	3421	V_{GS} = 12 V dc, condition A, pulsed (see 4.5.1), I_D = I_{D2}	$r_{DS(on)1}$			
2N7463					1.2	Ω
2N7464					1.6	Ω
Static drain to source on-state resistance	3421	V_{GS} = 12 V dc, condition A, pulsed (see 4.5.1), I_D = I_{D1}	$r_{DS(on)2}$			
2N7463					1.22	Ω
2N7464					1.62	Ω
Forward voltage	4011	Pulsed (see 4.5.1), I_D = I_{D1}, V_{GS} = 0 V dc	V_{SD}			
2N7463					1.4	V
2N7464					1.4	V

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 3						
High-temperature operation:		$T_C = T_J = +125°C$				
Gate current	3411	V_{GS} = +20 V dc and -20 V dc, bias condition C, V_{DS} = 0	I_{GSS2}		±200	nA dc
Drain current	3413	V_{GS} = 0 V dc, bi\as condition C, V_{DS} = 100 percent of rated V_{DS}	I_{DSS2}		1.0	mA dc
Drain current	3413	V_{GS} = 0 V dc, bias condition C, V_{DS} = 80 percent of rated V_{DS}	I_{DSS3}		0.25	mA dc
Static drain to source on-state resistance	3421	V_{GS} = 12 V dc, pulsed (see 4.5.1), $I_D = I_{D2}$	$r_{DS(on)3}$			
2N7463					2.4	Ω
2N7464					3.12	Ω
Gate to source voltage (thresholds)	3403	$V_{DS} \geq V_{GS}$, I_D = 1 mA dc	$V_{GS(TH)2}$	1.5		V dc
Low-temperature operation:		$T_C = T_J = -55°C$				
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$, I_D = 1 mA dc	$V_{GS(TH)3}$		5.5	V dc
Subgroup 4						
Forward transconductance	3475	I_D = rated I_{D2}, V_{DD} = 15 V (see 4.5.1)	g_{FS}			
2N7463				1.3		S
2N7464				1.2		S
Switching time test	3472	$I_D = I_{D1}$, V_{GS}= 12 V dc, R_G = 7.5Ω, V_{DD} = 50 percent of rated V_{DS}				
Turn-on delay time			$t_{d(on)}$			
2N7463					35	ns
2N7464					20	ns

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 4 - Continued						
Rise time			t_r			
2N7463					62	ns
2N7464					27	ns
Turn-off delay time			$t_{d(off)}$			
2N7463					58	ns
2N7464					65	ns
Fall time			t_f			
2N7463					58	ns
2N7464					45	ns
Subgroup 5						
Safe operating area test (high voltage)	3474	See figures 5 and 6; t_p = 10 ms V_{DS} = 200 V				
Electrical measurements		See table I, subgroup 2 herein.				
Subgroup 6						
Not applicable						
Subgroup 7						
Gate charge	3471	Condition B	$Q_{G(on)}$			
On-state gate charge						
2N7463					41	nC
2N7464					30	nC
Gate to source charge			Q_{GS}			
2N7463					7	nC
2N7464					7	nC

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

TABLE I. Group A inspection - Continued.

Inspection 1/	MIL-STD-750		Symbol	Limits		Unit
	Method	Conditions		Min	Max	
Subgroup 7 - Continued						
Gate to drain charge			Q_{GD}			
2N7463					20	nC
2N7464					18	nC
Reverse recovery time	3473	$d_i/ d_t \leq 100$ A/µs, $V_{DD} \leq 50$ V, $I_D = I_{D1}$	t_{rr}			
2N7463					516	ns
2N7464					600	ns

1/ For sampling plan, see MIL-PRF-19500.
2/ This test is required for the following endpoint measurements only (not intended for screen 13):
group B, subgroups 3 and 4 (JANS) or group B, subgroups 2 and 3 (JANTXV);
group C, subgroup 6;
group E, subgroup 1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

TABLE II. Group D inspection.

Inspection 1/, 2/, 3/	MIL-STD-750		Symbol	Preirradiation limits		Postirradiation limits		Unit
	Method	Conditions		R		R		
				Min	Max	Min	Max	
Subgroup 1								
Not applicable								
Subgroup 2		T_C = +25°C						
Steady-state total dose irradiation (V_{GS} bias) 4/	1019	V_{GS} = 12V V_{DS} = 0						
Steady-state total dose irradiation (V_{DS} bias) 4/	1019	V_{GS} = 0 V_{DS} = 80% of rated V_{DS} (pre-irradiation)						
End-point electricals		See table I, subgroup 2 herein.						
Breakdown voltage, drain to source	3407	V_{GS} = 0 I_D = 1 mA Bias Cond. C	$V_{(BR)DSS}$					
2N7463				400		400		V dc
2N7464				500		500		V dc
Gate to source voltage (threshold)	3403	$V_{DS} \geq V_{GS}$	V_{GSth1}					
2N7463				2.5	4.5	2.0	4.5	V dc
2N7464				2.5	4.5	2.0	4.5	V dc
Gate current	3411	V_{GS} = 20 V V_{DS} = 0 Bias Cond. C	I_{GSSF1}		100		100	nA dc
Gate current	3411	V_{GS} = -20 V V_{DS} = 0 Bias Cond. C	I_{GSSR1}		-100		-100	nA dc
Drain current	3413	V_{GS} = 0 Bias Cond. C V_{DS} = 80% of rated V_{DS} (pre-irradiation)	I_{DSS1}		50		50	µA dc

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

TABLE II. Group D inspection - Continued.

Inspection 1/ 2/ 3/	MIL-STD-750		Symbol	Preirradiation limits		Postirradiation limits		Unit
	Method	Conditions		R		R		
				Min	Max	Min	Max	
Static drain to source on-state voltage	3405	V_{GS} = 12 V Cond. A pulsed (see 4.5.1) $I_D = I_{D2}$	V_{DSon1}					
2N7463					2.28		2.28	V dc
2N7464					2.56		2.56	V dc
Forward voltage source to drain diode	4011	V_{GS} = 0 $I_D = I_{D1}$	V_{SD}					
2N7463					1.4		1.4	V dc
2N7464					1.4		1.4	V dc

1/ For sampling plan, see MIL-PRF-19500.
2/ Group D qualification may be performed anytime prior to lot formation. Wafers qualified to these group D QCI requirements may be used for any other detail specification utilizing the same die design.
3/ At the manufacturer's option, group D samples need not be subjected to the screening tests, and may be assembled in it's qualified package or in any qualified package that the manufacturer has data to correlate the performance to the designated package.
4/ Separate samples shall be pulled for each bias.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

TABLE III. Group E inspection (all quality levels) for qualification only.

Inspection	MIL-STD-750		Qualification and large lot quality conformance inspection
	Method	Conditions	
Subgroup 1			12 devices c = 0
Thermal shock (temperature cycling)	1051	Test condition G, 500 cycles	
Hermetic seal	1071		
Fine leak Gross leak			
Electrical measurements		See table I, group A, subgroup 2	
Subgroup 2 1/			12 devices c = 0
Steady-state reverse bias	1042	Condition B, 1,000 hours	
Electrical measurements		See table I, group A, subgroup 2	
Steady-state gate bias	1042	Condition A, 1,000 hours	
Electrical measurements		See table I, group A, subgroup 2	
Subgroup 3			
Not applicable			
Subgroup 4			22 devices c = 0
Thermal resistance	3161	$R_{\theta JC}$ = 5.0 °C/W maximum. See 4.5.2	
Subgroup 5			15 devices c = 0
Reduced Barometric Pressure	1001	V_{DS} = rated $V_{(BR)DSS}$, $I_{(ISO)}$ < 0.25 mA	
Subgroup 6			3 devices
ESD	1020		
Electrical measurements		See table I, group A, subgroup 2	

See footnotes at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

TABLE III. Group E inspection (all quality levels) for qualification only. - Continued

Inspection	MIL-STD-750		Qualification and large lot quality conformance inspection
	Method	Conditions	
Subgroup 7			3 devices
Single Event Effects (SEE) 2/ 3/ 4/	1080		
Electrical measurements 5/		I_{GSS1} and I_{DSS1} per table I, group A, subgroup 2	
SEE Irradiation		Fluence = 3E5 ± 20% ions/cm^2 Flux = 2E3 to 2E4 ions/cm^2/sec Temperature = +25 ± 5°C	
2N7463		LET = 28 MeV-cm^2/mg Range = 43 microns Energy = 285 MeV Insitu bias conditions: V_{DS} = 325V & V_{GS} = -15V LET = 37 MeV-cm^2/mg Range = 39 microns Energy = 305 MeV Insitu bias conditions: V_{DS} = 325V & V_{GS} = -10V V_{DS} = 275V & V_{GS} = -15V	
2N7464		LET = 28 MeV-cm^2/mg Range = 43 microns Energy = 285 MeV Insitu bias conditions: V_{DS} = 375V & V_{GS} = -20V LET = 37 MeV-cm^2/mg Range = 39 microns Energy = 305 MeV Insitu bias conditions: V_{DS} = 350V & V_{GS} = -10V V_{DS} = 325V & V_{GS} = -15V V_{DS} = 300V & V_{GS} = -20V	
Electrical measurements 2/		I_{GSS1} and I_{DSS1} per table I, group A, subgroup 2	

1/ A separate sample for each test shall be pulled.
2/ Group E qualification of single event effect testing may be performed prior to lot formation. Qualification may be extended to other performance specifications utilizing the same structurally identical die design.
3/ Device qualification to a higher level LET is sufficient to qualify all lower level LET's.
4/ The sampling plan applies to each bias condition.
5/ Examine I_{GSS1} and I_{DSS1} before and following SEE irradiation to determine acceptability for each bias condition. Other test conditions per table I, group A, subgroup 2, may be performed at the manufacturer's option.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.




FIGURE 3. SEE Safe Operation Area Graph.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.




FIGURE 4. Thermal impedance curves.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.




FIGURE 5. Safe operating area graph.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.




FIGURE 6. Safe operating area graph.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packaging. Packaging shall prevent mechanical damage of the devices during shipping and handling and shall not be detrimental to the device. When actual packaging of material is to be performed by DoD personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Points' packaging activity within the Military Department or Defense Agency, or within the Military Departments' System Command. Packaging data retrieval is available from the managing Military Departments' or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The notes specified in MIL-PRF-19500 are applicable to this specification.

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Issue of DODISS to be cited in the solicitation and, if required, the specific issue of individual documents referenced (see 2.2.1).

b. Lead finish (see 3.4.1).

c. Type designation and product assurance level.

d. Packaging requirements (see 5.1).

6.3 Qualification. With respect to products requiring qualification, awards will be made only for products which are, at the time of award of contract, qualified for inclusion in Qualified Manufacturers List QML No.19500 whether or not such products have actually been so listed by that date. The attention of the contractors is called to these requirements, and manufacturers are urged to arrange to have the products that they propose to offer to the Federal Government tested for qualification in order that they may be eligible to be awarded contracts or purchase orders for the products covered by this specification. Information pertaining to qualification of products may be obtained from Defense Supply Center Columbus, ATTN: DSCC-VQE, 3990 East Broad Street, Columbus, OH 43216-5000.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

6.4 Substitution information. Devices covered by this specification are substitutable for the manufacturer's and user's Part or Identifying Number (PIN). This information in no way implies that manufacturer's PIN's are suitable for the military PIN.

Preferred types	Commercial types	
	TO-205AF	LCC
2N7463T2, U5 2N7464T2, U5	IRHF7330SE IRHF7430SE	IRHE7330SE IRHE7430SE

Custodians:
Army - CR
Navy - EC
Air Force - 11
NASA - NA
DLA - CC

Preparing activity:
DLA - CC

(Project 5961-2264)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.

2. The submitter of this form must complete blocks 4, 5, 6, and 7.

3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-PRF-19500/675	2. DOCUMENT DATE 22 May 2000

3. **DOCUMENT TITLE** SEMICONDUCTOR DEVICE, FIELD EFFECT RADIATION HARDENED (TOTAL DOSE AND SINGLE EVENT EFFECTS) TRANSISTORS, N-CHANNEL, SILICON TYPES 2N7463T2 AND 2N7464T2 AND U3 SUFFIXES JANTXVR AND JANSR

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) COMMERCIAL DSN FAX EMAIL	7. DATE SUBMITTED

8. PREPARING ACTIVITY

a. Point of Contact Alan Barone	b. TELEPHONE Commercial 614-692-0510 DSN 850-0510 FAX 614-692-6939 EMAIL alan_barone@dscc.dla.mil
c. ADDRESS Defense Supply Center Columbus, ATTN: DSCC-VAC, 3990 East Broad Street, Columbus, OH 43213-1199	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Standardization Program Office (DLSC-LM) 8725 John J. Kingman, Suite 2533, Fort Belvoir, VA 22060-6221 Telephone (703) 767-6888 DSN 427-6888

DD Form 1426, Feb 1999 (EG) Previous editions are obsolete WHS/DIOR, Feb 99

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T04:42Z
Check the source to verify that this is the current version before use.