INCH-POUND
A-A-52095C
5 August 2019
SUPERSEDING
A-A-52095B
May 2, 2008

COMMERCIAL ITEM DESCRIPTION

THREAD, POLYESTER TEXTURED

The General Services Administration has authorized the use of this Commercial Item Description by all federal agencies.

1. SCOPE. This Commercial Item Description (CID) covers the requirements for textured polyester thread used for sewing various clothing, footwear and equipage items.

2. CLASSIFICATION. The textured polyester thread will be available in one type and in the following sizes. Tex size is determined by the weight, in grams, of 1,000 meters of the thread.

2.1 Sizes.

Tex
18
24
35
45
50
70
105

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data that may improve this document should be sent to: DLA Troop Support Standardization Team, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Since contact information can change, verify the currency of the address information using Acquisition Streamlining and Standardization Information System (ASSIST) online database https://assist.dla.mil.

AMSC N/A FSC 8310

DISTRIBUTION STATEMENT A. Approved for public release, distribution unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

3. SALIENT CHARACTERISTICS.

3.1 General description. The thread shall be a textured continuous multifilament polyester strand.

3.2 Physical characteristics and requirements. The thread shall conform to the physical characteristics specified in Table I, when tested as specified in Table II.

TABLE I. Physical characteristics.

Tex 1/	Breaking strength, lbs. (min)	Elongation, % (max)
18	1.4	35
24	1.9	35
35	2.5	35
45	3.2	35
50	3.9	35
70	5.8	35
105	6.9	35

1/ Tex size based on weight in grams/1,0000 meters of thread.

TABLE II. Requirements and test methods.

Characteristic	Requirement	Test method
Fiber Identification	Polyester	AATCC 20 (see 7.4)
Twists per inch (min.)	1.5	ASTM D204
Tex Size	Table I	ASTM D204
Breaking Strength	Table I	ASTM D204 1/ 2/
Elongation	Table I	ASTM D204 1/ 2/
Colorfastness:		
Crocking (min.)	3.5	AATCC 8 3/
Laundering (after 3 cycles) (min.)	3-4	AATCC 61 Test 3A 4/, 5/
Wet dry-cleaning (min.)	3-4	AATCC-132 4/, 6/

1/ Testing speed shall be 12 (±5.0) in./min., and a 10 (±0.1) inch gauge length shall be used.
2/ Five determinations per sample unit.
3/ AATCC Evaluation Procedure 8, AATCC 9- Step Chromatic Transference Scale
4/ AATCC Evaluation Procedure 1, Gray Scale for Color Change
5/ The color transfer cloth evaluation shall not apply.
6/ AATCC Evaluation Procedure 2, Gray Scale for Staining

3.3 Color. Unless otherwise specified in the applicable end item specification or in the contract purchase order, the thread shall be a good match to the applicable approved shade standard (see 7.6) when examined in accordance with paragraph 3.3.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

3.3.1 Visual shade matching. The color and appearance of the finished thread shall match the standard sample when viewed using AATCC Evaluation Procedure 9, Option A (2012), with sources stimulating artificial daylight D75 illuminant with a color temperature of 7500 K (±200), with illumination of 100 (±20) foot candles, and shall be a good match to the standard sample under incandescent A illuminant with a color temperature of 2856K (±200).

3.4 Finishing materials. The finished thread shall have no chemical finishes or treatments other than those, such as a water-repellent finish, commonly used on commercial threads which have been demonstrated to have no deleterious effects on the fiber, including effects of prolonged storage. No finish or treatment shall be applied for the purpose of increasing breaking strength. There shall be no noticeable wicking of the treatment on the thread to adjacent material when sewn.

3.5 Toxicity. The finished thread shall not present a health hazard and shall show compatibility with prolonged, direct skin contact when tested as specified in 3.5.1. Chemicals recognized by the Environmental Protection Agency (EPA) as human carcinogens shall not be used.

3.5.1 Toxicity test. When required (see 7.5), an acute dermal irritation study and a skin sensitization study shall be conducted. When the results of the studies indicate the thread is not a sensitizer or irritant, a Repeat Insult Patch Test shall be performed in accordance with the Modified Draize Procedure. (See 7.2.4) If the toxicity requirement (see 3.5) can be demonstrated with historical use data, toxicity testing may not be required.

3.6 Put-up. Unless otherwise specified, the thread shall be put-up on holders such as commercial spools, cones, or tubes as specified in the contract. The thread shall be wound around the specified holder in one continuous piece, so that each turn and layer is free of entanglement. The outside ending of the thread shall be secured to prevent unwinding, loosening, or slippage during handling, shipping, or storage.

3.7 Labeling. Each holder shall have a label, adhered securely so as to remain in place and be clearly legible until all thread has been removed. The label shall be printed and include information related to twists per inch, color, Tex size, name of thread manufacturer, weight, and nomenclature specifying fiber and construction type.

3.8 Workmanship. The finished thread shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the contractor's own quality assurance standards and the quality assurance standards defined by the technical data in the bid package.

4. REGULATORY REQUIREMENTS. The offeror/contractor is encouraged to use recovered, recycled, biobased, and environmentally preferable materials to the maximum extent practicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

5. PRODUCT CONFORMANCE PROVISIONS.

5.1 Product Conformance. The finished thread shall meet the salient characteristics of this Commercial Item Description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance.

5.2 Market acceptance. The thread must have been sold to the government or commercial market.

5.3 End item inspection procedures. Sampling for inspection shall be conducted in accordance with ANSI/ASQ Z1.4 - Sampling Procedures and Tables for Inspection of Attributes (see 7.2.3).

5.4 Acceptance criteria. Acceptance criteria shall be as specified in the contract or purchase order (see 7.5).

6. PACKAGING.

6.1 Packaging. Preservation, packing, and marking shall be specified in the contract or purchase order (see 7.5).

7. NOTES.

7.1 Sources of Government documents. N/A

7.2 Sources of Non-Government documents.

7.2.1 AATCC test methods are available online at https://www.aatcc.org.

7.2.2 ASTM Standards are available online at https://www.astm.org.

7.2.3 ASQ/ANSI Z1.4 – Sampling Procedures and Tables for Inspection of Attributes are available online at https://www.asq.org.

7.2.4 Principles and Methods of Toxicology, A Wallace Hayes (editor) are available online from https://www.crcpress.com/.

7.3 Intended use. This thread is intended to be used on stretchable clothing and individual equipment items.

7.4 Certificate of compliance. The contracting activity may select to accept a certificate of compliance for stated requirement.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

7.5 Ordering data. The contract or purchase order should specify the following:

a. Title, number, and date of this Commercial Item Description
b. Tex size of thread required (see 2.1)
c. Color required (see 3.3)
d. When toxicity testing is required (see 3.5)
e. Put-up required (see 3.6)
f. Labeling information (see 3.7)
g. Product conformance provisions (see 5.1)
h. Acceptance criteria (see 5.4)
i. Packaging requirements (see 6.1)

7.6 Standard sample. For access to samples address the contracting activity issuing the invitation for bids or request for proposal.

7.7 Key words.

Clothing
Machine, Sewing
Stretchable

MILITARY INTERESTS:

Custodians:
Army – GL
Navy – NU
Air Force – 11

Review Activities:
Army – MD
Navy – MC, CG1

CIVIL AGENCY COORDINATING ACTIVITY:

GSA – FAS

Preparing Activity:
DLA- CT

(Project: 8310-2019-007)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.