INCH-POUND

A-A-52096
March 26, 1991

COMMERCIAL ITEM DESCRIPTION

CLOTH, PRESSING, NYLON

The General Services Administration has authorized the use of this commercial item description in preference to CCC-C-482.

Abstract. This commercial item description covers nylon cloth intended for use in the fabrication of covers for flat bed laundry presses.

1. CLASSIFICATION

1.1 Classification. The cloth shall be of the following types as specified (see 5.1).

Type I - Spun warp and filling yarn, plain weave
Type II - Filament warp yarn and spun filling yarn, twill weave

2. SALIENT CHARACTERISTICS

2.1 General description. The type I cloth shall be woven from spun nylon warp and filling yarns. The type II cloth shall be woven from multifilament nylon warp yarns and spun nylon filling yarns. The yarns for the type I and II cloth shall be a polyamide prepared from hexamethylene diamine and adipic acid. The spun yarn for both types I and II shall be twisted into 2-ply. The weave for the type I cloth shall be plain and for the type II cloth shall be a 2 up-1 down right hand twill. The width shall be as specified (see 5.1) and shall be the minimum acceptable width inclusive of the selvage when fly-shuttle looms or shuttleless looms with tuck-in selvages are used. For all other shuttleless looms the width measurement shall be made between the last warp yarn on each side excluding the protruding fringe(s). The color of the finished cloth shall be natural. The cloth shall be heat treated to a 380°F minimum and if necessary given an additional heat treatment to increase heat resistant properties as well as to stabilize the cloth to a maximum 3.0 percent shrinkage or elongation in either fabric direction.

Beneficial comments, recommendations, additions, deletions, clarifications, etc., and any other data which may improve this document should be sent to: Commander, U.S. Army Natick Research, Development, and Engineering Center, ATTN: STRNC-IRT, Natick, MA 01760-5019.

AMSC N/A FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

2.2 Physical requirements. The finished cloth shall conform to the requirements listed in table I.

TABLE I. Physical requirements

Characteristic	Requirements Type I	Type II	Test method 1/
Material identification	Nylon	Nylon	1530
Weight, oz./sq.yd. (min)	7.0	5.6	5041
Yarns per inch (min):			
Warp	38	66	5050
Filling	36	54	5050
Breaking strength, lbs. (min):			
Initial:			
Warp	210	280	5100
Filling	200	240	5100
After accelerated aging:			
Warp	105	140	5850 2/
Filling	100	120	5850 2/
Adherence (max)	None	None	3/

1/ The test methods indicated, from FED-STD-191 Textile Test Methods, have been found acceptable to determine whether the cloth meets the stated requirements. If the government requires proof that the cloth meets the stated requirements, the test methods indicated shall be used.

2/ Except that five specimens from each of the warp and filling directions shall be tested and conditioned at 384 ± 4°F for 5 hours. After removal from the oven, the specimens may be tested as soon as they have reached moisture equilibrum with testing environment atmospheric conditions (temperature and humidity).

3/ Adherence test method. A sample of finished cloth 5 ± 0.5 inches square shall be placed on a flat surface. A heated hand iron, without any anti-stick agent treatment, weighing 4 to 5 pounds, with a temperature of 325°F to 355°F shall be placed on top of the sample for 60 seconds. After 60 seconds, the iron shall be lifted and observed for adherence of the specimen to the iron surface. The test is considered a failure if the specimen adheres to the iron when the iron is lifted off the flat surface.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

2.3 Length and put-up. For Government procurements only, unless otherwise specified (see 5.1), the cloth shall be furnished in continuous lengths of not less than 50 yards and shall be put-up full width on rolls as specified in 4.1.

3. QUALITY ASSURANCE

3.1 Certification. The contractor shall certify, and maintain substantiating evidence that the product offered meets the salient characteristics and requirements of this Commercial Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

3.2 Visual examination. Lots of cloth shall be inspected in accordance with MIL-STD-105. The inspection level shall be I and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 4.0. The lot size shall be expressed in units of yards. The sample unit shall be one linear yard. The cloth shall be examined for the following defects: hole, cut, tear, smash, knot, missing end or pick, permanent crease or wrinkle, area of no finish, baggy or ridgy, objectionable odor or overall uncleanness.

3.3 Length examination. During the visual examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than 2 yards less than the length marked on the roll ticket shall be considered a length defect. If two or more rolls in the sample are defective with respect to length or if the total of the actual lengths of rolls in the sample is less than the total of lengths marked on the roll tickets, the lot shall be rejected.

3.4 Regulatory requirements. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practicable.

4. PACKAGING

4.1 Packaging. The cloth shall be rolled on a convolute or spiral-wound chipboard tube. The tube shall have a smooth finish surface that will prevent the fibers of the chipboard from transferring to the cloth. Each roll of cloth, put-up as specified, shall be wrapped with 60-pound minimum basis weight kraft paper in such a way that the paper shall encircle the roll at least once with a minimum overlap of 3 inches, and the width of the paper shall be sufficient to fold over and protect the ends of the roll. Gummed paper tape, with a minimum width of 2-1/2 inches shall be applied to the overlap seam the full length of the roll and across each end. Alternately, each roll of cloth shall be enclosed in a polyethylene film tube and the tube secured at both ends by heat sealing or mechanical ties.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

4.2 Packing. Each wrapped roll shall be enclosed in bias-sewn tubing made from woven plypropylene cloth. The tube shall be secured by heat-sealing, by means of a mechanical tie, or by plastic ties with lock-end. Alternately, a maximum of 325 pounds of rolls of kraft-wrapped cloth shall be packed in a snug-fitting double-walled fiberboard container known as a double cover, and shall consist of a body or joined liner and two covers. Corrugated fiberboard with a minimum bursting strength of 500 pounds shall be used. The container shall be strapped with metallic straps not less than 1/2 by 0.020 inch or non-metallic straps not less than 7/16 by 0.030 inch.

4.3 Marking. In addition to any special markings required by the contract or purchase order, rolls and shipping containers shall be marked in accordance with MIL-STD-129. Each roll shall have a piece ticket (identification tag) affixed with a 5-ply minimum cotton string or a plastic tag hanger. The tag shall have a reinforced eyelet and shall be legibly printed, using water insoluble ink, with the following information:

Procurement Agency	Contract or Purchase Order Number
National Stock Number	Finish or Greige Mill
Item Description	Roll Number
Contractor	Lot Number
Width	Piece Number
Fiber Content	Yardage

5. NOTES

5.1 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number and date of this document.
b. Type required (see 1.1).
c. Width of cloth required (see 2.1).
d. Length and put-up if other than specified (see 2.3).

5.2 Sources of documents.

5.2.1 Source of government documents. Copies of Military and Federal documents are available from:

Standardization Documents Order Desk
Building 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

Custodians

Army - GL
Air Force - 99

Review Activities

Army - MD
Air Force - 82
DLA - CT

CIVIL AGENCY COORDINATING ACTIVITY:

GSA - GSS
USDA - AFS

PREPARING ACTIVITY:

Army - GL

Project 8305-0372

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.