INCH-POUND

A-A-52099
MARCH 29, 1991

COMMERCIAL ITEM DESCRIPTION

CLOTH, BIRDSEYE AND GAUZE, COTTON

The General Service Administration has authorized the use of this commercial item description in preference to Federal Specification CCC-C-425.

Abstract. This commercial item description covers cotton birdseye cloth (type I, class 1) and gauze (type II) intended for use in the fabrication of infant diapers. The class 2 and class 3 cloth is intended for use in the fabrication of cooling, toxicological agents protective, and rocket fuel handlers coveralls.

1. CLASSIFICATION

1.1 Classification. The cloth shall be of the following types and classes as specified (see 5.1).

Type I	-	Birdseye
Class 1	-	Diaper cloth (bleached)
Class 2	-	Coverall cloth (bleached)
Class 3	-	Coverall cloth (dyed)
Type II	-	Gauze - double layer (bleached)

2. Salient characteristics.

Beneficial comments, recommendations, additions, deletions, clarifications, etc., and any other data which may improve this document should be sent to: Commander, U.S. Army Natick Research, Development, and Engineering Center, ATTN: STRNC-IRT, Natick, MA 01760-5019.

AMSC N/A FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

2.1 General description. The yarn used for both type I and type II cloth shall be cotton that has been carded, drawn, and spun. The type I classes 1, 2, and 3 cloth shall be single layer in a birdseye weave. The type II cloth shall be a double layer woven in a plain interlocking type weave. The combining, or interlocking of the double layer to form a single layer shall be throughout the length of the cloth and at regular intervals filling-wise to form pinking bars. The panels of 2-ply cloth formed by the pinking bars shall measure 19 ± 1/2 inch in length from the inside of pinking bar to inside of pinking bar. Optional folding stripes may be included. If used, one stripe consisting of four ends weaving as one in a group of 3 or 4 shall be positioned 13 1/2 ± 1/2 inch from one selvage. A second stripe shall be positioned 8 ± 1/2 inch from the opposite selvage. The folding bar shall become part of the single layer pinking bars at point of intersection. Pieces of type II cloth shall begin and end with a pinked edge located in the middle of a pinking bar. No additive finishes shall be applied to either type and the charactor of the finished cloth shall be equal to that of the standard sample. The color of the finished cloth shall be bleached or dyed as specified. When dyed cloth is specified (see 5.1), the use of dyes or substances containing elementary sulfur compounds capable of oxidation to sulfuric acid is prohibited. The color shall match the available standard sample under artificial daylight and shall have a correlated color temperature of 7500 ± 200K with an illumination of 100 ± 20 foot candles and shall be a good match to the standard sample under incandescent lamplight at 2300 ± 200K.

2.2. Physical requirements. The finished cloth shall conform to the requirements specified in Table I.

Table I. Physical requirements

Characteristic	Type I Class 1	Type I 2	Type I 3	Type II	Test method 1/ FED-STD-191
Weight, oz/sq yd					
min	4.0	3.4	3.7	3.2	5041
max	---	3.8	4.2	---	5041
Width, inches (including selvage)					
min	26-1/2	---	---	38-1/2	---
max	27-1/2	---	---	40-1/2	---
Yarns, per inch (minimum)					
warp	60	60	60	---	5050
filling	43	46	46	---	5050
sum of warp and filling	---	---	---	74 2/	---

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

Table I. Physical requirements (cont'd)

Characteristic	Type I Class 1	Type I 2	Type I 3	Type II	Test method 1/ FED-STD-191
Breaking strength (pounds minimum)					
warp	40	40	40	45 3/	5100
filling	50	50	50	25 3/	5100
Discoloration	fair	fair	---	fair	5660 4/
Presence of labile sulfur	---	---	slight	---	2020
Colorfastness to					
laundering (3 cycles)	---	---	good	---	5610 5/
perspiration	---	---	good	---	5680
light	---	---	good	---	5680
crocking	---	---	3.5 6/	---	5651
Shrinkage in laundering (percent maximum)	20	2	2	20	5550 7/
Absorbency (percent minimum)	60	65	65	60	5502
Nonfibrous materials (percent maximum)	2	2	2	2	2611
pH					
min	5.5	5.5	5.5	5.5	2811
max	9.5	9.5	9.5	9.5	2811

1/ The test methods indicated, from FED-STD-191 Textile Test Methods, have been found acceptable to determine if the cloth meets the stated requirements. If the Government requires proof that the cloth meets the stated requirements, the test methods indicated shall be used.

2/ Determined on single ply of panel, but both single panels shall conform to this requirement.

3/ Utilizing two plys of panel.

4/ Except that time of exposure shall be for 20 standard fading hours.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

5/ The specimens must be dried after each of the three laundering cycles. On the color transfer cloth evaluation, only the stain on the cotton fibers of the color transfer cloth shall be evaluated.

6/ Refers to American Association of Textile Chemists and Colorists (AATCC) Chromatic Transference Scale rating.

7/ The specimens of type II cloth shall be a complete diaper, double layer and shall be cut the width of the cloth through the middle of the respective pinking bars, leaving a pinked edge. The samples shall be dried prior to pressing.

2.3 Length and put-up. For Government procurements only, unless otherwise specified (see 5.1), the cloth shall be furnished in continuous lengths of not less than 30 yards and shall be put-up full width on rolls, or for General Services Administration (GSA) procurements 50 ± 2-1/2 yard rolls or bolts.

3. QUALITY ASSURANCE

3.1 Certification. The contractor shall certify, and maintain substantiating evidence, that the product offered meets the salient characteristics and requirements of this Commerical Item Description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

3.2 Visual examination. Lots of cloth shall be inspected in accordance with MIL-STD-105. The inspection level shall be II and the acceptable quality level, expressed in terms of defects per hundred units, shall be 6.5. The lot size shall be expressed in units of yards. The sample unit shall be one linear yard. The cloth shall be examined for the following defects: hole, cut, tear, missing end or pick, thick or thin areas, permanent crease, slubs, slugs or gout, shade bar, streaks, spots, stains or uneven dying.

3.3 Length examination. During the visual examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified or more than 2 yards less than the length marked on the roll ticket shall be considered a length defect. If two or more rolls in the sample are defective with respect to length or if the total of the actual lengths of rolls in the sample is less than the total of lengths marked on the roll tickets, the lot shall be rejected.

3.4 Regulatory requirements. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580 to the maximum extent practicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

4. PACKAGING

4.1 Packaging. The cloth shall be rolled on a convolute or spiral-wound chipboard tube. The tube shall have a smooth finish surface that will prevent the fibers of the chipboard from transferring to the cloth. Each roll of cloth, put-up as specified, shall be wrapped with 70-pound minimum basis weight kraft paper in such a way that the paper shall encircle the roll at least once with a minimum overlap of 3 inches, and the width of the paper shall be sufficient to fold over and protect the ends of the roll. Gummed paper tape, with a minimum width of 2-1/2 inches shall be applied to the overlap seam the full length of the roll and across each end. Alternately, each wrapped roll shall be enclosed in a close-fitting polyethylene film tube.

4.1.1 Packaging of bolts (GSA procurements). When authorized by Aquisition Requirements (see 5.1), each bolt shall be wrapped in 50 pound minimum basis weight kraft paper. The kraft paper wrap shall be secured with gummed paper tape. Alternate method shall be wrap with plastic film not less than 0.002 inch thick.

4.2 Packing. Each wrapped roll shall be enclosed in a bias-sewn tubing made from woven polypropylene cloth. The tube shall be secured by heat-sealing, by means of a mechanical tie, or by plastic ties with a lock-end. Alternately, a maximum of four rolls of kraft-paper cloth shall be packed in a snug-fitting double-walled fiberboard container known as a double cover, and shall consist of a body or joined liner and two covers. Corrugated fiberboard with a minimum bursting strength of 500 pounds shall be used. The container shall be strapped with metallic straps not less than 1/2 by 0.020 inch or non-metallic straps not less than 7/16 by 0.030 inch. The net weight of contents in all fiberboard type containers shall not exceed 325 pounds.

4.2.1 Flat-folded pieces (bolts). Flat-folded pieces of fabric, put-up as specified, shall be packed in a snug-fitting wood-cleated plywood, wood-cleated fiberboard, or wood-cleated veneer container constructed, closed, and strapped. The net weight of contents in shipping containers shall not exceed 250 pounds.

4.3 Marking. In addition to any special markings required by the contract or purchase order, rolls and shipping containers shall be marked in accordance with MIL-STD-129. Each roll shall have a piece ticket (identification tag) affixed with a 5-ply minimum cotton string or a plastic tag hanger. The tag shall have a reinforced eyelet and shall be legibly printed, using water insoluble ink, with the following information:

Procurement Agency	Contract or Purchase Order Number
National Stock Number	Finish or Greige Mill
Item Description	Roll Number
Contractor	Lot Number
Width	Piece Number
Fiber Content	Yardage

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.

5. NOTES

5.1 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number and date of this document.
b. Class required (see 1.1).
c. Color of cloth required (see 2.1).
d. Width of cloth required (see 2.2).
e. Length and put-up, if other than specified (see 2.3).

5.2 Sources of documents.

5.2.1 Sources of non-government association documents. AATCC Chromatic Transference Scale Rating is available from:

American Association of Textile
Chemists and Colorists (AATCC)
P.O. Box 12215
Research Triangle Park, NC 27709-2215

5.2.2 Sources of government documents. Copies of Military and Federal documents are available from:

Standardization Documents Order Desk
Building 4D
700 Robbins Avenue
Philadelphia, PA 19111-5094

MILITARY INTERESTS:

Custodians

Army - GL
Navy - NU
Air Force - 99

Review Activities

Army - MD
Navy - MS

User Activity

DLA - CT

CIVIL AGENCY COORDINATING ACTIVITY:

COMMERCE - NBS
GSA - FSS
VA - OSS

PREPARING ACTIVITY:

Army - GL

(Project 8305-0368)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:06Z
Check the source to verify that this is the current version before use.