MIL-P-43743B(GL)
29 September 1988
SUPERSEDING
MIL-P-43743A(GL)
9 December 1976

MILITARY SPECIFICATION

PANEL MARKER, SURVIVAL, AVIATION PERSONNEL

This specification is approved for use by the U.S. Army Natick Research, Development, and Engineering Center, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers one type of fluorescent orange synthetic-fiber survival panel (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 Government documents.

* 2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

DDD-L-20	- Label; For Clothing, Equipage, and Tentage (General Use)
PPP-B-636	- Boxes, Shipping, Fiberboard

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8345

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:12Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-C-498 - Cloth, Parachute, Synthetic-Fiber (For Ammunition Parachutes)
MIL-L-35078 - Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing Personel Equipment and Equipage; General Specification For

STANDARDS

FEDERAL

FED-STD-191 - Textile Test Methods

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads

(Copies of specifications, standards, and handbooks required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D 3951 - Standard Practice for Commercial Packaging

(Copies should be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence. Nothing in this specification, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:12Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

* 3.1 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.4).

3.2 Guide samples. Guide samples, when furnished, are solely for guidance and information to the contractor (see 6.3). Variation from this document may appear in the sample, in which case this document shall govern.

* 3.3 Material. The material shall be 36-inches wide, synthetic-fiber parachute cloth conforming to type D of MIL-C-498 except that the requirements for tearing strength, elongation, air permeability and finish shall not apply and the cloth shall be scoured, heat set and calendered. The choloroform soluble material of the finished cloth shall not exceed 2.0 percent when tested as specified in 4.4.1.

3.3.1 Color and colorfastness. The color shall be Fluorescent Orange Shade No. 338 and shall match the standard sample when tested as specified in 4.4.1. The finished cloth shall show fastness to laundering, chlorine bleaching, crocking and light equal to or better than the standard sample when tested as specified in 4.4.1. When no standard sample is available, the finished cloth shall show "good" fastness to laundering, crocking, light and chlorine bleaching when tested as specified in 4.4.1.

3.4 Label, instruction. Each panel shall have an instruction label conforming to type IV, class 3 of DDD-L-20. The fastness to laundry requirements of DDD-L-20 shall apply. The contents of the instruction label shall be as follows:

PANEL MARKER, SURVIVAL, AVIATION PERSONNEL

Instructions For Use

This panel is to be used as a means of recognition for downed aircrewmen.

Insert panel, folded 9 by 2-1/2 inches with instruction label visible, into survival panel pocket located inside knife pocket or right thigh pocket.

Do not remove panel from pocket until needed. Launder coveralls with panel intact within pocket.

Each pair of coveralls shall have one panel.

3.5 Construction. The panel shall be formed by cutting the 36-inch wide cloth 36 ± 1/2 inches long. The panel shall not be off square by more than 1 inch.

* 3.5.1 Fusing of cut ends. The panel cut ends shall be fused smoothly throughout the full width of the cut width of the cloth.

Source: https://assist.dla.mil -- Downloaded: 20261O-21T22:12Z
Check the source to verify that this is the current version before use.

3.6 Marking. Locate instruction label so that it will appear on the outside of the folded panel when folded as specified in 5.1.1.

3.7 Removal of defective panels during spreading and cutting. During the spreading and cutting process, panels having material defects or damages that are classified as defects in 4.4.2 shall be removed from production.

3.8 Workmanship. The finished panel shall conform to the quality of product established by this document and the occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirement in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

* 4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for assuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point or at all points in the manufacturing process necessary to assure compliance with all dimensional requirements.

* 4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

* 4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.2. The presence of any defect shall be cause for rejection of the first article.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:12Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

* 4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified or qualified in this document or applicable purchase document. In addition, testing shall be performed on the component listed in table I for the characteristics noted. Unless otherwise indicated, testing shall be conducted in accordance with FED-STD-191. All requirements are applicable to the sample unit. All test reports shall contain the individual values utilized in expressing the final results. Unless otherwise specified in subsidiary documents, sampling shall be in accordance with the following:

Lot size	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

The lot shall be unacceptable if one or more sample units fail to meet any test requirements specified. The sample unit for testing the synthetic-fiber parachute cloth (see 3.3) shall be 1 yard, full width, and the lot shall be expressed in yards.

TABLE I. Component tests

Component	Characteristic	Requirement paragraph	Test method
Synthetic-fiber parachute cloth	Choloroform-soluble material	3.3	2611
	Colorfastness:	3.3.1	
	- Laundering		5614
	- Chlorine bleaching		5600
	- Crocking		5651
	- Light		5660
	- Color match		9010

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:12Z
Check the source to verify that this is the current version before use.

4.4.2 End item examination. The panel shall be examined for the defects listed below. The lot size shall be expressed in units of one panel. The sample unit shall be one panel. The inspection level shall be I and the acceptable quality level (AQL), expressed in defects per hundred units, shall be 15 (one class).

End item defects - one class

Hole, cut or tear
Mend, darn or patch
Spot or stain more than 1/4 inch in diameter
Off square by more than 1 inch
Either side (selvage edges) less than 35-1/2 or more than 36-1/2 inches long
Instruction label omitted, incorrect or illegible
Instruction label not positioned as specified
Fusing omitted
Cut end width not completely fused or not fused smoothly

* 4.4.3 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as incomplete sealing or closure of flap, improper taping, loose strapping, or inadequate stapling Instruction label not visible on the outside of the folded label Polyethylene bags heat sealed seams open, non-continuous or crooked Bulged or distorted container
Content	Number per container is more or less than required Number of panels per polyethylene bag is more or less than specified 1/

1/ For this defect one polyethylene bag shall be examined.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:12Z
Check the source to verify that this is the current version before use.

4.4.4 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Interlocking of loads not as specified Load not bonded as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A. Each panel shall be neatly folded to measure approximately 9 inches in length by 2-1/2 inches in width with the instruction label visible. Four folded panels shall be inserted in a snug-fitting clear polyethylene film bag of 0.00125-inch thickness (± 25 percent tolerance). The bag shall be formed with heat sealed seams that are straight, continuous and parallel to each other and to the formed edges of the bag. The final closure of the bag shall be heat sealed with the seal made as close as possible to open end.

* 5.1.2 Commercial. Panels shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

* 5.2.1 Level A packing. Four hundred panels, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V and reinforced as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.3. Shipping containers shall

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:12Z
Check the source to verify that this is the current version before use.

or, the contractor is responsible for the performance contract or purchase order

be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

* 5.2.2 Level B packing. Four hundred panels, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to stye RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.3.

5.2.2.1 Weather-resistant fiberboard containers. When specified (see 6.2), the shipping container shall be a grade V3c, V3s or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.3.

* 5.2.3 Commercial packing. Panels, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

5.3 Palletization. When specified (see 6.2), panels, packed as specified in 5.2.2 and 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet type shall be type I (4-way entry), type IV or type V in accordance with MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. Pallet pattern shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course.

* 5.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

5.4.1 Polyethylene bagged packages. Polyethylene bagged packages shall have the required identification information legibly printed or stamped in black directly on the bag across the center face or on a white paper label inserted within the bag so as to permit ready identification.

6. NOTES

6.1 Intended use. The survival panel marker, is an accessory of the Coveralls, Flyers Summer, Fire Resistant MIL-C-83141, worn by Army personnel. It is issued to Aviation Crewmen only.

Source: https://assist.dla.mil -- Downloaded: 202640-21T22:12Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. When a first article is required (see 3.1, 4.3, and 6.4).
c. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
d. Type and class of unit load required (see 5.2.1).
e. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
f. When palletization is required (see 5.3).

6.3 Standard sample. For access to samples, address the contracting activity issuing the invitation for bids.

* 6.4 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

6.5 Subject term (key word) listing.

Aviation crewmen
Personnel marker
Survival panel
Trousers, fire-resistant

6.6 Changes from previous issue. The margins of this document are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only, and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content, as written, irrespective of the marginal notations and relationship to the last previous issue.

Custodian:

Army - GL

Review activities:

Army - MD, AV
DLA - CT

Preparing activity:

Army - GL

Project No. 8345-A172

Source: https://assist.dla.mil -- Downloaded: 202640-21T22:12Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-P-43743B(GL)	Panel Marker, Survival, Aviation Personnel

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 1426

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:10Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS. In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

US Army Natick Research, Development, and
Engineering Center
Natick, MA 01760-5014

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300
STRNC-ES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research, Development,
and Engineering Center
ATTN: STRNC-ES
Box 14A
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:12Z
Check the source to verify that this is the current version before use.