MIL-W-43722(GL)

18 November 1970

MILITARY SPECIFICATION

WADDING, COTTON

1. SCOPE

1.1 This specification covers cotton wadding for use as packing.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

L-P-378	-	Plastic Sheet and Strip, Thin Gauge, Polyolefin
MMM-A-260	-	Adhesive, Water-Resistant, (For Sealing Waterproofed Paper)
PPP-B-1055	-	Barrier Material, Waterproofed, Flexible

MILITARY

MIL-T-40625	-	Tubing, Bias, Sewn (Burlap or Osnaburg) Cloth

STANDARDS

FEDERAL

FED-STD-191	-	Textile Test Methods

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	-	Marking for Shipment and Storage

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer).

FSC 8320

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:09Z
Check the source to verify that this is the current version before use.

2.2 Other publications.- The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC.

National Motor Freight Classification

(Application for copies should be addressed to American Trucking Associations, ATTN: Tariff Order Section, 1616 P Street, N.W., Washington, D. C. 20036.)

UNIFORM CLASSIFICATION COMMITTEE

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, 202 Union Station, Chicago, Illinois 60606.)

3. REQUIREMENTS

3.1 Material.- The wadding shall be fabricated from clean cotton fibers, natural or colored, utilizing card strippings, mill waste or reworked stock, and garnetted to produce unbroken layers for building up the wadding thickness.

3.1.1 Bonding agent.- There shall be a bonding agent uniformly applied to both sides of the material for stabilization in the handling of the wadding.

3.2 Physical requirements.- The bonded wadding shall conform to the following physical requirements when tested as specified in 4.4.

TABLE I.- Physical requirements

Width (min) inches	Weight (min) ounces sq. yd.	Thickness (min) inches
32	5.6	0.090

3.3 Length and put-up.- Unless otherwise specified (see 6.2), the wadding shall be in one continuous length of not less than 12 yards and shall be put up in rolls or flat folds. The length of the wadding shall be marked on one end of the roll or folded piece with black indelible ink.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:09Z
Check the source to verify that this is the current version before use.

3.4 Workmanship.- The wadding shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.- Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certification of compliance.- Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection.- Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection.- In accordance with 4.1 above, component and material shall be tested in accordance with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable procurement documents.

4.2.2 End item examination.- Examination of the end item shall be in accordance with the provisions of 4.2.2.1 through 4.2.3.2.

4.2.2.1 Yard-by-yard examination.- The required yardage shall be examined on one side for the visual defects listed below. The sample size shall be in accordance with level I of MIL-STD-105 and the acceptable quality level shall be 4.0 defects per 100 units. The sample unit shall be 1 yard full width of the wadding. The lot size shall be expressed in units of one yard. An approximate equal number of yards shall be examined from the rolls or pieces selected. The number of rolls or pieces from which the sample is to be selected shall be in accordance with table II.

Defects

Hole, cut or tear
Oil spots
Width less than specified
Presence of metallic objects
Bonding agent omitted or not uniformly applied

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:09Z
Check the source to verify that this is the current version before use.

TABLE II.- Sample size

Lot size in yards	Sample size in rolls or folded pieces	Acceptance number see 4.2.2.1
500 or less 1/	3	0
501 up to and including 1200	5	0
1201 up to and including 3200	8	0
3201 up to and including 10,000	13	1
10,001 up to and including 35,000	20	1
35,001 and over	32	2

1/ If a lot contains fewer than 3 rolls or pieces, each roll or piece in the lot shall be examined.

4.2.3 Examination for length.-

4.2.3.1 Individual rolls or folded pieces.- Any length found to be less than the specified minimum length, or more than 2 yards less than the length marked on the roll or folded piece shall be scored as a defect with respect to length. The sample unit shall be one roll or folded piece. The number of rolls or folded pieces selected as the sample size and the maximum acceptable number of defects shall be in accordance with table II.

4.2.3.2 Total yardage.- The lot shall be unacceptable if the total of the actual lengths of rolls or pieces in the sample is less than the total of lengths marked on the tickets.

4.3 Examination of preparation for delivery requirements.- An examination shall be made to determine that packing and marking complies with the section 5 requirements of this specification.

4.4 Tests.- The methods of testing specified in FED-STD-191 wherever applicable and as listed in table III shall be followed. The sample unit shall be 1 yard full width of the wadding. The sample size (number of sample units) shall be as shown in the table below. The lot size shall be expressed in units of 1 yard. The lot shall be unacceptable if one or more sample units fail to meet any test requirements specified.

Lot size (yards)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:09Z
Check the source to verify that this is the current version before use.

TABLE III.- Test methods

Characteristic	Requirement paragraph	Test method
Material	3.1	1/
Weight	3.2	5040 or 5041
Thickness	3.2	5030

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

5. PREPARATION FOR DELIVERY

5.1 Packing.- Packing shall be level A, B or C as specified (see 6.2).

5.1.1 Level A.- Wadding, put-up as specified, shall be packed in a bale provided with top and bottom pads of solid kraft paperboard or corrugated or solid fiberboard. Each pad shall be fabricated to overlap the sides of the bale to prevent damage to the wadding. Bales shall be compressed and bound with at least two bands of flat steel or round wire strapping. Each bale shall be wrapped with waterproofed barrier material conforming to class E-1 of PPP-B-105 with all folds, seams and laps completely sealed with a minimum 3/4-inch width continuous seam of adhesive conforming to type I or II, grade B, class 1 of MMM-A-260. Each bale shall then be inserted in bias-sewn tubing or bag (tubing presewn one end) conforming to MIL-T-40625. Closure shall be effected by securing each open end with two wire ties. The first wire tie shall be applied as close to the contents as possible. The second wire tie shall be applied approximately 1 inch from the first wire tie. The wire ties shall be not less than 6 inches long, 0.072-inch diameter galvanized or black soft iron or steel wire with a 1/2-inch diameter formed eye at each end. The weight of content of each bale shall not exceed 70 pounds.

5.1.2 Level B.- Wadding, put-up as specified, shall be packed as specified in 5.1.1, except that the waterproofed barrier material shall not be required. In lieu of the bias-sewn tubing or bags, bales may be inserted in polyethylene tubing. The minimum thickness of the polyethylene film shall be 0.005-inch conforming to type II, class 1, grade A, B or C, finish 1 or 2 of L-P-378. Closure shall be effected by securing each open end with wire ties as specified in 5.1.1. The weight of contents of each bale shall not exceed 70 pounds.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:09Z
Check the source to verify that this is the current version before use.

5.1.3 Level C.- Wadding shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with Uniform Freight Classification Rules or National Motor Freight classification Rules as applicable.

5.2 Marking.- In addition to any special marking required by the contract or order, shipments shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use.- The wadding is used when packing furniture for shipment.

6.2 Ordering data.- Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) When put-up other than specified is required (see 3.3).
(c) Selection of applicable levels of packing (see 5.1).

6.3 Supersession data.- This specification supersedes the requirements of Interim Purchase Description IP/DES S-28-4 dated 11 September 1964.

Custodian:

Army - GL

Preparing activity:

Army - GL

Project No. 8320-0054

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:09Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: *This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.*

SPECIFICATION
Wadding, Cotton MIL-W-43722(GL)

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?
   ☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T22:09Z
Check the source to verify that this is the current version before use.