A-A-1667C
November 10, 1992
SUPERSEDING
A-A-1667B
May 30, 1986

# COMMERCIAL ITEM DESCRIPTION

## BLANKET, BED

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification DDD-B-421, Type I, Class 2.

This blanket is intended for use in institutions where absorbency and comfort are desirable characteristics. Because of its absorbency and softness, it is especially suitable for use as a bath blanket.

Salient characteristics.

The blanket shall be white in color, meeting the requirements specified in this paragraph and the requirements listed in Table I. The fabric shall be a two-bar warp knit, knitted from 100 percent polyester in such a manner as to achieve a "waffle like" stitch. The fabric shall be (1) napped in order to provide a warm, comfortable, soft feel, and (2) treated with an absorbency treatment which will provide permanent absorbency characteristics which are maintained throughout the useful "life of the blanket" (see footnote 2/). The blanket shall conform to the standard sample with respect to color, softness, and "waffle like" stitch construction. A standard sample may be obtained from the contracting official issuing the invitation for bid.

TABLE I

| Characteristic | Requirement | Test Method |
|---|---|---|
| Finished weight, ounces per square yard | 2.50 (-5% + unlimited) | ASTM D 3776 |
| Bursting strength | 50 PSI (min.) | ASTM D 3993 |
| Dimensional change percentage warp/fill (wales & courses) | 3.5/3.5 (max.) | AATCC 96 IE - 5 complete washing drying cycles 1_/ |
| Wales/courses per sq. inch | 41 x 59 (± 5%) | ASTM D 3887 |
| Absorbency, sec. | 20 (max.) | AATCC 79 2/ |

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

FSC 7210

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.

TABLE I NOTES

1/ The washing and drying conditions for dimensional change shall be as prescribed, except that 0.015 percent available chlorine of total volume shall be added, and a VA approved antichlor shall be used to remove residual chlorine.

2/ Permanent Absorbency Test: The blanket must demonstrate an average wetting time of twenty (20) seconds or less when tested under the criteria specified in AATCC Test Method 79. Absorbency shall be permanent for the "life of the blanket" for testing purposes shall be deemed to be 200 "normal wash" cycles. For purposes of this test, a "normal wash" cycle will be as specified in AATCC Test Method 130, Sections 3,4,6 (washing procedure I), except that the amount of detergent shall be reduced to 20 grams since no oils or stains have been introduced. To prevent skewed results due to detergent buildup, the last three (3) normal wash cycles of each series (i.e., 8, 9, 10, 18, 19, 20;...198, 199, 200) will be run without adding any detergent. Initially and after each series of ten (10) wash cycles, the absorbency shall be checked on each of the removed samples per AATCC Test Method 79 as described above. Testing may be stopped after the samples have failed the absorbency test three consecutive times and the samples should be recorded as failing to meet requirements. The samples must meet the absorbency test on 18 or more of the 21 tests.

---

The issue of each Standard, Specification, or Test method in effect on the date of solicitation shall be used to determine compliance with the requirements of this commercial item description.

The finished blanket shall be a minimum of 66 inches wide and 90 inches long. Nonselvage edges shall be hemmed with polyester sewing thread. The hem shall be sewn with stitching class EFb-1 and stitch type 401 or 501 in accordance with FED STD No. 751. The finished hem width shall be a minimum of 3/4 inch with a minimum turn under of 1/4 inch. There shall be 6-10 stitches per inch, and the thread shall be a commercially available color that is the closest to the color of the blanket. Each blanket shall be labeled, ticketed, or invoiced for fiber content in accordance with the Rules and Regulations under the Textiles Fiber Products Identification Act.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.

Bath blankets being supplied to the Veterans' Administration must be legibly and permanently marked with the following information: "VA PROPERTY NOT FOR SALE", when specified. The marking shall be placed parallel to the selvege edge.

Workmanship. The blanket shall be free from defects such as holes, tears, misweaves, spots, loose or skipped stitches, raw edges, etc., that will affect appearance and serviceability.

Inspection of the end item. A lot shall consist of blankets of the same cloth manufactured using the same method and process. The sample unit shall be one blanket. Sampling shall be in accordance with MIL-STD-105.

A. Examination for construction and workmanship. The inspection level shall be S-3 with an acceptable quality level (AQL) of 4.0 percent defective.

B. Dimensional examination. Use S-3, AQL 2.5 percent defective. Examine for the following defects: Length or width less than specified. Length uneven by more than 1 1/2 inches. Width uneven by more than 1 inch. Hem width less than specified. Turn under less than specified.

C. Testing. Use level S-2 with an AQL of 2.5 percent defective for all tests in Table I, except for the absorbency test which requires at least 5 samples to be selected from each ten thousand (10,000) blankets and tested in accordance with AATCC 79 2_/. Any blanket that fails the absorbency test shall result in rejection of the lot.

Regulatory requirement. In accordance with section 23.403 of the Federal Acquisition Regulations, the Government's policy is to acquire items composed of the highest percentage of recovered materials practicable, consistent with maintaining a satisfactory level of competition without adversely affecting performance requirements or exposing suppliers' employees to undue hazards from the recovered materials.

Preservation, packaging, packing, labeling, and marking. Preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.

Notes. The commercial item description clause is not required when this commercial item description is used for procurement.

Purchaser should specify when the VA logo is required in the contract or purchase order.

ASTM methods are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

AATCC methods are available from the American Association of Textile Chemists and Colorists, P. O. Box 12215, Research Triangle Park, North Carolina 27709.

CIVIL AGENCY COORDINATING ACTIVITY:

VA - OSS

MILITARY COORDINATING ACTIVITIES

NAVY - SA
AIR FORCE -75
MARINE CORPS

PREPARING ACTIVITY:

GSA - FSS



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:15Z
Check the source to verify that this is the current version before use.