(A) THE TIRE SHALL BE IN ACCORDANCE WITH THE APPLICABLE REQUIREMENTS OF MIL-P-7726 EXCEPT AS SPECIFIED HEREIN

SIZE	PLY RATING	STATIC LOAD RATING LBS	INFL. PRESS PSI RATED	BURST PRESS PSI (MIN)	BEAD WIDTH IN. (MAX)	WEIGHT LBS (MAX)	STATIC UNBAL OZ.-IN. MAX	TREAD	MOLD SKID DEPTH + 2% - 4% (MIN)	DEFLC
28X9.0	1/22TL	16,650	235	825	2.25	52.5	14	2/PIB	.25	32%

1/TL TUBELESS
2/FIVE GROOVES WITH A 0.39 INCH MINIMUM WIDTH AT TOP OF GROOVE

RIM DATA:

WIDTH BETWEEN FLANGES (INCH)	FLANGE WIDTH (INCH)	LEDGE DIAMETER (INCH)	FLANGE HEIGHT (INCH)	HEEL RADIUS	FLANGE RADIUS	FLANGE EDGE RADIUS	LEDGE WIDTH
7.00	1.00	12.00	1.25	.625	.625	.09	2.25

THIS TIRE SHALL BE SUITABLE FOR USE AND PROVIDE REASONABLE SERVICE LIFE ON NAVY CARRIER TYPE AIRCRAFT DURING ALL NORMAL OPERATIONS AT TAKE-OFF SPEEDS OF NOT MORE THAN 173 MPH AND LANDING SPEEDS OF NOT MORE THAN 150 MPH ON ALL TYPES OF RUNWAYS AND ON AIRCRAFT CARRIERS.

TIRE 1.

DYNAMIC TEST - THE TIRE SHALL WITHSTAND WITHOUT FAILURE 50 CYCLES OF TEST A, 50 CYCLES OF TEST B, AND 15 CYCLES OF TESTS C, D AND E.

TEST A - TAXI/TAKE-OFF - TAXI THE TIRE ON THE FLYWHEEL FOR 10,000 FEET UNDER 16,650 LB LOAD AT 23 MPH. STOP THE FLYWHEEL UNDER FULL LOAD AND THEN ACCELERATE (SIMULATING TAKE-OFF) TO 173 MPH IN ACCORDANCE WITH THE FOLLOWING LOAD-SPEED-TIME DATA:

LOAD (LBS)	SPEED (MPH)	TIME (SEC)	DISTANCE (FT)
16,650	0	0	
16,000	35	5	
14,400	69	10	
12,500	98	15	
10,200	164	20	
7,500	150	25	
3,600	168	30	
0	173	32	4,475

TEST B - LANDING/TAXI - THE TIRE SHALL BE LANDED AGAINST THE FLYWHEEL ROTATING AT A PERIPHERAL SPEED OF 150 MPH, DECELERATED TO 0 MPH AND TAXIED IN ACCORDANCE WITH THE FOLLOWING LOAD-SPEED-TIME DATA:

	LOAD (LBS)	SPEED (MPH)	TIME (SEC)	DISTANCE (FT)
	0	150	0	
	5,000	135	5	
	7,200	110	10	
LAND	9,100	86	15	
	10,600	62	20	
	11,700	39	25	
	11,900	15	30	
	12,100	0	33	3,850
TAXI	12,100	23	296	10,000

TEST C - CATAPULT TAKE-OFF - THE TIRE SHALL BE LANDED AT A LOAD OF 45,000 LBS AGAINST THE FLYWHEEL ROTATING AT A PERIPHERAL SPEED OF 35 MPH AND UNLANDED AFTER A DISTANCE OF 300 FEET HAS BEEN COVERED. AN INFLATION PRESSURE OF 375 PSI ADJUSTED FOR FLYWHEEL CURVATURE SHALL BE USED.

TEST D - TAKE-OFF CAMBER

D_1- PERFORM THE TEST A SPECTRUM WITH THE PLANE OF THE TIRE INCLINED INBOARD AT AN ANGLE OF 5 DEGREES.

D_2- PERFORM THE TEST A SPECTRUM WITH THE PLANE OF THE TIRE INCLINED OUTBOARD AT AN ANGLE OF 5 DEGREES.

TEST E - LANDING CAMBER

E_1- PERFORM THE TEST B SPECTRUM WITH THE PLANE OF THE TIRE INCLINED INBOARD AT AN ANGLE OF 5 DEGREES.

E_2- PERFORM THE TEST B SPECTRUM WITH THE PLANE OF THE TIRE INCLINED OUTBOARD AT AN ANGLE OF 5 DEGREES.

(A)

(A) DENOTES CHANGES

APPROVED 18 FEB 1969 REVISED (A) 15 DEC 1982

This standard has been approved by the Naval Air Systems Command, Department of the Navy and is mandatory for use by that activity. All other military activities are required to employ this standard where suitable.

P.A. AS Other Cust	TITLE: TIRE, PNEUMATIC, AIRCRAFT, REBUILT 28 X 9.0 (173MPH) TYPE VII (NAVY)	MILITARY STANDARD MS3385(AS)
PROCUREMENT SPECIFICATION MIL-R-7726	SUPERSEDES:	SHEET 1 OF 2

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:03Z
Check the source to verify that this is the current version before use.

(A) TIRE 2.

GOVT LAB TEST - THIS TIRE SHALL BE REBUILT FROM THE SAME BATCH AS TEST TIRE 1 AND SHALL BE IDENTICALLY PROCESSED. THIS TIRE SHALL NOT BE CONTRACTOR TESTED AND SHALL BE PROVIDED FOR GOVERNMENT LABORATORY TESTING.

SECTION - A REPRESENTATIVE SECTION OF TIRE 1 AND TIRE 2 SHALL BE SUBMITTED TO A GOVERNMENT LABORATORY AS SPECIFIED IN MS 3377.

AIR RETENTION - THE TUBELESS TIRE SHALL BE INFLATED TO A PRESSURE OF 375 PSI AND ALLOWED TO STAND FOR A PERIOD OF 4 HOURS AT WHICH TIME THE PRESSURE DROP DUE TO GROWTH SHALL BE REPLACED. THE TIRE SHALL THEN STAND FOR AN ADDITIONAL 12 HOURS AT WHICH TIME THE PRESSURE SHALL BE MEASURED AND THE TIRE INSPECTED. THE AIR PRESSURE LOSS SHALL NOT EXCEED 5 PERCENT AND THE TIRE SHALL NOT REVEAL ANY APPEARANCE OR PERFORMANCE DEFECTS, SUCH AS SIDEWALL BLISTERS, TREAD SEPARATION, ETC.

(A)

NOTES -

1. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATIONS FOR BIDS, OR REQUEST FOR PROPOSAL EXCEPT THAT REFERENCE ADOPTED INDUSTRY STANDARDS SHALL GIVE DATE OF THE ISSUE ADOPTED

2. FOR DESIGN FEATURE PURPOSES, THIS STANDARD TAKES PRECEDENCE OVER PROCUREMENT DOCUMENTS REFERENCED HEREIN.

APPROVED 18 FEB 1969 REVISED (A) FOR CHANGES SEE SHEETS 1 AND 2

P.A. AS Other Cust	TITLE TIRE, PNEUMATIC, AIRCRAFT, REBUILT 28 X 9.0 (173 MPH) TYPE VII (NAVY)	MILITARY STANDARD MS3385(AS)
PROCUREMENT SPECIFICATION MIL-R-7726	SUPERSEDES:	SHEET 2 OF 2

This standard has been approved by the Naval Air Systems Command Department of the Navy and is mandatory for use by that activity. All other military activities are required to employ this standard where suitable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:03Z
Check the source to verify that this is the current version before use.