INCH-POUND
A-A-59813
3 JUNE 2008

COMMERCIAL ITEM DESCRIPTION

CHARCOAL, LUMP OR BRIQUETTE, WOOD

The General Services Administration has authorized the use of this commercial item description for all federal agencies.

1. SCOPE. This commercial item description (CID) covers charcoal using as a principal fuel for preparing food or for outdoor cooking.

2. CLASSIFICATION. Charcoal shall be of the following types:

Type I - Lump
Type II - Briquette

3. SALIENT CHARACTERISTICS.

3.1 General requirements. Charcoal shall consist of the product made by charring hard or soft Wood. Charcoal to be furnished shall be as specified (see 6.1) and shall conform to the physical characteristics as specified below and to the charcoal characteristics in Table 1 when tested in accordance with ASTM D1762.

Table 1. Charcoal characteristics

Charcoal Characteristics	Lump Charcoal Weight Percent (%)	Briquettes (Weight Percent)	
		Without Filler	With Filler
Ash	4 Max	8 Max	25 Max
Moisture	5 Max	5 Max	5 Max
Volatiles matter	10 Min 15 Max	10 Min 15 Max	10 Min 15 Max

Comments, suggestions, or questions on this document should be addressed to: Defense Supply Center Philadelphia, ATTN: DSCP-NASA, 700 Robbins Ave., Philadelphia, PA 19111-5096 or email to dscpg&inspccomments@dla.mil. Since contact information can change, you may want to verify the currency of this address information using the ASSIST Online database at http://assist.daps.dla.mil

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:28Z
Check the source to verify that this is the current version before use.

3.2 Physical characteristics.

3.2.1 Contamination. Incompletely charred wood, trash, and other material foreign to charcoal produced shall not exceed one (1) percent by weight.

3.2.2 Type I. Type I, lump form charcoal, shall be black, nonlustrous, with glossy conchoidal fracture.

3.2.2.1 Size. Lump charcoal size shall be within the following parameters: A minimum of 90 percent, by weight, shall remain on a 2-1/2 inch screen, and a maximum of two (2) percent by weight, shall pass through a 1-1/4 inch screen.

3.2.3 Type II. Type II, briquette form charcoal, shall be pulverized or granulated charcoal which is compressed and held together by binder. Unless otherwise specified, the briquette furnished shall be without filler (see 6.1).

3.2.3.1 Size. Briquette charcoal size shall be within the following parameters: A minimum of 90 percent, by weight, of these charcoal shall remain on the 1-1/4 inch screen, and a maximum of two (2) percent by weight, shall pass through a ¾ inch screen.

3. REGULATORY REQUIREMENTS. The offeror/contractor is encouraged to use recovered material to the maximum extent practicable, in accordance with paragraph 23.403 of the Federal Acquisition Regulation (FAR).

4. PRODUCT CONFORMANCE.

4.1 Product conformance. The products provided shall meet the salient characteristics of this commercial item description, conform to the producer's own drawings, specifications, standards, and quality assurance practices, and be the same product offered for sale in the commercial market. The government reserves the right to require proof of such conformance.

4.2 Inspection. The charcoal shall be inspected to determine compliance with all requirements specified in this CID.

4.3 Certification. Unless otherwise specified, the manufacturer shall certify that the charcoal furnished shall meet the characteristics requirements in Table 1.

5. PACKAGING. Preservation, packing, and marking shall be as specified in the contract or order.

6. NOTES.

6.1 Part or Identification Number (PIN). The following PIN procedure is for government purposes and does not constitute a requirement for the contractor.

This example describes a part numbering system for CID A-A-59813.

Example: AA59813 –A 10 F



Add "F" for with filler (Type II only); omit for without (see 3.2.3)
Pounds per bag
"A" for Type I; "B" for Type II
Basic CID numbers

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:28Z
Check the source to verify that this is the current version before use.

6.2 Source of documents.

6.2.1 FAR. The FAR may be obtained from the Regulatory Secretariat, 1800F Street NW, Washington, DC 20405 or online at http://www.acqnet.gov .

6.2.2 ASTM Standard:

ASTM D1762 - Standard Test Method for Chemical Analysis of Wood Charcoal.

Copies of ASTM standards may be obtained from the ASTM International, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or online at http://www.astm.org .

6.3 Ordering data. The contract or order should specify the following:

a. CID document number, revision, and CID PIN.
b. Product conformance provisions.
c. Packaging requirements.

6.4 Key words.

Ash
Coal
Moisture
Volatile matter

Military interests:

Custodians:
Army - GL
Navy - SA
Air Force - 68

Preparing activity:
DLA –IS
(Project 9110-2008-001)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at http://assist.daps.dla.mil .

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:28Z
Check the source to verify that this is the current version before use.