MIL-B-20292A(MU)
AMENDMENT 2
10 September 1968
SUPERSEDING
AMENDMENT 1
16 August 1968

MILITARY SPECIFICATION

BLANKS, ROTATING BAND, FOR PROJECTILES

This amendment form a part of Military Specification MIL-B-20292A(MU), dated 3 April 1967.

Page 2, under Military Specifications, change title of MIL-C-3993 to read "Copper and Copper Base Mill Products, Packaging of".

Page 2, add Para. 2.2.

"2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM Designation E8 - Tension Testing of Metallic Materials

(Application for copies should be addressed to American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa., 19103.)"

Page 2, Table I. Delete and substitute:

Table I. Chemical composition, percent

Copper and Copper Alloy Number	Copper[1]	Iron, max.	Lead, max.	Zinc,	Nickel	Manganese, max.	Total other impurities, max.
* 101-130 incl.	99.88 min.	-	-	-	-	-	0.12
220	89-91	0.05	0.05	Rem.	-	-	0.10
702	Rem.	0.10	0.05	-	2.0-3.0	0.40	0.30

[1] Silver counting as copper

FSC 1395

Source: https://assist.dla.mil -- Downloaded: 202610-19T07:34Z
Check the source to verify that this is the current version before use.

Page 3. Table II. Delete and substitute:

Table II. Mechanical properties of annealed rotating band blanks

Copper and Copper Alloy Number	Inside diameter of band blank, inches	Tensile strength, psi, max.	Elongation percent, min. in 1 in.	Elongation percent, min. in 2 in.	Bending test degrees
101-130 incl.	Up to 0.875 incl.	35,000	40	-	180
	Over 1.875	35,000	-	40	180
220	Up to 1.875 incl.	40,000	40	-	180
	Over 1.875	40,000	-	35	180
702	Over 7.50	40,000	-	35	180

Page 3, Table III. Delete and substitute:

Table III. Average grain size

Copper and Copper Alloy Number	Caliber	Average grain size (mm) min.	Average grain size (mm) max.
101-130 incl.	All	0.035	-
220	20 mm to 105 mm incl.	0.045	0.200
	Over 105 mm	0.045	-

Page 4, Para. 3.3.2, line 3. Change "9n" to "in".

Page 4, Para. 3.5. Add after first sentence: "Identification marking of the blanks is not allowed."

Page 4, Para. 4.3.2.3. Change copper and copper alloy number "130" to read "101-130 inclusive".

Page 5, Para. 4.5.1. Add the following sentence to the end of this paragraph. "For blanks of inside diameter 7.5 inches or more, use the specimen illustrated in ASTM E8-66 for the 8 in. gage length.(Fig. 6)."

Page 7, Para. 5.1. Delete "(See 6.1)" and substitute "(6.1 and 6.2)".

Page 7, Para. 6.1. Add "(f) Maximum gross weight of container."

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:34Z
Check the source to verify that this is the current version before use.

*The outside margin has been marked to indicate where addition to the previous amendment has been made. This has been done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in this notation. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content as written irrespective of the marginal notation and relationship to the last previous amendment.

Custodian:

Army - MU

Preparing activity:

Army - MU

Project No. 1395-A034

Source: https://assist.dla.mil -- Downloaded: 20261O-19T07:34Z
Check the source to verify that this is the current version before use.