MIL-K-20277F(MC)
7 July 1982
SUPERSEDING
MIL-K-20277E
17 October 1974

MILITARY SPECIFICATION

KNIFE, COMBAT: WITH SHEATH

This specification is approved for use by U. S. Marine Corps, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for one type of sheathed combat knife having a 7-inch (178mm) blade.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications and standards. Unless otherwise specified, the following specifications and standards of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DODISS) specified in the solicitation, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

O-L-164	- Leather Dressing, Mildew-Preventive.
V-T-295	- Thread, Nylon.
FF-R-556	- Rivets, Solid, Small; Rivets, Split, Small; Rivets, Tubular, Small; and Caps, Rivets; General Purpose.
KK-L-165	- Leather, Cattlehide, Vegetable-Tanned, and Chrome Retanned, Impregnated; and Soles.
KK-L-271	- Leather, Cattlehide, Strap, Vegetable-Tanned.

Beneficial comments (recommendations, additions, deletions), and any pertinent data which may be of use in improving this document, should be addressed to Commandant of the Marine Corps, Headquarters Marine Corps (Code LMA-1), Washington, DC 20380 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426), appearing at the end of this document, or by letter.

FSC 1095

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:32Z
Check the source to verify that this is the current version before use.

PPP-B-576 - Box, Wood, Cleated, Veneer, Paper Overlaid.
PPP-B-585 - Box, Wood, Wirebound.
PPP-B-591 - Boxes, Shipping, Fiberboard, Wood-Cleated.
PPP-B-601 - Boxes, Wood, Cleated Plywood.
PPP-B-621 - Box, Wood, Nailed and Lock Corner.
PPP-B-636 - Box, Shipping, Fiberboard.
PPP-T-60 - Tape, Packaging, Waterproof.

MILITARY

MIL-B-117 - Bag, Sleeve, and Tubing, - Interior Packaging.
MIL-H-6875 - Heat Treatment of Steels (Aircraft Practice) Process for.
MIL-S-8559 - Steel Bars, Carbon, AISI (1095), Aircraft Quality.
MIL-F-10884 - Fasteners, Snap.
DOD-P-16232 - Phosphate Coating, Heavy, Manganese or Zinc Base (For Ferrous Metals).

STANDARDS

FEDERAL

FED-STD-66 - Steel, Chemical Composition and Hardenability.
FED-STD-151 - Metal, Test Methods.
FED-STD-311 - Leather, Methods of Sampling and Testing.
FED-STD-595 - Color.
FED-STD-751 - Stitches, Seams and Stitchings.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-130 - Identification Marking of U. S. Military Property.
MIL-STD-1188 - Commercial Packaging of Supplies and Equipment.
MS27980 - Fastener, Snap, Style 2 (Regular Wire Spring Clamp Type).

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein.

DRAWINGS

MARINE CORPS

81A5020A0000 - Knife, Combat.
81A5020A0001 - Sheath for Combat Knife.

(Copies of specifications, standards, handbooks, drawings, and publications required by manufacturers in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:32Z
Check the source to verify that this is the current version before use.

2.1.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence.

2.2 Other publications. The following document(s) form a part of this specification to the extent specified herein. The issue of the documents which are indicated as DoD adopted shall be the issue listed in the current DODISS and the supplement thereto, if applicable.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM E112 - Estimating the Average Grain Size of Metals.

(Application for copies of ASTM publications should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

3. REQUIREMENTS

3.1 First article. Unless otherwise specified (see 4.3 and 6.2), as soon as practicable after award of contract or order and prior to starting regular production, the manufacturer shall submit first article consisting of two sheathed knives and two blades in the as quenched condition. The first article shall be representative of the construction, workmanship, components and materials to be used during production. When the contractor is in continuous production of the knives from contract to contract, submission of further first articles on the new contract may be waived at the discretion of the acquiring activity.

3.2 Materials. The knife and sheath shall be made from materials specified herein. The materials used may include reclaimed materials provided such materials will not jeopardize its intended use and performance. The reclaimed materials shall have been reprocessed, remanufactured, or recycled in a manner which will restore them to the same chemical composition and physical properties as the materials originally selected for use in the knife and sheath.

3.2.1 Blade. The blade shall be of the through tang type and shall be made of steel conforming to MIL-S-8559. The finished blade shall be hardened and tempered in accordance with MIL-H-6875, and shall have a Rockwell hardness range from C55 to C58, when inspected as specified in 4.8.4. There shall be a hardness transition zone from the heel of the blade to 0.75 inch (19.0mm) onto the tang, having a hardness of C35 to C45 at the midpoint. The remainder of the tang shall have a maximum hardness of C30 using the Rockwell scale. After hardening, the blade shall have a fracture grain size no coarser than 8, when compared with the Shepherd fracture grain size standard specified in ASTM E112.

Source: https://assist.dla.mil -- Downloaded: 20260-19T07:32Z
Check the source to verify that this is the current version before use.

3.2.2 Guard, butt plate and pin. The guard, butt plate and pin shall be made of SAE 1018 or 1020 steel conforming to FED-STD-66.

3.2.3 Leather. The leather shall be rendered mildew proof in accordance with type I or II of O-L-164. The treated leather shall contain between 0.2 and 0.5 percent paranitrophenol (see 4.8.2).

3.2.3.1 Grip. The grip shall be made of leather conforming to KK-L-165, except that class 5 material (OFFAL) shall not be used (see 4.5).

3.2.3.2 Sheath and welt filler. The sheath and welt filler shall be made of leather conforming to type II, Class 1, selection 3 of KK-L-271. The outer surface shall not be flaky and shall be free of all other defects (see 4.5).

3.2.4 Thread. The thread shall be nylon conforming to type I or II, letter size F of V-T-295. The color shall closely match the color of the sheath. Colorfastness is not applicable (see 4.5).

3.2.5 Rivets. The rivets shall be split type conforming to type XI, class 1, grade F of FF-R-556, black chemical finish (see 4.5).

3.2.6 Snap fasteners. The snap fasteners shall conform to style 2, finish 2 of MIL-F-10884 and MS27980 (see 4.5).

3.2.7 Color. The color of all components shall be black and match chip number 37038 of FED-STD-595 (see 4.5).

3.3 Design. The design of the knife and sheath shall conform to Drawing numbers 81A5020A0000 and 81A5020A0001 (see 4.5).

3.4 Construction.

3.4.1 Knife. The guard shall fit the tang snugly so that all edges of the slot are in contact. The slot shall provide for the tang fillet to allow the guard to be in full contact with the heel of the blade. The leather grip sections shall be assembled on the tang in appropriate sequence and of such thickness as to require compression thereof and permit the insertion of the pin through the butt plate to form a solid grip handle. This assembly shall be such that the grip shall form an integral part of the knife, with no play between the grip and the blade. The butt pin shall be peened at both ends and ground smooth. The end of the tang shall be flush with the butt plate. The grip shall be grooved at intervals and present a smooth profile as shown in Drawing number 81A5020A0000. The handle assembly shall be deburred and colored to match the sheath. The blade shall contain a blood groove on each side. The cutting edge of the blade shall be ground and sharpened to a keen edge. The cutting edge at the back of the blade near the tip shall be ground

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:32Z
Check the source to verify that this is the current version before use.

to a sharp edge. The assembled knife shall conform to Drawing number 81A5020A0000 (see 4.5).

3.4.2 Sheath. The leather sheath shall consist of a one-piece back section and a one-piece front section forming a pocket for the blade as shown on Drawing number 81A5020A0001. The flesh side of the leather shall be on the inside of the assembled sheath. The front welt and back sections shall be sewn and riveted together along the edges. The strap for holding the handle shall be riveted to the sheath at its longitudinal center as shown on Drawing number 81A5020A0001. The snap fasteners shall be centered and spaced on the holding strap as shown on Drawing number 81A5020A0001. The strap, when snapped closed, shall firmly hold the handle against the top of the sheath and shall prevent movement of the knife when the sheath is inverted or jarred. The hole near the bottom of the sheath for the insertion of a thong shall be punched out, not cut. The punch shall be made after assembly to assure alignment. After assembly, the sheath shall be trimmed to remove all loose ends, and rough edges shall be dyed to match the finished leather. The sheath shall conform to Drawing number 81A5020A0001 (see 4.5).

3.4.3 Sewing. All sewing shall be with nylon thread specified in 3.2.4. The stitch shall be type 301 conforming to FED-STD-751, five to seven stitches per inch (five to seven stitches per 25.4 millimeters). The stitching shall be straight and parallel to the leather edge. The sheath shall not contain any thread breaks, skips, run-offs, or needle chews. The thread ends shall be neatly trimmed (see 4.5).

3.4.4 Riveting. The sheath shall be riveted together with rivets as specified in 3.2.5. The head of the rivet shall be on upper side of the sheath and the split portion shall be flat aginst the underside of the sheath. All sharp edges shall be removed or turned under. The rivets shall be securely set but shall not straddle or cut the stitching, or unduly cut into the leather (see 4.5).

3.5 Performance. The performance characteristics of the knife shall be as follows:

3.5.1 Holding of the handle by the strap. When tested as specified in 4.8.3, the knife shall not move out of the position by more than 0.25 inch (6.35mm).

3.5.2 Cutting. When tested as specified in 4.8.5, the blade shall show no undue wear, such as turning over, nicking or breaking of any part of the cutting edge.

3.5.3 Flexibility. When tested as specified in 4.8.6, the blade shall not break, or fail to return to the original shape, when bent through an angle of 9°.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:32Z
Check the source to verify that this is the current version before use.

3.6 Dimensions. The dimensions and tolerances of the knife and sheath shall be as specified on Drawing numbers 81A5020A0000 and 81A5020A0001 (see 4.6).

3.7 Finish. All metal components of the knife shall be given a protective coating in accordance with type Z, class 2 of MIL-P-16232, after deburring and prior to assembly (see 4.5).

3.8 Identification of product. The letters US and the name or trademark of the manufacturer shall be stamped on the heel end of the blade as shown on Drawing number 81A5020A0000. The blade shall be indent stamped, without damage to the knife, with durable and legible letters in accordance with MIL-STD-130 (see 4.5).

3.9 Workmanship. Combat knives and sheaths shall be of high and uniform quality. The combat knife shall be free of sharp burrs and the sheath shall be free of sharp burrs or edges which may injure the hand of the user or adversely effect performance, reliability and durability. The appearance shall be of the highest commercial practice for this type item (see 4.5).

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

(a) First article inspection (see 4.3).
(b) Quality conformation inspection (see 4.4).
(c) Inspection of packaging (see 4.7).

4.3 First article inspection. The first article inspection shall consist of the examinations and tests as specified herein. Upon satisfactory completion of the first article inspection, the first article, together with recommendations and comments pertinent for use in monitoring production, shall be forwarded to the cognizant Government inspector. Approval of the first article does not preclude the requirements for performing the quality conformance inspections.

4.3.1 First article inspection routine. The first articles shall be subjected to inspection and tests specified in Table I in the order shown.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:32Z
Check the source to verify that this is the current version before use.

Table I. Examination and Tests.

Inspection	Requirement	Test Method
Materials	3.2	4.5
Visual	Section 3	4.5
Dimensions	3.6	4.6
Grain Size	3.2.1	4.8.1
Strap holding	3.5.1	4.8.3
Rockwell hardness	3.2.1	4.8.4
Cutting	3.5.2	4.8.5
Flexibility	3.5.3	4.8.6

4.3.2 First article sampling procedures. Sampling procedures shall be in accordance with MIL-STD-105 as specified in Table II. One or more major defects shall be cause for refusal to grant first article approval.

Table II. Sampling Procedures for Blades and Sheathed Knives.

Inspection	Inspection level	AQL	AQL expressed in terms of	Requirement	Method
Visual examination	II	2.5	Major defects per 100 units	Section 3	4.5
		4.0	Minor defects per 100 units		
Dimensional examination	II	4.0	Major defects per 100 units	3.6	4.6
Preparation for delivery	S-2	4.0	Major defects per 100 units	Section 5	4.7
Grain size	S-1	zero	----------	3.2.1	4.8.1
Hardness	S-1	zero	----------	3.2.1	4.8.4
Cutting	S-1	zero	----------	3.5.2	4.8.5
Strap holding	S-1	zero	----------	3.5.1	4.8.3
Flexibility	S-1	zero	----------	3.5.3	4.8.6

4.4 Quality conformance inspection. The quality conformance inspection shall be performed as specified in Table I.

4.4.1 Sample lot for inspection.

4.4.1.1 Blades. An inspection lot shall consist of all blades in the as quenched condition (untempered) made and treated under essentially the same conditions and from the same materials offered for acceptance at one time.

4.4.1.2 Sheathed knives. An inspection lot shall consist of all sheathed knives made under essentially the same conditions and from the same materials and components offered for acceptance at one time.

4.4.2 Sampling procedures. Sampling procedures shall be in accordance with MIL-STD-105 as specified in Table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:32Z
Check the source to verify that this is the current version before use.

4.5 Visual examination. The sheathed knife shall be examined for defects listed in Table III. The defects shall be classified as specified in Table III.

Table III. Classification of Defects for Visual Examination.

Defect	Classification	
	Major	Minor
1. Metal components:		
(a) Surface rough, misaligned, or containing cracks, burrs, dents, pit marks or otherwise defective.	101	
(b) Surface unclean or containing embedded foreign matter.	102 1/	
(c) Dented, misshaped, distorted or otherwise defective.	103	
(d) Phosphate or preservative coating missing.	104	
2. Leather:		
(a) Open briar, scratches or scars:		
- Single scratch longer than 2 inches (50.8mm).	105	
- Any scratch wider than 0.0625 inch (1.59mm).	106	
- Three or more short scratches.	107	
- Single scratch longer than 0.5 inch (12.7mm) but less than 2 inches (50.8mm).		201
- Two scratches, each less than 0.5 inch (12.7mm).		202
- Any die stab holes or cracky leather.		203
(b) Bronzing.	108	
(c) Fat wrinkles and heel scratches conspicuous at a distance of 4 feet (1.22m).	109	
(d) Bloom, hard or boney leather.		204
(e) Pitted leather:		
-Six pits anywhere or four pits within 0.25 inch (6.35mm).	110	
- Four pits anywhere or three pits within 0.25 inch (6.35mm).		205

1/ Major when it seriously affects the serviceability or appearance; otherwise, it is to be classified as a minor defect.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:32Z
Check the source to verify that this is the current version before use.

Table III. Classification of Defects for Visual Examination - Continued.

Defect	Classification	
	Major	Minor
(f) Slaughter cuts:		
- Cut longer than 0.50 inch (12.7mm).	111	
- Cut deeper than 0.25 of the thickness.	112	
- Cut wider than 0.0156 inch (0.397mm).	113	
- All other slaughter cuts.	114 1/	
(g) Cleanness:		
- More than one permanent spot.	115	
- Removable spots or stains not removed.		206
- Unremoved hair or other appearance factors.		207
(h) Flaky leather:		
- Two or more adjacent folds or wrinkles, each wider than 0.0625 inch (1.59mm).	116	
- Three adjacent folds or wrinkles, each over 0.0312 inch (0.794mm), but less than 0.0625 inch (1.59mm) wide.		208
3. Sheath components and assembly:		
(a) Any defective component or defect in assembly not classified herein.	117 1/	
(b) Any component or required operation omitted, but not classified herein.	118 1/	
(c) Flesh side of the leather on the outer side of the sheath.	119	
(d) Skived end of back inadequately attached.	120	
(e) Cut edges improperly colored or color not matching.		209
(f) Filler welt missing, improperly tapered or misaligned on outer edge.	121 1/	
(g) Sewing of sheath:		
(1) Needle chews.	122	

1/ Major when it seriously affects the serviceability or appearance; otherwise, it is to be classified as a minor defect.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:32Z
Check the source to verify that this is the current version before use.

Table III. Classification of Defects for Visual Examination - Continued.

Defect	Classification	
	Major	Minor
(2) Thread breaks, run-offs, incorrect type of stitch.	123	
(3) Thread color does not match the leather; various shades used.		210
(4) Loose seam.	124	
(5) Stitches per inch not within specified range.	125 1/	
(h) Strap holding not attached as required.	126 1/	
(i) Snap fastener:		
(1) Improper functioning. 2/	127	
(2) Loose, improperly clinched cutting into leather.	128	
(3) Any sharp burrs or metal slivers.	129	
(4) Not centered on strap.	130 1/	
(j) Riveting:		
(1) Insecurely set (i.e., pulling away from leather).	131	
(2) Improperly clinched, cutting of leather or stitches.	132	
(3) Improperly located or inverted (clinched on outside).	133 1/	
(4) Any sharp burrs or metal slivers.	134	
4. Knife handle:		
(a) Any component loose, handle not integral with blade.	135	

1/ Major when it seriously affects the serviceability or appearance; otherwise, it is to be classified as a minor defect.

2/ The snap fasteners shall be checked for proper functioning by snapping closed and unsnapping at least three times.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:32Z
Check the source to verify that this is the current version before use.

Table III. Classification of Defects for Visual Examination - Continued.

Defect	Classification	
	Major	Minor
(b) Leather portion not smooth, not grooved or not colored to match.	136 1/	
(c) Butt pin not peened or not ground smooth.	137	
(d) Tang protruding from butt plate surface.		211
(e) Guard not at right angles to the blade.	138 1/	
(f) Guard edges not flush with blade heel.	139	
5. Knife blade:		
(a) Blood groove not as specified.	140	
(b) Point broken or not sharp.	141	
(c) Cutting edge of blade not uniformly honed to a keen edge.	142	
(d) Cutting edge contains nicks or burrs.	143	
(e) Back edge of blade not ground to the tip.	144	
(f) Contour lines not clearly defined.		212
(g) Identification markings:		
(1) Missing or illegible.		213
(2) Method of application weakens tang.	145	
6. Color: Not as specified.	146 1/	

1/ Major when it seriously affects the serviceability or appearance; otherwise, it is to be classified as a minor defect.

4.6 Dimensional examination. The knife shall be examined for any nonconformance with dimensional requirements specified in Drawing numbers 81A5020A0000 and 81A5020A0001. Any deviations in the dimensions shall be classified as a major defect.

4.7 Examination of preparation for delivery. An inspection lot shall be expressed in units of one fully prepared shipping container containing sheathed knives, fully prepared for delivery from essentially the same materials and components offered for acceptance at one time. The sample

Source: https://assist.dla.mil -- Downloaded: 202610-19T07:32Z
Check the source to verify that this is the current version before use.

shipping container need not be sealed. Each of the fully prepared shipping containers selected as a sample unit from the lot shall be visually examined to determine that the packaging, packing and marking requirements conform to the requirements specified herein. The defects shall be classified as specified in Table IV.

Table IV. Examination of Packaging and Packing.

Examine	Defect	Classification Major
Markings	Missing, incorrect, illegible, improper size, location, sequence or method of application.	101
Materials	Any nonconforming component, component omitted, damaged or otherwise defective.	102
Workmanship	Incomplete closure of case liners or container flaps, loose strapping. Bulging or distortion of containers.	103
Weight and content	Number per container is more or less than required; gross weight exceeds maximum for container used.	104

4.8 Tests.

4.8.1 Grain size. The fracture grain size of the blade in the as quenched condition shall be determined by comparison with the Shepherd fracture grain size standards in ASTM E112. The blade shall be notched at the middle of the length and fractured by impact.

4.8.2 Paranitrophenol. The paranitrophenol content in the leather shall be determined as specified in method 6711 of FED-STD-311.

4.8.3 Strap holding. The effectiveness of the strap in holding the knife in the sheath shall be determined by the following test: with the strap snapped shut over the handle of the sheathed knife, grasp the sheath near the tip end without pinching the blade; raise the arm overhead with the knife butt uppermost then suddenly swing the arm downward through an arc in a rapid motion, stopping suddenly at the bottom of the arc. The guard of the knife shall not have moved away from the sheath at the completion of this hurl.

4.8.4 Rockwell hardness. The hardness of the steel shall be determined as specified in method 243, hardness scale C of FED-STD-151. The hardness of the blade shall be determined at the heel, center and point not less than 0.25 inch (6.35mm) from the cutting edge. The hardness of the tang in the transition area shall be determined in the center on the opposite side to the marking. Three hardness determinations shall be made on the remaining portion of the tang evenly distributed along its length.

Source: https://assist.dla.mil -- Downloaded: 202610-19T07:32Z
Check the source to verify that this is the currentversion before use.

4.8.5 Cutting. The keenness of the blade shall be tested by cutting at least ten shavings, not less than 0.0625 inch (1.59mm) thick, from a strip of oak or other wood of similar hardness. The blade shall enter into the wood at an angle of not less than 30° and all portions of the cutting edge shall be capable of producing a clean cut without undue effort. After ten shavings have been cut, the blade shall have no defects in the cutting edge.

4.8.6 Flexibility. The tip of the blade shall be secured by inserting the tip into a contoured metal fixture to a depth of 1.5 inches (38mm) from the point. Pressure shall be applied to the center of the hilt end of the blade. The pressure shall be of such magnitude that it shall cause bending of the blade through an angle of 9°. The blade shall not break during the bending and when the pressure is removed, the blade shall return to the original shape with no deformation.

5. PACKAGING

5.1 Preservation and packaging. Preservation and packaging shall be level B or commercial, as specified (see 6.2).

5.1.1 Level B. Each knife, prior to being packaged, shall be fully inserted into the sheath. The strap shall be snapped closed around the top of the handle. Each sheathed knife shall then be heat sealed within a snug fitting bag conforming to type I, class B, style 2 of MIL-B-117. Prior to and during the heat sealing operation, excess air shall be exhausted to the extent necessary to permit packaging of the required quantity in the fiberboard box. Ten bagged sheathed knives shall be placed within a fiberboard box conforming to PPP-B-636, type CF or SF, domestic class, variety SW, grade 275. All seams and joints shall be sealed with a minimum of 3 inch (76mm) wide tape, as specified in PPP-T-60.

5.1.2 Commercial. Commercial preservation and packaging shall be in accordance with MIL-STD-1188.

5.2 Packing. Packing shall be level A, B or commercial, as specified (see 6.2). Exterior containers (see 5.2.1, 5.2.2, and 5.2.3) shall be of a minimum tare weight and cube consistent with the protection required and shall contain equal quantities of identical stock.

5.2.1 Level A. Eight boxes, 80 sheathed knives, preserved and packaged as specified in 5.1, shall be packed in a shipping container conforming to one of the following:

PPP-B-576, class 2
PPP-B-585, class 3
PPP-B-591, class II
PPP-B-601, overseas type
PPP-B-621, class 2, style 4

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:32Z
Check the source to verify that this is the current version before use.

or, four boxes, 40 sheathed knives, preserved and packaged as specified in 5.1, shall be packed in a fiberboard container conforming to PPP-B-636, type CF or SF, weather resistant class, variety SW, grade V3c or V3s. Closure of wooden or fiberboard containers shall be as specified in the applicable box specification or appendix thereto.

5.2.2 Level B. A quantity of sheathed knives preserved and packaged as specified in 5.1 shall be packed in a shipping container conforming to one of the following:

PPP-B-576, class 1
PPP-B-585, class 1
PPP-B-591, class 1
PPP-B-601, domestic type
PPP-B-621, class 1, style 4
PPP-B-636, type CF, domestic class

5.2.3 Commercial. Commercial packing shall be as specified in MIL-STD-1188.

5.3 Marking.

5.3.1 Levels A and B. In addition to any special or other identification markings required by the contract (see 6.2), each unit pack, intermediate and exterior container and unitized load shall be marked as specifed in MIL-STD-129.

5.3.2 Commercial. Commercial marking shall be as specified in the requirements of MIL-STD-1188.

6. NOTES

6.1 Intended use. The knife with sheath covered by this specification is intended for combat use.

6.2 Ordering data. Purchasers should exercise any desired options offered herein, and acquisition documents should specify the following:

6.2.1 Acquisition requirements.

(a) Title, number and date of this specification.
(b) Whether first article is required (see 3.1).
(c) Level of preservation, packaging and packing required (see 5.1 and 5.2).

6.2.2 Data requirements. When this specification is used in an acquistion which incorporates a DD Form 1423, Contract Data Requirements List (CDRL), the data requirements identified below shall be developed as specified by an approved Data Item Description (DD Form 1664) and delivered in accordance with the approved CDRL incorporated into the contract. When the provisions of

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:32Z
Check the source to verify that this is the current version before use.

DAR 7-104.9 (n) (2) are invoked and the DD Form 1423 is not used, the data specified below shall be delivered by the contractor in accordance with the contract or purchase order requirements. Deliverable data required by this specification is cited in the following paragraphs.

Paragraph no.	Data Requirements	Applicable DID no.	Options
4.3	First Article Inspection Procedure	DI-T-4901	-------
4.3	First Article Inspection Report	DI-T-4902	-------
4.4	Production/Acceptance Inspection Procedures	DI-T-4903	-------
4.4	Production Inspection Reports	DI-T-4904	

(Copies of DIDs required by contractors in connection with specific acquisition functions should be obtained from the Naval Publications and Forms Center or as directed by the contracting officer.)

6.3 Instructions for first article. When first article is required, the contracting officer shall specify the location to which the first article is to be furnished for examination and test.

6.4 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Preparing activity:
Navy - MC

Project No. 1095-0161

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T07:32Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE MIL-K-20277F(MC)
KNIFE, COMBAT: WITH SHEATH

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?
   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED S/N 0102-LF-014-1802

Source: https://assist.dla.mil -- Downloaded: 202610-19T07:32Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY
Headquarters, U.S. Marine Corps
Washington, D.C. 20380

POSTAGE AND FEES PAID
DEPARTMENT OF THE NAVY
DOD-317

U.S.MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commandant of the Marine Corps
Headquarters, U.S. Marine Corps
(Code LMA-1)
Washington, D.C. 20380

FOLD

Source: https://assist.dla.mil -- Downloaded: 202610-19T07:32Z
Check the source to verify that this is the current version before use.