QUALIFICATIONS CERTIFIED
JUNE 1994

QPL-22397-23
21 June 1994
SUPERSEDING
QPL-22397-22
27 August 1991

QUALIFIED PRODUCTS LIST

OF

FSC 8040

PRODUCTS QUALIFIED UNDER MILITARY SPECIFICATION

MIL-A-22397

ADHESIVE, PHENOL AND RESORCINOL RESIN BASE (FOR MARINE SERVICE USE)

This list has been prepard for or by or for the Government in the acquisition of prducts covered by the subject specification and such listing of a product is not intended to and does not connote indorsement of the product by the Department of Defense. All products listd herein have been qualified under the requirements for the product as specified in the **latest effective issue of the applicable spcification. This list is subject to change Without notice; revision or amendment of this list will be issued as necessary. The listing of a procuct does not release the contractor from compliance with the specification requirements**

THE ACTIVITY RESPONSIBLE FOR THIS QUALIFIED PRODUCTS LIST IS THE NAVAL SEA SYSTEMS COMMAND, SEA 03R42, 2531 JEFFERSON DAVIS HWY, ARLINGTON, VA 22242-5160.

GOVERNMENT DESIGNATION	MANUFACTURER'S DESIGNATION	TEST OR QUALIFICATION REFERENCE	MANUFACTURER'S NAME AND ADDRESS
Grades A & B	CASCOPHEN RS-24OMD with Catalyst FM-124D 15-60 min. closed Assembly at 75°F Cure 150°F 7 hrs	Gen. Testing & Inspection Agency, Inc. Rpt. No. 2-6228	Borden Company 160 S. Second St. Springfield, OR 97477 Plant: Same address

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:13Z
Check the source to verify that this is the current version before use.

GOVERNMENT DESIGNATION	MANUFACTURER'S DESIGNATION	TEST OR QUALIFICATION REFERENCE	MANUFACTURER'S NAME AND ADDRESS
Grades A&B	Pencolite G-1260 with hardener G-1260-B (15-90 minutes closed assembly time at 80°F. ambient temperature; cured at 150°F glue line temperature for at least 6 hours)	PSNS E-209-D8a & PSNS E-209-D8b	INDSPEC chemical Corp. 411 7th Avenue Suite 300 Pittsburgh, PA 15219 Plant: Petrolia, PA 16050
Grades A&B	Penacolite adhesive G-4422 A with hardner G-4422-B (15-80 minutes closed assembly time at 75°F ambient temperature; cured at 1.50°F glue line temperature for at least 6 hours)	Koppers Rpts. Ref No. 2446 & Ref. No. 2517 Lots #611-32A and #610-2B	INDESPEC Chemical Corp. 411 7th Avenue suite 300 Pittsburgh, PA 15219 Plant: Petrolia, PA 16050
Grade B	CASCOPHEN LT-68D with Catalyst FM-282 15-60 min. Closed assembly at 75°F Cure 150°F 7 hrs	Gen. Testing & Inspection Agency, Inc. Rpt. No. 2-6228	Borden Company 160 S. Second St. Springfield, OR 97477 Plant: same address

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T13:13Z
Check the source to verify that this is the current version before use.