MIL-W-83144A(USAF)
AMENDMENT 3
8 June 1988
SUPERSEDING
AMENDMENT 2
16 November 1982

MILITARY SPECIFICATION

WEBBING, TEXTILE, WOVEN NYLON, ROLLED SELVAGE

This amendment forms a part of Military Specification MIL-W-83144A(USAF), dated 18 May 1970, and is approved for use with the Department of the Air Force and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

* Table I, under Width (including selvages); inches, under Types I through V, delete "2+0-1/16" and substitute "2±1/16."

PAGE 3

Add new paragraph 3.2.1 as follows:

"3.2.1 Resistance to light and heat. The nylon webbing shall not lose more than 25 percent of the original breaking strength upon exposure to the light and heat tests as specified in 4.5.1 and 4.5.2."

PAGE 11

Table V, under Breaking strength, Test Method FTMS 191, delete "2/ 5100" and substitute "4108."

At the bottom of Table V, delete footnote "2/" in its entirety.

Add new paragraphs 4.5.1 and 4.5.2 as follows:

"4.5.1 Resistance to light. Five tests shall be made. The test specimens shall be exposed in the accelerated weathering unit as specified in method 5804 of Fed Std 191. The specimens shall be placed side by side on the rack in such a manner that only the center portion of each specimen is exposed. Corex D filters and sunshine carbons shall be

FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:37Z
Check the source to verify that this is the current version before use.

used. The exposure time shall be 50 hours. The spray heads shall be shut off during the entire exposure period. At the end of the exposure period, the specimens shall be conditioned at 70°±2°F (21°1°C) and 65±2 percent relative humidity for 24 hours. They shall then be tested for breaking strength in accordance with method 4108 of Fed Std 191, and the percent of breaking strength (B.S.) loss shall be calculated as follows:

$$\frac{\text{Original B.S. - B.S. after aging}}{\text{Original B.S.}} \times 100 = \text{percent of B.S. loss}$$

"4.5.2 Resistance to heat. Five tests shall be made. The test specimens shall be suspended in a circulating air oven at a temperature of 180°±3°C be conditioned at 70°±2°F and 65±2 percent relative humidity for 24 hours. They shall then be tested for breaking strength in accordance with method 4108 of Fed Std 191 and the percent of breaking strength loss shall be calculated as specified in 4.5.1."

PAGE 12

Paragraph 4.6, lines 3 and 6. Delete "1/32" and substitute "1/16."

The margins of this amendment are marked with asterisks to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Air Force - 11

Reviewer Activity:
DLA - CT

Preparing Activity:
Air Force - 11

(Project No. 8305-F151)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:37Z
Check the source to verify that this is the current version before use.