[METRIC]

A-A-2803A
March 29, 1994
SUPERSEDES
A-A-2803
December 10, 1992

COMMERCIAL ITEM DESCRIPTION

NOTEBOOK, STENOGRAPHER'S

The General Services Administration has authorized the use of this commercial item description, for all Federal Agencies.

1. Scope. This description covers stenographer's notebook.

2. Salient characteristics:

2.1 Writing paper. The writing paper shall conform to the requirements of JCP D10, basis weight of 60 g/m^2 (16 lbs (17 x 22-500)). The color of the paper shall be white. The JCP D10 "below the line" requirements are not applicable.

2.2 Notebook board. Notebook board shall conform to the following physical requirements in Table 1.

Table 1

Characteristic	Requirement	TAPPI Test
Grain	Machine direction along the long dimension of notebook	T409
Thickness	0.8890 mm +/- 0.1270 mm (0.035 inch +/- 0.005 inch)	T411
Bursting Strength	680 kPa, min (100 lbs., min.)	T807

2.3 Color. The color or colors of the notebook board shall be at the option of the supplier.

2.4 Cleanliness. Notebook board shall be free from dirt spots, oil spots, foreign matter, and ink smears.

2.5 Wire hinge. The hinge of the notebook shall be metal wire with a diameter not less than 0.635 mm (0 025 inch) and coated so as to be bright finished. The hinge shall have a minimum of 24 coils.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to General Services Administration, Federal Supply Service, Engineering Branch, 26 Federal Plaza, New York, N.Y. 10278.

Distribution Statement A:
Approved for public release
Distribution is unlimited

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

2.6 Ruling of writing paper. Each page shall be ruled, both sides, parallel to the bound edge and bleed both edges. The spacing between the rulings shall be 7.620 - 9.652 mm (0.30 - 0.38 inch). There shall be a 19.050 mm (+ 4.763 mm, - 3.175 mm) (3/4 inch (+ 3/16, - 1/8 inch)) clearance between the top of the sheet to the first horizontal rule. The vertical line of the long dimension shall be located in the center of each page and shall not vary from the center by more than 3.175 mm (1/8 inch). The vertical line shall bleed both edges. All rulings shall be faint red in color.

2.7 Construction. The stenographer's notebook shall consist of a minimum of 80 sheets of writing paper, two stiff covers, and a wire hinge. The covers and writing paper shall be punched across one short dimension to accommodate the wire hinge. A "part hole" at the edge is permitted. The notebook shall be constructed so that the covers and pages can be turned without binding. The edges of the covers shall be flush with the edges of the sheets of writing paper.

2.8 Size of the stenographer's notebook. The stenographer's notebook shall be 152.401mm by 228.601mm +/- 1.588mm (6 by 9 inches +/- 1/16 inch).

2.9 Bleaching: To obtain an acceptable brightness, in accordance with the performance standards of this document, a chemical bleaching process may be used. When specified in the ordering data (See Ordering Data), the bleaching process shall not include the use of chlorine, chlorine dioxide, or other chlorine compounds. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

2.10 Workmanship. The notebook shall be free from holes (excluding hinge holes), tears, cuts, folds, scuff marks, lint, and shall not be crushed or warped. The ends of the wire hinge shall be bent in such a manner that there are not sharp edges protruding from the hinge. The notebook shall be free from any other defects which affect its utility or appearance and which may cause injury to the end user.

3. Quality Assurance Provisions. Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this commercial item description where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirement.

Table 2

Examine	Inspection Levels	AQLs (% defect)
Visual/Workmanship Defects	I	2.5
Dimensional Defects	S-3	4.0
Paper Characteristics Defects [1]	TAPPI	N/A

[1] Use TAPPI T410 for testing and with inspection level in accordance with TAPPI T400

3.1 Sampling for examination and tests shall be performed in accordance with MIL-STD-105, using the plans as specified in Table 2, unless otherwise stated. For the purpose of sampling, a lot shall consist of stenographer's notebooks. The sample unit shall be 1 stenographer's notebook for visual/workmanship and dimensional examination and one fully prepared shipping container for preparation for delivery examination, unless specified otherwise.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

3.2 Testing, when applicable, shall be in accordance with Part 2, Testing Standards and Definitions, of the Government Paper Specification Standards published by the Joint Committee on Printing. (Note: See individual TAPPI's for specific sampling instructions).

3.2.1 Acceptance criteria shall be as specified in Part 4, Acceptance Criteria, of the Government Paper Specification Standards published by the Joint Committee on Printing.

4. Regulatory Requirements.

4.1 The contractor shall certify that the minimum content standard for the writing paper shall be no less than 50% recovered materials including 20% post consumer materials in accordance with Executive Order 12873, section 504 (b), dated October 20, 1993 (See definition of post consumer materials and recovered materials in sections 203 and 205). As an alternative to meeting the standards of section 504(b) for all printing and writing papers, the minimum content standard shall be no less than 50% recovered materials that are a waste material byproduct of a finished product other than a paper or textile product which would otherwise be disposed of in a landfill, as determined by the State in which the facility is located, in accordance with Executive Order 12873, section 504 (c), dated October 20, 1993. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4.2 The contractor shall certify that the minimum content standard for the covers shall be no less than 90% postconsumer recovered materials in accordance with 40 CFR, Part 250. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4.3 Recycled Content Labeling. The recycled content shall be marked on the product or unit pack.

5. Preservation, packaging, packing, labeling, and marking. Preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

6. Application for copies of technical documents referenced herein: The issue date in effect on date of invitation for bids or request for proposal shall be apply.

(1) TAPPI test methods are available from the Technical Association of the Pulp and Paper Industry, P.O. Box 105113, Atlanta, GA 30348.
(2) MIL-STD-105 is available from Standardization Documents Order Desk, Bldg. 4D, 700 Robbins Ave., Philadelphia, PA 19111-5094.
(3) JCP specifications are for sale from Chief Paper Procurement Section, MMPP, U.S. Government Printing Office, North Capital and "H" St., NW, Wash DC 20401.
(4) Copies of Executive Order 12873, dated October 20, 1993 may be obtained from: The White House Publications Office, New Executive Office Building,White House, Att: Publications,Washington, DC 20500 (202) 395-7332
(5) Title 40, Code of Federal Regulation, Protection of Environment, Part 250 , Guideline for Federal Procurement of Paper and Paper Products containing Recovered Materials. Copies of the U.S. Code of Federal Regulations may be purchased with a VISA, Master Card, or prepaid check through: Government Printing Office, Washington, D.C. Phone: (202) 783-3238 When ordering, ask for: Title 40, Parts 190-250, Stock Number: 869-013-00-146-0

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.

7. Ordering Data. Purchasers should select the preferred options permitted herein, and include the following information in procurement documents:

A) Dimensions.
B) Packaging, packing labeling and marking.
C) Whether bleaching without use of chlorine, chlorine dioxide, or chlorine compound is required.

MILITARY INTERESTS:

DOD has waived coordination of this document

PREPARING ACTIVITY:
GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:26Z
Check the source to verify that this is the current version before use.