NOTICE: When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

PERMISSIBLE VARIATION IN DIMENSIONS

OUTSIDE DIAMETER (INCHES)	PERMISSIBLE VARIATION OUTSIDE DIAMETER (INCH)	PERMISSIBLE VARIATION WALL-THICKNESS (PERCENT)	OVALITY SHALL BE DOUBLE THE PERMISSIBLE VARIATION IN OUTSIDE DIAMETER WHEN THE WALL THICKNESS IS	PERMISSIBLE VARIATION IN CUT LENGTHS (INCH)
0 TO 0.499	±0.004	±10	LESS THAN 0.015 IN.	-0 +1/8
0.5 TO 1.499	±0.005	±10	LESS THAN 0.065 IN.	-0 +1/8
1.500 TO 3.499	±0.010	±10	LESS THAN 0.095 IN.	-0 +3/16
3.500 TO 5.499	±0.015	±10	LESS THAN 0.150 IN.	-0 +3/16
5.500 TO 7.999	±0.030	±10	LESS THAN 0.240 IN.	-0 +3/16

STRAIGHTNESS.- IN NO PORTION OF ANY PIECE OF TUBING SHALL THE DEPARTURE FROM STRAIGHTNESS EXCEED 0.060 INCH IN A LENGTH OF 3 FEET.

APPROVED 12 Jan 53 REVISED

THIS IS A DESIGN STANDARD. NOT USED AS A PART NUMBER

CUSTODIAN
Navy - BuAer
Air Force

PROCUREMENT SPECIFICATION
NONE

MILITARY STANDARD

TOLERANCES - SEAMLESS CORROSION-RESISTANT STEEL TUBING ROUND

MS33533(ASG)

SHEET 1 OF 1

Source: https://assist.dla.mil — Downloaded: 2026-10-23T17:04Z
Check the source to verify that this is the current version before use.