INCH-POUND

MIL-B-27486C
INT. AMENDMENT 1
3 August 1995

MILITARY SPECIFICATION

BOOTS, FLYER'S, FWU-3/P

This interim amendment forms a part of MIL-B-27486C, dated 4 October 1985, and is approved for use by all departments and agencies of the Department of Defense.

Page 2

2.1.1, under "SPECIFICATIONS, MILITARY", Add: "MIL-M-43758 Midsoles, Leatherboard".

Page 4

3.3.1, line 4, after "exceed", Delete: "22" and substitute: "28".

3.3.4, Delete in its entirety, and substitute with the following new paragraph:

"3.3.4 Lining leather. The leather for the quarter lining, the vamp lining, and the gusset (tongue) lining shall be soft, chrome-tanned, full grain or corrected grain cattlehide glove leather that is 2-1/2 to 3-1/2 ounces thick and shall not require a fungicide paranitrophenol treatment. The leather for the lining shall have only a light application of pigment finish applied to the top surface to obtain a sufficient uniformity in its color and finish. No loose, flanky or otherwise inferior cut parts shall be used.

a. Unless otherwise specified, the color of the leather lining shall be cream, light russet or gray color approximately matching color number 36492 of FED-STD-595.

AMSC N/A

FSC 8430

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-20T12:09Z
Check the source to verify that this is the current version before use.

b. As an alternate, the linings may be cut from 2-1/2 to 3-1/4 ounce thick, full grain chrome tanned or chrome vegetable retanned pigskin. The pigskin shall be finished on the grain side with a light application of aniline finish or on the flesh side with a clear lacquer sealer. When the flesh side is finished, the flesh side shall be smooth plated. The finished surface shall be worn next to the foot. Slaughter cuts, off stretch, or otherwise inferior cut parts shall not be used. Fungicide paranitrophenol treatment is not required."

Page 5

3.3.6, Midsoles, line 2, after "thickness.", Add the following:

"As an alternate, leatherboard midsoles in accordance with the requirements of MIL-M-43758 of 4-1/2 ± 1/2 iron thickness may be used".

Delete: 3.3.10 and 3.3.10.2 in their entirety.

3.3.10.1 Leather, leatherboard, or shoeboard., Delete in its entirety and substitute:

Add as new paragraph:

"3.3.10 Leather, leatherboard, or shoeboard. The leather, leatherboard or shoeboard counters shall conform to the requirements of MIL-C-41814 except that the leather or leatherboard counters' thickness shall be 5 to 5-1/2 irons."

Page 6

3.3.10.2, Table I. Requirements of polyethylene resin., Delete in its entirety.

Page 7

3.3.12.1, "Slide fastener tape.", line 4, after "and", Delete: "and amendment 1".

line 5, after "V-F-106E.", Delete: "The tape shall show a....only."

Page 9

3.3.20.2, line 3, after "from", Delete: "47 to 54" and substitute: "43 to 54".

Source: https://assist.dla.mil -- Downloaded: 2026-10-20T12:09Z
Check the source to verify that this is the current version before use.

3.3.23, lines 5 and 6, after "No." Add: "12 thru", after "brass" Add: "or steel".

Add as new paragraph:

"3.3.33 Leather, general leather components. All general leather components need not contain paranitrophenol. However, they may contain PNP provided it does not exceed 70 percent. When PNP is used in a component, the contractor's test report for that component shall indicate PNP content. Testing for PNP content shall be in accordance with method 6711 of FED-STD-311."

3.5 "Patterns and dies.", lines 6,7 and 8, after "exactly." Delete: "Last allowance, if required, may....patterns."

And substitute the following:

"When insulation lasting allowance is changed, the insulation shall always abutt the base of the insole rib. The stitched uppers may be sized up or down 1/2 size over/under the last size to accommodate variations in leather temper and maintain proper lasting margins."

3.7.3 "Crimping." line 1, after "tongues", Delete: "shall" and substitute: "may". Line 4, after "impressed." Delete: "The" and substitute: "When crimped, the".
line 5, after "time", Delete: "." and substitute: ", when crimped.".

3.7.4, "Marking quarter lining, permanent identification.", line 12, after "example: AB ", Add the following:

" As an alternative, the inside quarter lining of each boot shall be stamped with the correct size and width, the contractor's name, contract number, and the month and year (expressed in numerals) of the contract. Figures shall be Arabic and letters shall be Gothic, a minimum of 3/16 inch and a maximum of 3/8 inch in height."

3.7.5.1 "Closing quarters, vamps, vamp lining and quarter linings.", line 2, after type "304," Add: "or 404".

Source: https://assist.dla.mil -- Downloaded: 202640-20T12:09Z
Check the source to verify that this is the currentversion before use.

Page 17

3.7.5.3 Assemble lining to uppers., line 8, after "area.", Add the following:

" The vamp insulation shall be spot cemented to the lining, approximately half-way between the heel breast area and rear of the ball area on both sides of the boot. Deviation from referenced specification MIL-S-22777, Amendment 1,"

Page 18

3.7.9, line 7, after "outsole.", Add the following:

" When the alternate midsole is used, a single coat of adhesive shall be applied with or without buffing midsole."

3.7.9.2, line 3, after "machine.", Add the following: "As an alternate the lip score marks may be incorporated into the cutting die."

Page 22

4.3, line 3, Delete: "4.3.4", And substitute: "4.4.4".

Page 27

4.4.3.1.1 Examination of uppers after all fitting., Table VII, Quality of leather, under "Defect" after "Off stretch cut", Delete: "X", under "MAJOR" And substitute: "(*)" asterisk defect.

Page 30

Table IX, End item visual examination., under "MATERIAL", Delete: "Open grub or tick damage , brands, honey, loose, pipey, flanky, heavy fat wrinkles, veins, and any otherwise inferior leather", and substitute:

"Grub or tick damage, scars/scratches, brands or bony leather, fat wrinkles, flanky leather, course grain or veins, etc. that appreciably effect appearance/serviceability, (*) asterisk defect."

"A certificate of compliance shall be submitted and will be acceptable for the stated testing and inspection requirements contained in component or basic specification for the components. In addition to the certificate of compliance, a laboratory test report shall be provided with each component lot/shipment from each supplier for prime contractor records, and verification by the Government, when testing/inspection is deemed necessary on all components covered by certificate of compliance."

Source: https://assist.dla.mil -- Downloaded: 20260-20T12:09Z
Check the source to verify that this is the current version before use.

Component	Requirements Paragraph
Insoles	3.3.5
Midsoles	3.3.6
Heel pads	3.3.7
Welting	3.3.8
Counters	3.3.10, 3.3.10.1, 3.3.10.2
Stuck-on rib	3.3.11, 3.3.11.1
Slide fastener	3.3.12
Slide fastener	3.3.12.1
Insulation	3.3.13.1
Insulation	3.3.13.2
Insole reinforcement	3.3.15
Backseam tape	3.3.16
Insole cover	3.3.17
Box toes	3.3.18
Laces	3.3.19
Shanks	3.3.20.1
Shanks	3.3.20.2
Heel attaching nails	3.3.21
Tacks/nails	3.3.21
Heel seat fastener pegs/nails	3.3.23
Eyelets, qtr & slide	3.3.24
Bottom filler	3.3.25, 3.3.25.1, 3.3.25.2
Thread upper	3.3.26.1
Thread, goodyear	3.3.26.2, 3.3.26.2.1, 3.3.26.2.2
Thread, inseaming	3.3.26.2.2
Wax	3.3.27
Ink	3.3.28
Cleaning	3.3.29
Repairers	3.3.30
Fillers	3.3.31
Top finish	3.3.32

Preparing Activity:
DLA - CT

(Project 8430 - 0063)

Source: https://assist.dla.mil -- Downloaded: 20261-20T12:09Z
Check the source to verify that this is the current version before use.