MIL-P-10831B
Interim Amendment 1 (WC)
1 February 1966

MILITARY SPECIFICATION

PAPER, TARGET

This interim amendment is issued for use by the Department of the Army, with Military Specification MIL-P-10831B, dated 4 September 1964.

Page 2, paragraph 2.2 - Other publications. Add "Industrial Standard Method T402M" specified in paragraph 4.4.1, after the last technical manual indicated.

Page 4, paragraph 3.5.2 - Basic weight. In second line, delete "95 ± 5 pounds/500 sheets/24 inches x 36 inches," and substitute "120 ± 5 pounds/500 sheets/24 inches x 36 inches."

Page 5, paragraph 3.6.2 - Thickness. In second line delete "0.010 ± 0.0005 inch," and substitute "0.011 ± 0.0005 inch."

Page 5, paragraph 3.7 - Table I, Minimum physical characteristics. Delete Table I in its entirety and substitute the following:

Table I - Minimum Physical Characteristics

Characteristics	Type I	Type II
Tear, grams Cross direction	50	130

Page 5, paragraph 3.9 - Pick strength. In third line, delete "No. 11A" and substitute "No. 8A."

FSC 9310

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:28Z
Check the source to verify that this is the current version before use.

Page 14, Table II - Instructions for testing. Delete Table II in its entirety and substitute the following:

TABLE II - INSTRUCTIONS FOR TESTING

Characteristics	Specification Reference Requirement	Test(1) Method	Requirements Applicable to Lot Avg.	Number Determinations(2) Per Sample Unit	Results Reported As Numerically(3) to Nearest
Basic weight	3.5.1, 3.5.2	110	X	1 (Avg. of 5 sheets)	Pound
Thickness	3.6.1, 3.6.2	173	X	Avg. of 3	0.0001 inch
Tear, Grams Cross direction	Table I	170	X	Avg. of 5	Grams
Gloss	3.8	T-480M	X	Avg. of 3	Unit
Pick strength	3.9	T-459M	X	Avg. of 3	Number
pH	3.10	200	-	(2) Composite	0.1 pH Unit
Penetration	3.11	4.4.2	X	1 (10 rounds)	10 Percent

Note: 1. Three digit numbers refer to Federal Specification UU-P-31. Numbers preceded by the letter "T" refer to Tappi Standard Methods. Test Methods shall be performed in accordance with the applicable procedures, except that the stipulation as to the number of specimens to test, number of determinations to perform or number of results to report, shall be as indicated in this table. All testing shall be performed under atmospheric conditions as specified in 4.4.1.

2. The composite shall consist of representative portions taken from each sample unit and combined into a single sample.

3. Test reports shall include all values on which results are based.

4. Test specimens shall be immersed for 5 minutes in distilled water and tested as described in paragraph 4.3 and 4.4 of method 175 of UU-P-31.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:28Z
Check the source to verify that this is the current version before use.

Custodian:

Army - WC

Preparing activity:

Army - WC

Project No. 9310-A040

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:28Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:28Z
Check the source to verify that this is the current version before use.