MIL-P-10831B
INTERIM AMENDMENT 2 (WC)
30 June 1966
SUPERSEDING
INTERIM AMENDMENT 1(WC)
1 February 1966

MILITARY SPECIFICATION

PAPER, TARGET

This Interim Amendment is issued for use by the Department of the Army with Military Specification MIL-P-10831B, dated 4 September 1964.

Page 2, paragraph 2.2 - Other publications. Add TAPPI Standard "T402M".

Page 4, paragraph 3.5.2 - Basic weight. In second line, delete "95 ± 5 pounds/500 sheets/24 inches x 36 inches," and substitute "120 ± 5 pounds/500 sheets/24 inches x 36 inches."

Page 5, paragraph 3.6.2 - Thickness. In second line delete "0.010 ± 0.0005 inch," and substitute "0.011 ± 0.0005 inch."

Page 5, paragraph 3.7 - Table I, Minimum physical characteristics. Delete Table I in its entirety and substitue the following:

Table I - Minimum Physical Characteristics

Characteristics	Type I	Type II
Tear, grams Cross direction	50	130

Page 5, paragraph 3.9 - Pick strength. Delete entire paragraph and substitute: "3.9 Pick strength - The pick strength, or the surface bond strength, of the printing side (see 3.4.1) of the paper shall withstand not less than the values specified below with no picking, when tested as specified in Table II:

Type I Nr 6A Dennison Standard Wax

Type II Nr 8A Dennison Standard Wax"

FSC 9310

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:28Z
Check the source to verify that this is the current version before use.

Page 14, Table II - Instructions for testing. Delete Table II in its entirety and substitute the following:

TABLE II - INSTRUCTIONS FOR TESTING

Characteristics	Specification Reference Requirement	Test(1) Method	Requirements Applicable to Lot Avg.	Number Determinations(2) Per Sample Unit	Results Reported As Numerically to Nearest
Basic weight	3.5.1, 3.5.2	110	X	1 (Avg. of 5 sheets)	Pound
Thickness	3.6.1, 3.6.2	173	X	Avg. of 3	0.0001 inch
Tear, Grams Cross direction	Table I	170	X	Avg. of 5	Grams
Gloss	3.8	T-480M	X	Avg. of 3	Unit
Pick strength	3.9	T-459M	X	Avg. of 3	Number
pH	3.10	200	-	(2) Composite	0.1 pH Unit
Penetration	3.11	4.4.2	X	1 (10 rounds)	10 Percent

Note: 1. Three digit numbers refer to Federal Specification UU-P-31. Numbers preceded by the letter "T" refer to TAPPI Standard Methods. Test Methods shall be performed in accordance with the applicable procedures, except that the stipulation as to the number of specimens to test, number of determinations to perform or number of results to report, shall be as indicated in this table. All testing shall be performed under atmospheric conditions as specified in 4.4.1.

2. The composite shall consist of representative portions taken from each sample unit and combined into a single sample.

3. Test reports shall include all values on which results are based.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:08Z
Check the source to verify that this is the current version before use.

Custodian:

Army - WC

Preparing activity:

Army - WC

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:28Z
Check the source to verify that this is the current version before use.