INCH-POUND

MIL-P-10831B
INTERIM AMENDMENT 3 (AR)
08 December 1993
SUPERSEDING
INTERIM AMENDMENT 2 (WC)
30 June 1966

MILITARY SPECIFICATION

PAPER, TARGET

This Interim Amendment is approved for use within the Department of the Army with Military Specification MIL-P-10831B(WC), dated 4 September 1964.

PAGE 2

2.2: Add TAPPI Standard "T402M".

PAGE 3

* 3.2: Delete "...chip numbers 37855 through 37886 of Federal Standard No. 595. (See 6.1) " and substitute "...chip number 37855 or 37886 of Federal Standard No. 595. (See 6.1) "

PAGE 4

3.5.2: Second line, delete "...95 ± 5 pounds/500 sheets/24 inches x 36 inches," and substitute "120 ± 5 pounds/500 sheets/24 inches x 36 inches."

PAGE 5

3.6.2: In second line delete "0.010 ± 0.0005 inch" and substitute "0.011 ± 0.0005 inches"

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:28Z
Check the source to verify that this is the current version before use.

3.7: Delete Table I in its entirety and substitute the following:

TABLE I. Minimum Physical Characteristics

Characteristics	Type I	Type II
Tear, grams Cross direction	50	130

3.9: Delete in its entirety and substitute:

"3.9 Pick strength. The pick strength, or the surface bond strength, of the printing side (see 3.4.1) of the paper shall withstand not less than the values specified below with no picking, when tested as specified in Table II:

Type I Nr6A Dennison Standard Wax

Type II Nr8A Dennison Standard Wax"

* 3.10: Delete "6 ± 0.5 ph" and substitute "7 ± 1.5 ph"

See attached 3(14) page.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:28Z
Check the source to verify that this is the current version before use.

Delete Table II in its entirety and substitute the following:

TABLE II. Instructions for Testing

Characteristics	Specification Reference: Requirement	Test (1) Method	Requirements Applicable to Lot Avg.	Number Determinations (2) Per Sample Unit	Results Reported As Numerically (3) to Nearest
Basis weight	3.5.1, 3.5.2	110	X	1 (Avg. of 5 sheets)	Pound
Thickness	3.6.1, 3.6.2	173	X	Avg. of 3	0.0001 inch
Tear, grams cross direction	Table I	170	X	Avg. of 5	Grams
Gloss	3.8	T-480M	X	Avg. of 3	Unit
Pick strength	3.9	T-459M	X	Avg. of 3	Number
PH	3.10	200	-	(2) Composite	0.1 ph Unit
Penetration	3.11	4.4.2	X	1 (10 rounds)	10 Percent

Note: 1. Three digit numbers refer to Federal Specification UU-P-31. Numbers preceded by the letter "T" refer to TAPPI Standard Methods. Test Methods shall be performed in accordance with the applicable procedures, except that the stipulation as to the number of specimens to test, number of determinations to perform or number of results to report, shall be as indicated in this table. All testing shall be performed under atmospheric conditions as specified in 4.4.1.

2. The composite shall consist of representative portions taken from each sample unit and combined into a single sample.

3. Test reports shall include all values on which results are based.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:28Z
Check the source to verify that this is the current version before use.

* 6.2, In first line delete: "37855 through 37886" and substitute "37855 and 37886"

The margins of this amendment are marked with an asterisk or vertical lines to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Preparing activity:
Army-AR

(Project 9310-A113)

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T14:28Z
Check the source to verify that this is the current version before use.