MILITARY SPECIFICATION

CLOTH, KNIT, JERSEY, ARAMID

This amendment forms a part of MIL-C-85636(AS), dated 27 July 1984, and is approved for use within Naval Air Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

3.7, add to the end of the paragraph: "(see 6.2.1)"

PAGE 5

4.6, line 9, delete, "one or more units fail" and substitute "one or more sample units fail".

6.2.1, add:

"f. Length and put up requirements if different from standard (see 3.7)".

PAGE 7

Table I, delete and substitute:

TABLE I. Physical properties

Characteristics	Requirements
Weight, ounces per square yard	1.6 ± 0.4
Wales per inch (minimum)	28
Courses per inch (minimum)	31
Type of knit	Jersey
pH	5.0 - 8.0 1/

1/ Determined on the water extract of the cloth

AMSC N/A FSC 8305

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-28T11:13Z
Check the source to verify that this is the current version before use.

Table V, delete and substitute:

TABLE V. Test methods

Characteristic	FED-STD-191 Test Method
Denier per filament	1/
Twist	1/
Cut length of filament	1/
Material identification	1/
Weight	5041
Wales per inch	5070
Courses per inch	5070
pH	2811

1/ Unless otherwise specified, a certificate of compliance may be submitted for the stated requirements.

Preparing Activity
Navy - AS
(Project No. 8305-N113)

☆U.S. GOVERNMENT PRINTING OFFICE: 1986 — 606-038/45031

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T11:13Z
Check the source to verify that this is the current version before use.