COMMERCIAL ITEM DESCRIPTION

INK, DUPLICATING MACHINE STENCIL, PASTE, BLACK

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification TT-I-535.

This commercial item description covers the requirements for one type and two compositions of paste ink for use with stencil-process duplicating machines. The ink is formulated for use on hard-sized and mimeograph papers. The paste stencil ink shall be of the water-in-oil or oil-in-water emulsion type and of the following compositions:

Composition A - For use on single-cylinder (drum-type), internally inked machines.
Composition B - For use on dual-cylinder externally inked machines.

Salient characteristics.

The ink shall not contain oil soluble dyes or toners. It shall be free from caking, skinning, lumps or coarse particles, separated materials, and any materials that would tend to dry on the cylinder rollers, in the cylinder drum, or on the ink pad or tend to close or obstruct the openings in applicable style cylinders.

The consistency of composition A ink shall be 1200 to 1400 Saybolt Furol seconds at 100°F.

The ink shall not cause deterioration of the coating or base tissue of the stencil sheet and shall produce acceptable reproduction on both sides of the mimeograph paper.

When run with 40-pound chemical-wood mimeograph paper the ink shall produce clean and clear, black-image duplicated copies without strike-through or set off sufficient to interfere with the legibility of the finished work on either side of the mimeograph paper.

The ink shall not show an oily halo around character outlines when mimeographed on the 40-pound chemical-wood mimeograph paper.

When the printed copies are stacked, there shall be no objectionable transfer of ink from one sheet to the next.

The ink shall not run or drip off cylinders or drums, shall not leak, and shall not clog the stencil carrier, ink distributor, and other components of the machine, as applicable.

Color of ink on copies shall be uniformly black and clearly legible.

Specific gravity. Composition A ink shall be not greater then 1.060 at 25°C. Composition B ink shall be not greater than 1.100 at 25°C. The specific gravity of the ink shall be determined with a pycnometer bottle at 25°C, in accordance with test method ASTM D 891.

Fading. Ink impressions shall remain uniformly black with negligible loss in color value upon completion of the fading test shall be taken from the first 100 copies from typical run of stencil on the mimeograph machine. The specimen shall be exposed for a period of 48 hours to the radiation from a glass-enclosed carbon-arc such as the fading apparatus described in method No. 5660 of Fed Test Method Std. No. 191.

Odor. The ink shall at no time during a duplicating operation have or develop an objectionable odor.

Shelf life. The ink in original unopened containers (tubes) and not subjected to extremes of temperature and humidity, shall retain its utility and serviceability as defined by this description for not less than 12 months from date of receipt to the Government.

Usage instructions (composition B only). Comprehensive instructions for fitting the tube to the ink pump shall be provided by the manufacturer, and shall be enclosed with each tube of ink, or may be printed on the tube.

The issue of ASTM test method in effect on the date of the solicitation shall be used to determine compliance with this requirements.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:05Z
Check the source to verify that this is the currentversion before use.

Certification. The contractor shall certify that the product offered meets the salient characteristics of this description, and that the product conforms to the producer's own drawings, specifications, standards, and quality assurance practices, and is the same product sold in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements. The manufacture shall utilize recovered materials to the maximum extent practicable.

Packaging, packing and marking. The items shall be packaged in accordance with normal commercial practice and packed to assure acceptance by common carrier and provide product protection against loss and damage during multiple shipments, handling and storage. The shipping container shall be in compliance with the National Motor Freight Classification and Uniform Freight Classification. Shipping containers shall be marked as specified in the contract or order.

Federal Test Method Standards are available at GSA Business Service Centers and Specification and Consumer Information Distribution Section, Building 197, Washington Navy Yard, Washington, DC 20407.

ASTM Standards are available from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

Preparing activity:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.