MIL-C-43626A

20 December 1973

SUPERSEDING
MIL-C-43626
23 February 1969

MILITARY SPECIFICATION

CLOTH, INTERLINING, ACETATE AND COTTON

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers one type of acetate and cotton laminating cloth utilized as an interlining in clothing items.

2. APPLICABLE DOCUMENTS

★ 2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATION

FEDERAL

PPP-P-1134 - Packaging and Packing of Cotton and Cotton-Synthetic Fiber Blend Fabrics (Excluding Duck Fabrics)

STANDARDS

FEDERAL

FED-STD-4 - Glossary of Fabric Imperfections
FED-STD-191 - Textile Test Methods

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

FSC 8305

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:52Z
Check the source to verify that this is the current version before use.

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

PUBLICATION

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained from the Federal Trade Commission, Washington, DC 20580.)

3. REQUIREMENTS

3.1 Standard sample. The finished cloth shall match the standard sample for shade and shall be equal to or better than the standard sample with respect to all characteristics for which the standard sample is referenced (see 6.3).

3.2 Material.

3.2.1 Yarns.

3.2.1.1 Cotton. The cotton shall be carded, or combed drawn and spun into single yarns for warp and filling.

* 3.2.1.2 Acetate. The acetate yarn for warp shall be a dull continuous filament and shall be not less than 38 percent nor more than 45 percent, by weight, of the cloth, when tested as specified in 4.4.

3.2.1.3 Warp lay-out. The warp yarns shall be arranged by alternating 2 ends of cotton yarn and one end of acetate yarn, over the width of the warp.

3.3 Color. The color of the cloth shall be bleached white to match the standard sample. The degree of whiteness imparted by the bleaching shall not be supplemented by the use of optical brightener.

3.3.1 Color matching. The color of the finished cloth shall match the standard sample under natural (north sky) daylight, or artificial daylight having a color temperature of 7500° Kelvin and shall be a good approximation to the standard sample under incandescent lamplight at 2900° Kelvin.

3.3.2 Colorfastness. The white finished cloth shall show no more yellowing or loss in whiteness than the standard sample when tested for fastness to light, after 20 standard fading hours, and laundering as specified in 4.4. When no standard sample is available the degree of discoloration after exposure to light and laundering shall be not less than "good" when tested as specified in 4.4.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:52Z
Check the source to verify that this is the current version before use.

3.4 Physical requirements. The finished cloth shall conform to the requirements shown in table I when tested as specified in 4.4.

* TABLE I. Physical requirements

Weight oz./sq. yd. Minimum	Yarns per inch minimum		Weave
	Warp	Filling	
4.0	120	54	Plain

3.4.1 Width. The width shall be as specified (see 6.2) and shall be the minimum acceptable width, inclusive of selvages.

* 3.5 pH. The pH value of the water extract of the finished cloth shall be not less than 5.0 nor more than 8.5 when tested as specified in 4.4.

3.6 Shrinkage. The cloth shall not shrink more than 1.0 percent in the direction of the warp nor more than 1.0 percent in the direction of the filling when tested as specified in 4.4. The preshrinking process used shall not be identified by name or trademark, either on the cloth, ticket or package.

3.7 Length and put-up. Unless otherwise specified (see 6.2) the cloth shall be in continuous lengths, each not less than 40 yards and shall be put-up in rolls as specified in PPP-P-1134.

3.8 Fiber identification. Each roll shall be labeled, ticketed, or invoiced for fiber content in accordance with the Textile Fiber Products Identification Act.

3.9 Workmanship. The finished cloth shall conform to the quality established by this specification. The demerit points per 100 square yards when calculated as specified in section 4 shall not exceed the established maximum point values.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:52Z
Check the source to verify that this is the currentversion before use.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

* 4.2.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase document.

4.2.2 Examination of the end item. Examination of the end item shall be in accordance with 4.2.2.1 through 4.2.2.2.2.

* 4.2.2.1 Yard-by-yard examination. The required yardage of each roll shall be examined, and defects clearly noticeable at normal inspection distance (3 feet) shall be classified as listed. The defects found shall be counted regardless of their proximity to each other, except when two or more defects represent a single local condition of the cloth, only one shall be scored. A continuous defect shall be counted as one defect for each yard or fraction thereof in which it occurs. The sample unit shall be one linear yard. The acceptable quality level shall be 4.0 defects per 100 units (yards). The sample size shall be in accordance with level I of MIL-STD-105. The lot size shall be expressed in units of one yard each. The number of rolls selected shall be in accordance with table II.

Defects

Hole, cut or tear
Smash
Knots 1/
Spot or stain
Embedded crease or wrinkle
Two or more yarns out for more than nine inches

1/ To be scored when larger than limits shown on Sears Fabrics Defect Scales (see 6.4) E for slubs and D for knots.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:52Z
Check the source to verify that this is the current version before use.

4.2.2.2 Overall examination. Each defect shall be counted no more than once in each roll examined. The sample unit shall be one roll. The sample size (number of rolls selected as sample) and the acceptance number shall be as shown in table II.

Defects
Width less than specified 1/
Overall uncleanness

1/ Shall not be scored unless it occurs for more than 5 yards per piece.

TABLE II. Sample size

Lot size (yards)	Sample size (rolls)	Acceptance number
Up to and including 3200	3	0
3201 up to and including 10,000	5	0
10,001 up to and including 35,000	8	1
35,001 up to and including 150,000	13	2
150,001 and over	20	3

4.2.2.2.1 Examination for length.

4.2.2.2.1.1 Individual rolls. During the yard-by-yard examination, each roll in the sample shall be examined for length. Any length found to be less than the minimum specified, or more than two yards less than the length marked on the ticket, shall be considered a defect with respect to length. The lot shall be unacceptable if two or more rolls in the sample are defective in respect to length.

4.2.2.2.1.2 Total yardage in sample. The lot shall be unacceptable if the total of the actual lengths of rolls in the sample is less than the total of the lengths marked on the tickets. The rolls examined shall be those selected for the examination of individual rolls.

4.2.2.2.3 Examination for identification of preshrinkage process and non-compliance with the Textile Fiber Products Identification Act. During the yard-by-yard examination, each roll in the sample shall be examined for these defects. The lot shall be unacceptable if two or more rolls in the sample contain identification of the preshrinkage process by name or trade-mark on the cloth or ticket, or are not labeled or ticketed in accordance with the Textile Fiber Products Identification Act.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:52Z
Check the source to verify that this is the current version before use.

4.3 Examination of preparation for delivery requirements. An examination shall be made in accordance with the provisions of PPP-P-1134 to determine that packaging, packing and marking comply with section 5 requirements.

4.4 Testing of the end item. The methods of testing specified in FED-STD-191, wherever applicable, and as listed in table III shall be followed. The physical and chemical values specified in section 3, except where otherwise specified, apply to the results of the determinations made on the sample unit for test purposes as specified in the applicable test method. The sample unit shall be 2-1/2 continuous yards full width of the finished cloth for all physical and chemical tests. All test reports shall contain the individual values utilized in expressing the final result. The sample size shall be as shown in the list below. The lot shall be unacceptable if one or more sample units fail to meet any requirement specified.

Lot size (yards)	Sample size (units)
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

* TABLE III. Test methods

Characteristic	Requirement paragraph	Test method
Fiber identification		
Cotton	3.2.1.1	1200 1/
Acetate	3.2.1.2	1500 1/
Luster	3.2.1.2	1/
Bleached	3.3	1/
Optical brightener	3.3	4/
Acetate content	3.2.1.2	2510 2/
Warp layout	3.2.1.3	Visual 3/
Colorfastness		
Light	3.3.2	5660
Laundering	3.3.2	5610
Weight	3.4	5041
Yarns per inch		
Warp	3.4	5050
Filling	3.4	5050
Weave	3.4	Visual 3/
pH	3.5	2811
Shrinkage	3.6	5556

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:52Z
Check the source to verify that this is the current version before use.

2/ Based on the dry weight of the desized specimen.

3/ One determination shall be made from each sample unit and the result reported as "pass" or "fail".

4/ The supplier shall certify that no optical brightener has been used.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Levels A and C. The cloth put up as specified, shall be packaged in accordance with the applicable requirements of PPP-P-1134.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Levels A, B and C. The cloth shall be packed in accordance with the applicable requirements of PPP-P-1134.

5.3 Marking. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with the applicable requirements of PPP-P-1134.

6. NOTES

6.1 Intended use. The cloth covered by this specification is utilized as a laminating material, for shirt collars and nurse caps.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Width of cloth required (see 3.4.1).
(c) Length of roll required if other than specified (see 3.7).
(d) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 Standard sample. For access to standard sample address the procuring office issuing the invitation for bids.

* 6.4 Sears Fabric Defect Scales are available from Sears, Roebuck and Company, Department 769, "Fabric Defect Replica Kit", 925 South Homan Avenue, Chicago, IL 60607.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:52Z
Check the source to verify that this is the current version before use.

* 6.5 The margins of this specification have been marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and suppliers are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - SA
Air Force - 11

Review activities:

Army - MD
Air Force - 82

Preparing activity:

Army - GL

Project No. 8305-0125

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:52Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID

U.S. MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commander
US Army Natick Laboratories
ATTN: STSNLT-EQS
Natick, MA 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:52Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:52Z
Check the source to verify that this is the current version before use.