INCH-POUND

MIL-C-43627D
INTERIM AMENDMENT 1 (GL)
6 April 1992

MILITARY SPECIFICATION

CLOTH, DUCK, COTTON, PLIED YARNS, FIRE, WATER, WEATHER

AND MILDEW RESISTANT TREATED, LIGHTDRY FINISH

This interim amendment is approved for use within the Department of the Army, with MIL-C-43627D, dated 7 November 1990.

PAGE 4

3.5: Delete and substitute the following:

"3.5 Color. The color of the finished cloth shall be as specified (see 6.2) and shall match the standard sample."

3.5.3 and table II: Delete and substitute the following:

"3.5.3 Spectral reflectance. The spectral reflectance values (in percent) for the visible/near infrared wavelength range of 600 to 860 nanometers (nm) for Olive Green 107 and Olive Drab 7, and 700 to 860 nm for Desert Tan 459, Tan 380 and Tan 686 finished cloth shall meet the requirements specified in table II, when tested as specified in 4.4.3.

TABLE II. Spectral reflectance requirements

Wavelengths nanometers	Reflectance values (percent) Olive Green 107 and Olive Drab 7 Min.	Max.	Desert Tan 459 Tan 380 and Tan 686 Min.	Max.
600	3	12	-	-
620	3	12	-	-
640	3	12	-	-
660	3	13	-	-
680	3	15	-	-
700	3	21	25	58
720	5	30	25	59
740	7	42	25	61
760	11	50	26	62
780	17	56	27	63

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:52Z
Check the source to verify that this is the current version before use.

TABLE II. Spectral reflectance requirements (cont'd)

Wavelengths nanometers	Reflectance values (percent) Olive Green 107 and Olive Drab 7 Min.	Max.	Desert Tan 459 Tan 380 and Tan 686 Min.	Max.
800	24	60	28	64
820	32	63	30	66
840	37	65	33	68
860	40	66	36	69

"

PAGE 5

3.7.3, line 4, after "quinolinolate)": Insert "or copper napthenate combined with copper-8-quinolinolate to deposit not less than 0.35 percent and not greater than 1.48 percent total copper and shall have a percent of copper from copper-8-quinolinolate of not less than 0.05 percent and not greater than 0.18 percent."

Line 4: Delete "and the" and substitute "The".

PAGE 11

4.5.1, line 2: Delete "Olive Green and Forest Green 433" and substitute "Olive Green 107 and Olive Drab 7".

Line 3, after "Desert Tan 459": Insert ", Tan 686".

PAGE 15

6.6, line 4: Delete "National Bureau of Standards" and substitute "National Institute of Standards and Technology".

6.7: Delete and substitute the following:

"6.7 Spectrophotometers. Suitable spectrophotometers for measuring spectral reflectance in the visible/near infrared include the Diano Hardy, Diano Match Scan, Milton Roy Match Scan 2, Hunter D-54P-IR, Applied Color Systems Spectro Sensor I and II and CS-5, Hunter VIS/NIR Spectrocolorimeter and Macbeth 1500 with IR options."

Preparing activity:

Army - GL

(Project 8305-A460)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:52Z
Check the source to verify that this is the current version before use.