MIL-C-43603B
30 June 1980
SUPERSEDING
MIL-C-43603A
20 June 1972

MILITARY SPECIFICATION

CANTEEN, WATER, COLLAPSIBLE, 2-QUART CAPACITY

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a 2 quart capacity collapsible, plastic water canteen with or without a cover.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

L-P-390	-	Plastic, Molding and Extrusion Material, Polyethylene and Copolymers (Low, Medium and High Density).
UU-P-268	-	Paper, Kraft, Wrapping.
PPP-B-636	-	Boxes, Shipping, Fiberboard.
PPP-F-320	-	Fiberboard; Corrugated and Solid, Sheet Stock (Container Grade), and Cut Shapes.

MILITARY

MIL-C-43689	-	Cover, Water Canteen, 2-Quart, Collapsible (With Pile Lining).
MIL-C-51278	-	Cap, Water Canteen, Field Chemical-Biological Mask, M1

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Natick Research and Development Command, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

STANDARDS

FEDERAL

FED-STD-595 - Colors.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-147 - Palletized Unit Loads.
MIL-STD-1188 - Commercial Packaging of Supplies and Equipment

DRAWING

US ARMY NATICK RESEARCH AND DEVELOPMENT COMMAND

8-2-228 - Canteen, Water, Collapsible, 2 Quart Capacity; Assembly

(Copies of specifications, standards, drawings and publications required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer.)

LAWS AND REGULATIONS

21 CFR - Food and Drugs

(The Code of Federal Regulations (CFR) and the Federal Register (FR) are for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402. When indicated reprints of certain regulations may be obtained from the Federal agency responsible for the issuance thereof.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply:

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 638 - Tensile Properties of Plastics.
D 1505 - Density of Plastics by the Density-Gradient Technique.
D 1525 - Vicat Softening Point of Plastics.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race St., Philadelphia, PA 19103.)

3. REQUIREMENTS

3.1 Guide sample. Guide samples of the end item, when furnished, are solely for guidance and information to the contractor (see 6.3). Variation from this specification may appear in the sample, in which case this specification shall govern.

3.2 Material (see 6.5).

3.2.1 Resin purity. The ethylene-vinyl acetate (EVA) copolymer used in the manufacture of the canteen bladder and the polyethylene used in the manufacture of the canteen strap plus other substances used in the fabrication of the plastic shall conform to the requirements of 21 CFR - Part 177 - Indirect Food Additives: Polymers.

3.2.1.1 Plastic canteen bladder. The plastic canteen bladder shall be made from an EVA copolymer and shall contain no plasticizers. The vinyl acetate content shall be 18.5 ± 2 percent. The copolymer resin shall meet the requirements of table I when tested as specified in 4.3.1.

TABLE I. Physical characteristics of EVA resin

Characteristic	Requirement	
	Minimum	Maximum
Density, g/cm^3 at 23.4°C	0.935	0.943
Vicat softening point, °C	57	-
Tensile strength, pounds per square inch, psi	2000	-
Elongation, percent	650	-

3.2.1.2 Plastic canteen strap. The plastic strap of the canteen shall be made of low density polyethylene conforming to type I, class L, grade 2 of L-P-390. Clean, unfumed material in the form of imperfect parts, spruces, runners or other scraps of the same composition as the virgin material and produced in the molding or finishing operation, may be reground and mixed with the virgin material specified. When reground is mixed with the virgin material, the reground shall not exceed a level of 25 percent by weight of the blended mixture.

3.3 Design and construction. The design and construction of the canteen shall be as specified herein and as shown on the Drawing listed in 2.1. When the canteen is to be furnished with or without cover (see 6.2), the cover shall be in accordance with MIL-C-43689. The canteen capacity shall be not less than 1905 mL of water when tested as specified in 4.2.3. The color of the bladder, cap and strap shall approximate color No. 34087 olive drab lusterless of FED-STD-595. The strap and cap shall match the shade of the bladder body and neck.

3.3.1 Bladder. The bladder shall be blow molded from the material specified in 3.2.1.1 by a process in which the bladder is blown and molded in one piece and not as a result of a sheet forming operation. The neck may be molded separately and fused to the bladder in the blow molding operation. The lip of the neck which forms the sealing surface against the cap on assembly shall be flat, smooth and free from sink marks and depressions. The canteen neck shall be threaded with buttress type threads for a minimum of two full turns. The threads shall be fully formed and free from flash. The strap retention groove shall not be malformed, nor have a rough or feathered edge which may cause binding. There shall be no interference with the engagement of the cap to its fully seated position. The wall thickness at any point on the bladder shall be not less than 0.012 inch nor more than 0.056 inch, except as shown on Drawing 8-2-228 and at the parting line where the maximum thickness shall be 0.085 inch. The bladder shall be blow molded in such a manner that the material will be distributed to conform to the shape and general overall design as shown on Drawing 8-2-228. The bladder outer surface, except the identification area, shall have an embossed pebble grain finish to match the guide sample (see 6.3). All parting lines shall be free from flash except that flash extending not more than 1/32 inch at the bottom pinch-off area of the bladder shall be permitted. The grain shall be produced by the finish on the mold cavity and not by a protective coating or lacquer or other materials. The bladder weight shall be not greater than 110 grams and shall not be less than 60 grams when tested as specified in 4.2.3.

3.3.2 Strap. The strap shall be injection molded from the material specified in 3.2.1.2. Any die parting lines which may appear on the outside surface of the strap shall appear as lines only. No flash shall appear at the parting line. All gates shall be trimmed flush with the molding surface. The exterior surfaces of the both sides of the strap shall have a lusterless finish throughout and shall be of the uniform olive drab color specified in 3.3. The strap shall be free of dirt, dust, grease and foreign matter. The strap finish shall be produced from a die which has cavity surfaces finished in vapor blast, water hone or similar satin finish and not by the application of any protective coating, lacquers or other materials.

3.3.3 Cap. The cap shall be in accordance with MIL-C-51278 except that the color shall be as specified in 3.3.

3.4 Performance.

3.4.1 Porosity. The canteen shall not leak air when tested as specified in 4.2.3.

3.4.2 Leak resistance. The canteen shall show no leakage of water when tested as specified in 4.2.3.

3.4.3 Drop resistance. The canteen shall show no evidence of leakage of water or damage to the bladder, when tested as specified in 4.2.3.

3.5 Marking. One side of the bladder shall be permanently marked by an embossed molded in process, with US, year of manufacture, and contractor's name or trademark. The marking area shall be approximately a 1 inch square. The marking shall be clearly legible, and shall not impair the strength of the wall to which it is applied.

3.6 Workmanship. The canteen shall conform to the quality and grade of product established by this specification. The occurence of defects shall not exceed the applicable acceptable quality levels established herein.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the

TABLE II. Component testing

Characteristic	Requirement paragraph	Test method	No. or determinations per sample unit	Results reported to nearest
EVA resin:				
Density	3.2.1.1	ASTM D 1505	Average of 3	0.001 g/cm^3
Vicat softening	3.2.1.1	ASTM D 1525 1/ 2/	Average of 5	1°C
Tensile strength (psi) at yield	3.2.1.1	ASTM D 638 1/	Average of 6 (3 in each direction)	5 psi
Elongation (percent) at yield	3.2.1.1	ASTM D 638 1/	Average of 6 (3 in each direction)	5 percent

1/ Specimens shall be compression molded.

2/ Rate A shall be used for rate of temperature increase, and retesting provisions shall not be applicable.

4.2.1.1 Certification. Components and materials listed below may be accepted on the basis of a certificate of compliance for requirements specified in applicable paragraphs of this specification.

Component	Characteristic	Requirement paragraph
Plastic material	Purity	3.2.1
	Absence of plasticizers	3.2.1.1
	Vinyl acetate content	3.2.1.1

4.2.2 Inspection of the end item.

4.2.2.1 Examination of the end item. The end item shall be examined in accordance with the classification of defects in applicable subparagraphs below and at the inspection levels and acceptable quality levels (AQLs) specified in 4.2.2.2. The lot size for purposes of determining the sample size shall be expressed in units of one canteen for the examinations in 4.2.2.1.1 and 4.2.2.1.2. The sample unit for examinations in 4.2.2.1.1 and 4.2.2.1.2 shall be one finished canteen, including cap and strap.

4.2.2.1.1 Visual examination of canteen.

NOTE: Defects with an asterisk (*) in the classification column are to be classified as follows:

Major defect - When seriously affecting serviceability or appearance.
Minor defect - When affecting serviceability or appearance, but not seriously.

Examine	Defect	Classification Major	Minor
Quality and finish of canteen, neck, cap and strap	Color not as specified.	X	
	Exterior surfaces of the both sides of the strap not a lusterless finish.		X
	Any bubble, sharp crease, wrinkle, blister or gouge.	*	
	Any crazing, pit, chipping.	*	
	Outside surfaces of neck including threaded portion not smooth.	*	
	Finish produced by application of coating, lacquer, or other organic material.	X	
	Any cut, tear, hole, burn, break, or crack in canteen.	X	
	Weld mark, sink mark, shrink mark, dulling of surfaces, roughness, or abrasion in plastic.	*	
	Large permanent indentation, dimpling, or permament set.	*	
	Canteen has objectionable or vinegar-like odor.	X	
Design and construction	Varies from specified design and construction shown in specified drawing.	*	
	Not shape or contour specified.	*	
	Seam construction not as specified.	X	
	Taper in neck in excess of that permitted by drawing.	*	
Workmanship and assembly (general)	Any open seam.	X	
	Any patch, or repair of plastic material.	X	
	Malformed, distorted or out of round.	*	
	Any foreign matter or material not readily removable on the outside of the canteen that may cause damage to the material or have injurious effect on the user.	X	

Examine	Defect	Classification Major	Minor
Workmanship and assembly (general) (cont'd)	Any excessive lump on the inside or outside of the canteen, and of the same material as the canteen, not readily removable.		*
	Evidence of black or white spots on canteen.		*
	Any component misplaced or misaligned.	X	
	Any gate not trimmed flush with the molded surface.		X
	Any component missing.	X	
	Any component loose or not attached as specified.		*
	Heat seal of neck to canteen not complete or not free of excess material.		*
	Flash at the bottom pinch-off area of the bladder parting line extending more than 1/32 inch.		X
	Flash appearing on parting lines except as above.		X
Workmanship and assembly of neck	Sealing surface of lip is not flat, smooth, and free from sink marks or depression.		*
	Flash appearing on parting line.		*
	Neck not threaded with buttress type threads for a minimum of two full turns.		*
	Strap retention groove, malformed.	X	
	Strap retention groove has rough or feathered ledge.		*
	Rough surface below lower ledge of retention groove.		X
	Void or rough area in interior of neck.		*
Workmanship and assembly of cap	Flash appearing on parting line.		X
	Top surface of cap bulges in or out.		*
	Canteen cap will not screw onto neck of canteen.	X	
	Inside ring of cap not completely molded.	X	
	Cap binds when screwing onto neck of canteen.		*

Examine	Defect	Classification Major	Minor
Workmanship of threads	Threads on canteen neck stripped, not permitting tight closure.	X	
	Threads not smooth.	X	
	Threads not fully formed, not free from flash, misaligned at parting line or other imperfection.	X	
Cleanliness	Dirt, grease, dust or other foreign matter on inside of the canteen.	*	
Marking	Missing, incomplete, illegible, misspelled, not in specified location or not applied in specified manner.		X
	Marking impairs strength of wall to which it is applied.	*	

4.2.2.1.1.1 Examination for wall thickness. The end item shall be examined for wall thickness requirements specified in 3.3.1. For this examination, the bladder of the canteen shall be cut in half along the parting line and each half cut 90° to the parting line to give four quarters. Measurements shall be made on each quarter selected. Five measurements shall be made along the parting line and five areas selected throughout the body of each quarter. A failure of any sample unit to meet the requirement shall be scored as a defect. Measurements on a sample unit shall not be averaged. The sample unit shall be one finished canteen and the sample size shall be five regardless of lot size. Any defect found in this examination shall cause the lot represented by the sample to be rejected. Measurements shall be to the nearest 0.001 inch.

4.2.2.1.2 Dimensional examination of canteen. Any dimension, other than wall thickness, that is not within the specified tolerances shall be classified as a defect.

4.2.2.2 Inspection levels and AQLs. The inspection levels and AQLs expressed in defects per hundred units shall be as follows:

Examination paragraph	Inspection level	AQL Major	Total
4.2.2.1.1	I	4.0	10.0
4.2.2.1.2	S-2	One class	6.5

4.2.3 End item testing. Testing of the completely fabricated canteen shall be performed in accordance with table III for the characteristics shown therein. The sample unit shall be four completely fabricated canteens. The sample size for the designated lot size shall be as shown below. Any test failure shall be cause for rejection of the lot. All test reports shall contain the individual values utilized in expressing the final result.

Lot size (canteens)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 or more	5

TABLE III. End item tests

Characteristic	Requirement	Test method	Number of determinations per sample unit	Results reported as: Pass or fail	Results reported as: Numerically to nearest
Capacity	3.3	4.3.2	1	X	-
Weight	3.3.1	1/	1	-	0.5 g
Porosity	3.4.1	4.3.1	1	X	-
Leak resistance	3.4.2	4.3.2	1	X	-
Drop resistance	3.4.3	4.3.3	1	X	-

1/ A balance, sensitive to 0.5 gram, shall be used.

4.2.4 Packaging inspection. An examination shall be made to determine that the preservation, packing and marking comply with section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully packaged with the exception that it need not be closed. Defects of closure listed below shall be examined on shipping containers fully packaged. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per hundred units.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Any component missing. Any component damaged, affecting serviceability.

Examine	Defect
Workmanship	Inadequate application of components, such as incomplete closure of container flaps. loose strapping, improper taping, or inadequate stapling. Bulged or distorted container.
Content	Number of items per package or container is more or less than required.

4.2.5 Inspection for palletization. An examination shall be made to determine that the palletization complies with section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one palletized load fully packaged. The lot size shall be the number of palletized unit loads in the end item inspection lot. The inspection level shall be S-1 and the AQL shall be 6.5 defects per hundred units.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement.
Palletization	Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded with required straps as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.

4.3 Methods of inspection.

4.3.1 Porosity test. The canteen shall be inflated with air to 1 $\pm$ 0.1 psi and maintained at this pressure while submerged a minimum of 6 inches in water for 30 $\pm$ 5 seconds at room temperature. Any leakage of air shall be considered a test failure.

4.3.2 Capacity and leak resistance test. A measured volume of 1905 mL of distilled water at room temperature shall be poured into the canteen. The test for capacity of the canteen shall be considered passed if no overflow occurs. Add additional water to the canteen (if required) till brimmed, then tightly cap the canteen and suspend it in an inverted position (cap at bottom) for 6 hours and examine for leakage. The test for leak resistance of the canteen shall be considered passed if, when the cap is removed, the canteen is still brimming and no dripping of water has occurred during the test.

4.3.3 Drop resistance test. A new canteen shall be completely filled with water at room temperature, capped tightly and dropped from a height of 6 feet (1829 mm) onto a smooth concrete floor. Any resultant leakage or damage to the bladder shall be considered a test failure.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Canteen with cover, when procured as an assembly (see 6.2). Each canteen assembly, consisting of a canteen cover and sling, shall be arranged as hereinafter specified. The canteen shall have the cap screwed on finger-tight with the strap turned under the cap, and then be placed within the cover. The sling shall be neatly folded (with the snap fasteners captured inside the webbing) and securely tied with cotton tape or twine, and then be placed against the canteen inside the cover. The cover flaps and keepers shall be closed. Five canteen assemblies shall be stacked upright side-by-side, necks up and alternately reversed, and then securely crosstied with cotton tape or twine to form a bundle measuring approximately 12-1/2 by 9-3/4 by 9 inches.

5.1.1.2 Canteen, when procured separately (see 6.2). Preservation is not required.

5.1.2 Commercial. Canteen assmeblies shall be preserved in accordance with MIL-STD-1188.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A packing.

5.2.1.1 Canteen with cover, when procured as an assembly (see 6.2). Forty canteen assemblies, preserved as specified in 5.1.1.1, shall be packed in the fiberboard shipping container specified in 5.2.1.3. The approximate inside dimensions of the shipping container and the packing arrangement of the canteen assemblies within the container shall be in accordance with the applicable requirements specified in table IV.

TABLE IV. Approximate inside dimensions of shipping containers and pack arrangement of canteen assemblies

Approximate inside dimensions of containers (inches) 1/	Pack arrangement within containers length x width x depth
25-1/2 x 20 x 18	2 x 2 x 2 (necks up in first tier, necks down and offset nested in second tier to make an even height pack)

1/ Approximate dimensions are furnished as a guide only.

5.2.1.2 Canteen, when procured separately (see 6.2). Forty canteens, with caps screwed on finger-tight and straps turned under the caps, shall be packed in a fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. The inside of each container shall be fitted with two 20-celled fiberboard partitions. The inside dimensions of each partition cell shall be approximately 2-3/4 by 9 by 9 inches. The upper and lower partitions shall be separated by a layer (tier) fiberboard pad. The length and width dimensions of each layer pad shall be 1/4 inch less than the corresponding inside dimensions of the shipping container. Each partition and layer pad shall be fabricated from fiberboard conforming to grade W5c or PPP-F-320. The canteens shall be packed upright (caps facing the center) 10 in length, 2 in width, and 2 in depth within a shipping container. Inside dimensions of each shipping container shall approximate 30 inches in length, 18-1/4 inches in width, and 18-1/4 inches in depth. Approximate dimensions are furnished as a guide only. Each shipping container shall have the contents completely covered on the top and bottom with a sheet of 30 pound minimum basis weight kraft paper conforming to type I, grade B of UU-P-268. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V and reinforced as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.2.4.

5.2.1.3 Fiberboard shipping container. The fiberboard shipping container for the canteen assemblies specified in 5.2.1.1 shall conform to style RSC-L, grade V2s of PPP-B-636. The inside of each fiberboard container shall be fitted with a box liner conforming to type CF, class weather-resistant variety DW, grade V15c of PPP-B-636. Each container shall have the contents completely covered on the top and bottom with a sheet of 30 pound minimum basis weight kraft paper conforming to type I, grade B of UU-P-268. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V and reinforced as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.2.4.

5.2.2 Level B packing.

5.2.2.1 Canteen with cover, when procured as assembly (see 6.2). Forty canteen assemblies, preserved as specified in 5.1.1.1, shall be packed in the fiberboard shipping container specified in 5.2.2.3. The approximate inside dimensions of the shipping container and the packing arrangement of the canteen assemblies within the container shall be in accordance with the applicable requirements specified in table IV.

5.2.2.2 Canteens, when procured separately (see 6.2). Forty canteens, with caps screwed on finger-tight and straps turned under the caps, shall be packed in a fiberboard shipping container conforming to style RSC, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each container shall be fitted with two 20-celled fiberboard partitions. The inside dimensions of each partition cell shall be approximately 2-3/4 by 9 by 9 inches. The upper and lower partition shall be separated by a layer (tier) fiberboard pad. The length

and width dimensions of each layer pad shall be 1/4 inch less than the corresponding inside dimensions of the shipping container. Each partition and layer pad shall be fabricated from fiberboard conforming to type CF, class domestic, variety SW, grade 275 of PPP-F-320. The canteens shall be packed upright (caps facing the center) 10 in length, 2 in width, and 2 in depth within a shipping container. Inside dimensions of each shipping container shall approximate 30 inches in length, 18-1/4 inches in width, and 18-1/4 inches in depth. Approximate dimensions are furnished as a guide only. Each shipping container shall have the contents completely covered on the top and bottom with a sheet of 30 pound minimum basis weight kraft paper conforming to type I, grade B of UU-P-268. Each container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.2.4.

5.2.2.3 Fiberboard shipping container. The fiberboard shipping container for the canteen assemblies specified in 5.2.2.1 shall conform to style RSC-L, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each fiberboard container shall be fitted with a box liner conforming to class domestic, variety DW, grade 275 of PPP-B-636. Each container shall have the contents completely covered on the top and bottom with a sheet of 30 pound minimum basis weight kraft paper conforming to type I, grade B of UU-P-268. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.2.4.

5.2.2.4 Weather-resistant containers. When specified (see 6.2), the fiberboard shipping containers specified in 5.2.2.2 and 5.2.2.3 shall be grade V3c, V3s, or V4s fiberboard boxes fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.2.4.

5.2.3 Commercial packing. Canteen assemblies or separately procured canteens, preserved as specified in 5.1 (when applicable), shall be packed in accordance with MIL-STD-1188.

5.3 Palletization. When specified (see 6.2), canteens packed as specified in 5.2, shall be palletized in accordance with load type I of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L. Pallet patterns shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course. If the container is of a size which does not conform to any of the pallet patterns specified in MIL-STD-147, the pallet pattern used shall first be approved by the contracting officer.

5.4 Marking. In addition to any special marking required by the contract, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or MIL-STD-1188, as applicable.

6. NOTES

6.1 Intended use. The collapsible canteen with or without a cover is intended for use in temperate and tropical environments by individual military personnel for carrying drinking water.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) When the canteen and cover are to be procured as an assembly (see 3.3, 5.1.1.1, 5.2.1.1, and 5.2.2.1).
(c) When the canteen is to be procured separately (see 3.3, 5.1.1.2, 5.2.1.2 and 5.2.2.2).
(d) Selection of the applicable levels of preservation and packing (see 5.1 and 5.2).
(e) When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.4).
(f) When palletization is required (see 5.3).

6.3 Guide sample. For access to the guide sample, address the procuring activity issuing the invitation for bids.

6.4 Material shrinkage. Since the shrinkage characteristics of plastic materials are well recognized, it is the responsibility of the contractor to compensate for this factor in mold design in order to produce and supply a finished product in accordance with the specified drawings.

6.5 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the specification (see 3.2).

6.6 Changes from previous issue. Asterisks are not used in this revision to identify the changes with respect to the previous issue, due to the extensiveness of the changes.

Custodians:

Army - GL
Navy - SA
Air Force - 99

Preparing activity:

Army - GL

Project No. 8465-0650

Review activity:

Army - MD

User activity:

Navy - MC

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-C-43603B - Canteen, Water, Collapsible, 2-Quart Capacity

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*	TELEPHONE NO.
	DATE

DD FORM 1 OCT 76 1426 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.