MIL-P-43604A(GL)

22 September 1971
SUPERSEDING
MIL-P-43604(GL)
10 October 1968

MILITARY SPECIFICATION

PLASTIC TUBING (FLEXIBLE, POLYURETHANE FILM)

1. SCOPE

1.1 This specification covers the requirements for one type and size of flexible polyurethane plastic film (see 6.1 and 6.4).

1.2 Classification.- The film shall be in either of the following colors.

Color a - Aviation orange.
Color b - Natural.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

UU-P-268	-	Paper, Kraft, Untreated, Wrapping.
PPP-B-591	-	Boxes, Shipping, Fiberboard, Wood-Cleated.
PPP-B-601	-	Boxes, Wood, Cleated-Plywood.
PPP-B-636	-	Boxes, Shipping, Fiberboard.
PPP-D-723	-	Drums, Fiber.
PPP-T-45	-	Tape, Gummed, Paper, Reinforced and Plain, For Sealing and Securing.
PPP-T-60	-	Tape: Pressure-Sensitive Adhesive; Waterproof, For Packaging.
PPP-T-76	-	Tape, Pressure-Sensitive, Adhesive Paper, (For Carton Sealing).

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:48Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-L-10547 - Liners, Case, and Sheet, Overwrap; Water-Vaporproof Or Waterproof, Flexible

STANDARDS

FEDERAL

FED-STD-406 - Plastic, Methods of Testing.
FED-STD-191 - Textile Test Methods.
FED-STD-595 - Colors.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-147 - Palletized And Containerized Unit Loads 40" x 48" Pallets, Skids, Runners, Or Pallet Type Base.

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting officer).

2.2 Other publications.- The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issues in effect on date of invitation for bids or request for proposal shall apply.

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to American Trucking Associations, Inc., Tariff Order Section, 1616 P Street, N. W., Washington, D.C. 20036.)

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 202, Union Station, 516 W. Jackson Blvd., Chicago, Illinois 60606.)

Source: https://assist.dla.mil -- Downloaded: 20260-21T21:48Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Material.- The flexible film covered by this specification shall be made from a suitably formulated thermoplastic, heat sealable, modified, polyurethane plastic material. If the film is for use in contact with potable water the formulation shall be approved by the Surgeon General, Department of the Army (see 6.3).

3.2 Construction.- The film, made of the material specified in 3.1, shall be furnished in rolls of extruded tubing as produced in applicable commercial manufacturing processes.

3.3 Physical requirements.- Film shall meet the requirements of table I when tested as specified in 4.3.6.

TABLE I.- Physical requirements of film

Characteristics	Requirement
Size (thickness), inches	0.005 + 0.002, - 0.0005
Tensile strength, minimum pounds per square inch	
Machine direction	4500
Transverse direction	4500
Elongation at break min. percent	
Machine direction	700
Transverse direction	700
Stress at 10 percent elongation, min. p.s.i.	
Machine direction	80
Transverse direction	80
Tear strength, gms/mil, min.	
Machine direction	150
Transverse direction	150

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:48Z
Check the source to verify that this is the current version before use.

3.4 Bonding strength.- The film shall be capable of being bonded to itself by commercially available heat or electronic sealing devices and methods. The strength of such bonds in either the machine or transverse direction of each film shall be not less than 6.0 pounds per inch of width and the average seam strength shall be not less than 7.5 pounds per inch of width. Bonded samples shall be tested as specified in 4.3.6 not less than 24 hours after the date of bonding.

3.5 Breaking strength of folds. The breaking strength of each flat side fold of rolled film, of each color, shall be not less than 2250 pounds per square inch (p.s.i). The flat side folds shall be tested as specified in 4.3.6 not less than 24 hours after the date of rolling.

3.6 Dimensions.-

3.6.1 Rolls of film.- The width of the rolls of film shall be as specified in the contract or order (see 6.2). The tolerance shall be ± 1/2 inch. Width shall be measured on the manufacturer's rolls of tubing. The rolled film tubing shall be furnished in continuous lengths of not less than 50 yards. No more than twenty percent of the rolls in a given order shall be spliced rolls.

3.7 Color.-

3.7.1 Color a.- The color a polyurethane film shall be pigmented or printed to approximate Aviation Orange color No. 12197 of FED-STD-595. The color shall be uniform throughout the film. The color a film shall be used as the outermost layer of the container (see 6.1).

3.7.2 Color b.- The color b polyurethane film shall be a natural color.

3.8 Finish.- The film shall have a smooth, glossy finish on both sides.

3.9 Odor.- The color a and b film shall be free from objectionable odors when tested as specified in 4.3.6.

3.10 Workmanship.- The film shall be clean, finished and free from dirt, oil, foreign matter, rough or sharp edges, scratches, scuffs, creases, blisters, bubbles, pimples, streaks, fish eyes or gels, tears, cuts and holes (including any pinholes and cracks (see 4.3.6). The occurrence of defects shall not exceed the acceptable quality levels (AQL's) specified herein.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:48Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.- Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificates of compliance.- Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Inspection.- Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.2.1 Component and material inspection.- In accordance with 4.1, above, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase document.

4.2.1.1 Certification.- Components and materials listed below may be accepted on the basis of a supplier's certificate of compliance for requirements specified in applicable paragraphs of this specification:

Component	Characteristic	Requirement paragraph
Plastic material	Composition	3.1

4.3 Examination of the end item.- The end item shall be examined for defects in applicable sub-paragraphs below and at the inspection levels and acceptable quality levels (AQL's) set forth in 4.3.5. Random samples shall be drawn from each lot of end items for examination of visual and dimensional defects. The lot size for purposes of determining the sample size in accordance with MIL-STD-105 shall be expressed in units of one roll each, of the specified color for the examinations in 4.3.1, 4.3.2 and 4.3.3.

4.3.1 Visual examination.- The finished plastic material shall be examined for defects in appearance, construction, assembly and workmanship. The sample unit selected shall be four consecutive yards full roll width for the examination for defects within rolls. The sample unit shall not be taken from the first or last convolutions of the roll. No more than three sample units shall be examined from any one roll. All sides of the material, as applicable, shall be examined. Defects shall be scored only once within each sample unit for rolls.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:48Z
Check the source to verify that this is the current version before use.

Examine	Defect
Color	
Color a	Not as specified. Not uniform.
Color b	Not as specified. Not uniform.
Finish	Not finished as specified on both sides.
Workmanship	Any dirt, oil, or foreign matter affecting appearance. Any gouge or scratch. Any hole. Any streak, tear, porous area, blister or pimple. Any mottling, wrinkle or fold (other than side fold in rolls of extruded tubing). Any cut, bubble, scuff or crease. Any rough or sharp edge or chipping. Any fish eye, gel or unfused rein particles affecting serviceability. Any spot, stain or other discoloration affecting appearance.

4.3.2 Dimensional examination.- The sample unit shall be one complete roll of plastic film, as applicable.

Examine	Defect
Width of roll	Any width 1/2 inch less than specified. Any width exceeding that specified by more than 1/2 inch.
Length	Less than specified.

4.3.3 Defects in rolls.- The sample unit shall be one complete roll as applicable.

Examine	Defect
Rolls	Not suitably restrained from unwinding. Material blocks to the extent that unrolling causes damage or tearing, rendering material unserviceable. Roll not continuous. Roll length less than 50 yards.

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:48Z
Check the source to verify that this is the currentversion before use.

4.3.4 Examination of preparation for delivery requirements.- An examination shall be made to determine that the packaging, packing, and marking complies with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully prepared for delivery with the exception that it need not be sealed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per 100 units.

Examine	Defect
Marking (exterior and interior)	Incorrect, incomplete, illegible; omitted; of improper size, location, sequence or method of application.
Materials	Any nonconforming component; component missing or damaged.
Workmanship	Inadequate application of components, such as incomplete closure of container flaps, case liners, improper taping, loose or inadequate sealing, strapping or stapling.
	Bulged or distorted container.
Weight	Weight of contents per shipping container exceeds amounts specified.

4.3.4.1 Examination for palletization.- An examination shall be made to determine that the palletization complies with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one palletized unit load fully prepared for delivery. The lot size shall be the number of palletized unit loads in the end item inspection lot. The inspection level shall be S-1 and the AQL shall be 6.5 defects per 100 units.

Examine	Defect
Finished dimension	Length, width, or height exceeds specified maximum
Palletization	Not as specified. Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded with required straps as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence or method of application.

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:48Z
Check the source to verify that this is the currentversion before use.

4.3.5 Inspection levels and acceptable quality levels (AQL's).- The inspection levels for determining the sample size and the acceptable quality levels (AQL's) expressed as defects per hundred units shall be as follows:

Examination paragraph 1/	Inspection levels	AQLs
4.3.1	I	2.5
4.3.2	S-2	2.5
4.3.3	S-2	2.5

1/ The rolls used in examination under 4.3.1 may be used in examinations under 4.3.2 and 4.3.3.

4.3.6 Testing of the end item.- The end item shall be tested for the characteristics listed in table II for each lot presented for inspection. The lot size shall be expressed in units of one roll each. The sample unit shall be 21 square feet of film. Each sample unit shall be sampled from a different roll. The sampling plan shall be in accordance with the following:

Lot size (lot unit)	Sample size (sample unit)
800 or less	2
801 up to and including 22,000	3
22,001 and more	5

There shall be no evidence of failure of any sample unit to meet the requirement as specified. The number of determinations per sample unit as well as the reporting of test results shall be as required by the referenced test method, except as otherwise indicated in table II.

TABLE II.- Instructions for testing of the end item

Characteristic	Specification reference: Requirement	Specification reference: Test method	Requirement applicable to: Indiv. unit	Requirement applicable to: Lot avg.	Determinations per sample unit	Results reported as: Pass or fail 1/	Results reported as: Numerically to nearest 2/
Thickness	3.3	4.4.2		X	Avg. of 5		0.0001
Tensile strength	3.3	4.4.3	X		Avg. of 5		p.s.i.
Elongation	3.3	4.4.3	X		Avg. of 5		percent
Stress	3.3	4.4.3	X		Avg. of 5		p.s.i.
Tear strength	3.3	4.4.4	X		Avg. of 5		gram.

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:48Z
Check the source to verify that this is the current version before use.

TABLE II.- Instructions for testing of the end item (cont'd)

Characteristic	Specification reference: Requirement	Specification reference: Test method	Requirement applicable to: Indiv. unit	Requirement applicable to: Lot avg.	Determinations per sample unit	Results reported as: Pass or fail 1/	Results reported as: Numerically to nearest 2/
Bonding strength	3.4	4.4.3	X		1	X	
Breaking strength of folds	3.5	4.4.5	X		1		p.s.i
Odor	3.9	4.4.6	X		1	X	
Pinholes and cracks	3.10	4.4.7	X		1	X	

1/ If failure is indicated, report description of failure.

2/ Test report shall include all values on which results are based.

4.4 Tests.-

4.4.1 Standard conditioning.- Unless otherwise specified, samples for test shall be conditioned at a temperature of 73.5° ± 2°F. (23.1° ± 1.1°C.) and a relative humidity of 50 ± 4 percent for a period of not less than 16 hours.

4.4.2 Thickness.- The gage used for the measurement of thickness shall be a dead weight type equipped with a dial graduated to read directly to 0.0001 inch. The presser foot shall be circular with a diameter of 0.25 ± 0.01 inch. The presser foot and moving parts connected therewith shall be weighted so as to apply a total load of 3 ± 0.1 ounce to the specimen. The presser foot and anvil surface shall be plane to within 0.0001 inch and parallel to each other within 0.0001 inch. Measurement shall be taken across the full width of the roll. No individual measurement shall be less than the nominal thickness and the tolerance and the average of all measurements on the unit shall not be greater than the nominal thickness and the tolerance. The lay flat tubing shall be cut open and the thickness measurement made on a single thickness.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:48Z
Check the source to verify that this is the current version before use.

4.4.3 Tensile strength, elongation, stress and bonding strength.- Tensile strength, elongation, stress and bonding strength shall be determined as specified in Method 1013 of FED-STD-406 except that a flat faced clamp shall be used. The test specimens shall be 1 inch wide. For breaking strength of bonded seams, the seam shall be at the center of the specimen and perpendicular to the center line. The specimen shall be prepared for peel stress (bonding strength) by placing one strip of film (centered) on top of another and sealing one end, leaving the free ends to be gripped in the jaws of the testing machine. The sealed seam shall be positioned equidistant from the top and bottom jaws prior to the start of the test.

4.4.4 Tear strength.- Tear resistance, Elmendorf, shall be determined as specified in Method 5132 of FED-STD-191.

4.4.5 Breaking strength of folds.- The breaking strength of each side fold shall be determined as specified in Method 1013 of FED-STD-406. The The test specimens shall be one inch wide. The fold shall be at the center of the specimens and perpendicular to the center line. The crease of the fold shall be positioned equidistant from the top and bottom jaws prior to the start of the test.

4.4.6 Odor.- Determination of odor shall be made on a 12-inch square sample of each color of film, as applicable. The sample shall be freely exposed to circulating air at 75° ± 5°F. (23.9° ± 2.8°C) for not less than 24 hours.

4.4.7 Pinholes and cracks.- Examination for pinholes and cracks shall be made by viewing the surface of the film held under light tension. A bright light source shall be positioned behind the film so as to clearly illuminate the surface without producing glare in the observer's eyes. A pinhole is defined as any opening observed in the film under the conditions specified above which is not visible when the film is viewed normally in average daylight or the equivalent thereof.

5. PREPARATION FOR DELIVERY

5.1 Packaging.- Packaging shall be level A or C as specified (see 6.2).

5.1.1 Level A.- Plastic tubing shall be uniformly rolled on a convolute or spiral wound paperboard tube with an inside diameter of not less than two inches. Each roll shall be restrained from unwinding and then wrapped with at least one thickness of 30-pound minimum basis weight kraft

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:48Z
Check the source to verify that this is the currentversion before use.

paper conforming to grade B of UU-P-268. The wrap shall be lapped approximately six inches and secured the entire length of the roll with 2-inch minimum width pressure-sensitive tape conforming to PPP-T-60 or PPP-T-76; or gummed paper tape conforming to type III, grade B of PPP-T-45. The width of the wrapper shall be such that the wrapper can be folded over the ends of the roll. The folded ends of the wrapper shall be fastened either by tucking into the tube and placing a restraining device into the tube or by gluing a circular piece of paper over the folded wrapper ends. Alternative to wrapping with kraft paper, each roll may be placed in plastic tubing identical to that on the roll and the tubing ends secured with pressure-sensitive tape specified herein or heat sealed.

5.1.2 Level C.- Plastic tubing shall be packaged to afford adequate protection against physical damage during shipment from the supply source to the first receiving activity. The supplier may use his standard practice when it meets this requirement.

5.2 Packing.- Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Level A.- Plastic tubing of one color only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636, except that the dimensional limitation shall not apply; class II, style A of PPP-B-591; overseas type, style A or I, grade A or B of PPP-B-601; or type III, grade D of PPP-D-723, as specified (see 6.2). Each fiberboard container shall be waterproofed in accordance with the appendix of PPP-B-636. Each fiber drum shall be closed in accordance with PPP-D-723 with pressure-sensitive tape conforming to of PPP-T-60. Each PPP-B-591 and PPP-B-601 container shall be provided with a type I or II, grade C sealed case liner conforming to MIL-L-10547. The foregoing waterproofing requirements shall not apply when rolls are packaged in plastic tubing as specified in 5.1.1. Each shipping container shall be closed and reinforced in accordance with the applicable container specification. The weight of the contents of each PPP-B-636 container shall not exceed 65 pounds or 150 pounds for each of the other shipping containers.

5.2.2 Level B.- Plastic tubing of one color only, packaged as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636, except that the dimensional limitations shall not apply; class I, style A of PPP-B-591; domestic type, style A or I, grade B of PPP-B-601; or type I, grade D of PPP-D-723, as specified (see 6.2). Each shipping container shall be closed in accordance with the applicable container specification. The weight of the contents of each PPP-B-636 container shall not exceed 65 pounds or 150 pounds for each of the other shipping containers.

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:48Z
Check the source to verify that this is the currentversion before use.

5.2.2.1 When specified (see 6.2), the PPP-B-636 shipping container specified in 5.2.2 shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of the container specification.

5.2.3 Level C.- Plastic tubing, packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. Containers shall be in accordance with Uniform Freight Classification Rules or National Motor Freight Classification Rules, as applicable.

5.3 Palletization.- Unless otherwise specified (see 6.2), plastic tubing of one color only, packed as specified in 5.2, shall be palletized in accordance with load type I or XIII (as applicable) of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L. The load type I pallet pattern shall be in accordance with the appendix of MIL-STD-147. Interlocking of load type I containers shall be effected by reversing the pattern of each course. If the load type I container is of a size which does not conform to any of the pallet patterns specified in MIL-STD-147, the pallet pattern used shall first be approved by the contracting officer. The load type XIII containers shall be stacked vertically in a single course with a wood cap over and under the load. A strap shall be positioned girthwise around the load type XIII containers outside of and at the vertical center of the fiber drums and shall be the first strap applied to the load.

5.4 Marking.- In addition to any special marking required by the contract or order, interior packages, shipping containers, and palletized unit loads shall be marked in accordance with MIL-STD-129.

5.4.1 Precautionary marking.- The following precautionary marking shall appear in letters not less than 3/4-inches in height on at least one side and wherever practical on two sides of each shipping container:

STAND ON END

KEEP COOL AND DRY

6. NOTES

6.1 Intended use.- The flexible plastic polyurethane film covered by this specification is intended for use in fabrication of Free Drop Containers for water. The color a film shall be used only as the outermost layer of the container. The color b film shall be used in contact with water for a maximum period of two weeks only.

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:48Z
Check the source to verify that this is the currentversion before use.

6.2 Ordering data.- Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Color required (see 1.2).
(c) Width required for flat tubing (see 3.6.1).
(d) Selection of the applicable levels of packaging and packing (see 5.1 and 5.2).
(e) Type of shipping container desired (see 5.2.1 and 5.2.2).
(f) When weather resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
(g) When palletization is not required (see 5.3).

6.3 Formulation approval.- Perflex E Code 101 produced by Union Carbide Corporation, Chicago, Illinois has received limited approval from Office of Surgeon General, Department of Army, as a single use container for potable water for special uses in Southeast Asia.

6.4 Supersession data.- The previous issue of this specification described two types and three sizes of product as follows:

Type I - Plastic sheet
Type II - Plastic tubing
Size 1 - 0.005 $\pm$ 0.0010 inch thick
Size 2 - 0.010 $\pm$ 0.0020 inch thick
Size 3 - 0.015 $\pm$ 0.0030 inch thick

Type I and sizes 2 and 3 have been deleted.

Custodian:

Army - GL

Review activities:

Army - MD, MR

User activity:

Army - AV

Preparing activity:

Army - GL

Project No. 9330-A476

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:48Z
Check the source to verify that this is the currentversion before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:48Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION: Plastic Tubing (Flexible, Polyurethane Film) MIL-P-43604A(GL)

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:48Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01760

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRES-EQS
Natick, Massachusetts 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:48Z
Check the source to verify that this is the current version before use.