MILITARY SPECIFICATION

CLOTH, TAFFETA, NYLON

This interim amendment is approved for use within the Department of the Army, with MIL-C-21852E dated 25 August 1981.

PAGE 1

1.2, under "Type III": Add the following:

"Class 1 - Plain finish
Class 2 - Water repellent treated"

PAGE 3

Table I, in "Type IV" column for "Yarns per inch (min)" warp and filling: Delete "108 (43.2)" and "71 (28.4)" and substitute: "100 (39.4)" and "68 (26.8)" respectively.

PAGE 5

Add the following:

"3.7.5 Water repellency (Type III, Class 2 only). The cloth shall be given an approved fluorocarbon type water repellent treatment (see 6.6) and shall conform to the requirements of 3.7.5.1 through 3.7.5.3 when tested as specified in 4.5.

3.7.5.1 Hydrostatic pressure. The hydrostatic pressure initially shall be not less than 35 cm for the average of the sample units with no sample unit less 31 cm. After 3 launderings the hydrostatic pressure shall be not less than 32 cm for the average of the sample units with no sample unit less than 28 cm.

3.7.5.2 Dynamic absorption. The dynamic absorption initially and after 3 launderings shall be not more than 18 percent for the average of the sample units with no sample unit greater than 20 percent.

3.7.5.3 Spray rating. The results of the three individual determination on the sample unit for spray rating shall be equal to or better than ratings 100, 100, 90 initially and 80, 80, 70 after 3 launderings.

3.7.6 Resistance to organic liquids (Type III, Class 2 only). The finished cloth shall show no wetting by n-tetradecane initially and after 3 launderings when tested as specified in 4.5."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:30Z
Check the source to verify that this is the current version before use.

PAGE 8

Table II: Add the following:

Characteristic	Requirement Paragraph	Test method
"Water repellency (Type III, Class 2 only)	3.7.5	6/
Hydrostatic pressure		
Initial	3.7.5.1	5514
After 3 launderings	3.7.5.1	5552, 5514, 7/
Dynamic absorption		
Initial	3.7.5.2	5500
After 3 launderings	3.7.5.2	5552, 5500, 7/
Spray rating		
Initial	3.7.5.3	5526
After 3 launderings	3.7.5.3	5552, 5526, 7/
Resistance to organic liquid		
Initial	3.7.6	4.5.3
After 3 launderings	3.7.6	5552, 4.5.3, 7/"

PAGE 9

Table II, add the following:

"6/ The contractor shall report the water repellents used.

7/ Specimens shall be subjected to 3 complete cycles (wash and dry) prior to determination of hydrostatic pressure, dynamic absorption, spray rating, and resistance to organic liquid after laundering."

PAGE 10

Add the following:

"4.5.3 Resistance to organic liquid test. Place a small specimen of the cloth face up on a smooth horizontal surface. Using a pipette or eye dropper, gently deposit one drop of n-tetradecane on the surface of the specimen. After one minute, examine the specimen under light at an angle. Absence of light reflectance at the fabric-drop interface shall be taken as evidence of wetting. Three specimens (or areas) taken at various locations across the sample shall be tested. Evidence of wetting on one or more specimens shall constitute a test failure."

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:30Z
Check the source to verify that this is the current version before use.

PAGE 10 (cont'd)

6.2 b., after "Type": Add "and class".

PAGE 11

"6.6 Approval of fluorocarbon water repellent. Approval of the fluorocarbon type water repellent treatment is the responsibility of the U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 and is based on extensive tests, including those for toxicity, which are not set forth in this document. Because of the time necessary to conduct full evaluation (approximately 6 months), only those chemical treatments already approved and so listed in the invitation for bids or request for proposal shall be considered acceptable for the related procurement."

Custodian:

Army - GL

Preparing activity:

Army - GL

Review activities:

Army - MD
DLA - CT

Project No. 8305- A127

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:30Z
Check the source to verify that this is the current version before use.