[METRIC]

A-A-2948
May 1, 1996

COMMERCIAL ITEM DESCRIPTION

PAPER, GRAPH

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification UU-P-202 which is cancelled.

1. **SCOPE:** This Commercial Item Description covers graph paper.

2. **CLASSIFICATION:** Graph papers covered by this specification shall be of the following types, grades, and classes:

Type I - Drawing

Grade B - 50% cotton or linen rag
Grade C - Chemical wood pulp

Type II - Tracing

Class 1 - Natural tracing paper
Grade A - 100% cotton or linen rag
Grade B - 50% cotton or linen rag

Class 2 - Transparentized tracing paper
Grade A - 100% cotton or linen rag
Style 1 - High translucency
Style 2 - Medium translucency

Type III - Ledger

Beneficial comments, recommendations, additions, deletions, clarification's, etc. and any data which may improve this document should be sent to General Services Administration, Federal Supply Service, Engineering Branch, 26 Federal Plaza, New York, NY 10278

Distribution Statement A:
Approved for public release; Distribution is unlimited.

FSC 7530

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

3. SALIENT CHARACTERISTICS:

3.1 Materials: Graph papers shall be made from the designated pulps, or blends of pulps and additives needed to meet the salient characteristics of this specification and the physical requirements of Tables I and II; and paragraphs 3.2 and 3.3.

Table I - Type I Drawing Paper

Characteristic	Grade B	Grade C	TAPPI test method
Basis Weight, avg. g/m^2 (lb. 17x22-500) +/- 5%	90 (24)	60 (16)	T410
Smoothness, both sides, avg. sec.	30 - 50	20 - 30	T479
Fold endurance before aging, min. avg. each direction, Schopper (MIT) double folds	100 (100)	-	T423 (T511)
Fold endurance after aging, min. avg. each direction, Schopper (MIT) double folds [1]	50 (50)	-	T423 (T511)

Table II - Type II, Class 1 Tracing Paper

Characteristic	Grade A	Grade B	TAPPI test method
Basis Weight, avg. g/m^2 (lb. 17x22-500) +/- 5%	45 (12)	45 (12)	T410
Tearing strength, MD:CD avg., (grams)	34	20	T414
Opacity, (contrast ratio method) max. percent [2]	60	60	T425
Smoothness, both sides avg. sec.	30-50	30-50	T479
Fold endurance before aging, min. avg. each direction, Schopper (MIT) double folds	250 (250)	200 (250)	T423 (T511)
Fold endurance after aging, min. avg. each direction, Schopper (MIT) double folds [1]	125 (125)	75 (75)	T423 (T511)

1/ Use TAPPI T544 for aging samples.
2/ Variations between individual readings shall be no more than 4% points.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

3.2 Requirements for Type II, Class 2 - Type II, class 2 graph papers shall conform to the requirements types III and IV of CID A-A-2946, Paper, Tracing, for the specified basis weight.

3.3 Requirements for Type III - Ledger graph paper shall conform to the requirements of CID A-A-2814, Paper, Ledger, Unruled Type III **(JCP J10)**, with a basis weight of 165 g/m^2 (44 lb.- 17x22-50).

3.4 Configuration: Configuration lines on the graph paper, its specific pattern such as cross section, logarithmic scale or other, shall be as specified.

3.5 Writing and erasing quality: There shall be no visible change of color of erased surfaces, no erasure of the printed lines and no perceptible linting of the paper when pencil lines/characters are erased. There shall be no visible spreading or feathering of inked lines/characters when applied after erasure of penciled characters.

3.6 Printing and ruling: Lines shall be produced by printing or machine ruling. The overall size of the printed or ruled area shall be as specified. Lines shall be visually continuous and of uniform width and color. There shall be no blotting or feathering of intersecting lines. When specified, lines shall be printed in nonreproducible blue ink.

3.7 Construction: Graph paper shall be furnished in rolls, sheets or pads, as specified. Rolls or sheets of paper shall contain no splices.

3.8 Rolls: Rolls of graph paper shall be at least the minimum length specified in the ordering document. The width shall be as specified, with a tolerance of +0.6 cm, -0 cm (+1/4", -0"). The paper shall be uniformly and smoothly wound on a fiberboard core having an inside diameter of 4.8 cm, +/-0.6 cm (1-7/8", +/- 1/4") and suitably secured to prevent unwinding or slippage on the core. The core dimensions shall be the specified roll width, with a tolerance of +0.3 cm, -0 cm (+1/8", -0").

3.9 Sheets: Sheets of graph paper shall be cut square on four sides and furnished in the sizes specified. A tolerance of +0.2 cm, -0 cm (+1/16", -0") is allowed in either dimension for sizes 20.3 x 26.7 cm (8" x 10-1/2") through 38.1 x 45.7 cm (15" x 18"). A tolerance of +0.3 cm, -0 cm (+1/8", -0") is allowed in either dimension for sheets larger than 38.1 x 45.7 cm (15" x 18"). Any flat paper with a long dimension of 81.3 cm (32") or less will be considered square-cut if the variation of the diagonals does not exceed 0.8 mm (1/32"); over 81.3 cm (32"), 0.2 cm (1/16").

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

3.10 Pads: Pads shall be furnished in widths and lengths as specified, with a tolerance of +/-0.3 cm (+/-1/8"). The number of sheets per pad shall be as specified. Pads shall be continuously and securely padded together along the specified edge, in accordance with normal commercial practice. Backs of pads shall be chipboard or other suitable material.

3.11 Perforations: When specified, the pads shall be perforated 1.8 cm +/-0.16 cm (3/4" +/- 1/16") from the bound edge. The perforations shall be parallel to the bound edge and shall extend the entire length or width, as applicable.

3.12 Binder holes: When specified, graph paper in sheet or pad form shall have 5 punched holes 0.6 cm +/-0.8 mm (1/4" +/-1/32") in diameter along the specified edge and spaced to fit a standard 2 or 3 ring binder.

3.13 Marking of paper: The margin of each sheet of graph paper shall be identified with the manufacturer's name or trademark and the configuration of rulings in accordance with normal commercial practice. Identification markings shall be spaced at intervals of not more than 91.4 cm (36") in the bottom margin of roll graph paper. When the printed or ruled area is identical to the overall sheet size, identification markings shall be omitted.

3.14 Workmanship: Graph paper shall be uniform throughout, sheets shall lie flat, be square, with clean cut and dust free edges. The roll edges shall be clean cut, even and dust-free. Assembled pads shall have clean cut and dust free edges.

3.15 Bleaching: To obtain an acceptable brightness, in accordance with the performance standards of this document, a chemical bleaching process may be used. When specified in the ordering data (See Ordering Data), the bleaching process shall not include the use of chlorine, chlorine dioxide, or other chlorine compounds. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4. **REGULATORY REQUIREMENTS:**

4.1 Regulatory requirements. The contractor shall certify that the product offered contains the minimum amount of recycled content in accordance with the contract or purchase order. The government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4.2 Labeling: The recycled content shall be marked on the product or unit pack.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

5. **QUALITY ASSURANCE:**

The products provided shall conform to the producer's own drawings, specifications, and quality assurance practices and be the product offered for sale in the commercial market. The government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

5.1 Sampling for TAPPI tests shall be in accordance with TAPPI T400, plan II.

5.2 An inspection lot shall consist of all like items submitted for inspection at one time. The inspection level for visual and performance characteristics shall be S-3 with an Acceptable Quality Level (AQL) of 4.0 percent defective. The sample unit shall be one unit of issue. The supplier must provide objective evidence (tests and inspection records) that the presented material meets the requirements of the sampling plan as indicated above.

6. **PREPARATION FOR DELIVERY:**

Packaging, packing and marking shall be as specified in the contract or purchase order.

7. **REFERENCED DOCUMENTS:** The issue of each document in effect on the date of the solicitation shall be used to determine compliance with these requirements.

TAPPI test methods are available from:

Technical Association of the Pulp and Paper Industry
Technology Park/Atlanta, PO Box 105113
Atlanta, GA 30348
(404) 446-1400

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

8. **NOTES:**

A. Ordering Data: Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(1) Type, class, grade and style.
(2) Basis weight.
(3) Form: sheets, rolls or pads.
(4) Dimensions.
(5) Location of perforations and/or edge to be fastened (pads only).
(6) Location of punched holes.
(7) Number of sheets.
(8) Size of ruled area.
(9) Ruling type.
(10) When nonreproducible blue lines are required.
(11) Color.
(11) Whether chlorine or chlorine compound bleaching is acceptable.
(12) Specific packaging, packing, palletization and, marking requirements.

B. **Item Identifiers/Reference Part Number System (For Cataloging Use Only)**

AA2948 - B2A1: This example describes a high translucency transparentized tracing graph paper consisting of 100% cotton or linen rag.

- STYLE: 1 - High translucency; 2 - Medium translucency
- GRADE: A - 100% cotton or linen rag.; B - 50% cotton or linen rag.; C - Chemical wood pulp.
- CLASS: 1 - Natural tracing paper.; 2 - Transparentized tracing paper.
- TYPE: A: I - Drawing.; B: II - Tracing.; C: III - Ledger.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.

C. List of NSNs:

Sheets	Pads	Rolls
7530-00-268-4148	7530-00-272-6917	7530-00-286-6910
7530-00-281-3437	7530-00-307-5920	7530-00-286-6919
7530-00-286-6908	7530-00-558-1152	
7530-00-286-6911	7530-00-558-1153	
7530-00-286-6912	7530-00-582-4196	
7530-00-286-6915	7530-00-634-5028	
7530-00-286-6916		
7530-00-286-6917		
7530-00-286-6918		
7530-00-431-2780		
7530-00-971-8468		

Military custodians:

No military interest

Preparing activity:

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:27Z
Check the source to verify that this is the current version before use.