COMMERCIAL ITEM DESCRIPTION

PASTE, PERIODONTAL PROTECTIVE, SURGICAL (Medium Firm Dressing)

The General Services Administration has authorized the use of this Commercial Item Description.

This commercial item description covers a periodontal paste suitable for use in periodontal surgery to cover and protect the surface of surgical wounds.

Salient characteristics:

The periodontal paste shall consist of a base paste, an accelerator (catalyst) paste, and an emollient (lubricant). When the pastes are mixed in accordance with the manufacturer's instructions, the mixture shall have a soft plastic consistency and shall be easily molded to any desired shape. The paste shall be easy to apply to a wound and easy to remove from the wound. The paste shall not dissolve in mouth fluids and shall not be dislodged by the movement associated with eating and speaking. The emollient shall prevent the mixed materials from sticking to the hands and lips but shall not retard the set of the paste. No component of the paste shall contain eugenol, asbestos, or cotton fibers.

Materials. Materials shall be of the highest quality throughout and shall be suitable in all respects for the purpose intended. Where applicable, materials shall be in accordance with the requirements of the latest edition of the United States Pharmacopeia (USP) or the National Formulary (NF). Any material used in the periodontal paste which is not included in the USP or NF shall be of a quality suitable for dental use.

Base. The base paste shall contain the following ingredients: fatty acids, resins, benzocaine, parabens, and waxes.

Accelerator. The accelerator paste shall contain the following ingredients: mineral oil, petroleum jelly, zinc oxide and other metal oxides.

Emollient. The emollient shall be a silicone based lubricant.

AMSC N/A FSC 6520

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:35Z
Check the source to verify that this is the current version before use.

Color. The base paste and the accelerator paste shall be distinctly different in color. The mixture of the base and accelerator shall be pink.

Performance. When tested as specified below, working time shall be 4 minutes ± 1 minute. Setting time shall be a maximum of 15 minutes.

Immediate container. Base and accelerator pastes shall be in suitable metal, collapsible tubes with round opening and screw cap closure. The emollient shall be in a suitable plastic jar with screw cap closure.

Capacity. Net weight of base shall be at least 90 grams; net weight of catalyst shall be at least 45 grams; net weight of emollient shall be at least 20 grams. Volume after mixing a tube of base with a tube of catalyst shall be at least 120 milliliters.

Marking. The tube of accelerator paste shall be marked "ACCELERATOR" or "CATALYST". The tube of base paste shall be marked "BASE". The jar of emollient shall be marked "EMOLLIENT". The lot number shall be marked on all immediate containers. The date of manufacture shall be marked on the box (unit package).

ADA Acceptance. The contractor shall furnish proof that the offered periodontal paste has been accepted by the Council on Dental Therapeutics of the American Dental Association (ADA). Compliance with this acceptance requirement does not absolve the contractor from complete compliance with the requirements of this specification.

Mixing pad. A suitable mixing pad shall be included in each unit package. The pad shall be a minimum of 6 inches long and 5 inches wide. The pad shall contain a minimum of 15 sheets of coated kraft paper.

Instructions. Adequate and accurate instructions for proportioning and manipulating pastes shall accompany each unit package. Instructions shall contain information about the use of the emollient.

Workmanship. All components and immediate containers shall be free from defects which detract from their appearance or may impair their serviceability.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:35Z
Check the source to verify that this is the current version before use.

Unit. Package (PG). One package containing one tube of base paste, one tube of accelerator paste, one jar of emolliant, one mixing pad, and instructions for use, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after the delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Sampling for inspection. Sampling for inspection shall be conducted in accordance with MIL-STD-105. Where feasible, the same sample shall be used for the determination of two or more inspection characteristics. The unit of product for inspection purposes shall be one package of periodontal paste. Unless otherwise specified, sampling for examination shall be conducted at inspection level II, AQL 2.5, and sampling for tests (when applicable) shall be conducted at inspection level S-1, AQL 1.0.

Examination. The periodontal paste shall be examined to determine compliance with specification requirements.

Tests. Tests shall be conducted to determine compliance with specification requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:35Z
Check the source to verify that this is the current version before use.

Weight and volume. Net weight of base and accelerator pastes in tubes and net weight of emollient in jar shall be measured with a suitable balance. Volume after mixing a tube of base paste with a tube of accelerator paste shall be measured by a suitable method.

Working time. Extrude equal lengths of catalyst and base paste onto a mixing pad. Start a stopwatch and begin to spatulate the two pastes together. Mix for one minute. Lubricate hands with emollient and pick up the mixed paste. Slowly knead the paste between lubricated fingers while occasionally stretching the material. It will be noted that initially the material will stretch without breaking, but eventually it will snap when stretched. This is the working time.

Setting time. This is a continuation of the working time test above. Remove portions of the mixed material from the mixing pad with a spatula or a tongue depressor and place these samples in a water bath at 98°F. Remove a sample from the water bath 11 minutes after the start of the mix. Remove samples from the water bath at 30-second intervals thereafter. The material is set when a hard, resilient mass has formed.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch/pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met. If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable. The contracting officer has the option of accepting or rejecting the product.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producer's own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:35Z
Check the source to verify that this is the current version before use.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Number is covered by this document:

National Stock Number	Item Identification
6520-01-103-8579	PASTE, PERIODONTAL PROTECTIVE, Fast Setting, Medium Firm Dressing

Ordering data. Intermediate/exterior package quantities, labeling, and marking must be as specified in the contract and/or order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:35Z
Check the source to verify that this is the current version before use.

A-A-54518

MILITARY INTERESTS:

Custodians:

Army-MD
Navy-MS
Air Force-03

Preparing Activity:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

Project No. 6520-2509
Location: PL #2 CDWAX

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:35Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

1. RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	A-A-54518	20 November 1991

3. DOCUMENT TITLE
PASTE, PERIODONTAL PROTECTIVE, SURGICAL (Medium Firm Dressing)

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	e. DATE SUBMITTED (YYMMDD)

7. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial	(2) AUTOVON
Defense Personnel Support Center	(215)737-2870	444-2870
c. ADDRESS (Include Zip Code) ATTN: DPSC-MSE 2800 S. 20th Street Philadelphia, PA 19101	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT Defense Quality and Standardization Office 5203 Leesburg Pike Suite 1403 Falls Church VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

DD Form 1426, OCT 89 — Previous editions are obsolete — 98/290

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:35Z
Check the source to verify that this is the current version before use.