MIL-C-48045 (MU)
28 January 1972
SUPERSEDING
(See 6.5)

MILITARY SPECIFICATION

CARTRIDGE, 40MM, PROOF, XM387E4;

BODY ASSEMBLY AND OGIVE FOR

METAL PARTS

1. SCOPE

1.1 This specification covers the metal parts for one type of body assembly and ogive.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-A-2550	-	Ammunition and Special Weapons, General Specification for
MIL-I-45607	-	Inspection Equipment, Acquisition, Maintenance and Disposition of

STANDARDS

FEDERAL

FED-STD-151	-	Metals; Test Methods

FSC: 1310

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes (ABC-STD-105)
MIL-STD-109	-	Quality Assurance Terms and Definitions
MIL-STD-1168	-	Lot Numbering of Ammunition
MIL-STD-1169	-	Packaging, Packing and Marking for Shipment of Inert Ammunition Components
MIL-STD-1235	-	Single and Multilevel Continuous Sampling Procedures and Tables for Inspection by Attributes

DRAWINGS

U.S. ARMY MUNITIONS COMMAND

8889313	-	Body Assembly
8840508	-	Ogive
9224169	-	Ogive

PUBLICATIONS

ARMY

ET-8889313	-	Equipment Tabulation

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the Contracting Officer).

3. REQUIREMENTS

3.1 Material.-Materials shall be in accordance with the applicable drawings and specifications.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

3.2 Parts.-The parts shall comply with all requirements specified on Drawings (Dwgs) 8889313, 8840508, 9224169, all associated drawings, and with all requirements specified in applicable specifications.

3.3 Skirt hardness and compression.

3.3.1 Hardness.-The hardness shall be 68 + 10 on the Rockwell E. Scale when tested as specified in 4.4.2. This requirement is not applicable when skirt is made from tubing or bar stock.

3.3.2 Compression.-The skirt when compressed to 3/4 inch in a plane normal to its longitudinal axis, shall show no evidence of cracks when tested as specified in 4.4.3. This requirement is not applicable when skirt is made from tubing or bar stock.

3.4 Workmanship.-All parts and assemblies shall be fabricated and finished in a thorough, workmanlike manner. They shall be free of burrs, chips, sharp edges, cracks, unblended radii, surface defects, dirt, grease, rust, corrosion products, and other foreign matter. The cleaning method used shall not be injurious to any parts, nor shall the parts be contaminated by the cleaning agents. All marking and stamping shall be neat and sharply defined.

3.5 Submission of results of contractor-conducted examinations and tests.-The contractor shall forward copies of the results of any of his examinations or tests to the designated address as required by the contract. (see 6.4).

3.6 First article testing.-This specification makes provisions for first article testing. Submission of first article quantity by the contractor shall be as specified in the contract.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection.-Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

assure supplies and services conform to prescribed requirements. Reference shall be made to MIL-STD-109 to define terms used herein. The provisions of MIL-A-2550 shall apply.

4.1.1 Submission of product.-At the time the completed lot of items deliverable under the contract is submitted to the Government for acceptance, the contractor shall supply the following information accompanied by a certificate which attests that the information provided is correct and applicable to the product being submitted:

a. A statement that the lot complies with all the quality assurance provisions specified in this specification.
b. Drawing and specification number and date, together with identification and date of changes thereto.
c. A statement that all material purchased by the contractor meets requirements, when such material is controlled by Government or commercial specifications references in any of the contractual documents, and that certificates of conformance are on file and available for review.
d. Number of items in the lot.
e. Date submitted.

The certificate shall be signed by a responsible agent of the certifying organization. The initial certificate submitted shall be substantiated by evidence of the agent's authority to bind his principal. Substantiation of the agent's authority will not be required with subsequent certificates unless, during the course of the contract, this authority is vested in another agent of the certifying organization.

4.2 First article inspection.

4.2.1 Submission.-The contractor shall submit a first article quantity as designated by the Contracting Officer for evaluation in accordance with the provisions of 4.2.2. (See 6.1) The first article sample shall consist of the following:

a. Fifty (50) body assemblies.
b. Twenty-five (25) bodies.
c. Twenty-five (25) skirts.
d. Twenty-five (25) ogives (as applicable).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

All parts and completed assemblies submitted shall have been produced by the contractor (or furnished by a supplier) using the same production processes, procedures and equipment as will be used in fulfilling the contract. All parts and materials, including packaging and packing, shall be obtained from the same sources of supply as will be used in regular production. The sample shall be accompanied by certificates of conformance. A first article quantity, or portion thereof, as directed by the Contracting Officer, shall also be submitted whenever there is a lapse in production for a period in excess of 90 days, or whenever a change occurs in manufacturing process (including heat treatment procedures and equipment), material used, drawing, specification or source of supply as to significantly affect product uniformity as determined by the Government. Prior to submission, the contractor shall inspect the sample to the degree necessary to assure that if conforms to the requirements of the contract and submit a record of this inspection with the sample. A sample containing knonw defects will not be submitted unless specifically authorized by the Contracting Officer.

4.2.2 Inspection to be performed.-All parts and assemblies shall be subjected by the Government to any or all the examinations or tests specified in this specification and any or all requirements of the applicable drawings.

4.2.3 Rejection.-If any assembly or component fails to comply with any of the applicable requirements, the first article quantity shall be rejected. The Government reserves the right to terminate its inspection upon any failure of an assembly or component in the sample to comply with any of the stated requirements. In the event of rejection, the Government reserves the right to require the contractor to take corrective action and submit a new first article quantity or portion thereof. Until a first article quantity is accepted, the contractor is in no way authorized by the Government to resume regular production unless otherwise directed by the Contracting Officer.

4.2.4 Inspection.-This paragraph provides guidelines for minimum first article inspection in cases where there is more than one source of supply for one or more components:

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

4.2.4.1 Body (Dwg. 8883766).-Inspect each body for all drawing dimensions and requirements.

4.2.4.2 Skirt (Dwg. 8840512).-Inspect each skirt for all dimensions in main view except inside spherical radius. Inspect ten (10) skirts visually for other features.

Bodies and skirts which have met the above inspection requirements, shall be assembled by any one manufacturer and the body assemblies shall be inspected and tested to the requirements of 4.2.2. Each supplier's components shall be included in at least one first article sample of body assemblies.

In regular production, components which have passed first article inspection may be mixed in any combination regardless of source of supply to make body assemblies.

4.3 Inspection provisions

4.3.1 Lot formation.-The term "inspection lot" as used in this specification is defined as an essentially homogeneous collection of units of product from which a representative sample is drawn and inspected to determine conformance with applicable requirements. The sample selected shall represent only that quantity of units from which the sample was drawn and shall not be construed to represent any prior or subsequent quantities presented for inspection. Homogeneity shall be considered to exist provided the inspection lot has been produced by one manufacturer, in one unchanged process, in accordance with the same drawing, same drawing revision, same specification and same specification revision and complies with the provisions for submission of product as specified in MIL-STD-105. Changes to process, specification, or drawing not affecting safety, performance, interchangeability, or storage, as determined by the Government, shall not be deemed to alter the homogeneity of an inspection lot. All material submitted for inspection in accordance with this specification shall comply with the homogeneity criteria specified herein regardless of the type of sampling procedure which is being applied to determine conformance with requirements. Lot numbering, as required, shall be in accordance with MIL-STD-1168.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

4.3.2 Examination.-The examinations listed in the following subparagraphs shall be performed on inspection lots (See 4.3.1) of the components or assemblies designated in the applicable paragraph headings. Inspection for critical defects (and major defects, when so specified) shall be 100 percent. Sampling plans for major and minor defects shall be in accordance with MIL-STD-105 except that continuous sampling plans in accordance with MIL-STD-1235 may be used if approved by the Government. Instead of applying the AQL's designated herein to the groups of major and minor defects listed, the contractor may elect to apply AQL's to individual defects using an AQL of 0.40 percent for each major defect and an AQL of 0.65 percent for each minor defect. When this method is elected, it shall be applied to all of the major and minor defects listed in the applicable subparagraph of this section, except where 100 percent inspection is specified, and be documented as part of the contractor's inspection system. Equipment necessary for the performance of the inspections listed shall be in accordance with 4.3.4.

4.3.2.1 Body (See Dwg. 8883766 covering a detail of Dwg. 8889313).

Categories	Defects	Method of Inspection (See 4.3.3.1)	Code No. (See 6.2)
Critical:	None defined		
Major:	AQL 0.40 Percent		
101.	Weight	Balance	01001
102.	Any foreign matter prior to assembling to skirt	Visual	01002
Minor:	AQL 1.50 Percent		
201.	Spherical diameter, maximum (max.)	Gage	01003
202.	Diameter, straight portion	Gage	01004
203.	Total length	Gage	01005
204.	Evidence of poor workmanship (See 3.4)	Visual	01006

4.3.2.2 Body Assembly (See Dwg. 8889313).

Categories	Defects	Method of Inspection	Code No.
Critical:	None defined		

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

Major:	AQL 1.50 Percent		
101.	Concentricity of body diameter with bourrelet diameter	Gage	02001
102.	Bourrelet diameter	Gage	02002
103.	Concentricity of outside diameter for ogive on skirt with bourrelet diameter	Gage	02003
104.	Profile of rotating bands	Gage	02004
105.	Location of rotating bands	Gage	02005
106.	Profile ogive crimp groove on skirt	Gage	02006
107.	Location of ogive crimp groove on skirt	Gage	02007
108.	Diameter of rotating bands	Gage	02008
109.	Profile of cartridge case groove on skirt	Gage	02009
110.	Diameter of cartridge case groove on skirt	Gage	02010
111.	Diameter ogive crimp end on skirt	Gage	02011
112.	Distance from curved surface to rotating bands	Gage	02012
113.	Diameter at curved end of body	Gage	02013
114.	Distance from curved surface to top end of skirt	Gage	02014
Major:	AQL 2.50 Percent		
*115.	Gap, max.	Gage	02015

*The lot shall be rejected if any item in the sample has a gap exceeding .035 or the number of defectives over .20 exceeds the acceptance number.

Minor:	AQL 1.50 Percent		
201.	Total length	Gage	02016
202.	Protective coating missing	Visual	02017
203.	Skirt color incorrect	Visual	02018
204.	Evidence of poor workmanship (See 3.4)	Visual	02019

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

4.3.2.3 Body and skirt, prior to applying adhesive (See Dwg. 8889313).

Categories	Defects	Method of Inspection	Code No.
Critical:	None defined		
Major:	AQL 0.40 Percent		
101.	Evidence of protective coating	Visual	03001
Minor:	None defined		

4.3.2.4 Ogive (See Dwg. 8840508) (as applicable).

Categories	Defects	Method of Inspection (See 4.3.3.1)	Code No.
Critical:	None defined		
Major:	AQL 0.65 Percent		
101.	Total length	Gage	04001
102.	Inside diameter	Gage	04002
103.	Radius	Gage	04003
104.	Wall thickness, min for required distance	Gage	04004
Minor:	AQL 1.50 Percent		
201.	Diameter of flat	Gage	04005
202.	Protective finish with bare spot	Visual	04006
203.	Color incorrect	Visual	04007
204.	Evidence of poor workmanship (See 3.4)	Visual	04008

4.3.2.5 Ogive (See Dwg. 9224169) (as applicable).

Categories	Defects	Method of Inspection	Code No.
Critical:	None defined		
Major:	AQL 0.65 Percent		
101.	Total length	Gage	05001
102.	Inside diameter	Gage	05002

Source: https://assist.dla.mil - Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

103.	Large outside radius	Gage	05003
104.	Depth of inside diameter	Gage	05004
Minor:	AQL 2.50 Percent		
201.	Diameter of flat	Gage	05005
202.	Wall thickness through bottom	Gage	05006
203.	Height of inside protrustion	Gage	05007
204.	Wall thickness, open end	Gage	05008
205.	Color incorrect	Visual	05009
206.	Evidence of poor workmanship (See 3.4)	Visual	05010

4.3.3 Testing.

4.3.3.1 Dimensional control of plastic parts.-In place of the normal sampling associated with the Classification of Defects, and with the approval of the Contracting Officer, and after a curing time for the parts has been approved (See Note 1), a sample of three (3) parts (as molded) from each cavity may be dimensionally inspected to qualify a new or reworked cavity for use in production or as a control of each cavity during production.

The inspection of the parts shall be performed only when the curing time for the parts has been reached. The inspection for control of each cavity during production shall be performed on the above quantities from each cavity after production of each 5000 parts or at the end of each shift, providing the number of parts produced during that shift is less than 5000 parts. Of the three (3) samples, one (1) sample shall be the last part produced. Parts that fail to comply with dimensional requirements after dimensional stability has been attained shall be classed defective.

If any defective parts are found during qualification of the cavity, the cavity producing the defective part will not be used in production. If any defective parts are found when inspection is performed for control of the cavity, the cavity producing the defective part shall be removed from production. Further, that portion of production since the last control check shall be returned to the contractor for corrective action.

All cavities formerly removed from production because of some fault, may, after reworking, be returned to production providing they pass the qualification test as above. The contractor may request a change of inspection frequency providing he presents objective evidence to substantiate the request to the Contracting Officer.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

(NOTE 1) - In establishing a curing time, dimensionally check ten (10) parts from each cavity at periodic intervals (e.g. every 30, 60, etc. mins.) until dimensional stability is attained. The curing time will be from the time the part comes out of the mold until dimensional stability is attained. The inspection data used in determining the curing time shall be sent to Picatinny Arsenal, SMUPA-QA-A-S. If any new change in material, cycle time, a reworked cavity, or new cavity is used, a new curing time shall be established and approved.

4.3.3.2 Hardness of skirt (See Paragraph (Para.) 3.3.1), Major defect, Code No. 06001.-The sampling plan for this test shall be in accordance with MIL-STD-105, Table I, Level II with an AQL of 0.40 percent. The test shall be performed as specified in 4.4.1 using equipment in accordance with 4.3.4.

4.3.3.3 Compression of skirt (See Para. 3.3.2), Major defect, Code No. 07001.-Fifty (50) skirts shall be selected from each shift's production and subjected to this test. If any skirt fails to comply with the applicable requirement, the shifts production represented by the sample shall be rejected. The test shall be performed as specified in 4.4.2 using equipment in accordance with 4.3.4.

4.3.3.4 Push test of body on body assembly (See Dwg. 8889313), Major defect, Code No. 08001.-Fifty (50) body assemblies shall be selected from each lot and subjected to this test. If two (2) or more body assemblies fail to comply with the requirement specified on the applicable drawing, or if one (1) or more is below a reading of 1000 lbs., the lot shall be rejected. The reading used shall be the adhesive separation, not the crimp separation reading. The test shall be performed as specified in 4.4.3 using equipment in accordance with 4.3.4.

4.3.3.5 Pot life of adhesive (See 6.6), (See dwg. 9242717), Major defect, Code No. 09001.-Each batch of adhesive mixed for use in assembling body assemblies shall be subjected to this determination. If any material fails to comply with the applicable requirement, it shall not be used for assembly of body assemblies. Body and skirts which have been assembled with adhesive which exceeded the pot life requirement shalll be rejected. The test shall be performed as specified in 4.4.4.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

4.3.3.6 Curing temperature of body assembly, before removal from oven (See Dwg. 9247217), Major defect, Code No. 10001.-Five (5) body assemblies shall be selected from each four (4) hours production or portion thereof and subjected to measurement of the curing temperature specified on the applicable drawing. If any assembly fails to comply with the specified requirement, the quantity represented by the failing part shall be rejected. The test shall be performed as specified in 4.4.5.

4.3.4 Inspection equipment.-Equipment Tabulation (ET) number 8889313 and Equipment Lists (EL's) referenced theron identify the inspection equipment required to perform the examinations and tests prescribed in this section. The contractor shall design inspection equipment in accordance with the instructions in 6.3. Supply and maintenance of the equipment listed on the EL's shall be in accordance with MIL-I-45607.

4.3.4.1 Government rights to documentation.-Inspection equipment drawings and lists provided and revised in accordance with the requirements of this specification may be used by DOD activities for design, procurement, manufacture, testing, evaluation, production and receiving inspection, overhaul, shipping, storage, identification of stock, ordering and storage of replacement parts, inspection of items at overhaul, general maintenance of equipment, construction, survey, and whenever inspection equipment drawings are needed.

4.4 Test methods and procedures.

4.4.1 Hardness of skirt.-This test shall be conducted in accordance with Federal Standard FED-STD-151, Method 243. This test is a non-destructive test. Parts so tested may be returned to the lot.

4.4.2 Compression of skirt.-The skirt shall be placed in a fixture and a load shall be applied in a plane normal to its longitudinal axis to compress the skirt to the dimension specified in Para. 3.3.2. Any equipment considered satisfactory to the Contracting Officer may be used in performing this test. This test is a destructive test. Parts so tested shall not be returned to the lot.

4.4.3 Push test of body on body assembly.-The body assembly shall be placed in the fixture specified on the Equipment List and the force specified on Dwg. 8889313 shall be applied until

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

complete separation occurs. NOTE: If any body and skirt shows no adhesive sticking, corrective action shall be taken. This test is a destructive test. Parts so tested shall not be returned to the lot.

4.4.4 Pot life of adhesive.-The time from preparation of the adhesive for use in assembly of the body and skirt to its applicable to the skirt shall be determined. Any method considered satisfactory to the Contracting Officer may be used in performing this determination. This test is a non-destructive test. Adhesive so tested may be returned to the lot.

4.4.5 Curing temperature of body assembly, before removal from oven.-The body assembly shall be subjected to this test using equipment specified on the Equipment List. This test is a non-destructive test. Parts so tested may be returned to the lot.

5. PREPARATION FOR DELIVERY

5.1 Preservation and packaging.

5.1.1 Level C.-The body assembly shall be preserved and packaged in accordance with MIL-STD-1169.

5.2 Packing.

5.2.1 Level C.-The body assembly, preserved and packaged as specified in 5.1.1, shall be packed for shipment in accordance with MIL-STD-1169. (No dwgs available and items contains no loaded components)

5.3 Marking.-Marking of the cartons shall comply with MIL-STD-1169.

5.4 Shipping.-When components from more than one lot are shipped as a carload, each lot shall be kept separate, and the division between lots clearly indicated to prevent mixing of the lots in transit.

6. NOTES

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

6.1 Ordering data.-Procurement documents shall specify the following:

a. Title, number and date of this specification.
b. Data cards shall be prepared for each lot in accordance with the information specified in Standard MIL-STD-1167.
c. Provisions for submission of first article samples.

6.2 Inspection code numbers.-The five-digit code numbers assigned to the inspections herein are to facilitate future data collection and analysis by the Government. These code numbers are also used to correlate the characteristics cited on Equipment Lists with the inspections listed in this specification. These code numbers shall be listed on drawings of equipment designs submitted by the contractor (see 6.3.5).

6.3 Inspection equipment.-The contractor shall design inspection equipment as required by the referenced Equipment Lists (EL) in accordance with the instructions of paragraphs 6.3.1 through 6.3.5.

6.3.1 Equipment lists.-Equipment lists indicate the availability of inspection equipment designs by showing in the "Part Number" column of the list of inspection equipment (Form SMUPA 1010) the numbers of drawings or Federal Stock numbers of existing equipment designs, or codes as indicated in paragraph 6.3.2. Design action required of the contractor is described in paragraphs 6.3.3 and 6.3.4. The contractor will be required to prepare detailed drawings in accordance with 6.3.4 for all the equipment coded as "Contractor Design" in the "Part Number" column. These contractor designs must be approved by the Government prior to fabrication or procuring of the equipment. Designs shall be submitted for approval as specified in 6.3.5.

6.3.2 Equipment list codes.-The inspection equipment as defined in 6.3.3 and 6.3.4 will be designated in the EL by the following codes:

CD - Contractor design on controlled contractor format and/or commercial equipment.
MU - Army design, mandatory for use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

6.3.3 Army designs.-Army designs are reflected on detailed drawings which completely depict all the information necessary for the fabrication of the item of inspection equipment. The contractor need provide no design when an Army design is listed for an item of inspection equipment. Army designs fall into two basic classifications: Mandatory (designated "MU") and non-mandatory (indicated by drawing or Federal Stock Number). When an equipment list references mandatory Army Designs, the contractor shall comply with, and use these designs accordingly. The contractor may, however, in connection with non-mandatory designs, with the approval of the Government, design alternate inspection equipment to facilitate his operations. Such contractor-prepared designs (see 6.3.4) or commercial equipment selections must be approved by the Government prior to fabrication or procuring of the equipment. Designs shall be submitted for approval as specified in 6.3.5.

6.3.4 Contractor designs.-Contractor designs are designs of inspection equipment for which the Government has assigned design responsibility to the contractor. Contractor designs shall be supported by detailed drawings which depict all information necessary to completely fabricate, calibrate and operate an item of inspection equipment. This requires that the necessary views, dimensions, materials, finishes, notes and operating and calibration instructions be properly depicted in accordance with approved practices to the extent that further calculation or clarification will not be required. Unless otherwise specified, contractor designs may be developed on the format the contractor normally employs in his equipment design procedure provided such format reflects the detail and information specified above, subject to the following controls: All submitted contractor designs shall conform to Specification MIL-D-1000, Category A, Form 3. Legibility and reproducibility shall permit conventional making of clearly understandable, high-contrast reproductions. Contractors shall submit three copies of final designs as a flat set. Designs shall be submitted for approval as specified in 6.3.5.

6.3.5 Submission of contractor design.-All submitted designs shall contain a reference to the applicable 5-digit code number contained in Section 4 of this specification and the appropriate component or assembly drawing number and revision letter to which the specific design applies. Unless otherwise specified on the EL, all

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

designs of equipment for inspection of defects classified as critical and major shall be submitted for approval to the Commanding Officer, Picatinny Arsenal, ATTN: SMUPA-QA-A-S. All other designs of inspection equipment shall be approved by the inspection element of the agency administering the contract. Submission shall be as directed by the contracting officer. Partial submission of inspection equipment designs is permissible and encouraged. However, the Arsenal completion date for design review will be based on the date of the final submission of designs. Picatinny Arsenal design review will be accomplished, normally, within one month after receipt.

6.4 Submission of results of contractor-conducted examinations and tests.-Unless otherwise specified by the Contracting Officer, the contractor shall forward requested records of examinations or tests to Commanding Officer, Picatinny Arsenal, ATTN: SMUPA-QA-A-S.

6.5 Supersession data.-This specification includes the requirements of, and supersedes, Purchase Specification AEI-289. dated 28 May 1965.

6.6 The pot life of the adhesive is defined as the time from mixing the adhesive to its application to the skirt. If the adhesive is frozen immediately after mixing, the pot life is defined as the time the adhesive reaches ambient temperature to the time of application to the skirt.

Custodian:
Army-MU

Preparing activity:
Army-MU

Project Number: 1310-A013

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity.

SPECIFICATION

ORGANIZATION | CITY AND STATE

CONTRACT NO. | QUANTITY OF ITEMS PROCURED | DOLLAR AMOUNT $

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)* | DATE

DD FORM 1 OCT 64 1426

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T19:10Z
Check the source to verify that this is the current version before use.