INCH-POUND

MIL-C-44347(GL)
17 November 1988

MILITARY SPECIFICATION

CARRIER, WATER CANTEEN, COLD WEATHER, CRS

This specification is approved for use by the U.S. Army Natick Research, Development, and Engineering Center, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers one type and size of canteen and cup carrier fabricated from nylon duck, nylon taffeta cloth and an insulation batting core, nylon tape and webbing, hook and pile fastener tape, plastic stiffeners, polyester thread, snap fasteners, and sliding keepers.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

SPECIFICATIONS

FEDERAL

A-A-203	-	Paper, Kraft, Untreated
DDD-L-20	-	Label: For Clothing, Equipage, and Tentage, (General Use)
PPP-B-636	-	Boxes, Shipping, Fiberboard

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8465

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-L-35078 - Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification For

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads
MIL-STD-731 - Quality of Wood Members for Containers and Pallets

(Copies of specifications, standards, and handbooks required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein. Unless otherwise specified, the issues shall be those in effect on the date of the solicitation.

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

2-2-479 - Carrier, Water Canteen, Cold Weather CRS

(Copies of drawings, publications, and other Government documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Copies should be obtained from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Nongovernment standards and other publications are normally available from the organizations which prepare or which distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence. Nothing in this document, however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Guide samples. Guide samples, when furnished, are solely for guidance and information (see 6.3). Variations from the document may appear in the sample, in which case the document shall govern.

3.2 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.4).

3.3 Materials. The materials shall be as specified on drawing 2-2-479 and all subsidiary drawings and parts lists pertaining thereto (see 6.5).

3.4 Design and construction. The design and construction of the carrier shall be as specified herein and as shown on Drawing 2-2-479 and all subsidiary drawings and parts lists (PLS) pertaining thereto.

3.4.1 Stitches, seams and stitching. All seams and stitchings shall be as specified on the drawings.

3.4.1.1 Automatic stitching. Automatic machines may be used to perform any of the stitch patterns provided the requirements for the stitch pattern, stitches per inch, and size and type of thread are met; and at least three tying, overlapping or backstitches are used to secure the ends of the stitching.

3.4.1.2 Lubrication of thread. There shall be no lubrication of the thread prior to or during sewing (see 4.4.1.1).

3.4.1.3 Type 301 stitching. Ends of all stitching shall be backstitched or overstitched as specified on the drawings except where ends are turned under or caught in other seams or stitching. Thread tensions shall be maintained so that there will be no loose stitching resulting in loose bobbin or top thread or excessively tight stitching resulting in puckering of the materials sewn. The lock shall be imbedded in the materials sewed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

3.4.1.3.1 Repairs of type 301 stitching. Repairs of type 301 stitching shall be as follows:

a. When thread breaks or bobbin run-outs occur during stitching, the stitching shall be repaired by restarting the stitching a minimum of 1 inch (1/2 inch for box stitching) back of the end of the stitching.

b. Thread breaks or two or more consecutive skipped or runoff stitches noted during inspection of the item (in-process or end item) shall be repaired by overstitching. The stitching shall start a minimum of 1 inch in back of the defective area (1/2 inch on box stitching), continue over the defective area, and continue a minimum of 1 inch (1/2 inch on box stitching) beyond the defective area onto the existing stitching. Loose or excessively tight stitching shall be repaired by removing the defective stitching without damaging the materials and restitching in the required manner.

(When making the above repairs in a. and b. above, the ends of the stitching are not required to be backstitched.)

3.4.1.4 Types 503 or 504 stitching. Thread tension shall be maintained so that there will be no loose stitching. All repairs shall be in accordance with 3.4.1.3.1a and 3.4.1.3.1b, except substitute 3/4 inch for 1 inch wherever 1 inch appears.

3.4.1.5 Thread ends. All thread ends shall be trimmed to 1/4 inch maximum length.

3.4.2 Setting of snap fasteners. A hole shall be prepunched through the materials to receive the button and eyelet components of the snap fasteners. The hole shall be smaller than the outside diameter of the button and eyelet barrels so that the barrel must be forced through the hole. The hole shall not be punched in the setting operation with the button or eyelet barrel. The fasteners shall be securely clinched without cutting the surrounding materials and no more than three splits shall occur in the button or eyelet barrels.

3.4.3 Location marks. Location marks shall not be drilled. Printed markings shall not be more than 1/32-inch in width.

3.5 Repairs. Repairs such as mends, darns, patches, or splices are not permitted on the canteen carriers.

3.6 Replacement of defective components. During the spreading, cutting and manufacturing process, components having material defects or damages that are classified as defects in 4.4.3, shall be removed from production and replaced with non-defective and properly matched components.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

3.7 Marking. The identification marking shall be applied in the location shown on Drawing 2-2-481 and shall conform to type IV, class 5 of DDD-L-20. The letters "US" shall be applied in the size characters and in the location indicated on Drawing 2-2-480 and shall conform to type IV, class 9 of DDD-L-20. Fastness of the class 9 marking shall be as specified for class 5 marking.

3.7.1 Instruction label. An instruction label of the size and requirements specified on PL 2-2-483 shall be sewn on the inside of the flap as indicated on Drawing 2-2-490. The characters used in printing the label shall be of maximum size commensurate with the area and contents specified. The legend shall be located on the label so that no part of the legend will be obscured by stitching or binding when sewn in the cover.

3.7.1.1 Legend. The contents of the instruction label shall be as follows:

FILLING AND THAWING OF THE CANTEEN

Fill the canteen to the Fill Mark stamped on the canteen. Do not fill canteen over the fill mark as overfilling will damage the canteen.

Remove all Plastic Parts before thawing the canteen over an open fire.

HAND WASHING

Wash the carrier, the canteen and the cup in a pail of warm water using mild detergent or soap.
Do not use Chlorine Bleach, Yellow Soap, Cleaning Fluids or Solvents as these cleaners will discolor/deteriorate the items.
Rinse thoroughly in clean warm water.
Dry the items in shade or indoors.
Do not dry in direct sunlight, direct heat or open flame.

3.8 Workmanship. The carrier shall conform to the quality of product established by this document and occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 202610-22T01:46Z
Check the source to verify that this is the current version before use.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for ensuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points in the manufacturing process necessary to assure compliance with all dimensional requirements.

4.1.3 Certificates of compliance. When certificates of compliance are submitted, the Government reserves the right to inspect such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.3 and 4.4.4. The presence of any defect shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced specifications unless otherwise excluded, amended, modified or qualified in this specification or applicable purchase specification.

4.4.1.1 Certification. The contractor shall furnish a certificate of compliance for the requirement of 3.4.1.2 prohibiting use of thread lubricants prior to or during sewing.

4.4.2 In-process inspection. Inspection shall be made at any point or during any phase of the manufacturing process to determine whether cut lengths, cut parts, fabricated parts before assembly, and marking for location of components are in accordance with specified requirements for dimensions and that operations

Source: https://assist.dla.mil -- Downloaded: 202610-22T01:46Z
Check the source to verify that this is the currentversion before use.

and assemblies are accomplished as specified. In addition, inspection shall be made during the manufacturing process to ensure that holes for receiving hardware are prepunched smaller than the outside diameter of the tube. Whenever nonconformance is noted, corrections shall be made to the items and lot in-process. Items which cannot be corrected shall be removed from production.

4.4.3 End item visual examination. The end items shall be examined for the defects listed in table I. The lot size shall be expressed in units of carriers. The sample unit shall be one completely fabricated carrier. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5 for major and 6.5 for total (major and minor combined) defects.

TABLE I. End item visual defects

Examine	Defect	Classification Major	Minor
Cloth, duck, nylon	Any hole, cut or tear, smash, broken or missing yarns, or open place clearly visible at normal inspection distance (approximately 3 feet)	101	
Fastener tape-hook and pile	Any hole, cut or tear	102	
	Hooks missing or flattened impairing function	103	
	Broken or missing yarn in pile impairing function	104	
	Ends not fused		201
Webbing and tape	Any hole, cut, tear, smash, broken end, or pick	105	
	Not firmly and tightly woven; edge frayed or scalloped	106	
	Abrasion mark		202
Hardware	Broken or malformed, failing to serve intended purpose; corroded area, burr, or sharp edge	107	
	Finish omitted or not as specified	108	
	Finish defects (i.e., objectionable orange peel, wrinkle, drop, streak, thin film, or no film)	109	
	Not attached or assembled as specified	110	
	Misplaced, failing to serve intended purpose	111	

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Classification Minor
Snap fastener	Any fastener not functioning properly, i.e., fails to snap closed, to provide a secure closure, or to open freely	112	
	Clinched excessively tight, cutting surrounding material	113	
	Clinched loosely, permitting male components to rotate freely in the hole in the material		203
NOTE:	The fasteners shall be snapped and unsnapped twice to determine whether parts of fastener separate freely and also effect a secure closure.		
Keeper	Slide portion of keeper jams, failing to effect a secure closure	114	
Seams and stitching			
Open seams	More than 1 inch	115	
	1 inch or less		204
NOTE:	A seam shall be classified as open when one or more stitches joining a seam are broken or when two or more skipped or run-off stitches occur. On double stitched seams, a seam shall be considered open when either one or both sides of the seam are open.		
Raw edge (on edge required to be finished)	More than 1/2 inch when securely caught in stitching		205
NOTE:	Raw edges not securely caught in stitching shall be classified as open seam.		

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Classification Minor
Seams and stitching (cont'd)			
Run-off (see open seams)			
Seam and stitch type	Wrong seam or stitch type	116	
Stitch tension	Loose, resulting in a loosely exposed bobbin or top thread; tight, resulting in excessive puckering of fabric on seam		206
Stitches per inch	One stitch less than minimum specified.		207
	Two or more stitches less than minimum specified.	117	
	One or more stitches in excess of maximum specified.		208
	NOTE: Variation in the number of stitches per inch, caused by the operator speeding up the machine and pulling the fabric in order to sew over heavy places or heavy seams, or in turning corners shall be classified as follows: a. Within the minor B defect classification - no defect. b. Within the minor A defect classification - minor B defect.		
Stitching margins or stitching gage	Not as specified		209
End of stitching (not held down by other stitching or turned under in a hem)	Not backstitched or secured	118	
	Backstitched less than 1/2 inch		210

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects (cont'd)

Examine	Defect	Classification Major	Classification Minor
Seams and stitching (cont'd)			
Thread breaks	Backstitched less than 1 inch (type 301)		211
	Backstitched less than 1/2 inch (box stitching)		212
	Overstitched less than 3/4 inch (overedge stitching)		213
	NOTE: Thread break not backstitched or overstitched shall be classified as an open seam.		
Stitching	One or more rows of required stitching omitted (except on box stitching)	119	
Box stitching	Two or more rows of stitching omitted	120	
	One row of stitching omitted		214
Components and assembly	Any component part or required operation omitted or not as specified (unless otherwise classified herein)	121	
	Needle chews	122	
	Mend or darn	123	
Binding	Improperly or loosely applied, badly puckered		215
Cleanness	Grease or oil stains clearly noticeable, thread ends not trimmed throughout		216
Markings: US, identification and instructions	Omitted, incorrect, illegible, misplaced, or size of characters not as specified.		217
Thread ends	Not trimmed to 1/4 inch maximum length		218

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

4.4.4 End item fit examination. The end items shall be examined for the defects listed below. The lot size shall be expressed in units of carriers. The sample unit shall be one carrier. The inspection level shall be S-3 and the AQL, expressed in terms of defects per hundred units, shall be 0.65.

NOTE: Fit examination shall be performed with standard canteen and with a standard cup (see 6.3). The assembled canteen and cup shall be inserted into the carrier. To determine whether canteen and cup fit in the carrier, ease canteen and cup into carrier without effort and close flaps by snapping fasteners in a closed position.

Fit of canteen cup in carrier	Carrier too small (i.e. assembled canteen and cup fail to fit in carrier) Flaps too short, causing failure of snap fastener to effect a smooth and secure closure Flap wrinkled or puckered, does not hug body of canteen carrier when snapped closed

4.4.5 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components, such as: incomplete sealing or closure of flap, improper taping, loose strapping or inadequate stapling. Bulged or distorted container.
Content	Number of carriers per bundle is more or less than specified. 1/ Number of bundles per shipping container is more or less than specified.

1/ For this defect, three bundles from each shipping container in the sample shall be examined.

Source: https://assist.dla.mil -- Downloaded: 202610-22T01:46Z
Check the source to verify that this is the current version before use.

4.4.6 Palletization examination. The fully packaged and palletized end item shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirements.
Palletization	Pallet pattern not as specified. Load not bonded as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A. Each carrier shall have its flaps overlapped in place. Ten carriers, alternating top and bottom, shall be stacked in a bundle. Each bundle shall be cross-tied with cotton tape or twine.

5.1.2 Commercial. Carriers shall be preserved in accordance with ASTM D 3951.

5.2 Packing. Packing shall be level A, B, or Commercial, as specified (see 6.2).

5.2.1 Level A packing. Sixty carriers, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Inside dimensions of the shipping container shall be approximately 24 inches in length, 19 inches in width, and 12 inches in depth. Each shipping container shall have contents covered on top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to A-A-203. Each shipping container shall be closed, water-proofed, and reinforced with strapping or tape banding in accordance with the appendix of PPP-B-636 except that the inspection shall be in accordance with 4.4.5. Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

5.2.2 Level B packing. Sixty carriers, preserved as specified in 5.1, shall be packed in a snug-fitting fiberboard shipping container conforming to style RSC-L, style CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Inside dimensions of the shipping container shall be approximately 24 inches in length, 19 inches in width, and 12 inches in depth. Each shipping container shall have contents covered on top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to A-A-203. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636 except that the inspection shall be in accordance with 4.4.5.

5.2.2.1 Weather-resistant shipping container. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, V4s, fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of PPP-B-636 except that the inspection shall be in accordance with 4.4.5.

5.2.3 Commercial packing. Carriers, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

5.3 Palletization. When specified (see 6.2), carriers, packed as specified in 5.2.2 and 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet types shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. Pallet pattern shall be number 90 in accordance with MIL-STD-147.

5.4 Marking. In addition to any special marking required by the contract or purchase order, shipping containers and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951.

6. NOTES

6.1 Intended use. The canteen carrier is designed to serve as a suitable carrier for the cold weather water canteen and cup.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. When a first article is required (see 3.2, 4.3, and 6.4).
c. Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
d. Type and class of unit load required (see 5.2.1).
e. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
f. When palletization is required (see 5.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

6.3 Samples. For access to guide samples, and to standard samples of the canteen (MIL-C-44348) and the cup (MIL-C-44349), address the contracting activity issuing the invitation for bids.

6.4 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

6.5 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of this document (see 3.3).

6.6 Subject term (key word) listing.

Carrier, water canteen
Cold weather canteen

Custodian:

Army - GL

Review activities:

Army - MD
DLA - CT

Preparing activity:

Army - GL

Project No. 8465-A005

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-C-44347(GL)	Carrier, Water Canteen, Cold Weather, CRS

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

Source: https://assist.dla.mil -- Downloaded: 2026/10-22T01:46Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

U.S. ARMY NATICK RESEARCH, DEVELOPMENT
and ENGINEERING CENTER
ATTN: STRNC-ES
Natick, MA 01760-5014

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
U.S. Army Natick Research, Development
and Engineering Center
ATTN: STRNC-ES
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 202610-22T01:46Z
Check the source to verify that this is the current version before use.