INCH-POUND

MIL-C-44348(GL)
13 December 1988

MILITARY SPECIFICATION

CANTEEN, WATER, COLD WEATHER, CRS

This specification is approved for use by the U.S. Army Natick Research, Development, and Engineering Center, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a canteen fabricated of corrosion-resisting steel having a capacity of 36 ounces.

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

QQ-P-35	-	Passivation Treatments for Corrosion-Resisting Steel
PPP-B-636	-	Boxes, Shipping, Fiberboard
PPP-T-45	-	Tape, Gummed, Paper, Reinforced and Plain for Sealing and Securing

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8465

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202640-22T01:46Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-L-35078 - Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification for
MIL-C-51278 - Cap, Water Canteen, Field, 1 Quart and 2 Quart Canteens

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized Unit Loads
MIL-STD-731 - Quality of Wood Members for Containers and Pallets

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from the Naval Publications and Forms Center, (ATTN: NPODS), 5801 Tabor Avenue, Philadelphia, PA 19120-5099.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

2-10-443 - Canteen Assembly
2-10-444 - Canteen Body
2-10-445 - Bottom, Canteen
2-10-446 - Top, Canteen

(Copies of drawings are available from the U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014.)

2.2 Non-Government publications. The following document forms a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.3.

3.2 Guide samples. Guide samples, when furnished, are solely for guidance and information (see 6.4). Variations from the document may appear in the samples, in which case the document shall govern.

3.3 Materials. The materials shall be as specified on Drawing 2-10-443 and all subsidiary drawings and parts lists pertaining thereto. It is encouraged that recycled material be used when practical as long as it meets the requirements of this specification.

3.4 Design and construction. The design and construction of the canteen shall conform to the design, shape and dimensions shown on Drawing 2-10-443 and as specified herein.

3.4.1 Body weldment. The body weldment shall consist of the upper and lower parts of the body with threaded neck, less cap assembly. The body weldment shall be fabricated from corrosion-resisting steel specified on Drawing 2-10-445 and 2-10-446. The body weldment shall be free from pipe, crack, seam, pit, and lap.

3.4.2 Cap assembly. The cap shall conform to the requirements specified in MIL-C-51278.

3.5 Finish. The canteen shall be given a uniform frosted lusterless finish approximating a commercial 2D sheet finish and passivated in accordance with QQ-P-35. There shall be no evidence of rusting, staining, pitting, or spotting when tested as specified in 4.4.4.

Source: https://assist.dla.mil -- Downloaded: 202610-22T01:46Z
Check the source to verify that this is the current version before use.

3.6 Workmanship. The end item shall conform to the quality of product established by this specification and the occurrence of defects shall not exceed the applicable acceptable quality levels. The completely finished canteen shall be thoroughly clean and free from pit, dig, burr, fin, dents, cracks, sliver, machine tool or dye mark, and foreign matter.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to the requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Responsibility for dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for ensuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point or at all points in the manufacturing process necessary to assure compliance with all dimensional requirements.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4).

4.3 First article inspection. When a first article is required (see 3.1 and 6.2), it shall be examined for the defects specified in 4.4.2 and 4.4.3 and tested for the characteristics specified in 4.4.4. The presence of any defect or failure to pass any test shall be cause for rejection of the first article.

4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

Source: https://assist.dla.mil -- Downloaded: 202610-22T01:46Z
Check the source to verify that this is the current version before use.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.4.2 End item visual examination. The end items shall be examined for the defects listed in table I. The lot size shall be expressed in units of canteens. The sample unit shall be one canteen. The inspection level shall be II and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 1.0 for major defects, 4.0 for major and minor A combined defects, and 15.0 for total (major, minor A and minor B combined) defects.

TABLE I. End item visual defects

Examine	Defect	Classification Major	Minor A	Minor B
Exterior surface of canteen	Not finished	101		
	Type of finish not as specified	102		
	Area of no finish (check areas at peripheries and at weldments)		201	
	Foreign matter imbedded			301
Design	Does not conform to the applicable drawing	103		
Quality of metal on canteen or	Component broken, split, fractured, cracked	104		
	Component malformed, bent or twisted	105		
	Dent, pit, or dig		202	
	Burr, fin, or sliver		203	
	Machine tool, or die mark			302
	Unspecified hole	106		
Construction and workmanship, general	Any part not connected or joined as specified, or operation poorly accomplished	107		
	Any part missing	108		
	Any operation omitted or not properly performed, for example, edge or corner not broken or rounded where required		204	

Source: https://assist.dla.mil -- Downloaded: 202610-22T01:46Z
Check the source to verify that this is the current version before use.

TABLE I. End item visual defects

Examine	Defect	Classification Major	Minor A	Minor B
Welding of canteen	Weldment not smooth and uniform, e.g., protrusion of crevice:			
	a. Joining of lower and upper bodies	109		
	b. Joining of threaded neck to body	110		
	Weld missing	111		
	Metal burned or damaged in welding	112		
	Weld spatter		205	
	Any weld incomplete, fractured, porous, cracked, or not fused	113		
Interior of canteen	Not clean, for example, scale, slag, segregation, inclusion of foreign matter, or not thoroughly dry	114		
	Surface of metal contains pipe, crack, seam, pit, or lap that may permit retention of food particles	115		
	NOTE: The interior surfaces of the canteen shall be examined for defects with the aid of an internal periscope. The periscope shall be equipped with an electric light and mirror. The mirror shall be capable of being rotated a minimum of 180 degrees. The instrument shall be of such size that it will pass through the neck of the canteen (after removal of the adapter). The light shall be of sufficient power to adequately illuminate the interior surface of the canteen.			

4.4.3 End item dimensional examination. The end items shall be examined for conformance to the dimensions specified on the drawings that can be determined on the end items without damaging or disassembling the end items. Any dimension not within the specified tolerance shall be classified as a defect. The lot size shall be expressed in units of canteens. The sample unit shall be one canteen. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 4.0.

Source: https://assist.dla.mil -- Downloaded: 202610-22T01:46Z
Check the source to verify that this is the current version before use.

4.4.4 In-process inspection. Inspection of sub-assemblies shall be made to

4.4.4 End item testing. The end items shall be tested as follows for conformance to the corrosion-resistance requirement in 3.5. The uncapped canteen shall be exposed to a relative humidity of 90 to 100 percent at 72° ± 2°F for not less than 16 hours and then examined on both interior and exterior surfaces. Any evidence of rusting, staining, pitting, or spotting shall constitute a defect. The lot size shall be expressed in units of canteens. The sample unit shall be one canteen. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

4.4.5 Packaging examination. The fully packaged end items shall be examined for the defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as: incomplete sealing or closure of flap, improper taping, loose strapping, or inadequate stapling Bulged or distorted container
Content	Number of canteens per shipping container is more or less than required

4.4.6 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load, fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement
Palletization	Pallet pattern not as specified Load not as specified
Weight	Exceeds maximum load limits
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application

Source: https://assist.dla.mil -- Downloaded: 202610-22T01:46Z
Check the source to verify that this is the current version before use.

of the seam are open.

5. PACKAGING

5.1 Preservation. Preservation shall be level A.

5.1.1 Level A. Each canteen, with cap secured in place, shall be unit packed in a fiberboard box conforming to style OPF or FOL, type CF, class domestic, variety optional of PPP-B-636. The inside dimensions of the box shall be approximately 5-7/8 inches in length, 2-3/4 inches in width, and 8-1/2 inches in depth. Box closure shall be secured with 2-inch minimum width gummed paper tape conforming to type III, grade B of PPP-T-45.

5.2 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.2.1 Level A packing. Thirty canteens, preserved as specified in 5.1, shall be packed in a sung-fitting fiberboard shipping container conforming to style RSC-L, grade V2s of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class weather-resistant, variety DW, grade V15c of PPP-B-636. Inside dimensions of the shipping container shall be approximately 28 inches in length, 17-1/4 inches in width, and 8-3/4 inches in depth. Each shipping container shall be closed, waterproofed, and reinforced with strapping or tape banding in accordance with the appendix of PPP-B-636 except that the inspection shall be in accordance with 4.4.5. Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

5.2.2 Level B packing. Thirty canteens, preserved as specified in 5.1, shall be packed in a sung-fitting fiberboard shipping container conforming to style RSC-L, type CF, (variety SW) or SF, class domestic, grade 275 of PPP-B-636. The inside of each shipping container shall be fitted with a box liner conforming to type CF, class domestic, variety DW, grade 275 of PPP-B-636. Inside dimensions of the shipping container shall be approximately 28 inches in length, 17-1/4 inches in width, and 8-3/4 inches in depth. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636 except that the inspection shall be in accordance with 4.4.5.

5.2.2.1 Weather-resistant fiberboard containers. When specified (see 6.2), the shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with the appendix of PPP-B-636.

5.2.3 Commercial packing. Canteens, preserved as specified in 5.1, shall be packed in accordance with ASTM D 3951.

Source: https://assist.dla.mil -- Downloaded: 202610-22T01:46Z
Check the source to verify that this is the current version before use.

follows:

5.3 Palletization. When specified (see 6.2), canteens, packed as specified in 5.2.2 and 5.2.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet types shall be type I (4-way entry), type IV or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accordance with bonding means K and L or film bonding means O or P. Pallet pattern shall be number 1 in accordance with the appendix of MIL-STD-147.

5.4 Marking. In addition to any special marking required by the contract or purchase order, unit packs, shipping containers, and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES:

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The canteen is intended for use by individual Military personnel in the field for keeping drinking water in the liquid state in cold climates. The canteen is intended to be used with the cold weather canteen carrier and cup.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number and date of this specification.
b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).
c. When a first article is required (see 3.1, 4.3 and 6.3).
d Levels of preservation and packing (see 5.1 and 5.2).
e. Type and class of unit load (see 5.2.1).
f. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.2.2.1).
g. When palletization is required (see 5.3).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection and approval of the first article.

6.4 Sample. For access to samples, address the contracting activity issuing the invitation for bids.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

6.6 Subject term (key word) listing.

Corrosion-resisting steel
Drinking water

Custodian:
Army - GL

Preparing activity:
Army - GL

(Project 8465-A006)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-C-44348(GL)	Canteen, Water, Cold Weather, CRS

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)*: _____
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK/OP-1, Feb 86

Source: https://assist.dla.mil - Downloaded: 2025-10-22T01:46Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

U.S. ARMY NATICK RESEARCH, DEVELOPMENT
and ENGINEERING CENTER
ATTN: STRNC-ES
Natick, MA 01760-5014

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
U.S. Army Natick Research, Development
and Engineering Center
ATTN: STRNC-ES
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T01:46Z
Check the source to verify that this is the current version before use.