MIL-G-82248D(NU)
4 September 1985
SUPERSEDING
MIL-G-82248C(SA)
11 June 1976

MILITARY SPECIFICATION

GLOVES, HEAT PROTECTIVE (TERRY KNIT)

This specification is approved for use by the Navy Clothing and Textile Research Facility, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for heat protective gloves.

1.2 Classification. The gloves shall be of one type and size in the following classes:

Class 1 - Cotton knit
Class 2 - Rayon knit

2. APPLICABLE DOCUMENTS

2.1 Government documents.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Officer in Charge, Navy Clothing and Textile Research Facility, 21 Strathmore Road, Natick, MA 01760-2490 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8415

DISTRIBUTION STATEMENT A. Approved for public release, distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

2.1.1 Specifications, standards, and handbooks. Unless otherwise specified, the following specifications, standards, and handbooks of the issue listed in that issue of the Department of Defense Index of Specifications and Standards (DoDISS) specified in the solicitation form a part of this specification to the extent specified.

SPECIFICATIONS

FEDERAL

V-T-276	- Thread Cotton
NN-P-71	- Pallet, Material Handling, Wood Stringer Construction, 2 Way and 4 Way Entry
CCC-C-443	- Cloth, Duck, Cloth (Single and Plied Filling Yarns Flat)
DDD-L-20	- Label; for Clothing, Equipage, and Tentage (General Use)

MILITARY

MIL-P-15011	- Pallet Material Handling Wood Post Construction, 4 Way Entry
MIL-B-17757	- Boxes, Shipping, Fiberboard (Modular Size)

STANDARDS

FEDERAL

FED-STD-191	- Textile Test Methods
FED-STD-751	- Stitches, Seams, and Stitchings

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection
MIL-STD-129	- Marking for Shipment and Storage
MIL-STD-147	- Palletized Unit Loads

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this specification to the extent specified herein.

LAWS AND REGULATIONS

U.S. POSTAL SERVICE MANUAL

(Copies of the manual may be obtained from the Superintendent of Documents, US Government Printing Office, Washington, DC 20402).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

(Copies of documents required by contractors in connection with specific procurement functions should be obtained from the procuring agency or as directed by the contracting office.)

2.2 Other publications. The following document(s) form a part of this specification to the extent specified herein. The issues of documents which are indicated as DoD adopted shall be the issue listed in the current DoDISS and supplement thereto, if applicable.

NATIONAL MOTOR FREIGHT TRAFFIC ASSOCIATION, INC., AGENT

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Association, ATTN: Traffic Department, 1616 P Street N.W., Washington. DC 20036).

UNIFORM CLASSIFICATION COMMITTEE, AGENT

Uniform Freight Classification

(Application for copies should be addressed to the Uniform Classification Committee, Room 1106, 222 South Riverside Plaza, Chicago. Illinois 60606).

2.3 Order of precedence. In the event of a conflict between the text of this specification and the references cited herein, the text of this specification shall take precedence.

3. REQUIREMENTS

3.1 Guide sample. Samples, when furnished, are solely for guidance and information to the contractor (see 6.3). Variations from this specification may appear in the sample in which case this specification shall govern.

3.2 First article. When specified, the contractor shall furnish sample unit(s) for first article inspection and approval (see 4.2, 6.4 and 6.2).

3.3 Material.

3.3.1 Basic material. The basic materials used for the hand portion of the gloves shall be an unbleached cotton terry knit fabric or a natural rayon terry knit fabric, each knitted with singles yarn. Both materials shall be treated for fire retardancy using compounds that will not cause fabric deterioration during use or storage and shall not contain toxic ingredients that will cause itching, irritation, or other harmful effects on the skin. Only those fire retardant treatments approved by the Government shall be considered acceptable for the related procurement (see 6.2).

The treated terry knit fabrics shall conform to the physical properties listed in Table I when tested as specified in 4.3.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

Table I - Physical properties of treated terry

Characteristics	Requirements
Weight, oz per sq yd	27 to 30
Wales per inch	8 (Min)
Courses per inch	13 (Min)
Thickness, inch	
- 0.1 lbs per sq inch pressure	0.120 (Min)
- 1.1 lbs per sq inch pressure	0.110 (Min)
Bursting strength, lbs	60.0 (Min)
Flame resistance, flame time, seconds	
Wale direction:	
- Initial	5.0 (Max)
- After three launderings	5.0 (Max)
Course direction	
- Initial	5.0 (Max)
- After three launderings	5.0 (Max)
Char length, inch	
Wale direction:	
- Initial	4.0 (Max)
- After three launderings	4.0 (Max)
Course direction	
- Initial	4.0 (Max)
- After three launderings	4.0 (Max)

3.3.2 Cloth cotton duck. The material used for the gauntlet portion of the gloves shall be woven cotton duck fabric conforming to type I of CCC-C-443. The cotton duck shall be treated for fire retardancy using compounds that will not cause fabric deterioration during use or storage and shall not contain toxic ingredients that will cause itching, irritation or other harmful effects on the skin. Only those fire retardant treatments approved by the Government shall be considered acceptable for the related procurement (see 6.2). The treated cotton duck fabric shall conform to the physical properties listed in Table II when tested as specified in 4.3.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

Table II - Physical properties of cotton duck

Characteristics	Requirements
Flame resistance, flame time, seconds	
Warp direction	
- Initial	2.0 (Max)
- After three launderings	2.0 (Max)
Filling direction	
- Initial	2.0 (Max)
- After three launderings	2.0 (Max)
Char length, inches	
Warp direction	
- Initial	4.5 (Max)
- After three launderings	4.5 (Max)
Filling direction	4.5 (Max)
- Initial	4.5 (Max)
- After three launderings	4.5 (Max)

3.3.3 Thread. The thread used for seaming and stitching the gloves shall be unbleached cotton conforming to type IA1, ticket no. 30, 3 ply and ticket no. 24, 4 ply of V-T-276.

3.4 Label. Each glove shall be marked with a label conforming to type III or IV, class 4 of DDD-L-20, except that the size shall not be applicable - and the inscription shall read as follows:

GLOVES, HEAT PROTECTIVE (TERRY KNIT)
CONTRACT NO: DLA-100-00-000-0000 (EXAMPLE)
STOCK NO: 8451-00-000-0000 (EXAMPLE)
CONTRACTOR'S NAME:

3.5 Design. The gloves shall be of a Clute-cut pattern style, consisting of a one-piece cotton duck gauntlet attached to a full inseamed terry knit hand portion (see Figure 1).

3.5.1 Figure. Figure 1 is furnished for information purposes only. To the extent of any inconsistencies between the written specification and the figure, the written specification shall govern.

3.6 Dies and patterns. The dies or patterns for cutting all parts of the gloves shall be furnished by the contractor, and shall be of the proper proportions to provide for good fitting gloves conforming to finished measurements specified in Table IV.

3.6.1 Pattern parts. The component parts of the gloves shall be cut from the materials specified below, and in accordance with the following pattern parts required for the manufacturing process.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

Material	Nomenclature of pattern parts	Cut parts per pair
Cloth, terry knit	No. 2 finger	2
	No. 3 finger	2
	No. 4 finger	2
	Thumb	2
	Palm	2
Cloth, cotton duck	Gauntlet	2

3.7 Construction.

3.7.1 Stitches, seams, and stitchings. Stitch, seam, and stitching types specified in Table III shall conform to FED-STD-751. Whenever two or more methods of stitch types are given for the same part of the operation, any one may be used.

3.7.2 Stitches per inch. The minimum and maximum number of stitches per inch shall be as specified in Table III.

3.7.3 Type 301 stitching. Ends of 301 stitching shall be backstitched or backtacked not less than 3/8 inch, except where ends are caught in other seams and stitching. Thread tension shall be maintained so there will be no loose stitching resulting in a loose bobbin or top thread, or no excessively tight stitching resulting in puckering of the material sewn. The lock shall be embedded in the materials sewn.

3.7.3.1 Repairs of type 301 stitching. Repairs of type 301 stitching shall be as follows:

a. When thread breaks or bobbin run-outs occur during sewing, the stitching shall be repaired by restarting the stitching a minimum of 3/8 inch back of the end of the stitching. When making this repair the ends of stitching are not required to be backstitched.

b. Thread breaks, or two or more consecutive skipped stitches or run-offs noted during inspection of the item (in-process or end item) shall be repaired. The stitching shall start a minimum of 3/8 inch back of the defective area, continue over the defective area, and continue a minimum of 3/8 inch beyond the defective area onto the existing stitching. Loose or tight stitching shall be repaired by removing the defective stitching without damaging the material and restitching in the required manner. When making the above repairs, the ends of stitching are not required to be backstitched.

3.7.4 Type 401 stitching. Thread tension shall be maintained so that there will be no loose stitching. Where stitch type 401 is used, the looper thread shall be on the inside of the gloves. Both ends of all seams or stitching produced with 401 stitch type, when not caught on other seams or stitching, shall have 1/2 to 3/4 inch chain extending beyond each end. All repairs shall be in accordance with 3.7.3.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

3.8 Manufacturing operations. The gloves shall be manufactured in accordance with operation requirements specified in Table III. The contractor is not required to follow the exact sequence of operations, provided the finished gloves are identical to those produced by following the exact sequence shown.

3.9 Abbreviations in table of operations. The abbreviations used in table I are as follows:

Stch	-	Stitch
in	-	inch
Ndl	-	Needle
Bob	-	Bobbin
Lpr	-	Looper
Mchne	-	Machine
Brtck	-	Bartack
Comrcl	-	Commercial
smlr	-	similar
Btnhl	-	Buttonhole
incl	-	including
dbl	-	double

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

TABLE III - CONSTRUCTION OF GLOVES

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH IN	THREAD NDL	THREAD BOB/ LPR
1.	Cutting.					
	a. Cut the component parts of the hand portion of the gloves (knitted terry) in the length (wale) direction (see 3.3.1 and 3.6.1).					
	b. Cut the gauntlet piece for the gloves from one piece of cotton duck material in the length (warp) direction (see 3.3.2 and 3.6.1).					
	c. The face side of the knitted terry shall be the uncut loop pile side.					
2.	Replacement of defective components. During the spreading, cutting, and manufacturing process, components having materials defects or damages that are classified as defects in 4.3.2.1 shall be removed from production and replaced with non-defective and properly matched component.					
3.	Marking. Mark, ticket, or bundle all component cut parts to insure proper assembly of the gloves.					
4.	Assemble hand portion of gloves (thumb and fingers).					
	a. Stitch the thumb piece to thumb section of palm, face to face, along the periphery of thumb, 3/16 to 1/4 inch from the raw edge.	301 or 401	SSa-1	7-9	24/ 4	24/4 or 30/3
	b. Stitch the No. 2 finger portion to the No. 3 finger portion, face to face, from the wrist end to the finger crotch, 3/16 to 1/4 inch from the raw edge.	301 or	SSa-1	7-9	24/ 4	24/4 or 30/3
	c. Stitch the No. 3 finger portion to the No. 4 finger portion, face to face, from the wrist end to the finger crotch, 3/16 to 1/4 inch from the raw edge.	301 or 401	SSa-1	7-9	24/ 4	24/4 or 30/3
	d. Stitch the No. 2 finger portion to the first (index) finger, face to face, from the wrist end to the finger crotch, 3/16 to 1/4 inch from the raw edge.	301 or	SSa-1	7-0	24/ 4	24/4 or 30/3

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

TABLE III - CONSTRUCTION OF GLOVES

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH IN	THREAD NDL	THREAD BOB/ LPR
5.	Assemble and attach quantlet.					
	a. Overedge stitch the longer raw edge of the gauntlet (glove opening end).	503 or 504	EFd-1	7-9	24/ 4	24/4 or 30/3
	b. Turn under the serged edge 3/8 (+ 1/16) inch and stitch 3/16 to 1/4 inch from the folded edge forming a hem.	301 or 401	EFa-1	7-9	24/ 4	24/4 or 30/3
	c. Superimpose the unstitched edge of gauntlet to the face side of hand portion of gloves at wrist end and stitch 3/16 to 1/4 inch from the raw edge.	301 or 401	LSq-2(a)	7-9	24/ 4	24/4 or 30/3
	d. Turn gauntlet to finished position with seam allowances facing towards top of glove and topstitch gauntlet side 1/8 inch from the folded edge.	301 or 401	LSq-2(b)	7-9	24/ 4	24/4 or 30/3
	e. As an alternate to sequences "c" and "d" superimpose, face to face, the unstitched edge of gauntlet to the hand portion of glove at wrist end and double stitch 1/8 to 1/4 inch gauge.	301	SSa-2	7-9	24/ 4	24/4 or 30/3
6.	Closing.					
	a. Close the gloves by stitching face to face, from the top edge of the first (index) finger and along the periphery of the fingers and side of gloves to the top of gauntlet, 3/16 to 1/4 inch from the raw edge. When stitch type 401 is used, the end of the joining seam at gauntlet hem shall be tacked or backstitched.	301 or 401	SSa-1	7-9	24/ 4	24/4 or 30/3
	b. Trim when necessary excess material from end of side seam of gauntlet opening and snip off corner.					
	OR					

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

TABLE III - CONSTRUCTION OF GLOVES

NO.	OPERATION	STCH TYPE	SEAM/ STCH TYPE	STCH IN	THREAD NDL	THREAD BOB/ LPR
	c. Close the glove by stitching, face to face, from the top edge of the first (index) finger and along the periphery of the fingers and side of gloves to the wrist seam 3/16 to 1/4 inch from the raw edge.	301 or 401	SSa-1	7-9	24/ 4	24/4 or 30/3
	d. Close the gauntlet along side. When stitch type 401 is used, the end of the joining seam at gauntlet hem shall be tacked or backstitched.	301 or 401	SSa-1	7-9	24/ 4	24/4 or 30/3
7.	Finishing. Turn glove to its finished position, terry loop on the outside.					
8.	Labeling. Each glove shall have the label marking (see 3.4) applied to the inside of the guantlet on the front or back of glove, centered and positioned so that the bottom line of the marking is facing towards, parallel to and approximately one inch down from the folded edge of gauntlet hem.					
9.	Trimming and cleaning. a. Trim thread ends and remove all loose threads.					
	b. Remove all spots and stains					
10.	Pairing. The finished gloves shall be paired and tacked or stapled together in a manner that will permit the gloves to be separated from each other without damaging the material.					

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

3.9 Measurements. The measurements of the finished gloves shall conform to the dimensions specified in Table IV. All measurements and tolerances are expressed in inches and shall be made with the glove laid flat under no tension with the palm side facing up.

Table IV - Finished measurements

Measurement	Dimension	Tolerance
Hand length (A)	8-1/4	+ 1/4
Gauntlet length (B)	4-1/2	Minimum
Width of gauntlet at wrist seam (C)	5-1/4	± 1/4
Width of gauntlet at top opening (D)	7	± 1/4

NOTE: A, B, C, and D refer to Figure 1.

A. Measurement taken from tip of second finger to wrist seam.
B. Measurement taken from top open edge to wrist seam.
C. Measurement taken across gauntlet at wrist seam, folded edge to folded edge.
D. Measurement taken across gauntlet at top open edge, folded edge to folded edge.

3.10 Workmanship. The finished gloves shall conform to the quality established by this specification. The occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.1.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

1. First article inspection (see 4.2).
2. Quality conformance inspection (see 4.3).

4.2 First article inspection. When required, the first article submitted in accordance with 3.2, shall be inspected as specified in 4.3.2.1 and 4.3.2.2 for compliance with design, construction, workmanship, and dimensional requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

4.3 Quality conformance inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated.

4.3.1 Component and material inspection. In accordance with 4.1 above, components and materials shall be tested in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable procurement documents. In addition, testing shall be performed on the cloth component materials listed in Table V for the characteristics specified and in accordance with the referenced test methods of FED-STD-191 whenever applicable. Testing for all the requirements listed in Table V is applicable to the sample unit. For the treated terry knit and cotton duck material, the lot size shall be expressed in units of yards and the sample unit shall be 1/2 yard full width. The sample size shall be as follows:

Lot size	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

The lot shall be unacceptable if one or more units fail to meet and requirement specified.

Table V - Component testing

Component	Characteristic	Requirement Paragraph	Test Method
Cloth, terry knit	Material identification	3.3.1	1200 1/
	Type of knit	3.3.1	Visual 2/
	Weight	Table I	5041
	Wales per inch	Table I	5070
	Courses per inch	Table I	5070
	Bursting strength	Table I	5120
	Thickness		
	- 0.1 lbs per square inch pressure	Table I	5030 3/
	- 1.1 lbs per square inch pressure	Table I	5030 3/
	Flame resistance		
	Wale direction:		
	- Initial	Table I	5903
	- After three launderings	Table I	5556 4/ 5903
	Course direction		
	- Initial	Table I	5903
	- After three launderings	Table I	5556 4/ 5903
	Char length		
	Wale direction:		
	- Initial	Table I	5903
	- After three launderings	Table I	5556 4/ 5903
	Course direction		
	- Initial	Table I	5903
	- After three launderings	Table I	5556 4/ 5903

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

Table V - Component Testing (Cont'd)

Component	Characteristic	Requirement Paragraph	Test Method
Cloth, cotton, duck	Flame resistance		
	Warp direction:		
	- Initial	Table II	5903
	- After three launderings	Table II	5556 4/ 5903
	Filling direction		
	- Initial	Table II	5903
	- After three launderings	Table II	5556 4/ 5903
	Char length		
	Warp direction:		
	- Initial	Table II	5903
	- After three launderings	Table II	5556 4/ 5903
	Filling direction		
	- Initial	Table II	5903
	- After three launderings	Table II	5556 4/ 5903

1/ Unless otherwise specified, a certificate of compliance shall be submitted and will be acceptable for the stated requirement.
2/ One determination shall be performed per sample unit and the results reported as "pass" or "fail".
3/ Test shall be performed with the uncut loop pile side of the glove face up.
4/ Use cotton laundering procedure.

4.3.2 Examination of the end item. Examination of the end item shall be in accordance with 4.3.2.1 through 4.3.2.2. The applicable inspection levels and acceptable quality levels (AQL's) shall be as indicated in 4.4.2.3. The lot size shall be expressed in units of one glove each. The sample unit shall be one glove and selection shall be by pairs. Defects for pairing shall be classified as a single defect.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

4.3.2.1 Visual examination.

Defects	Classification Major	Minor
I. MATERIAL DEFECTS AND DAMAGES		
a. Any hole, cut, tear, misweave, knit deficiency or burn	X	
b. Any visible mend, loose yarn, broken yarn, snagged yarn, or slubby yarn more than twice the size of the normal diameter of the yarn		X
c. Pile on face side of terry cloth cut	X	
d. Ruptured fibers in the line of stitching (caused by a blunt or broken needle)		X
e. Any run or dropped stitch in the knitted terry cloth	X	
II. CLEANNESS		
a. Any spot or stain		X
b. Thread ends not trimmed or loose threads not removed throughout major portion of glove		X
c. Surplus material on seams not evenly trimmed		X
III. CUTTING		
Any component part not cut in accordance with specification requirements, e.g , any hand component part not cut in the length (wale) direction of the terry knit material.	X	
IV. PAIRING		
a. Mispaired, i.e., two left or two right hand gloves submitted as a pair	X	
b. Pair not securely tacked or stapled together		X
c. Tacking or stapling too tight, i.e., not permitting the gloves to be separated without damaging the material.	X	
V. COMPONENTS AND ASSEMBLY		
a. Any component part or operation omitted	X	
b. Any component not as specified	X	
c. Any component misplaced or not serving intended purpose		X
d. Any component not securely attached e.g., gauntlet loosely stitched to hand portion of glove		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

Defects	Classification Major	Minor
VI. SEAMS AND STITCHING		
a. Any open seam not repaired, except on gauntlet hem	X	
b. Open seam repaired, but not repaired as specified		X
c. Open stitching on gauntlet hem		X
NOTE: The seam or stitching shall be classified open when one or more stitches joining a seam or a line of stitching are broken, or when two or more continuous skipped or runoff stitches occur.		
d. Not specified seam or stitch type	X	
e. Any line of stitching omitted	X	
f. Any line of stitching misplaced or not beginning or ending where specified		X
g. Any part of glove caught in an unrelated operation	X	
h. Loose tension resulting in a loose seam	X	
i. Loose tension on hem resulting in loosely exposed thread		X
j. Tight tension (stitches break when normal strain is applied in the direction of the seam or stitching)	X	
k. End of 301 stitching, when not caught in other seams or stitching not backstitched or backstitched less than 3/8 inch		X
l. End of seam or stitching produced with stitch type 401 not caught in other seams or stitching		
1. Chain does not extend beyond each end	X	
2. Chain extends less than 1/2 inch or more than 3/4 inch beyond each end	X	
m. Looper thread of 401 stitch type on outside of glove	X	
n. Stitches per inch (to be scored only when the condition exists on the major portion of seam or stitching)		
1. One or two stitches per inch less than the minimum		X
2. Three or more stitches per inch less than the minimum	X	
3. More than the maximum number of stitches per inch, damaging assembly	X	
4. More than the maximum number of stitches per inch, but not damaging assembly		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

Defects	Classification Major	Minor
o. Gage of stitching irregular or not as specified		
1. Seriously affecting serviceability	X	
2. Affecting serviceability, but not seriously		X
VII. LABEL (MARKING)		
a. Omitted, incorrect, illegible, or incomplete on one or both gloves		X
b. Not positioned as specified		X

4.3.2.2 Dimensional examination. The gloves shall be examined for dimensional defects. Any dimension that is not within the established tolerance, shall be classified as a defect (see 3.9).

4.3.2.3 Inspection levels and acceptable quality levels (AQL's). The inspection levels, expressed in defects per 100 units for visual and dimensional examination, shall be as follows:

	Inspection Level	AQL's Major	AQL's Total
For visual examination - 4.3.2.1	II	2.5	6.5
For dimensional examination - 4.3.2.2	S-3	-	4.0

4.3.3 Examination of packaging requirements. An examination shall be made to determine that packaging, packing, and marking complies with Section 5 requirements of this specification. Defects shall be scored in accordance with the list below. The sample unit shall be one shipping container fully packaged except that it need not be closed. Defects of closure listed below shall be examined on shipping containers fully packaged for delivery. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 and the AQL shall be 2.5 defects per 100 units.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

Examine	Defect
Marking (exterior and interior)	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application
Materials	Any component missing, damaged, or not as specified
Workmanship	Inadequate application of components, such as incomplete closure of container flaps, improper taping, loose strapping, or inadequate stapling, bulging, or distorted container
Content	Number of pairs of gloves per bundle is more or less than specified. 1/ Number of bundles per container is more or less than specified. 1/

1/ For these defects one shipping container within the inspection lot shall be examined.

4.3.4 Palletization examination. An examination shall be made to determine that the palletization complies with the section 5 requirements. Defects shall be scored in accordance with the list below. The sample unit shall be one palletized unit load full packaged. The lot size shall be the number of palletized unit loads in the end item inspection lot. The inspection level shall be S-1 and the AQL expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirements
Palletization	Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded with required straps as specified
Weight	Exceed maximum load limits
Marking	Omitted, incorrect, illegible, of improper size, location, sequence, or method of application

5. PACKAGING

5.1 Presevation packaging. Packaging shal be level A or C as specified (see 6.2).

5.1.1 Level A. Twelve (12) pairs of gloves shall be evenly stacked in a bundle with every other pair reversed end for end. Each bundle shall be securely tied at each end with cotton tape or twine.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

5.1.2 Level C (Commercial packaging). Gloves shall be packaged to afford adequate protection against physical damage during shipment from the contractor to the first receiving activity. The contractor may use his standard practice when it meets this requirement. The package and the quantity per package shall be the same as that normally used by the contactor for retail distribution.

5.2 Packing. Packing shall be level A, B, or C as specified (see 6.2).

5.2.1 Level A. Thirty-six (36) pairs of gloves, packaged as specified in 5.1, shall be packed in a fiberboard shipping container assembled, closed, and reinforced conforming to class weather-resistant, type CF, variety DW, grade V15c, size 2A of MIL-B-17757. The fiberboard used for the liner shall conform to type CF, class domestic of MIL-B-17757. Level A packages shall be packed flat, three in length, one in width, and one in depth within the shipping container. Each container shall have the contents completely covered on the top and bottom with a sheet of kraft paper of any suitable commercial grade.

5.2.2 Level B. Thirty-six (36) pairs of gloves, packaged as specified in 5.1, shall be packed in a fiberboard shipping container assembled and closed conforming to class domestic, type CF, variety DW, grade 200, size 2A of MIL-B-17757. The fiberboard used for the liner shall conform to type CF, class domestic of MIL-B-17757. Level B packages shall be packed flat, three in length, one in width, and one in depth within the shipping container. Each container shall have the contents completely covered on the top and bottom with a sheet of kraft paper of any suitable commercial grade.

5.2.3 Level C (Commercial Packing). Gloves packaged as specified in 5.1, shall be packed in a manner to insure carrier acceptance and safe delivery at destination at the lowest transportation rate for such supplies. The quantity per shipping container shall be the same as that normally used by the contractor for retail distribution. Containers shall comply with the US Postal Service Manual, Uniform Freight Classification Rules, or National Motor Freight Classification Rules, as applicable.

5.3 Palletization. When specified (see 6.2), gloves packed as specified in 5.2, shall be palletized in accordance with load type Ia of MIL-STD-147. Each prepared load shall be bonded with primary and secondary straps in accordance with the bonding means (C, K, and L) or O or P. Pallet pattern shall be in accordance with the appendix of MIL-STD-147. The pallet shall be 4-way, Type III, Class 1, Style A, Size 2, Wood Group I, Grade A of NN-P-71, or 4-way, Style (1, 1A or 1B), Size A, Type I, Class 1 of MIL-P-15011. Interlocking of loads shall be effected by reversing the pattern of each course. If the container is of a size which does not conform to any of the patterns specified in MIL-STD-147, the pallet pattern used shall be approved by the contracting officer.

5.4 Marking. In addition to any special marking required by the contract, shipping containers shall be marked in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The gloves covered by this specification are intended to be worn by Naval Military personnel to protect the hands in handling moderately hot objects.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification
b. Whether first article sample is required (see 3.2, 4.2, and 6.4)
c. List of approved flame retardant treatments (see 3.3.1 and 3.3.2)
d. Selection of applicable levels of packaging and packing (see 5.1 and 5.2)
e. When palletization is required (see 5.3)

6.3 Samples. For access to samples, address the procuring activity issuing the invitation for bids.

6.4 First article. When a first article sample is required, it shall be a preproduction sample and it shall be inspected and approved. The contracting officer should include specific instructions in acquisition documents regarding arrangements for inspections, quantity, and testing and approval of the first article.

Custodian:
Navy - NU

Preparing Activity:
Navy _ NU

Review Activity:
DLA-CT

Project No. 8415-N402

User Activity:
Navy - OS

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-G-82248D(NU)	GLOVES, HEAT PROTECTIVE (TERRY KNIT)

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR ☐ USER ☐ MANUFACTURER ☐ OTHER *(Specify)*: _____
b. ADDRESS *(Street, City, State, ZIP Code)*	

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T06:57Z
Check the source to verify that this is the current version before use.