MILITARY SPECIFICATION SHEET

PLASTIC SHEET, LAMINATED, MATERIALS (FOR PRINTED WIRING BOARDS), BASE MATERIAL, AI, ARAMID, WOVEN, MAJORITY POLYIMIDE, RESIN PREIMPREGNATED (B-STAGE)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the plastic sheets described herein shall consist of this specification and the latest issue of MIL-P-13949.

REQUIREMENTS:

Property values: See table I.

TABLE I. Property values.

Property to be tested	Test condition 1/	Values required
1. Volatile content	E1/4 163°C E1/4 163°C	1.5 maximum
2. Electric strength, perpendicular to laminations, average, minimum volts/mil	D-48/50 + D-0.5/23	750
3. Permittivity at 1 MHz maximum	C-40/23/50	4.2
4. Loss tangent at 1 MHz maximum	C-40/23/50	0.035
5. Flammability, maximum burntime, seconds each flame application	A	15

1/ See specimen conditioning requirements, conditioning tolerances and testing information table XXVI of MIL-P-13949.

Custodians:
Army - ER
Navy - EC
Air Force - 17

Review activities:
Army - AR, MI
Navy - AS, OS, SH
Air Force - 11, 85
NSA - S5
DLA - ES

User activities:
Army - AT, ME
Navy - MC
Air Force - 19

Preparing activity:
Army - ER

Agent:
DLA - ES

(Project 5999-0179-04)

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202640-18T02:40Z
Check the source to verify that this is the current version before use.