INCH-POUND

MIL-S-13949/12B
16 August 1993
SUPERSEDING
MIL-P-13949/12A
11 February 1987

MILITARY SPECIFICATION SHEET

SHEET, PRINTED WIRING BOARD, PREPREG, BASE MATERIAL GF (WOVEN E-GLASS REINFORCEMENT, MAJORITY DIFUNCTIONAL EPOXY RESIN, FLAME RESISTANT)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DODISS) specified in the solicitation: MIL-S-13949.

REQUIREMENTS:

Reinforcement material: G in accordance with MIL-S-13949.

Resin system: F in accordance with MIL-S-13949.

Special consideration (third letter designator): G, K, N, P or T in accordance with MIL-S-13949.

Qualification inspection: The inspection routine shall include permittivity and loss tangent at 1 MHz.

Conditioning of specimens prior to test: Unless otherwise specified herein, specimens shall be conditioned in accordance with the applicable test method.

Property values, all reinforcement styles.

Flammability, duration of burning time, each flame application: 15 seconds maximum.

Volatile content (conditioning of specimen prior to test, E-0.25/163): 0.75 percent maximum.

Electric strength, average: 750 volts/mil minimum.

Loss tangent at 1 MHz: 0.035 maximum.

Permittivity at 1 MHz: 5.4 maximum.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-18T02:39Z
Check the source to verify that this is the current version before use.

Supersession information: Not applicable.

Type designation: Consists of "PGF" prefix followed by coded alphas and numeric characters as shown in the following example:



Revision letters are not used to denote changes due to the extensiveness of the changes.

CONCLUDING MATERIAL

Custodians:
Army - ER
Navy - EC
Air Force - 85

Review activities:
Army - AR, MI
Navy - AS, OS, SH
Air Force - 11, 99
DLA - ES
NASA - NS

User activities:
Army - AT, ME
Navy - MC
Air Force - 19

Preparing activity:
Army - ER

Agent:
DLA - ES

(Project 5998-0027-06)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:39Z
Check the source to verify that this is the current version before use.