INCH-POUND

MIL-S-13949/16B
28 March 1993
SUPERSEDING
MIL-S-13949/16A
12 October 1988

MILITARY SPECIFICATION SHEET

SHEET, PRINTED WIRING BOARD, PREPREG, BASE MATERIAL AF (WOVEN ARAMID REINFORCEMENT, EPOXY RESIN, FLAME RESISTANT)

This specification is approved for use by all Departments and Agencies of the Department of Defense

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DODISS) specified in the solicitation MIL-S-13949

REQUIREMENTS

Reinforcement material A in accordance with MIL-S-13949

Resin system F in accordance with MIL-S-13949

Special consideration (third letter designator) G, K, M, N, P or T in accordance with MIL-S-13949

Qualification inspection The inspection routine shall include permittivity and loss tangent at 1 MHz

Extent of qualification Qualification to third letter designator G or T does not extend to each other

Conditioning of specimens prior to test Unless otherwise specified herein, specimens shall be conditioned in accordance with the applicable test method

Property values, all reinforcement styles

Flammability, duration of burning time, each flame application	15 seconds maximum
Volatile content (conditioning of specimen prior to test, E-0 25/163)	1 5 percent maximum
Electric strength, average	750 volts/mil minimum
Loss tangent at 1 MHz	045 maximum
Permittivity at 1 MHz	4 5 maximum

DISTRIBUTION STATEMENT A Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:40Z
Check the source to verify that this is the current version before use.

Supersession information See table I

TABLE I Supersession information 1/

Superseding type designation	Superseded type designation in accordance with MIL-S-13949/16A, 12 October 1988	Superseded type designation in accordance with MIL-P-13949/16, 21 January 1986
PAF*3080********	PAF*0108********	P-AE**********
PAF*3081********	PAF*0108********	P-AE**********
PAF*3500********	PAF*0120********	P-AE**********

1/ Asterisks are used in place of identifiers that did not change

Type designation Consists of "PAF" prefix followed by coded alphas and numeric characters as shown in the following example

P AF N 3080 R 30 10 60

Prepreg material
Base material
Special considerations (G, K, M, N, P, or T, see MIL-S-13949)
Reinforcement fabric style (see MIL-S-13949)
Flow test method (see MIL-S-13949)
Resin flow value (see MIL-S-13949)
Nominal gel time (see MIL-S-13949)
Nominal resin content (see MIL-S-13949)

Revision letters are not used to denote changes due to the extensiveness of the changes

CONCLUDING MATERIAL

Custodians
Army - ER
Navy - EC
Air Force - 85

Review activities
Army - AR, MI
Navy - AS, OS, SH
Air Force - 11, 99
NASA - S5
DLA - ES

User activities
Army - AT, ME
Navy - MC
Air Force - 19

Preparing activity
Army - ER

Agent
DLA - ES

(Project 5998-0027-07)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T02:40Z
Check the source to verify that this is the current version before use.