DOD-T-46151A
19 December 1979
SUPERSEDING
MIL-T-46151
16 October 1970

MILITARY SPECIFICATION

TAPE, ADHESIVE, RUBBER (METRIC)

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers polyurethane foam, pressure-sensitive, adhesive tape.

2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on the date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

PPP-B-585 - Boxes, Wood, Wirebound
PPP-B-601 - Boxes, Wood, Cleated-Plywood
PPP-B-621 - Boxes, Wood, Nailed and Lock-Corner
PPP-B-636 - Box, Fiberboard
PPP-B-640 - Boxes, Fiberboard, Corrugated, Tripple-Wall

MILITARY

MIL-B-117 - Bags, Sleeves and Tubing, Interior Packaging

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-147 - Palletized and Containerized Unit Load 40" x 48" Pallets, Skids, Runners or Pallet-Type Base
MIL-STD-1188 - Commercial Packaging of Supplies and Equipment

FSC 9320

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Army Materials and Mechanics Research Center, Watertown, MA 02172 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426 appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM) STANDARDS

C 177 - Test for Steady-State Thermal Transmission Properties by Means of the Guarded Hot Plate
D 882 - Tests for Tensile Properties of Thin Plastic Sheeting
D 1938 - Test for Tear Propagation Resistance of Plastic Film and Thin Sheeting by a Single-Tear Method
D 2117 - Test for Melting Point of Semicrystalline Polymers
D 3574 - Testing Flexible Cellular Materials - Slab, Bonded, and Molded Urethane Foams)

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

PRESSURE SENSITIVE TAPE COUNCIL
Test Methods for Pressure Sensitive Tapes

PSTC-1 - 180° Peel Adhesion (PSTC)
PSTC-7 - Shear Adhesion (Holding Power)
PSTC-31 - Tensile Strength and Elongation

(Application for copies should be addressed to the Pressure Sensitive Tape Council, 1201 Waukegan Road, Glenview, Illinois 60025.)

3. REQUIREMENTS

3.1 Material and construction. The polyurethane foam, pressure-sensitive adhesive tape shall consist of five layers of materials as follows:

a. A layer of polyurethane foam of the polyester or polyether type (see 3.1.1).

b. An adhesive to form a permanent bond that is uniform and smooth between the polyurethane foam and the polyester film carrier (see 3.1.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

c. A plastic film carrier of the polyester type (poly(ethylene terephthalate) or equal) (see 3.1.3).

d. The other side of the film shall be entirely coated with a pressure-sensitive, water-insoluble adhesive (see 3.1.4) to provide a firm bond by pressure without heat or any other preparation prior to use.

e. The pressure-sensitive adhesive shall have a protective covering of silicone-coated release paper (see 3.1.6) which can be readily removed prior to application of the tape to be bonded.

3.1.1 Polyurethane foam. The polyurethane foam shall be of the polyester or polyether type and shall be a 60 (-5 +10) PPI (pores per inch) custom foam. The contractor shall show written proof or certification (see 4.8) that the foam is polyurethane foam of the polyester or polyether type and a 60 (-5 +10) PPI custom foam. The foam shall be "clickable" (i.e., die cuttable without "welding" of the edges (see 4.5.1). The foam shall be of the specified dimensions (see 3.3) and shall have a fire retardant additive to permit passage of the flammability test. The foam shall be flexible, free of non-expanded resin areas and uniform in texture and cell structure. The foam when tested as specified in 4.6.1 shall conform to the requirements of table I.

3.1.1.1 Color of polyurethane foam. Unless otherwise specified the color of the polyurethane foam shall be charcoal (see 4.5.1 and 6.2).

3.1.2 Adhesive (foam to carrier). The adhesive between the polyurethane foam and the polyester film carrier shall meet the requirements of this specification. The adhesive shall be flexible (see 4.5.1) and shall not fail before the pressure-sensitive adhesive when tested as specified in 4.6.3.1.

3.1.3 Polyester film. The film shall be plastic of the polyester type (poly(ethylene terephthalate) or equal) (see 4.8) and shall conform to the requirements of table II.

3.1.4 Pressure sensitive adhesive. The pressure-sensitive adhesive on the tape shall be flexible, uniform and smooth. There shall be no bare spots, lumps, blisters or flaking. The pressure-sensitive adhesive when tested as specified in 4.6.3 shall comply with the requirements as specified in table III.

3.1.5 Tape.

3.1.5.1 Tensile strength. The finished tape after removal of release paper shall show a tensile strength of not less than 1751 newtons per meter of width (10 lbf/inch of width) without breakage in any layer (see 3.1) when tested as specified in 4.6.3.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

3.1.5.2 Elongation. The finished tape after removal of release paper shall show an elongation of not less than 30 percent without breakage in any layer (see 3.1) when tested as specified in 4.6.3.1.

Table I. Physical properties of polyurethane foam

Property 1/	Requirements Minimum	Maximum	Test paragraph
Density, kg/m^3 (lb/ft^3)	28.8 (1.8)	35.2 (2.2)	4.6.1
Tensile strength, kPa ($lbf/in.^2$)	138 (20)	-- --	4.6.1
Elongation, ultimate, %	200	--	4.6.1
Tear strength, N/m (lbf/in.)	367 (2.1)	-- --	4.6.1
Compression set at 50 percent deflection, %	--	20	4.6.1
Indentation force deflection, N			
At 25 percent deflection	2.2	38	4.6.1
At 65 percent deflection	4.0	9.0	4.6.1
Steam autoclave tests (results after treatment)			
Compression set at 50 percent deflection, %	--	70	4.6.1
Indentation force deflection, % (loss from original indentation force deflection)			
At 25 percent deflection	--	30	4.6.1
At 65 percent deflection	--	40	4.6.1
Thermal conductivity, W/(m k); (Btu in./s ft^2 ^oF)	-- --	0.036 (0.25)	4.6.1

1/ Metric symbols are used as the primary standard of measurement. Numbers in parentheses represent the English equivalents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

Table II. Properties of polyester film

Property	Requirements Minimum	Maximum	Test paragraph
Melting point[1/], °C (°F)	245 (473)	250 (482)	4.6.2
Tensile strength, N/m	1751		4.6.2
Elongation, %	30	100	4.6.2
Tear strength, Kg	0.014		4.6.2

[1/]The test for melting point may be waived upon certification (see 4.8) that the film is plastic of the polyester type (poly(ethylene terephthalate) or equal).

Table III. Properties of adhesive

Test	Original force minimum (see 4.6.3.1)	Force after exposure to humidity minimum (see 4.6.3.1.1)
180° peel adhesion, N/m (lbf/in.)		
1 minute after mounting	560 (3.2)	508 (2.9)
20 minutes after mounting	595 (3.4)	543 (3.1)
60 minutes after mounting	648 (3.7)	595 (3.4)
24 hours after mounting	736 (4.2)	666 (3.8)
Shear adhesion (holding power)		
Hours to failure (minimum) (1000 grams per square inch)	48 hrs.	48 hrs.

3.1.6 Release paper. The release paper shall be coated with a silicone release so as to permit easy peelability without adherence of the pressure-sensitive adhesive to the release paper or breakage of the tape or paper.

3.2 Rolls. The tape shall be furnished in rolls.

3.3 Dimensions. Unless otherwise specified (see 6.2 and 6.3) the tape on each roll shall be in one continuous length with the thickness, length, and width as specified. Tolerances in the thickness, length, and width of the tape shall be as specified in table IV.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

Table IV. Tolerances in thickness, length, and width of tape.

Thickness in millimeters (inches)			Length and width in millimeters (inches)		
	Tolerance			Tolerance	
Dimension	Plus	Minus	Dimension	Plus	Minus
0 to 6.4 (0 to 1/4)	0.8 (1/32)	0.8 (1/32)	0 to 152.4 (0 to 6)	3.2 (1/8)	1.6 (1/16)
Over 6.4 to 38.1 (1/4 to 1-1/2)	1.6 (1/16)	1.6 (1/16)	Over 152.4 to 304.8 (6 to 12)	6.4 (1/4)	3.2 (1/8)
Over 38.1 to 76.2 (1-1/2 to 3)	3.2 (3/16)	1.6 (1/16)	Over 304.8 to 609.6 (12 to 24)	12.7 (1/2)	6.4 (1/4)
Over 76.2 to 127 (3 to 5)	4.8 (3/16)	1.6 (1/16)	Over 609.6 to 1219.2 (24 to 48)	15.9 (5/8)	9.5 (3/8)
Over 127 (5)	4.8 (3/16)	3.2 (1/8)	Over 1219.2 to 1828.8 (48 to 72)	22.2 (7/8)	12.7 (1/2)
			Over 1828.8 (72)	31.8 (1-1/4)	

3.4 Storage life. The tape shall meet all the requirements of this specification after 6 months of storage as specified in 4.7. Tape that meets the requirements of 4.6.3 after 6 months of storage may be considered to meet the storage life requirements.

3.5 Workmanship. The tape shall be clean and free from creases, folds, cracks, scuffing, ragged or uneven edges, or any other defect that detracts from its appearance, or that may affect its serviceability. The finished rolls of tape shall conform to the acceptable quality levels for the defects listed in table V.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

4.2 Lot. A lot of tape shall consist of all tape made by the same process from the same components and submitted for inspection at one time.

4.3 Classfication of inspection. Unless otherwise specified, sampling and all visual and dimensional inspection shall be done at the manufacturer's plant. All testing shall be performed in accordance with 4.6 and 4.7 and the inspections shall be classified as follows:

a. Complete inspection (see 4.3.1).
b. Lot acceptance inspection (see 4.3.2).

4.3.1 Complete inspection. Complete inspection shall be performed on the first lot of finished tape furnished under this specification and whenever there is a change in the manufacturing method or in the materials (see 3.1) that comprise the tape. In addition complete inspection shall be performed on every 20th lot of the same material furnished thereafter, or once in every two years whichever is the more frequent, or it may be performed at the discretion of the procuring activity. Unless otherwise specified by the procuring activity complete inspection shall consist of all examinations and tests of this specification.

4.3.2 Lot acceptance inspection. Lot acceptance inspection shall be made on each lot of tape and shall be the basis for acceptance or rejection of the lot. The lot acceptance inspection shall consist of the examinations specified in 4.5.1 and 4.5.2 plus the tests specified in 4.6.3.

4.4 Sampling.

4.4.1 Sampling for examination of tape. Unless otherwise specified a random sample of rolls of finished tape shall be selected for examination in accordance with level 1 of MIL-STD-105. The sample unit shall be one roll.

4.4.2 Sampling for examination of packaging. Unless otherwise specified (see 6.2) a random sample of shipping containers shall be selected for examination in accordance with level S-1 of MIL-STD-105. The sample unit shall be one shipping container fully packed selected just prior to the closing operation.

4.4.3 Sampling for tests. Representative samples of the finished tape shall be selected from each lot for the applicable tests listed in 4.6.1, 4.6.2 and 4.6.3. (For lot acceptance inspection the tests of 4.6.3 only will apply.) The sample shall consist of sufficient material to prepare all specimens required for testing. When the polyurethane foam or the polyester film in the finished tape are not suitable for testing, representative samples of these materials may be used for the tests. The results of these tests should be compared with those of the finished tape.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

4.5 Examination.

4.5.1 Examination of tape. Sample rolls of tape selected in accordance with 4.4.1 shall be examined for the defects and at the acceptable quality level shown in table V.

4.5.2 Examination of packaging. Sample shipping containers selected as specified in 4.4.2 shall be examined for the defects and at the acceptable quality level shown in table VI.

4.6 Tests.

4.6.1 Polyurethane foam. Polyurethane foam selected as specified in 4.4.3 shall be tested for the requirements of 3.1.1 in accordance with the test method indicated in table VII.

4.6.2 Polyester film. Polyester film (poly(ethlene terephthalate) or equal) selected as specified in 4.4.3 shall be tested for the requirements of 3.1.3 in accordance with the test methods specified in table VIII.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

Table V. Classification of defects in tape

Category	Examine	AQL percent	Defect	Method of inspection
Major 101	Foam (see 3.1.1 and 3.1.1.1)	1.00	Not "clickable" ("welded" edges)	Visual
Major 102			Not flexible (with adhesive)	Bend
Major 103			Not free of non-expanded areas	Visual
Major 104			Not uniform in texture and cell structure	Visual
Major 105			Color not as specified	Visual
Major 106	Polyester film (see 3.1 and 3.1.3)	1.00	Film not adhering uniformly and smoothly to foam	Visual
Major 107			Film missing or wrong type	Visual
Major 108	Pressure-sensitive adhesive (see 3.1 and 3.1.4)	1.00	Entire area not covered	Visual
Major 109			Coating not smooth and uniform	Visual
Major 110			Bare spots, lumps, blisters or flaking	Visual
Major 111	Release paper (see 3.1.6)	1.00	Release paper missing or wrong type	Visual
Major 112			Paper not easily peeled or breaks while unwinding or not properly coated	Peel
Major 113	Rolls (see 3.2)	1.00	Tape not evenly and uniformly wound	Visual
Major 114			Adhesive side not wound toward the inside	Visual
Major 115			Rolls not suitably restrained from unwinding	Visual
Major 116	Cores (see 3.2.1)	1.00	Core missing, damaged, crushed or distorted	Visual
Major 117			Core with insufficient rigidity	Visual
Major 118			Core the wrong size	Measure
Major 119	Dimensions (see 3.3)	1.00	Tape not one continuous length (or as specified)	Visual
Major 120			Tape the wrong thickness	Measure
Major 121			Tape the wrong length	Measure
Major 122			Tape the wrong width	Measure
Major 123	Workmanship (see 3.5)	1.00	Tape not clean	Visual
Major 124			Creases, folds, cracks, scuffing, or ragged or uneven edges	Visual

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

Table VI. Packaging - classification of defects

Tape	AQL percent	Classification of defects	Defects	Method of inspection
Unit pack (see 4.5.2 and 5.1.1.1 or 5.1.2)	1.5	Major 125	Tape not on roll per unit box	Visual
		Major 126	Wrong type of box	Visual
		Major 127	Coated separator missing or improper	Visual
		Major 128	Centering device missing or improper	Visual
		Major 129	Bag missing or improper	Visual
		Major 130	Bag improperly sealed	Visual
Intermediate pack (if required) (see 4.5.2 and 5.1.1.2 or 5.1.2)	1.5	Major 131	Number of rolls not as specified	Count
		Major 132	Wrong size of container	Visual
		Major 133	Wrong type of container	Visual
		Major 134	Container improperly closed	Visual
Box open (see 4.5.2 and 5.2)	1.5	Major 135	Wrong type box	Visual
		Major 136	Wrong size box	Visual
Box closed (see 4.5.2, 5.2, 5.3 and 5.4)	1.5	Major 137	Lack of or improper strapping	Visual
		Major 138	Improperly closed	Visual
		Major 139	Gross weight maximum	Approved scale[1/]
		Major 140	Marking improper or unidentifiable	Visual
		Major 141	Not palletized (if required)	Visual

[1/] Approved by procuring activity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

Table VII. Test methods for polyurethane foam

Property	Test method ASTM
Density	D 3574
Tensile strength	D 3574
Elongation, ultimate	D 3574
Tear strength	D 3574
Compression set at 50 percent deflection	D 3574
Indentation force deflection	D 3574
Steam autoclave test	D 3574
Thermal conductivity	C 177

Table VIII. Test method for polyester film

Property	Test method ASTM
Melting point	D 2117
Tensile strength	D 882 Method A
Elongation	D 882 Method A
Tear strength	D 1938

4.6.3 Acceptance tests

4.6.3.1 Tape. Tape selected as specified in 4.4.3 shall be tested for the requirements specified in 3.1.4 in accordance with the number of determinations and the Pressure Sensitive Tape Council (PSTC) methods specified in table IX.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

Table IX. Test methods for tape

Test	Number of determinations	Report results as	Test method
180° peel adhesion[1/]			
1 ± 1/4 minute after mounting	10[2/]	Average	PSTC-1
20 ± 1 minutes after mounting	10[2/]	Average	PSTC-1
60 ± 2 minutes after mounting	10[2/]	Average	PSTC-1
24 ± 3 hours after mounting[3/]	10[2/]	Average	PSTC-1
Shear adhesion (holding power)[1/]	10[2/]	Average	PSTC-7
Tensile strength of tape	10[2/]	Average	PSTC-31
Elongation of tape	10[2/]	Average	PSTC-31
Humidity resistance[3/]	5 tests 10 each	Average (for each test)	(see 4.6.3.1.1)

[1/] Failure shall be in the pressure-sensitive adhesive and not in the adhesive between the polyurethane foam and the polyester film carrier (see 3.1.2).
[2/] Tests to be repeated to determine humidity resistance (see 4.6.3.1.1).
[3/] When authorized by the procuring activity the tests for 24 ± 3 hours peel adhesion and humidity resistance may be omitted from the lot acceptance tests.

4.6.3.1.1 Humidity resistance. Prepare and condition test specimens as specified in PSTC-1, PSTC-7 and PSTC-31 (for the number of specimens see 4.6.3.1). Place the specimens in a conditioning cabinet or oven over water so as to give a relative humidity of 94 to 100 percent. Maintain the temperature of the cabinet or over at 51.7 ± 2 C (125 ± 3.6 F) for 7 days ± 4 hours. At the end of the exposure period test the specimens as conditioned with the exception that the specimens shall be brought to and tested at room temperature. The tests and test methods shall be as specified in 4.6.3.1. Compare the results with the requirements as specified in 3.1.4.

4.7 Storage life. Unless otherwise specified (see 4.8 and 6.2) two sample rolls of the tape from each lot shall be stored in their original containers for 6 months at a temperature of 23 ± 2 C (73.4 ± 3.6 F) and 50 ± 5 percent relative humidity. The tape shall then be tested as specified in 4.6.3.1.

4.8 Certification report. When specified (see 6.2) for the complete inspection (see 4.3.1) the supplier shall submit to the procuring activity a report certifying that the foam is polyurethane of the polyester or

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

polyether type and a 60 (-5 +10) PPI custom foam (see 3.1.1), that the film is plastic of the polyester type (see 3.1.3) and that the tape shall meet the storage life requirements of 4.7. The report shall be signed by a responsible agent of the certifying organization and shall be accompanied by evidence of this agent's authority to bind his principal. The Government reserves the right to check test material submitted by the supplier under certification.

5. PACKAGING

5.1 Preservation. Preservation shall be level A or commercial as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Unit pack. Unless otherwise specified by the procuring activity each roll of tape shall be unit packed in a standard commercial paper-board box, one roll per unit box. A coated separator shall be used between the roll and the box top and bottom to prevent sticking. A centering device or fiber-board ring shall be provided in each individual box to prevent the outside diameter of the tape roll from coming in contact with the sides of the box. Each unit box shall be inclosed in a bag conforming to MIL-B-117, type III, class B, style 1. The bag shall be heat sealed.

5.1.1.2 Intermediate pack. A quantity of unit packs specified by procuring activity (see 6.2) shall be intermediate packed in a fiberboard container conforming to PPP-B-636 class weather-resistant. Closure of the container shall conform to the appendix of the container specification.

5.1.2 Commercial. Commercial preservation of tape shall be in accordance with MIL-STD-1188.

5.2 Packing. Packing shall be level A, B or commercial as specified (see 6.2).

5.2.1 Level A. Unless otherwise specified by the procuring activity (see 6.2) interior containers unit packed as specified in 5.1 shall be packed in wood boxes conforming to the overseas type of either PPP-B-601 or PPP-B-621. Containers shall be closed and strapped in accordance with the applicable container specification or appendix thereto.

5.2.2 Level B. Unless otherwise specified (see 6.2) intermediate containers packaged as in 5.1.1.2 require no further packing. When specified (see 6.2) interior containers shall be packed in domestic type wood boxes conforming to PPP-B-585, PPP-B-601 or PPP-B-621 or in fiberboard boxes conforming to PPP-B-636 class weather resistant, or PPP-B-640, class 2. Containers shall be closed and strapped in accordance with the applicable specification or appendix thereto. The gross weight of fiberboard boxes shall not exceed the weight limitation of the specification.

5.2.3 Commercial. The tape shall be packed in accordance with MIL-STD-1188.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

5.3 Marking.

5.3.1 Marking. Unit, intermediate, and exterior containers shall be marked in accordance with MIL-STD-129 or MIL-STD-1188 as applicable. In addition, each shipping container shall be marked to show the month and year of the date of packing, expressed numerically (e.g. 10-70), and the quantity and the thickness width and length of tape on a roll. The following precautionary marking shall appear on two panels of each shipping container.

Recommended Storage Conditions

STORE BEHIND PRESENT STOCK

Store in a clean dry place

Temperature of 21 degrees Centigrade (70 degrees Farenheit)

and 40 to 50 percent relative .

humidity are recommended

ROTATE YOUR STOCK

5.4 Palletization. When specified (see 6.2) exterior containers shall be palletized in accordance with the requirements of MIL-STD-147.

6. NOTES

6.1 Intended use. The tape is used for weather stripping, dust sealing, air sealing, dampending, thermal insulation, sound absorption and packaging. Although this type of tape is made with a fire retardant foam, the tape should not be considered fire resistant due to the adhesives and the type of test on the foam which is not intended to be a criterion for fire hazard.

6.2 Ordering data. Procuring documents should specify:

6.2.1 Procurement requirements.

a. Title, number and date of this specification.
b. Thickness, length and width of tape (see 3.3).
c. Length of tape on each roll and whether the tape on each roll shall be in one continuous length (see 3.3).
d. Quantity of tape required.
e. Color of foam if other than charcoal (see 3.1.1.1).
f. Cores if other than 1-1/2 ± 1/16 inches in diameter (see 3.2.1).
g. If shelf life test not required (see 4.7).
h. If certification report is required (see 4.8)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

i. Degree of preservation and packing required (see 5.1 and 5.2).
j. When intermediate containers are other than that specified (see (see 5.1.1.2)
k. When wood or fiberboard container is required (see 5.2.2).
l. Whether special marking is required (see 5.3).
m. Whether exterior containers shall be palletized (see 5.4).

6.2.2 Contract data requirements. When this specification is used in a procurement which incorporates a DD Form 1423 and invokes the provisions of the Defense Acquisition Regulatory System (DARS), the date requirements identified below will be developed as specified by an approved Data Item Description (DD Form 1664) and delivered in accordance with the approved Contract Data Requirements List (DD Form 1423) incorporated into the contract. When the provisions of DARS are not invoked, the date specified below may be delivered by the contractor in accordance with the contract requirements. Deliverable data required by this specification is cited in the following paragraphs:

Paragraph No.	Data requirement title	Applicable DID No
4.8	Certification Data/Report	UDI-A-23264

(Copies of Data Item Descriptions required by the contractors in connection with specific acquisition functions should be obtained from the acquiring activity or as directed by the contracting officer.)

6.3 Standard dimensions. Standard dimensions for polyurethane foam pressure sensitive, adhesive tape are as follows:

a. Thickness 1.6mm (1/16 in.) and up in 1.6mm increments
b. Width 6.4mm (1/4 in.) and up in 1.6mm increments

6.4 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue, due to the extensiveness of the changes.

Custodians:
Army - MR
Navy - AS

Preparing activity:
Army - MR

Project No. 9320-0308

Review activities:
Army - SM

User activities:
Navy - MC, OS, SH
DLA - GS

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS. This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

DOD-T-46151A, Tape, Adhesive, Rubber (Metric)

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

[ ] VENDOR [ ] USER [ ] MANUFACTURER

1. [ ] HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? [ ] IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*	TELEPHONE NO.
	DATE

DD FORM 1 OCT 76 1426 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:01Z
Check the source to verify that this is the current version before use.