MIL-P-14839(MU)
AMENDMENT 2
29 May 1969
SUPERSEDING
Amendment 1
21 April 1969

MILITARY SPECIFICATION
PROJECTILE, 105MM, SMOKE, BE, M84E1
METAL PARTS ASSEMBLY

This amendment forms a part of Military Specification MIL-P-14839(MU) dated 9 February 1968.

Paragraph 3.2 Line 2 delete "projectile body" and substitute "any component part"

Line 3 delete "projectile body" and substitute "component"

* Paragraph 3.2.1 Delete in its entirety and substitute:

"3.2.1 Body and base plug.-Mechanical properties specified on the applicable drawing shall apply throughout each component in the lot."

Paragraph 3.3.1 Line 1 delete "Projectile body.-" and substitute "Body and base plug.-"

Line 2 delete "throughout the projectile body".

* Add Paragraph 4.3.1.6

"4.3.1.6 Bar stock lots.-Bar stock lots shall contain not more than one heat of steel. Bar stock lots thus constituted shall be the basis for the selection of samples for the tension test hereinafter prescribed."

* Paragraph 4.3.2.2 Under MAJOR 114 after "base plug cavity" add "max."

Under MINOR delete 214 in its entirety and substitute:

"214. Diameter of chamfer at rear of small cavity - - - - - - - - Gage"

MINOR 216 delete in its entirety and substitute:

"216. Presence of nose thread chamfer - - - - - - - - - - - - - - - Visual (See 6.1)"

* Paragraph 4.3.2.3 Under MAJOR add:

"107. Front face not perpendicular to surface forward of thread- Gage
108. Length from front face to start of thread - - - - - - - - - Gage"

* Paragraph 4.3.2.6 Under MAJOR add:

"108. Diameter of rotating band - - - - - - - - - - - - - - - - - - Gage"

and change numbers accordingly.

Under MINOR add:

"206. Paint on rotating band bearing surface - - - - - - - - - - - Visual"

Paragraph 4.3.3.1.2.5 Add the following new paragraph:

"4.3.3.1.2.5 Base plug.-Two base plugs from each lot shall be subjected to the tension test to determine compliance with the mechanical properties requirements of the applicable drawing. Failure of any tension test specimen to comply with the requirements for yield strength, tensile strength or elongation shall be cause for rejection of the lot."

* Paragraph 4.3.3.1.2.5 Line 4 delete "tensile strength".

FSC 1315

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T04:53Z
Check the source to verify that this is the current version before use.

* Add Paragraph 4.3.3.1.2.5.1:

"4.3.3.1.2.5.1 Machined from bar stock.-With the approval of the procuring activity when the base plug is machined from bar stock in such a manner that the mechanical properties are not altered, test coupons approximately 6 inches in length may be removed from one end of each of three bars representing the heat lot and tested in lieu of testing the component. Failure of one or more tension test specimen to comply with the yield strength and elongation requirements of the applicable component drawing shall be cause for rejection of the bar stock lot."

* Paragraph 4.4.1.2.3 Delete paragraph added by previous amendment in its entirety and substitute:

"4.4.1.2.3 Base plugs.-From each sample supplied in accordance with 4.3.3.1.2.5, two tension test specimens conforming to the largest obtainable "R" type specimen as prescribed by Federal Standard No. 151 shall be taken in a transverse direction. The criteria for determining yield strength and elongation shall be as prescribed by Federal Standard No. 151. Yield strength shall be determined by the offset method, the limiting set shall be 0.1 percent (0.001 inch per inch of gage length)."

* Add Paragraph 4.4.1.2.3.1:

"4.4.1.2.3.1 Bar stock.-From the samples supplied by 4.3.3.1.1.4, one type "R" tension test specimen shall be taken longitudinally from midradius of each coupon, and tested in accordance with the criteria for determining yield strength and elongation as specified by Federal Standard No. 151. Yield strength shall be determined by the offset method, the limiting set shall be 0.1 percent (0.001 inch per inch of gage length)."

* Paragraph 4.4.4 Lines 4 and 5 delete "salt spray test ---------- No. 141."

* Add Paragraph 4.4.4.1:

"4.4.4.1 Salt spray.-From the samples provided in accordance with 4.3.3.3 two full length specimens shall be taken by cutting longitudinally through the projectile at mid-diameter. The specimens shall be positioned in the test cabinet in such a manner that on one specimen the inside surface will be designated as the significant surface, on the other specimen the outside surface will be the significant surface. The test shall be performed utilizing the equipment and procedures prescribed by Federal Test Method Standard No. 141."

* The margins of this amendment are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodian:

Army - MU

Preparing activity

Army - MU

Project No. 1315-A709

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T04:53Z
Check the source to verify that this is the current version before use.