MILITARY SPECIFICATION

PROJECTILE, 105MM, TACTICAL, CS, XM632
METAL PARTS ASSEMBLY

This Amendment forms a part of Military Specification MIL-P-14840(MU) dated 20 September 1968.

Paragraph 3.2 lines 2 and 3 after "projectile body" add "or base plug".

Paragraph 3.2.1 line 2 after "projectile body" add "or base plug".

Add paragraph 3.2.4
"3.2.4 Base plugs.-The base plug shall be heat treated to obtain the specified mechanical properties in a transverse direction."

Paragraph 3.3.1 Line 1 after "Projectile body" add "and base plug".
Line 2 after "projectile body" add "or base plug".

Paragraph 4.3.1.2 Line 1 add "and base plugs"
Line 2 delete "forgings"

Paragraph 4.3.2.2 delete "Title" and substitute "Plug, Base (prior to painting) Drawing C10543035 covering a detail of Drawing F10543036"
Under MAJOR delete "Major 107." in its entirety.
Under MAJOR add:

"110. Flatness of front face of flange - - - - - - - - - - - Gage
111. Perpendicularity of front face of flange with press fit surface - Gage"

Paragraph 4.3.2.3 delete "Title" and substitute "Plug, Base (after painting) Drawing C10543035 covering a detail of Drawing F10543036"

FSC 1315

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T04:53Z
Check the source to verify that this is the current version before use.

Add paragraph 4.3.3.1.2.6

"4.3.3.1.2.6 Base plug.-Two base plugs shall be selected from each heat treated lot and subjected to this test to determine compliance with the mechanical properties requirement of the applicable drawing. Failure to comply shall be cause for rejection of the base plugs represented by the sample."

Paragraph 4.3.3.3 line 4 after "specification" add "except that test panels shall not be used for the salt spray test."

Add paragraph 4.4.1.2.3

"4.4.1.2.3 Base plug.-From sample provided by 4.3.3.1.2.6 for the convenience of the Government one tension test specimen conforming to the largest obtainable standard "R" type specimen as prescribed by Federal Test Methods Standard No. 151 shall be taken from the base plug in a transverse direction. The criteria for performing this test shall be as prescribed by Federal Test Standard No. 151, yield strength shall be determined by the offset method. The limiting set shall be 0.1 percent (0.001 inch per inch of gage length)."

Add paragraph 4.4.3.1

"4.4.3.1 Salt spray.-From each sample provided by 4.3.3.3, two full length specimens shall be prepared by cutting longitudinally through the body assembly at mid diameter. The specimens shall be positioned in the test cabinet in such a manner that on one specimen from each sample the inside surface will be the significant surface, and the other two specimens, the outside surface will be the significant surface. The test shall be performed utilizing the equipment and procedures specified in Federal Test Method No. 141."

Custodian

Army - MU

Preparing activity

Army - MU

Project No. 1315-A717

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T04:53Z
Check the source to verify that this is the current version before use.