INCH-POUND


MIL-DTL-52525/36C
16 December 2019
SUPERSEDING
MIL-DTL-52525/36B
2 December 2008

DETAIL SPECIFICATION SHEET

# FITTINGS, HOSE, CRIMP TYPE, SPLIT-FLANGE, 90 DEGREE BENT TUBE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and MIL-DTL-52525.




See notes at end of figure.

FIGURE 1. Fitting, screw-on to 4-bolt split-flange, 90° bent tube.

AMSC N/A

FSC 4730

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:23Z
Check the source to verify that this is the current version before use.

| Part or Identifying Number (PIN) | Hose | | Hose OD Inches (mm) | Tube OD Inches (mm) | Flange | |
|---|---|---|---|---|---|---|
| | ID Inches (mm) | Size dash no. | | | Size Inches (mm) | Size dash no. |
| M52525/36-12-12 | .75 (19.05) | -12 | 1.26 (32.00) | .75 (19.05) | .75 (19.05) | -12 |
| M52525/36-16-16 | 1.00 (25.40) | -16 | 1.51 (38.35) | 1.00 (25.40) | .75 (19.05) | -16 |

| PIN | A max inches (cm) | B max inches (mm) | C max inches (mm) | D min inches (mm) |
|---|---|---|---|---|
| M52525/36-12-12 | 6.10 (15.49) | 2.25 (57.15) | 1.88 (47.75) | .60 (15.24) |
| M52525/36-16-16 | 6.86 (17.42) | 2.50 (63.50) | 2.31 (58.67) | .75 (19.05) |

NOTES:
1. Dimensions are in inches.
2. Metric equivalents are given for information only.
3. These fittings are for use with MIL-DTL-52471/7 hose and MIL-DTL-52471/8 hose assemblies.

FIGURE 1. Fitting, screw-on to 4-bolt split-flange, 90° bent tube - Continued.

REQUIREMENTS:

The fittings described herein are for use with hose in accordance with MIL-DTL-52471/7, type 100RE, 4-spiral-wrap reinforcement hose and hose assemblies in accordance with MIL-DTL-52471/8.

Fittings shall be as specified on figure 1 and in tables I and II.

If fittings are to be used on an oxygen hose, see MIL-DTL-52525.

Materials and finishes shall be in accordance with MIL-DTL-52525 and in table I.

Finish. Finishes shall be in accordance with table I.

All plating's shall be capable of meeting 96-hour salt spray test in accordance with ASTM B117. The fittings shall show no evidence of red corrosion after 96 hours of salt spray. Fluid passages, other openings, and internal threads shall not be subject to the plating thickness requirement and may have bare areas provided they are protected with a light film of oil.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:23Z
Check the source to verify that this is the current version before use.

TABLE I. Material and finish identification codes.

| PIN code material/plating finish | Material | Plating finish |
|---|---|---|
| A | Aluminum alloy 6061 or 7075 | Anodize in accordance with MIL-A-8625, type II. |
| AN | | Anodize in accordance with MIL-A-8625, type II and NAVAIR trivalent chromium pretreatment (TCP) in accordance with MIL-DTL-81706, type II, class 1A. TCP Applied after anodizing. |
| BN | | Bare aluminum with NAVAIR TCP in accordance with MIL-DTL-81706, type II, class 1A. |
| C | Steel 2/ | Cadmium plating in accordance with SAE-AMS-C-81562, type II, class 3 or SAE-AMS-QQ-P-416, type II, class 2. 1/ 5/ 8/ |
| YC | Chrome-molybdenum steel alloy 4130 | Cadmium plating in accordance with SAE-AMS-C-81562, type II, class 3 or SAE-AMS-QQ-P-416, type II, class 2. 1/ 5/ 8/ |
| G | Steel 2/ | Zinc plating with colorless passivate in accordance with ASTM B633, type V, Fe/Zn 25. 3/ 4/ |
| YG | Chrome-molybdenum steel alloy 4130 | |
| H | Steel 2/ | Zinc phosphate finish in accordance MIL-DTL-16232, type Z, class1. |
| YH | Chrome-molybdenum steel alloy 4130 | |
| J | Steel 2/ | Zinc plating with a colored chromate conversion in accordance with ASTM B633; type II, Fe/Zn 8, or ASTM B695, type II, class 8. 3/ 5/ |
| YJ | Chrome-molybdenum steel alloy 4130 | |
| K | Nickel-copper alloy UNS N04400 | No additional finish. |
| M | High-chromium nickel alloy UNS N06690 | No additional finish. |
| N | Steel 2/ | Zinc-aluminum in accordance with ASTM F1136/F1136M, grade 3, NC. 4/ |
| YA | Chrome-molybdenum steel alloy 4130 | |
| YN | | Zinc-nickel in accordance with SAE-AMS2417, type 2, grade B. 4/ 7/. |
| P | Steel 2/ | Zinc plating with colorless passivate in accordance with ASTM B633, type V, Fe/Zn 8. 3/ 4/ |
| YP | Chrome-molybdenum steel alloy 4130 | |
| S | Corrosion resistant steel | No additional finish. Passivation in accordance with SAE-AMS2700, type 6 or 7. |
| T | Titanium | Anodize in accordance with SAE-AMS2488, type 2. 6/ 9/ |
| TF | | Fluoride phosphate in accordance with SAE-AMS2486. 6/ 9/ |
| U | Steel 2/ | Zinc-aluminum in accordance with ASTM F1136/F1136M, grade 3, NC. 4/ |
| V | | Zinc-nickel in accordance with SAE-AMS2417, type 2, grade B. 4/ 7/. |
| W | Steel 2/ | Any zinc plating above. 3/ |
| YW | Chrome-molybdenum steel alloy 4130 | |
| Z | Steel | Zinc plating in accordance with ASTM B695, type II, class 8. 3/ 5/ |

1/ Embrittlement test need not be run.
2/ All steels except 4130.
3/ Not for use in aircraft. Requires approval from the Program Office for all applications. Zinc-plated materials should be avoided in hydraulic systems with water-glycol fluids. Reference ASTM MNL37 - Fuels and Lubricants Handbook.
4/ Hexavalent chromium free. Finish shall be RoHS compliant.
5/ These finishes have a chromate conversion coating or chromic acid rinse which includes hexavalent chromium and are not recommended. The use of coatings depositing hexavalent chromium for Army vehicles is prohibited unless otherwise explicitly stated in the contract as a requirement.
6/ A pretreatment, a modification of the fluoride treatment, or a post treatment shall be applied so the final color of the fittings shall be similar to SAE-AMS-STD-595 colors 36076 through 36293.
7/ The zinc-nickel alloy plate shall contain 12% to 16% nickel. The coating thickness shall be 315µ inches (8µm) minimum.
8/ Cadmium shall not be used in oxygen or potable water systems. Cadmium is prohibited from use in NAVSEA-owned shipboard systems in accordance with the requirements of T9070-AL-DPC-020/077-2, unless otherwise approved by NAVSEA. The use of cadmium plating for Army vehicles is prohibited unless otherwise explicitly stated in the contract as a requirement.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:23Z
Check the source to verify that this is the current version before use.

9/ Titanium shall not be used in oxygen or potable water systems.


The operating pressure shall be as specified in table II. Maximum operating pressures are for low carbon steel fittings consult manufacturer for values on other materials.

TABLE II. Maximum operating pressures of fittings. 1/ 2/

| SAE dash size | Hose ID inches (mm) | psi | MPa |
|---|---|---|---|
| -12 | .75 (19.05) | 6250 | 43.1 |
| -16 | 1.00 (25.40) | 5000 | 34.5 |

1/ Dimensions are in inches.
2/ Metric equivalents are given for information only.

PIN: The PIN consists of the letter “M” the specification sheet number, a dash, a number for the hose size a dash, a number for flange size, and a material finish designator.




PIN example: M52525/36-16-16A, describes a split flange 90° for a 1.00 inch (25.40 mm) hose, and a 1.00 inch (25.40 mm) flange, aluminum with an anodized finish.

To the users of this document, it is recommended that the use of carbon steel material with cadmium plating be used only when the other materials and finishes specified in this document cannot meet performance requirements.

Cadmium is prohibited from use in NAVSEA-owned shipboard systems in accordance with the requirements of T9070-AL-DPC-020/077-2, unless otherwise approved by NAVSEA.

The use of cadmium plating or coatings depositing hexavalent chromium for Army vehicles is prohibited unless otherwise explicitly stated in the contract as a requirement.

Class I and II ozone depleting substances (ODS) shall not be used in MIL-DTL-52525/35 or any referenced procedures.

Referenced documents shall be of the issue in effect on date of invitations for bid.

Color identification. Color identification shall be in accordance with SAE-AS4841.

Marking shall include the manufacturer’s name or trademark, size, and hose identifier 100RE. Location of marking is optional.

Harmonization to SAE-J516 cross reference PIN in table III is for reference only. SAE-J516 style



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:23Z
Check the source to verify that this is the current version before use.

fittings may not have the same material/finish as required by MIL-DTL-52525 and legacy with MIL-DTL-52471. SAE-J517 codes for standard hoses are explained further in MIL-DTL-52471.

TABLE III. Harmonization to SAE-J516 cross reference PIN. 1/

| Superseded PIN | SAE-J516 Equivalent PIN 2/ 3/ |
|---|---|
| M52525/36-12-12 | SAE J516 12-12 P4914**EE |
| M52525/36-16-16 | SAE J516 16-16 P4914**EE |

1/ Material and finish designators are omitted from PIN's see table II and SAE-J846.
2/ ** indicates that SAE never had a type 100RE hose.
3/ The "EE" at the end of the SAE PIN is to indicate a nonstandard part.

Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue, due to the extent of the changes.

Referenced documents. In addition to MIL-DTL-52525, this document references the following:

| | | |
|---|---|---|
| MIL-A-8625 | SAE-AMS-STD-595/36076 | SAE-AMS-STD-595/36293 |
| MIL-DTL-16232 | SAE-AMS-STD-595/36081 | SAE-AMS-C-81562 |
| MIL-DTL-52471 | SAE-AMS-STD-595/36099 | SAE-AMS-QQ-P-416 |
| MIL-DTL-52471/7 | SAE-AMS-STD-595/36118 | SAE-AMS2417 |
| MIL-DTL-52471/8 | SAE-AMS-STD-595/36134 | SAE-AMS2488 |
| MIL-DTL-52525/16 | SAE-AMS-STD-595/36152 | SAE-AMS2486 |
| MIL-DTL-52525/17 | SAE-AMS-STD-595/36170 | SAE-AMS2700 |
| MIL-DTL-81706 | SAE-AMS-STD-595/36173 | SAE-AS4841 |
| ASTM B117 | SAE-AMS-STD-595/36176 | SAE-J516 |
| ASTM B633 | SAE-AMS-STD-595/36231 | SAE-J518-2 |
| ASTM B695 | SAE-AMS-STD-595/36251 | SAE-J846 |
| ASTM F1136/F1136M | SAE-AMS-STD-595/36270 | T9070-AL-DPC-020/077-2 |
| ASTM MNL37 | SAE-AMS-STD-595/36280 | |

## CONCLUDING MATERIAL

Custodians:
Army - AT
Navy - SH
Air Force - 71
DLA - CC

Preparing activity:
DLA - CC

(Project 4730-2020-008)

Review activities:
Army - CR4
Navy - AS, CG, SA, YD

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST Online database at https://assist.dla.mil.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:23Z
Check the source to verify that this is the current version before use.