NOT MEASUREMENT SENSITIVE

MIL-C-81309E
AMENDMENT 2
31 July 1996
SUPERSEDING
AMENDMENT 1
16 December 1993

MILITARY SPECIFICATION

CORROSION PREVENTIVE COMPOUNDS, WATER DISPLACING, ULTRA-THIN FILM

This amendment forms a part of MIL-C-81309E, dated 31 March 1993, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 1

1.2.2, line 3: Delete "Grade 22 - Hydrochlorofluorocarbon (HCFC) propellant" and substitute "Grade CO_2 - Carbon Dioxide (CO_2) propellant."

PAGE 5

3.2.1.1: Delete in entirety and substitute: "3.2.1.1 Grade CO_2 propellant. The propellant for Grade CO_2 shall consist of carbon dioxide. The propellant shall contain no chlorinated solvents, hydrochlorofluorocarbons, or fully halogenated chlorofluorocarbons."

PAGE 6

3.5.2: Delete in entirety and substitute: "3.5.2 Fill. When tested as specified in 4.7.12.2, the pressurized cans containing the compound shall have a net minimum weight as shown below:

Type 2 Grade 134A	14.5 ounces
Type 2 Grade CO_2	11.0 ounces
Type 3 Grade 134A	14.0 ounces
Type 3 Grade CO_2	11.0 ounces"

PAGE 12

4.7.1, line 1: After "test" add new sentence: "Flash point shall be determined in accordance with FED-STD-791, method 1103.6."

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T05:11Z
Check the source to verify that this is the current version before use.

4.7.1.1: Delete in entirety.

PAGE 14

* Add the following paragraphs:

"4.7.3 Synthetic sea water displacement.

4.7.3.1 Procedure. Panels prepared as specified in 4.6.3 and 4.6.4 shall be placed so that a 2-inch end shall be raised 1 inch above a horizontal surface. The panels shall then be sprayed with the synthetic sea water of 4.7.2.1.1 so that the entire upper surface of the specimen is covered with tiny droplets. Within one minute after spraying, 1 milliliter (mL) of the test compound shall be poured along the upper 2-inch edge of the panels and allowed to run slowly down the specimen so as to completely cover the test panel. After another minute, another 1 mL portion of the test compound shall be poured and allowed to run down the panels in a like manner. After waiting an additional minute, the panels shall be picked up and held in a vertical position for one minute and shall then be placed flat (test side up) above distilled water at 22° C (72° F) in a closed desiccator. After 4 hours, they shall be removed and cleaned with mineral spirits and then evaluated for presence of visible corrosion (see table I)."

PAGE 16

4.7.10.1, line 4, after "at": Delete the remainder of paragraph and substitute:
"77° ±1° C (170° ±2° F) for 15 minutes. There shall be sedimentation or evidence of chemical precipitation or reaction immediately after the 15-minute period at the elevated temperature or after 24 hours at 25° ±3° C (77° ±5° F) (see table I). A slight separation of liquid shall be acceptable."

PAGE 22

6.6, delete the "Class" designation in the part number breakout and substitute:
"Class (see 1.2.1) Class 1 = 1; Class 2 = 2."

6.7, delete "HCFC propellant" and substitute "Carbon dioxide propellant."

NOTE: The margins of this amendment are marked with asterisks to indicate where changes from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the margins notations and relationship to the last previous amendment.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T05:11Z
Check the source to verify that this is the current version before use.

Custodians:
Army - EA
Navy - AS
Air Force - 99

Review Activities:
Army - AT, MR
Navy - CG, OS
Air Force - 84
Other activities - DS

Preparing activity:
Navy - AS
(Project 8030-0719)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T05:11Z
Check the source to verify that this is the current version before use.