INCH-POUND
MIL-DTL-11199J
14 October 2021
SUPERSEDDING
MIL-M-11199H
5 April 1988

DETAIL SPECIFICATION

MITTEN, HEAT PROTECTIVE

This document is approved for use by all Departments and Agencies of the Department of Defense (DoD).

1. SCOPE

1.1 Scope. This specification covers the requirements for a heat protective mitten.

1.2 Classification. This specification covers one (1) type and one (1) size of ambidextrous mitten.

2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3 and 4 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of this list, document users are cautioned that they must meet all specified requirements of documents cited in sections 3 and 4 of this specification, whether or not they are listed.

Comments, suggestions, or questions on this document should be addressed: Attn: DLA Troop Support, 700 Robbins Avenue, Philadelphia, PA 19111-5096. Since contact information can change, verify the currency of the address information using Acquisition Streamlining and Standardization Information System (ASSIST) online database https://assist.dla.mil.

AMSC N/A FSC 8415

DISTRIBUTION STATEMENT A. Approved for public release. Distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

2.2 Government documents.

2.2.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

COMMERCIAL ITEM DESCRIPTIONS

A-A-50195 - Thread, Aramid
A-A-52094 - Thread, Cotton
A-A-55195 - Thread, Para-Aramid, Spun, Intermediate Modulus

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-DTL-3390 - Rings, Dee
MIL-DTL-32075 - Label for Clothing, Equipage, and Tentage, (General Use)
MIL-DTL-43566 - Tape, Textile, Cotton or Polyester, General Purpose, Natural or in Colors

(Copies of these documents are available online at https://quicksearch.dla.mil.)

2.2.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation or contract.

DRAWINGS

U.S. ARMY COMBAT CAPABILITIES DEVELOPMENT COMMAND SOLDIER CENTER

2-1-23 - Mitten, Heat Protective (Assembly and Details)

(Copies of drawings are available from the U.S. Army, DEVCOM – Soldier Center, ATTN: FCDD-SCD-PE, 10 General Greene Avenue, Natick, MA 01760-5019.)

OTHER GOVERNMENT DOCUMENTS AND PUBLICATIONS

FEDERAL TRADE COMMISSION

16 CFR Part 303 - Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies of this document are available online at https://www.ftc.gov)

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

AMERICAN ASSOCIATION OF TEXTILE CHEMISTS AND COLORISTS (AATCC)

AATCC TM20A - Test Method for Fiber Analysis: Quantitative

(Copies of these documents are available online at https://www.aatcc.org.)

AMERICAN SOCIETY FOR QUALITY (ASQ)

ASQ/ANSI Z1.4 - Sampling Procedures and Tables for Inspection by Attributes

(Copies of this document are available online at https://asq.org.)

ASTM INTERNATIONAL

ASTM D737	- Standard Test Method for Air Permeability of Textiles Fabrics
ASTM D1059	- Standard Test Method for Yarn Number Based on Short-Length Specimens
ASTM D1777	- Standard Test Method for Thickness of Textile Materials
ASTM D3776/D3776M	- Standard Test Method for Mass Per Unit Area (Weight) of Fabric
ASTM D5034	- Standard Test Method for Breaking Strength and Elongation of Textiles Fabrics (Grab Test)
ASTM D6193	- Standard Practice for Stitches and Seams
ASTM D8007	- Standard Test Method for Wale and Course Count of Weft Knitted Fabrics

(Copies of these documents are available online at https://www.astm.org.)

INFORMA HEALTHCARE

Repeat Insult Patch Test - Modified Draize Procedure –
Principles and Methods of Toxicology, A Wallace Hayes (editor).

(Copies of this document are available online at https://www.crcpress.com.)

2.4 Order of precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 Guide sample. Guide samples, when furnished, are solely for guidance and information. To the extent of any inconsistencies between the written document and the sample, the written document shall govern.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

3.2 First article. When specified (see 6.2), a sample shall be subjected to first article inspection in accordance with 4.2.

3.3 Recycled, recovered, environmentally preferable, or biobased materials. Recycled, recovered, environmentally preferable, or biobased materials should be used to the maximum extent possible, provided that the material meets or exceeds the operational and maintenance requirements, and promotes economically advantageous life cycle costs.

3.4 Design. The mitten shall be an ambidextrous design consisting of an outer terry cloth shall, and interlining, and an inner duck lining.

3.5 Materials.

3.5.1 Terry cloth, knitted. The outer layer of fabric for the mittens shall be of a knitted terry loop construction having a terry yarn face and a backing yarn. The yarn shall be no coarser than 6/1 nor finer than 20/2 (cotton count) yarn size. Two (2) ends of the yarn shall be used in knitting the terry loop face and one (1) yarn shall be used in knitting the back of the fabric. The color of the fabric shall be the natural color of the fiber as produced by the manufacturer. Bleach or a color modifier shall not be used. Yarn and fabric requirements shall conform to Table I, when tested as specified in 4.4.1.

TABLE I. Knitted terry cloth requirements.

Characteristic	Requirements	
	Construction A	Construction B
Fiber content	100 % para-aramid or 80/20% para-aramid/PFR rayon 1/	2/
Yarns per inch (min.) Wales Courses	 10 12	 10 12
Thickness, inch (min.)	0.140	0.124
Weight, oz./sq.yd. (min.)	23.5	20.0

1/ Maximum of 20 percent permanently flame retardant (PFR) rayon.
2/ The yarns shall be made by wrapping a blend of equal amounts pf para-aramid and meta-aramid fibers around a central core of fiberglass. The amount of fiberglass in the total yarn blend shall not exceed 30 percent.

3.5.2 Cloth, duck, cotton, unbleached. The unbleached cotton duck lining shall be 9.85-11.00 ounces per square yard, with a minimum breaking strength of: warp 150 pounds and filling 110 pounds and air permeability of 5.0 cub.ft/min/sq.ft when tested as specified in 4.4.1. The warp yarns shall be plied and the filling yarns shall be singles or plied.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

3.5.3 Cloth, knitted, napped (interlining). The interlining shall be made of natural or unbleached yarns. The back of the knitted lining shall be made from singles, carded cotton yarn. The napped face of the knitted interlining shall be made from singles, woolen yarn spun on the woolen system of manufacture. The wool content of the cloth shall be no less than 70 percent (based on the dry desized specimen) and the remaining percentage shall be cotton. The weight of the cloth shall be 9.0 to 11.00 ounces per square yard when tested as specified in 4.4.1.

3.5.4 Tape, cotton. The tape shall conform to Type I, Class 1, 3/4-inch width of MIL-DTL-43566.

3.5.5 Thread.

3.5.5.1 Thread, cotton. The thread for stitching interlining to duck lining shall be unbleached cotton conforming to Type I, Tex 60, 3-ply of A-A-52094. The thread for closing the inner shall and attaching the thumb of inner shall to palm of inner shell shall be unbleached cotton conforming to Type I, Tex 105, 4-ply of A-A-52094.

3.5.5.2 Thread, aramid and para-aramid. The thread for all operations other than specified in 3.5.5.1 shall be either aramid thread conforming to Tex 60 of A-A-50195, or para-aramid spun thread confirming to Type I, Tex 59, 3-ply of A-A-55195. The color of the thread of the aramid or para-aramid shall be natural.

3.5.6 Rings, "D". "D" rings shall conform to Class 2, configuration A of MIL-DTL-3390.

3.5.7 Identification label. Each mitten shall have an identification label conforming to Type VI, Class5 of MIL-DT- 32075. The item description for use on the label shall be: Mitten, Heat, Protective.

3.5.71 Label/Tag. Each item shall have a tag in accordance with Type VIII, Class 17 of MIL-DTL-32075. The tag shall be completely visible on the item when it is folded and/or packaged as specified and shall not cause any damage to the item.

3.6 Patterns. The patterns and dies for cutting the parts of the mitten shall be furnished by the contractor and shall be of proper proportions to provide mittens conforming to the measurements specified in Table IV. Standard patterns will be furnished by the Government. The Government pattern shall not be altered in any way and shall be used to create the contractor's working patterns/dies. Minor pattern modifications are permitted to accommodate manufacturing procedures; however, the design and finished measurements must be maintained. Pattern guidelines shall not be modified. The pattern parts, materials, and cutting quantities shall be as specified in Table II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

TABLE II. List of pattern parts.

Material	Nomenclature	Cut number per mitten
Terry cloth for shell (see 3.5.1)	- Thumb body - Body	1 1
Cotton duck cloth for lining (see 3.5.2)	- Thumb lining - Body lining	1 1
Wool and cotton, knitted napped cloth for interlining (see 3.5.3)	- Thumb interlining - Body interlining	1 1

3.7 Construction.

3.7.1 Stitches, seams, and stitching. All stitches, seams, and stitching shall conform to ASTM D6193. The type of seam, and stitching shall be as specified in Table III. The stitches per inch for the mitten shall be 8-10, except for the terry cloth shell (2.a. and 2.b. of Table III) it shall be 6-8 stiches per inch. Seam allowances shall be maintained with seams sewn so that no raw edges, run-offs, twists, pleats, puckers, or open seams occur.

3.7.1.2 Type 301 stitching. Ends of 301 stitching shall be backstitched or overstitched 1/4-inch minimum except where ends are turned under in a hem or held down by other stitching. Thread tension shall be maintained so there will be no loose stitching resulting in a loose bobbin or top thread or no excessively tight stitching resulting in puckering of the materials sewn. The lock shall be embedded in the sewn materials.

3.7.1.2.1 Repairs of Type 301 stitching. Repairs of Type 301 stitching shall be as follows:

a. When thread breaks or bobbin run-outs occur during sewing, the stitching shall be repaired by restarting the stitching a minimum of 1-inch back of the end of the stitching.

b. Thread breaks or two (2) or more consecutive skipped or run-off stitches noted during inspection of the item shall be repaired by overstitching. The stitching shall start a minimum of 1-inch back of the defective area, continue over the defective area, and continue a minimum of 3/8-inch beyond the defective area onto the existing stitching. Loose or excessively tight stitching shall be repaired by removing the defective stitching, without damaging the materials, and re-stitching in the required manner. 1/

1/ When making the above repairs, the ends of stitching are not required to be backstitched.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

3.7.1.3 Type 401 stitching. As alternate, mittens can be sewn using Type 401 stitch. Ends of 401 stitching shall be backstitched or overstitched 1/4-inch minimum except where ends are turned under in a hem or held down by other stitching. Thread tension shall be maintained so there will be no loose stitching resulting in a loose bobbin or top thread or no excessively tight stitching resulting in puckering of the materials sewn. The lock shall be embedded in the sewn materials. All repairs shall be made in accordance with 3.7.1.2.1a. and 3.7.1.2.1b. Repairs to Type 401 stitching may be accomplished by using Type 301 stitch type.

3.7.2 Manufacturing operations requirements. The mitten shall be manufactured in accordance with the operation requirements specified in Table III. The contractor is not required to follow the exact sequence of operations. In the event of a conflict between the written document and the referenced drawing (see 2.2.2), the written document shall govern.

THIS SPACE LEFT INTENTIONALLY BLANK

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

TABLE III. Manufacturing operations requirements.

No.	Requirement	Stitch type	Seams and stitching type	Thread	
				Needle	Bobbin/looper
1.	Cutting: Fabric components shall be cut on a straight line with the cuff to fingertip direction in the length direction of the fabric. Components having material defects or damages that are classified as defects in 4.4 shall be removed from production and replaced with non-defective and properly matched components.	--	--	--	--
2.	Terry cloth shell: a. Join thumb to hand. The thumb piece shall be inseam sewn to hand with two rows of stitching 1/16 to 1/8-inch apart, 3/8 (±1/16)-inch from edge.	301	SSa-2	E	E
	b. Closing. The hand shall be closed with two rows of stitching, 1/16 to 1/8-inch apart, 3/8(±1/16) –inch from edge.	301	SSa-2	E	E
3.	Attach identification label: The label shall be attached to the palm side of the terry cloth shall (i.e., side that does not have the “D” ring). Attach label to the outside of each terry cloth shall by stitching the four sides of the label to the shell. The stitch margin shall be 3/16(±1/16)-inch from the edge of the label. The label shall be located at the center of the palm approximately 1/2-inch below the top opening.	301	SSa-1	E	E

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

TABLE III. Manufacturing operations requirements. - Continued

No.	Requirement	Stitch type	Seams and stitching type	Thread	
				Needle	Bobbin/looper
4.	Make inner shell (consisting of knitted napped interlining and cotton duck lining): a. Place hand portion of knitted interlining on hand portion of duck lining with cotton back of knitted interlining next to duck lining. Join the linings together to form hand portion of inner shell by stitching around the periphery 1/4 to 3/48-inch in from edge of interlining.	301 or 401	SSa-1	30-3	30-3
	b. Join thumb portion of interlining and duck lining together to form thumb portion of inner shell using the same procedure described in 4.a. above.	301 or 401	SSa-1	30-3	30-3
	c. Attach thumb portion of inner shell to hand portion of inner shell with one (1) row of stitches 1/4 (±1/16)-inch from edge of duck lining.	301	SSa-1	16-4	16-4
	d. Close inner shell with one (1) row of stitches 1/4 (±1/16)-inch from edge of duck lining.	301	SSa-1	16-4	16-4
5.	Attach inner shell (knitted napped fabric and duck lining) to terry cloth outer shell: Attach inner shell to terry cloth shell by tacking at hand portion and thumb (see stage 7, Drawing 2-1-23).	301	SSa-1	E	E
6.	Turn mitten: The terry cloth mitten shall be turned right side out by pulling it down over the lining.				

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

TABLE III. Manufacturing operations requirements. – Continued

No.	Requirement	Stitch type	Seams and stitching type	Thread	
				Needle	Bobbin/looper
7.	Hemming: The top raw edges of the terry cloth shell and the duck lining shall be hemmed by turning in both cloths not less than 5/8-inch and stitching through both cloths not more than 3/8-inch down from the top of the gauntlet or cuff. The edge of the duck lining shall be turned over the knitted interlining. The stitches may pass through the interlining but shall not be super-imposed on the stitching joining duck to interlining. The duck lining shall not extend beyond the edge of the terry cloth.	301	SSc-1	E	E
8.	"D" ring attachment: The "D" ring shall be attached using 3/4-inch unbleached webbing. The tape and "D" ring shall be assembled and attached to the mitten as shown in section M-M of Drawing 2-1-23.	301	--	E	E

THIS SPACE LEFT INTENTIONALLY BLANK

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

3.8 Measurements. The finished mitten shall conform to the measurements shown in Table IV.

TABLE IV. Finished measurements.

Location	Measure - inches	Tolerance - inches
Overall length	12-1/2	+1, -1/2
Width (measure across mitten 3-1/2-inches from closed end)	5-3/4	+1/2, -1/4
Width (measure across mitten 6-inches (±1/4)-inch from open end)	6	+1/4, -0
Thumb length (measure from inside fold to top of thumb)	3	+1/2, -1/4
Thumb width (measure across back of thumb 1-1/2-inches from top of thumb)	2-1/2	+1/4, -0

3.9 Toxicity. The finished textile materials shall not present a health hazard and shall show compatibility with prolonged, direct skin contact when tested as specified in 4.5. Chemicals recognized by the Environmental Protection Agency (EPA) as human carcinogens shall not be used.

3.10 Workmanship. The finished gloves shall be uniform in quality and shall conform to the quality of product established by this specification. The occurrence of defects, as specified in 4.4, shall not exceed the criteria specified in the contract or purchase order.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.2).
b. Conformance inspection (see 4.3).

4.2 First article inspection. A first article, submitted in accordance with 3.2, shall be inspected, examined for appearance, color, finished measurements listed in Table IV, finished defects listed in 4.4 and tested for the characteristics as specified in 4.4.1.

4.3 Conformance inspection. Conformance inspection shall include the visual examination of 4.4 and the tests of 4.4.1 through 4.5 as applicable. Sampling for inspection shall be performed in accordance with ASQ/ANSI Z1.4 and with acceptance quality limits (AQLs) as specified in the contract and/or order, except where otherwise indicated (see 6.2).

4.3.1 Inspection conditions. Unless otherwise specified in this specification or applicable procurements documents (see 6.2), all inspections shall be performed in accordance with this specification and all the requirements of referenced documents.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

4.4 End item visual examination. The finished mittens shall be examined for the defects listed in Table V. The lot size shall be expressed in units of mittens. The sample unit shall be one pair of mittens and selection shall be by pairs. Defects for pairing shall be classified as a single defect.

TABLE V. End item visual defects.

Examine	Defect	Classification	
		Major	Minor
Material	- Cut, hole, tear, smash, or rip - Mend - Terry cloth has area with no terry loops	101 102 103	
Construction and workmanship (applicable to all components and assemblies, unless otherwise indicated herein)	- Component not fabricated of specified material - Component or operation omitted - Component misplaced - Needle chew - Not assembled as specified - Component not securely attached - Liner does not fit properly inside of shell (e.g. liner too short or too narrow)	104 105 106 107 108 109	201

THIS SPACE LEFT INTENTIONALLY BLANK

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

TABLE V. End item visual defects. – Continued

Examine	Defect	Classification	
		Major	Minor
Seams and stitching	- Not specified seam or stitch type	110	
	- Row of stitching omitted	111	
	- open seam (except “D” ring attachment or hem)	112	
	- Open seam on “D” ring attachment or hem		202
	NOTE: A seam shall be classified as open when one or more stitches joining a seam are broken or when two or more consecutive skipped or runoff stitches occur.		
	- Repair of open seam not as specified		203
	- Loose stitch tension resulting in a loosely secured seam	113	
	- Tight stitch tension resulting in cutting of fabric or breaking of stitches when normal pull is applied	114	
	- Ends of seams or stitching produced with stitch Type 301 when not caught in another row of stitching:		
	a. Not backstitched or not overstitched, or backstitched or overstitched less than 1-inch		204
	- Ends of seam or stitching produced with stitch Type 401 when not caught in other seam or stitching:		
	a. Chain extends less than 1/2-inch or more than 3/4-inch beyond each end		
	b. Chain does not extend beyond each end		205
	- Part caught in unrelated row of stitching	115	
	- One stitch per inch less than minimum specified	116	
	- Two or more stitches per inch less than minimum specified		206
	- More than the specified maximum number of stitches per inch resulting in damage to assembly	117	
	- Gage or margin of stitching irregularly accomplished	118	
			207

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

TABLE V. End item visual defects. – Continued

Examine	Defect	Classification	
		Major	Minor
Assembly detail	- Part malformed	119	
	- Lining seriously wrinkled or excessive bulk in crotch of thumb or hand	120	
	- Three or more thread ends not trimmed to 1/4-inch on outside		208
	- Duck lining extends beyond edge of terry cloth fabric	121	
Label	- Missing, incomplete, incorrect, illegible	122	
	- Not specified type, not in proper location, or not accomplished in the specified manner		209
	- Bar code omitted or not readable by scanner	123	
	- Human-readable interpretation (HRI) omitted or illegible	124	
	- Bar code not visible on folded packaged item		210
	- Bar code causes damage to the item.	125	
D-ring	- Wrong size	126	
	- Finish not black enamel	127	
	- Area of no finish		211
	- Finish not adherent, (e.g. flaking or peeling)		212
	- Sharp edge or projection	128	
	- Cracked or broken	129	
	- Bent or malformed		213
Cleanness	- Spot, stain, or foreign matter not removable		214

4.4.1 Material/end item testing. The finished fabrics shall be tested for the characteristics listed in Table VI. The methods of testing as specified wherever applicable and as listed in Table VI shall be followed. All test reports shall contain the individual values utilized in expressing the final results. The sample unit shall be one (1) yard full width of each finished fabric for all physical tests. The lot shall be unacceptable if one (1) or more sample units or the lot average fail to meet any requirement specified. The sample size shall be in accordance with the following:

Lot size (units)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

TABLE VI. Material/component tests.

Characteristic	Requirement reference	Test method
Cloth, terry: Fiber content	Table I	AATCC TM20A (see 6.4)
Yarn number	See 3.5.1	ASTM 1059
Yarns per inch (min.) Wales Courses	Table I	ASTM D8007
Thickness, inch (min.)	Table I	ASTM D1777
Weight, oz./sq.yd. (min.)	Table I	ASTM D3776/D3776M
Cloth, duck, cotton: Weight, oz./sq.yd.	See 3.5.2	ASTM D3776/D3776M
Breaking strength, lbs (min.) Warp Filling	See 3.5.2	ASTM D5034
Air permeability, cu.ft./min./sq.ft. (min.)	See 3.5.2	ASTM D737
Cloth, knitted napped: Fiber content	See 3.5.3	AATCC TM20A (see 6.4)
Weight, oz./sq.yd.	See 3.5.3	ASTM D3776/D3776M

4.5 Toxicity test. When required, (see 6.2) an acute dermal irritation study and a skin sensitization study shall be conducted. When the results of these studies indicate the textile material is not a sensitizer or irritant, a Repeat Insult Patch Test shall be performed in accordance with the Modified Draize Procedure (see 2.3). If toxicity requirement (see 3.9) can be demonstrated with historical use data, on the finishing treatments used, toxicity testing may not be required (see 6.2).

5. PACKAGING

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When actual packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain requisite packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Department or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The mittens are worn by Military personnel of the Department of Defense to protect the hands from heat or burns when handling hot metals or objects

6.2 Acquisition requirements. Acquisition documents should specify the following:

a. Title, number, and date of this specification.
b. The specific issue of individual documents referenced (see 2.2).
c. When a first article is required (see 3.2, 4.2).
d. Conformance inspection acceptance quality limits (AQLs) (see 4.3)
e. Inspection conditions (see 4.3.1)
f. Packaging requirements (see 5.1).

6.3 Samples. For access to samples, address the contracting activity issuing the invitation for bids or request for proposals.

6.4 Certificate of compliance. The contracting activity may select to accept a certificate of compliance for stated requirement.

6.5 Subject term (key word) listing.

Handwear
Hot metals
Terry cloth

6.6 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issues, due to the extensiveness of the changes.

Custodians:
Army - GL
Navy - NU
Air Force - 11

Review Activities:
Army - MD
Navy – MC, YD

Preparing Activity:
DLA - CT

(Project: 8415-2021-058)

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using ASSIST Online database at https://assist.dla.mil.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T15:43Z
Check the source to verify that this is the current version before use.