MIL-P-50601A(MU)
23 April 1976
SUPERSEDING
MIL-P-50601(MU)
16 November 1970

MILITARY SPECIFICATION

PROJECTILE, 20MM, TP-T, M212A1; METAL PARTS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers the metal parts for Projectile, 20mm, Target Practice - Tracer (TP-T), M212A1. (see 6.1)

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids, or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

TT-C-490	- Cleaning Methods and Pretreatment of Ferrous Surfaces for Organic Coatings

MILITARY

MIL-S-46070	- Steel Bar for Projectile Stock
MIL-A-2550	- Ammunition, General Specification for

STANDARDS

MILITARY

MIL-STD-105	- Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-109	- Quality Assurance Terms and Definitions
MIL-STD-651	- Visual Inspection Standards for 20mm Ammunition and Components
MIL-STD-1168	- Ammunition Lot Numbering
MIL-STD-1169	- Packaging, Packing and Marking for Shipment of Inert Ammunition Components
MIL-STD-1235	- Single and Multilevel Continuous Sampling Procedures and Tables for Inspection by Attributes

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

2.1 (Cont)

DRAWINGS

ARMAMENT COMMAND

C10542660	- Nose
B10542556	- Blank, Rotating Band, for Projectiles, 20mm
D11731531	- Shipping Container for Inert Projectiles, 20mm
D10542655	- Cartridge, 20mm Target Practice-Tracer M206A1
LI 11731537	- Index of Inspection Equipment Lists for: Projectile, 20mm, TP-T, M212A1, Metal Parts
D10542658	- Metal Parts, Projectile, 20mm, TP-T, M212A1
D10542659	- Body and Rotating Band Assembly, Projectile, 20mm, TP-T, M212A1
D11731537	- Metal Parts Assembly, Projectile, 20mm, TP-T, M212A1

PUBLICATIONS

U. S. ARMY MATERIEL COMMAND

AMCR 715-505	- Ammunition Ballistic Acceptance Test Methods, Volume 8, Test Procedures for 20mm Cartridges

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 OTHER PUBLICATIONS.-The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials (ASTM)

ASTM B117-64	- Method of Test for Salt Spray (Fog) Testing

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103)

Technical Society and Technical Association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using federal agencies.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 Materials.-Materials shall be in accordance with applicable drawings and specification. Prior to producing projectile bodies from a heat of steel, the contractor shall have bar stock verification tests conducted, in a manner acceptable to the Government, to establish that the bar stock meets the requirement of MIL-S-46070.

3.2 Parts and assembly. -The parts and assemblies shall be in accordance with all the requirements of Drawing (Dwg.) D11731537 and with all requirements of the drawings and specification shown thereon.

3.3 First Article Sample.-Unless otherwise directed by the contracting officer, a first article sample shall be required.

3.4 Manufacturing process. -All parts and assemblies shall be manufactured by a process approved by the contracting officer and no deviation from that process shall be made without his prior approval. (See 6.4)

3.5 Banding. -The rotating band blank and the rotating band seat shall be clean at the time of banding. Shot or sandblasting shall not be used to clean the serrated band seat after knurling. The rotating band blank shall fill the band seat.

3.6 Soundness. -Metal discontinuity in the projectile body, as determined by eddy current inspection, shall be less than that represented by Production Check Standard (PCS) No. 1.

3.7 Projectile nose torque. -The nose of the projectile shall withstand a minimum torque as specified by Dwg. D11731537.

3.8 Protective coating.

3.8.1 Phosphate coating.-The pretreatment process used shall be in accordance with the applicable requirements of Dwg. D10542658. The phosphate coating shall be in accordance with the requirements of TT-C-490 for appearance and minimum weight, as applicable to the type of phosphate coating used.

3.8.2 Paint adhesion.-The painted exterior of the body shall meet the requirements of TT-C-490 for adhesion.

3.8.3 Corrosion resistance. -The painted exterior of the body assembly shall show no evidence of corrosion (red rust) after exposure to a 5 percent solution of atomized salt spray for 24 hours.

3.9 Metal parts security. -The sample projectile, metal parts, when assembled into cartridges having a mean instrumental velocity at 78 feet of 3450 ± 25 feet per second (fps), shall not separate or break up in the metal parts security test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

3.10 Workmanship. -The requirements for workmanship are as specified by applicable drawings, referenced specifications and the following:

3.10.1 Processing defects. -The components and assemblies shall be free from dents, scratches, cuts, sharp edges, burrs, and other forms of sub-standard workmanship.

3.10.2 Cleanliness. -The components and assemblies shall be free from all foreign matter.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. -Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection require-ments specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the speci-fication where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Quality assurance terms and definitions .-Reference shall be made to MIL-STD-109 for definition of quality assurance terms.

4.1.2 Bar stock verification. -Independent of tests and inspections per-formed by the steel bar supplier, an examination shall be made on each lot of bars. The inspection and tests used to verify the bar stock quality shall be as specified by MIL-S-46070, Table IV, using the requirements, acceptance criteria and test methods referenced therein, with the following modifications:

Chemical composition: Sulphur only is required.
Mechanical properties: Unmodified.
Grain size: Unmodified.
Soundness:
Macro-etch
Billet: See Note 1.
Bar: See Note 1.
Magnetic: See Note 1.
Surface decarburization: Not required.
Dimensions: Diameter only.
Workmanship: See Note 1.

NOTE 1: The supplier’s macro-etch, magnetic and visual inspection shall be monitored to the extent necessary to assure compliance with MIL-S-46070.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

4.2 Classification of inspections.-The inspection requirements specified herein are classified as follows:

1. First article inspection (see 4.3)
2. Quality conformance inspection (see 4.4)

4.3 First Article Inspection.

4.3.1 First article sample. -The sample shall be delivered for inspection in accordance with first article approval provisions of the contract and MIL-A-2550, and shall consist of:

a. Inspection and nonfiring tests:

3 standard test panels (see TT-C-490)
32 rotating band blanks
125 noses
125 bodies, without rotating band
125 body, rotating band assemblies, uncoated
125 projectile metal parts assemblies, painted

b. Firing test:

4,000 projectile metal parts assemblies

The projectile assemblies shall be identified in accordance with MIL-STD-1168.

4.3.1.1 Inspection. -After inspection by the contractor and provisional acceptance by the Government activity, the sample will be inspected in accordance with the provisions of MIL-A-2550. Failure of the original first article sample to be in accordance with the applicable drawings and the requirements of Para. 3, as specified herein, will result in sample disapproval. (see 6.3)

4.4 Quality Conformance Inspection.

4.4.1 Submission of product. -The product shall be submitted in accordance with MIL-STD-105 or MIL-STD-1235, as applicable.

4.4.1.1 Lot. -A lot shall consist of projectile metal parts assemblies produced by one manufacturer in one unchanged process, in accordance with the same drawings and drawing revisions, and same specification and specification revision.

4.4.1.2 Lot identification. -Each projectile metal part assembly and each packed lot shall be identified in accordance with applicable drawings and MIL-STD-1168.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

4.4.2 Examination.-One hundred percent examination shall be performed by the contractor for all critical defects. Examination for major and minor defects shall be performed as specified herein. Each part and each assembly found to be defective shall be rejected.

4.4.2.1 Sampling and acceptance criteria.-The sampling plans and procedures shall be in accordance with MIL-STD-105 or MIL-STD-1235. To determine product acceptability, major or minor defects as listed herein may be considered collectively on a class basis or they may be considered Individually. However, where major defects are considered collectively on a class basis, the acceptance number for any individual defect of the class shall be limited by the assigned Acceptable Quality Level (AQL) for individual defect associated with the class. (see 4.4.2.2.c) In addition, where three or less defects appear in a classification, or, where MIL-STD-1235 is used, sampling plans applicable to a class shall not be used for major defects. (see 6.5)

4.4.2.2 AQL's. -The following AQL's are assigned to major and minor defects:

a. Individual:

Major	0. 25%
Minor	0. 40%

b. Class basis:

Major	1 .50%
Minor	2.50%

c. Individual defects associated with the class basis:

Major	0.40%

4.4.3 Classification of defects. -1/ The classification of defects shall be as specified herein. (see 6.6)

4.4.3.1 Rotating band blank (see Dwg. B10542556).

Categories and Defects	Method of Inspection
Critical: None defined.	
Major:	
101. Foreign matter	Visual (see 3.10.2)
102. Defective metal, including lamination	Visual
103. Incomplete or deformed	Visual 2/
Minor:	
201. Width, max.	Gage

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

4.4.3.2 Nose (see Dwg. C10542660)

Categories and Defects	Method of Inspection
Critical: None defined.	
Major:	
101. Diameter, ogive at shoulder, min.	Gage
102. Length, nose to shoulder, max.	Gage
103. Pitch diameter of threads	Gage
104. Major diameter of threads	Gage
105. Runout, ogive surface with thread including perpendicularity with shoulder	Gage
Minor:	
201. Diameter, ogive at shoulder, max.	Gage
202. Length, nose to shoulder, min.	Gage
203. Diameter, cylindrical surface rear of threads	Gage
204. Length, rear of thread to shoulder face	Gage
205. Finish	Visual
206. Foreign matter	Visual
207. Mutilated	Visual

4.4.3.3 Body prior to banding (see Dwg. D10542659)

Critical: None defined.	
Major:	
101. Length, mouth to rear of rotating band seat	Gage
102. Knurling missing or incomplete	Visual
103. Foreign matter in rotating band seat	Visual (see 3.5)
104. Depth of knurling, min.	Visual **3/**
Minor:	
201. Diameter, rotating band seat, knurled	Gage
202. Width, rotating band seat	Gage
203. Width, knurling, min.	Visual **3/**

4.4.3.4 Body and rotating band assembly (see Dwg. D10542659)

Critical:	
1. Ferrous metal discontinuity	Soundness

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

4.4.3.4 (Cont)

Categories and Defects		Method of Inspection
Major:		
101.	Length, mouth to rear of rotating band	Gage
102.	Diameter, body rear of rotating band, min.	Gage
103.	Diameter, rotating band	Gage
104.	Width, rotating band	Gage
105.	Location, crimp groove	Gage
106.	Profile, crimp groove	Gage
107.	Radius, rear edge of crimp groove, max.	Gage
108.	Depth, crimp lip to bottom of tracer cavity	Gage
109.	Runout, rotating band, with datum surface	Gage
110.	Diameter, bourrelet, min.	Gage
111.	Diameter, body cavity	Gage
112.	Runout, body cavity with datum surface	Gage
113.	Diameter, tracer cavity	Gage
114.	Runout, tracer cavity with datum surface	Gage
115.	Diameter, metering disc cavity	Gage
116.	Depth, metering disc cavity	Gage
117.	Width, crimp lip	Gage
118.	Runout, metering disc cavity with datum surface	Gage
119.	Perforation or fracture in tracer cavity	Visual
Minor:		
201.	Outside diameter, mouth end	Gage
202.	Depth and width of undercut, front and rear of rotating band	Gage
203.	Overall length	Gage
204.	Foreign matter	Visual 5/
205.	Finish improper	Visual 4/

4.4.3.5 Body (coated, prior to painting) (see Dwg. D10542659)

Critical: None defined.

Major:		
101.	Pitch diameter, thread	Gage
102.	Runout, thread with datum surface	Gage
Minor:		
201.	Minor diameter, thread	Gage
202.	Length, complete thread, min.	Gage

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

4.4.3.6 Projectile, 20mm, metal parts assembly (see Dwgs. D10542658 and D11731537)

	Categories and Defects	Method of Inspection
Critical:	None defined.	
Major:		
101.	Diameter, bourrelet, max.	Gage
102.	Diameter, body, rear rotating band, max.	Gage
103.	Diameter, metering disc cavity, min.	Gage
104.	Diameter, tracer cavity, min.	Gage
105.	Depth, crimp lip to bottom of tracer cavity, min.	Gage
106.	Length, nose to rear of rotating band, max.	Gage
107.	Weight	Scale
Minor:		
201.	Overall length, max.	Gage
202.	Paint not dry	Tactile
203.	Marking incorrect, incomplete, illegible or missing	Visual
204.	Paint on rotating band	Visual
205.	Rotating band damaged	Visual
206.	Exterior paint inadequate	Visual
207.	Foreign matter on exterior	Visual 5/

1/ MIL-STD-651 shall apply in defining and evaluating visual defects.

2/ A rotating band blank which is deformed or judged to lack sufficient metal in any part of its width or thickness to provide for complete band seat fill and minimum rotating band profile dimensions shall be classed a defect.

3/ Measurement of knurling for compliance with the minimum depth and width requirements shall apply where visual inspection indicates that either dimension is borderline.

4/ Measurement of surface roughness shall apply where visual inspection indicates that the specified finish is exceeded.

5/ An assembly that has foreign matter on the exterior or contained in the threads or body shall be classed a defect. Particular attention shall be given to the examination of the cavities for steel chips or shavings.

4.4.4 Tests.-The tests listed in Table I shall be performed on each projectile lot in accordance with the test methods prescribed in 4.5. Sample size and acceptance criteria for each test shall be as specified. Only projectiles having met the visual and dimensional requirements and having been selected in such a manner that the sample is representative of the entire lot shall be used in the tests. The selected projectiles shall be thoroughly mixed before being divided into samples for the various tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

4.4.4 (Cont)

Table I

Test		Sample Size	Item	Req. Para.
Band tightness	1/	315	Assemblies, painted	3.5
Soundness verification	2/	315	Assemblies, unpainted (see 4.5.5)	3.6
Automatic inspection effectiveness	3/		PCS No. 1 (see 4.5.3)	- -
Projectile nose torque	4/	50	Assemblies, painted	3.7
Phosphate coating (appearance and weight)	5/		3 standard panels, TT-C-490	3.8.1
Paint adhesion	6/	13	Assemblies, painted, TT-C-490	3.8.2
Corrosion resistance	7/	32	Assemblies, painted	3.8.3
Metal parts security	8/	250	Assemblies, painted	3.9

1/ If two or more units of the sample have an average radial void, between the seated band and the band seat, greater than 0.004 inch, the lot shall be rejected. If one unit of the sample has an average radial void greater than 0.004 inch, a second sample consisting of the same number of units as specified for the first sample shall be tested. If, in the accumulated samples, two or more units have an average radial void greater than 0.004 inch, the lot shall be rejected.

2/ Rejection of one or more units of the sample by the flaw detector in the test for body metal soundness shall be cause for rejection of the lot.

3/ Failure of the flaw detector to reject PCS No. 1 shall be cause for rejection of all assemblies inspected for “soundness” since the preceding test and shall require requalification of the equipment for automatic inspection. (see 4.5.3)

4/ Projectile nose torque. -Failure of one or more of the sample projectiles to comply with the specified torque requirement shall be cause for rejection of the lot.

5/ Failure of the phosphate coating on the standard panels to comply with the applicable requirements, shall cause rejection of all production assemblies phosphate since the preceding test.

6/ If two or more units of the sample fail to comply with the requirement for paint adhesion, the lot shall be rejected. If one unit of the sample fails to comply with the requirement, a second sample consisting of the same number of units as specified for the first sample shall be tested. If in the accumulated samples, two or more units fail to comply with the requirement for paint adhesion, the lot shall be rejected.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

4.4.4 (Cont)

7/ If two or more units of the sample fail to comply with the corrosion resistance requirement, the lot shall be rejected. If one unit fails to comply with the requirement, a second sample consisting of the same number of units as specified for the first sample shall be tested. If in the accumulated samples two or more units fail to comply with the corrosion resistance requirement, the lot shall be rejected.

8/ The lot will be rejected, not subject to retest, if any one of the following types of metal parts separation or breakup occurs in the metal parts security test, as witnessed by hole(s) in the fragmentation screen(s), or recovery of the part(s) or fragment(s):

a. Body breakup

b. Loss of nose

c. Complete rotating band separation. This is defined as detachment of all or part of the band having band seat knurling imprint. The following acceptance criteria shall apply to thrown band fragments having no evidence of band seat knurling imprint:

(1) The lot will be rejected if three or more assemblies throw band fragments having length not greater than 0.500 inch.

(2) The lot will be rejected if any assembly throws a band fragment having length greater than 0.500 inch (indicative of deep-seated band lamination).

(3) The lot will not be penalized for band particles thrown as a result of normal band fringing or slivering.

4.4.5 Packaging. packing and marking inspection. -Inspection for packing and marking shall be in accordance with the applicable requirements of MIL-STD-1169.

4.4.6 Inspection equipment. -Index of Inspection Equipment List (LI) 11731537 identifies the applicable Inspection Equipment Lists (IEL) required to perform examination and tests as specified herein. Equipment design(s) shall be in accordance with the applicable IEL code designations. The code designations are defined on Dwg. B11075228, a detail of LI 11731537. The provisions of MIL-A-2550 shall apply.

4.5 Test Methods and procedures.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

4.5.1 Band tightness. -The method of test shall comply with all requirements of the operating instructions for the band tightness tester (see Dwg. B7259545, a detail-of LI 11731537). The inspection sample shall be cycled through the tester to determine compliance with the rotating band tightness requirement. The total measurement of radial void (band looseness), registered on the tester indicator at final ram pressure, shall be divided by four (number of indenters) to determine the average radial void.

4.5.2 Soundness.-The method of inspection shall comply with all requirements of Operating Instructions, Eddy Current Flaw Detector, (see Dwg. D11075203, a detail of LI 11731537) for Detecting Metal Discontinuity in Projectile Bodies for 20mm Ammunition, except for those inspection requirements which are reserved for Government application, as specified herein.

4.5.3 Automatic eddy current inspection effectiveness. -Equipment checkout shall be performed as stated in the Operating Instruction Manual at the start of each shift and after any adjustment or shutdown. Upon completion of checkout, cycle the PCS #1, front slot and rear slot standards through the inspection system during automatic operation. All three standards must be rejected to assure correct adjustment for reject level and scan limits. During the remainder of shift the PCS #1 shall be cycled through the equipment at intervals of 20 ± 5 minutes during automatic operation.

4.5.4 Equipment verification. -The Government inspector will maintain independent of the contractor, a set of standards and may cycle these standards through the equipment at any time. Failure of equipment to reject standards will be evidence that the equipment is not properly adjusted and the contractor will be so notified. (see 6.7)

4.5.5 Soundness verification. -After equipment checkout and verification as specified in 4.5.3 and 4.5.4 the entire lot sample will be inspected with the equipment operating automatically. Any rejected unit of the sample will be automatically cycled through the equipment with the CAL. button pressed (to lower the sensitivity one step below that used for production inspection). Any unit which is rejected at the lower sensitivity shall be classed as defective.

4.5.6 Projectile nose torque. -Equipment shall be as specified in LI 11731537. Each projectile nose of the test sample shall be marked with a light scratch extending axially across the nose and projectile body. Torque as specified in 3.7 shall be applied slowly to the nose. Movement of the nose with respect to the projectile body, detectable by misalignment in the scratch mark, shall be recorded.

4.5.7 Phosphate coating. -The method of test shall be as specified in TT-C-490 for the type of coating used. The standard panels shall be processed , with the projectiles to be represented, at the start of daily production and at four hour intervals, maximum, thereafter. Appearance and weight of the coating shall be recorded.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

4.5.8 Paint adhesion. -The method of test shall be as specified in TT-C-490. The test shall be made on the painted bourrelet of each unit of the sample.

4.5.9 Corrosion resistance. -The method of test shall be as specified in American Society for Testing Materials (ASTM), ASTM B117. The paint shall not be disturbed, however, the rotating band and unpainted surfaces of the sample assemblies may be masked out by a wax coating or other suitable material. The salt spray solution and exposure time shall be as specified in 3.8.3.

4.5.10 Metal parts security. -The method of test will be as specified in AMCR 715-505, Volume 8, as applicable. The sample assemblies will be loaded and assembled as specified on Dwg. D10542655, Cartridge, 20mm, for projectile metal parts test. The test cartridge, at ambient temperature, will be fired in bursts of twenty-five shots in the M139 Gun. The gun barrel will be at ambient temperature for the firing of each burst. The cyclic rate of fire will be recorded for informational purposes.

5. PREPARATION FOR DELIVERY

5.1 Packing, Level C.-Each lot of projectile metal parts assemblies shall be packed as specified by Dwg. D11731531.

5.2 Marking.-Marking of shipping containers shall comply with Dwg. D11731531 and with the applicable requirements of MIL-STD-1169.

6. NOTES

6.1 Intended use. -These projectiles are intended for use with the M204 type cartridge case in the assembly of target practice cartridges with tracer.

6.2 Ordering data.-Procurement documents should specify the following:

6.2.1 Title, number and date of this specification.

6.2.2 Place of inspection, if not at place of manufacture.

6.2.3 First article sample requirements (see 3.3, 4.3 and 6.2).

6.2.4 Packing and marking instructions (see 5.1 and 5.2).

6.2.5 Provisions for shipment and testing of first article and production lot samples.

6.2.6 Provision for the supply, maintenance and disposition of Government furnished inspection equipment for acceptance inspection purposes.

6.2.7 Provision for the submission and approval of the manufacturing process. (see 3.4)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

6.2.8 Provisions for the inclusion of MIL-STD-1167, Ammunition Data Cards on DD form 1423, Contract Data Requirement List.

6.3 First article sample. -In order to minimize inspection costs, the firing test. as specified in 4.3, will be performed after the sample has been found acceptable for all other requirements. Additional projectile metal parts may be required by the testing facility.

6.4 Process deviation.-A process deviation is defined as a change in the approved basic method of manufacture, or an operational change which may alter the metallurgical or physical properties of the item.

6.5 AQL's.-The optional use of AQL values for either individual defects or classes of defects, with individual major defect limitations, is intended to minimize inspection agency administrative burden which might result from an exclusive assignment of individual defect AQL's. The option also permits flexibility where sampling inspection for acceptance is integrated into the manufacturing process.

6.6 Intermediate point inspection. -The classification of defects identifies the defect characteristics for acceptance inspection. It may be necessary to modify the sequence of inspection stations to best suit the manufacturing process. Inspection for defect characteristics which will be hidden or altered by subsequent processing operations (including unrelated operations), should be scheduled to prevent premature acceptance which could be detrimental to the attainment of optimum product quality of the item.

6.7 Defect standards. -The initial supply of defect standards and instructions for contractor and Government application to the eddy current method of inspection, will be furnished with the eddy current inspection equipment. Replacement standards should be requisitioned through normal channels by the Government agency having contract administration responsibility.

Custodian:

Army - MU

Preparing Activity:

Army - MU

Project No. 1305-A792

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE
MIL-P-50601A(MU) Projectile, 20MM, TP-T, M212A1; Metal Parts

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?
   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.

FOLD

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY
DOD - 314

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

Commander
Frankford Arsenal
ATTN: SARFA-MDM
Phila., PA 19137

FOLD

☆ U.S. GOVERNMENT PRINTING OFFICE: 1976— 603-766/4047

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:30Z
Check the source to verify that this is the current version before use.