INCH-POUND

MIL-P-51432A(EA)
AMENDMENT 3
2 January 1991
SUPERSEDING
AMENDMENT 2
25 September 1990

MILITARY SPECIFICATION

PLASTIC SHEET, POLYETHYLENE COPOLYMER

This amendment forms a part of MIL-P-51432A(EA), dated 31 August 1988, and is approved for use by the U.S. Army Chemical Research, Development and Engineering Center, Department of the Army and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 3

3.5, table I: Change requirement for flow rate characteristic from "2.0" to "**" in two places and add the following note below table I: "**The sheet produced is allowed to increase in flow rate a maximum of 100 percent from pelletized resin to extruded sheet, or to a maximum value of 3.0 grams per 10 minutes, whichever is less."

3.6: Delete paragraph in its entirety and substitute the following:

"**3.6 Workmanship.** The plastic sheet shall have a smooth finish and shall be free of ripples, waves, cracks, streaks, blisters, bubbles, discoloration, craze, foreign material, pitting, and scratches that form definite indentations and other defects that affect appearance or could affect serviceability."

AMSC N/A

FSC 9330

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:00Z
Check the source to verify that this is the current version before use.

PAGE 5

4.3.3.2: Delete paragraph in its entirety and substitute the following:

"**4.3.3.2 For test.** The sample shall be tested as specified in 4.4.4. Two specimens from each sample shall be separately tested for environmental stress-cracking resistance, tensile strength at yield, and elongation at break. One of the specimens shall be die cut from the sample in the direction of extrusion. The other specimen shall be die cut from the sample at an angle of 90° to the direction of extrusion. Failure of either specimen shall be cause for rejection."

4.4.2.3, line 1: Delete "**4.4.2.3 For physical characteristics tests.**" and substitute "**4.4.2.3 For flow rate and tensile strength at yield.**"

4.4.2.4, line 1: Delete "**4.4.2.4 For infrared spectrum characteristics and water content tests.**" and substitute "**4.4.2.4 For infrared spectrum characteristics, water content, density, hardness, elongation at break, and vicat softening point.**"

PAGE 6

4.4.3.3: Delete paragraph in its entirety and substitute the following:

"**4.4.3.3 For test.** Each sample taken in 4.4.2.3 and 4.4.2.4 shall be tested as specified in 4.4.4. Two specimens from each sample shall be separately tested for tensile strength at yield and elongation at break. One of the specimens shall be die cut from the sample in the direction of extrusion. The other sample shall be die cut from the sample at an angle of 90° to the direction of extrusion. Failure of either specimen shall be cause for rejection of the lot represented. Failure of any other test by the sample shall be cause for rejection of the lot represented."

Custodian:

Army - EA

Preparing activity:

Army - EA

Project No. 9330-A041

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T21:00Z
Check the source to verify that this is the current version before use.