MILITARY SPECIFICATION

CORD, LACING, SILK
(FOR ASSEMBLY OF PROPELLING CHARGES)

This interim amendment is approved for use by the U.S. Army Armament Research and Development Command, with Military Specification MIL-C-453C(OS), dated 5 November 1976.

PAGE 2

3.2 Table I. Delete in its entirety and substitute the following:

TABLE I. Chemical Requirements

Property	Requirement
Foreign material	None
Ether extract	10.0% max
Acidity	
pH of water extract	4.4 to 9.7
Organic or alkalinity	0.1%, max
Ash	2.0%, max

3.3 Table II. Under Class C, yards per pound, delete "260 ± 20" and substitute "240 (min)".

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 4020-A009)

FSC 4020

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:29Z
Check the source to verify that this is the current version before use.