[METRIC]

A-A-59315/6
September 4, 1998
SUPERSEDING
MIL-P-85856/6
December 7, 1988

COMMERCIAL ITEM DESCRIPTION SHEET

POWDER MATERIALS FOR FLAME AND PLASMA SPRAYED COATINGS COBALT BASE, TYPE I, CLASS 2

The General Services Administration has authorized the use of this commercial item description sheet as a replacement for MIL-P-85856/6 by all federal agencies.

The complete requirements for procuring the powder material described herein shall consist of this document and the issue in effect of commercial item description A-A-59315/GEN.

1. SCOPE. This commercial item description sheet (CID) covers a cobalt base powder that is applied using either plasma arc or combustion gas (flame spray) techniques.

2. SALIENT CHARACTERISTICS.

2.1 Chemical composition. Chemical composition shall conform to the following percentages, by weight, as shown in table I.

2.2 Particle size distribution. The particle size distribution shall conform to table II.

3. REGULATORY REQUIREMENTS. Regulatory requirements shall be in accordance with A-A-59315/GEN.

4. QUALITY ASSURANCE PROVISIONS. Quality assurance provisions shall be in accordance with A-A-59315/GEN.

5. PACKAGING. Packaging shall be in accordance with A-A-59315/GEN.

6. NOTES. The notes specified in A-A-59315/GEN are applicable to this CID sheet.

Beneficial comments, recommendations, additions, deletions, clarifications, etc., and any data which may improve this document should be sent to: Commander, Naval Air Warfare Center Aircraft Division, Code 414100B120-3, Highway 547, Lakehurst, NJ 08733-5100.

FSC 3439

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:09Z
Check the source to verify that this is the current version before use.

TABLE I. Chemical composition. 1/

Element	Percentage	
	min.	max.
Chromium	24.5	26.5
Nickel	9.5	11.5
Iron	--	2.0
Tungsten	7.0	8.0
Carbon	0.42	0.55
Manganese	--	1.0
Silicon	--	1.0
Cobalt	Balance	
Phosphorus	--	0.04
Sulfur	--	0.04

1/ The powder shall be reduced by heating in a vacuum or dry hydrogen atmosphere for 2 to 4 hours at 955° to 1010°C (1750° to 1850°F). This requirement is waived for powder that is produced by atomizing in an inert atmosphere.

TABLE II. Particle size distribution by weight (percent).

Sieve Designation		Weight passed through sieve	Weight retained on sieve
Mesh	Microns (μm)		
170	90	100.0 min.	--
200	75	95.0 min	--
325	45	--	90.0 min.

MILITARY INTERESTS:

Custodians:
Army - MR
Navy - AS
Air Force - 11
DLA - GS

Review activities:
Navy - SH
Air Force - 71, 99

CIVIL AGENCY COORDINATING ACTIVITY:

GSA/FSS-7FXE

Preparing activity:
Navy - AS
(Project 3439-0916)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T10:09Z
Check the source to verify that this is the current version before use.