
MILITARY SPECIFICATION SHEET

WIRE, ELECTRIC, FLUOROPOLYMER-INSULATED, EXTRUDED TYPE,
NICKEL-COATED HIGH STRENGTH COPPER ALLOY CONDUCTOR, 1000-VOLT

This specification is approved by the Naval Air Systems Command, Department of the Navy.

The complete requirements for procuring the wire described herein shall consist of this document and the issue in effect of Specification MIL-W-22759.



TFE-Polytetrafluoroethylene

TABLE I. CONSTRUCTION DETAILS

Part No 1/	Wire size	Stranding (Number of strands X AWG gage of strands)	Diameter of stranded conductor (inches)		Finished wire		
			(min)	(max)	Resistance at 20°C (68°F) (ohms/1000 ft) (max)	Diameter (inches)	Weight (lbs/1000 ft) (max)
M22759/21-28-*	28	7 X 36	.014	0.016	79.0	.043 ±.002	1.93
M22759/21-26-*	26	19 X 38	.018	0.020	49.4	.048 ±.002	2.60
M22759/21-24-*	24	19 X 36	.023	0.025	30.1	.053 ±.002	3.38
M22759/21-22-*	22	19 X 34	.029	0.031	18.6	.060 ±.002	4.61
M22759/21-20-*	20	19 X 32	.037	0.040	11.4	.068 ±.002	6.43

1/ PART NO.: The asterisks in the part number column, Tables I and II, shall be replaced by color code designators in accordance with MIL-STD-681. Examples: Size 20, white - M22759/21-20-9; white with orange stripe - M22759/21-20-93.

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:47Z
Check the source to verify that this is the current version before use.

TABLE II. PERFORMANCE DETAILS

Part No.	Abrasion resistance (Procedure II)				Bend testing			
					Mandrel diameter (inches) (±3%)		Test load (lbs) (±3%)	
	Resistance (inches of tape) (min) (initial condition)	Weight support bracket	Weight (lbs)	Tension load (lbs)	Life cycle (oven & bend tests) 1/	Cold bend test	Life cycle (oven & bend tests) 1/	Cold bend test
M22759/21-28-*	24	A	.50	1.0	.125	.250	.50	
M22759/21-26-*	24	A	.50	1.0	.125	.250	.50	
M22759/21-24-*	30	A	.50	1.0	.125	.250	.50	
M22759/21-22-*	30	A	.50	1.0	.250	.375	.75	
M22759/21-20-*	30	A	.50	1.0	.250	.375	.75	

1/ Also for bend tests after immersion.

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 260°C (500°F) max conductor temperature
VOLTAGE RATING: 1000 volts (rms) at sea level
ABRASION RESISTANCE AFTER IMMERSION: No requirement
ACID RESISTANCE: Required
Dielectric test, 3000 volts (rms), 60Hz
BLOCKING: 260 ±2°C (500 ±3.6°F)
COLOR: In accordance with MIL-STD-104, Class 1; white preferred
COLOR STRIPING OR BANDING DURABILITY: 250 cycles (500 strokes) (min), 500 grams weight
DIELECTRIC TEST AFTER IMMERSION: 3000 volts (rms), 60Hz
FLAMMABILITY: Post-flame dielectric test not required
HUMIDITY RESISTANCE: No requirement

IDENTIFICATION DURABILITY: 125 cycles (250 strokes) (min), 500 grams weight
IMPULSE DIELECTRIC TEST: 9.5 kilovolts (peak), 100% test
INSULATION RESISTANCE: 50,000 megohms for 1000 ft (min)
LIFE CYCLE: Oven temperature 275 ±2°C (527 ±3.6°F)
Dielectric test, 3000 volts (rms), 60Hz
LOW TEMPERATURE (COLD BEND):
Bend temperature: -65 ±2°C (-85 ±3.6°F)
Dielectric test, 3000 volts (rms), 60Hz
SHRINKAGE: 0.03 inch max at 290 ±2°C (554 ±3.6°F)
SMOKE: 290°C (554°F)
SPARK TEST OF PRIMARY INSULATION: Not required
SURFACE RESISTANCE: 500 megohm-inches (min), initial and final readings
THERMAL SHOCK: Oven temperature, 260 ±2°C (500 ±3.6°F)
Max change in measurement, 0.060 inch
WICKING: No requirement
WIRE LENGTH REQUIREMENTS: Schedule A
WRAP TEST: "Wrap back" test required; no cracking
Oven temperature, 313 ±2°C (595.4 ±3.6°F)

Preparing activity:
Navy - AS
(Project No. 6145-N241

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:47Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge (DO NOT STAPLE), and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12503 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Engineering Specifications And Standards
Department (Code ES)
Naval Air Engineering Center
Philadelphia, PA 19112

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T13:47Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil – Downloaded: 2026-10-19T13:47Z
Check the source to verify that this is the current version before use.